



THE CHEMICAL FACTORY

— Built to Dominate —

Chem Bitu Guard

Damp Proofing with Asphalt Emulsions



WATERPROOF
PROTECTION



EXCELLENT
ADHESION



UV & WEATHER
RESISTANT



DURABLE
FINISH



DESCRIPTION

Chem Bitu Guard is a high-quality asphalt emulsion with bentonite clay that creates a damp-proof barrier for concrete or masonry walls. This permeable layer prevents moisture migration without reducing vapour transmission.

- ✓ Outstanding binding strength to a range of surface textures and substrates.
- ✓ It can be used on green concrete or moist surfaces.
- ✓ Reduces moisture and vapour transmission through below-grade walls.
- ✓ Unaffected by organic matter, minerals, or the acidity or alkalinity of the soil.



RECOMMENDE USES

- Above or below grade, interior or exterior.
- Form and pour or tilt wall concrete, concrete block, masonry, or stone surfaces.
- Foundations, retaining walls, and fire barriers.
- Culverts, bridge abutments, coping, and parapets.
- Designed for durable service under industrial traffic



SERVICES



Admixtures



Surface Treatment



Concrete Repair



Water Proofings



Industrial Flooring System



Grouts & Anchors



Adhesives



Joint Sealants



Bitumin Products



Miscellaneous



SUPERIOR
WATERPROOFING



LONG LASTING
DURABILITY



ENHANCED SURFACE
PROTECTION



Office #1, building 99-c, jami commercial
street no 11, phase 7, DHA Karachi.



+92 21 35885870



www.thechemicalfactory.com



info@dechemicalfactory.com





TECHNICAL DATA

Property	Value
Property	Value
Type	Bituminous, cold-applied (solvent-based)
Appearance (wet / dry)	Black liquid / Black satin film
V.O.C. Content	9 gm/L
Specific Gravity	1.0–1.05
Solids	50% by weight and volume
Recoat Time	4–6 h (25 °C; RH 50%)
Full Cure	24–48 h
Viscosity	77°F (25°C):* 800–1000 cps
Elongation / Flexibility	Flexible bituminous film
pH	6.2–7.0
Colour	Black
Packaging	250 kg Drum / 15 kg bucket
Drying time	70°F (21°C), 50% RH

* Values vary with temperature, humidity and substrate absorption.



CONSUMPTION

Coverage:	100 Ft ² per U.S. gallon per coat* *2.5 m ² per liter per coat.
Guidance:	Apply Chem Bitu Guard in two coats, allowing first coat to become tacky or dry to touch before applying second coat.



STANDARDS

- Tested in accordance with DIN 1048 Water Permeability Test.
- Complies with Water Research Council requirements for potable water contact.



IMPORTANT INFORMATION

Supplied in: 250 Kg Drum / 15 Kg Bucket.

Storage: Store dry, frost-free, out of direct sunlight

Shelf Life: 1 year in original packaging

Hazard Class: Non-hazardous goods.
Consult MSDS for details.



APPLICATION GUIDELINES



Surface Preparation

Apply Chem Bitu Guard in two coats, allowing first coat to become tacky or dry to touch before applying second coat.



Mixing

Chem Bitu Guard is packaged ready to use. Stir prior to using.



Application

Surface to be coated must be kept damp during application procedure. Do not apply to dry substrates. Apply directly from container using a brush, Tarzan roller applicator or power spray equipment.



Curing & Protection

Clean tools and equipment immediately after use with clean water (or the recommended cleaner for solvent-containing systems). Cured material can only be removed mechanically.



Cleaning of Equipment

Clean tools and equipment with detergent and water.



Storage & Handling

Store Tightly closed containers in warm area, away from direct sunlight and sources of heat. Protect containers from freezing during storage and shipment.



ENHANCED
DURABILITY



FASTER
PLACEMENT



BETTER FINISH
& PERFORMANCE

The information above reflects The Chemical Factory's current knowledge and is provided to assist specifiers and contractors. It does not replace project-specific trials to confirm suitability. Data are typical values under standard conditions; on-site results may vary. Recommendations are offered in good faith without warranty, as factors beyond our control can affect performance. The Chemical Factory may revise specifications without prior notice. Users are responsible for compliance with applicable standards and regulations. Technical assistance is available on request.



Office #1, building 99-c, jami commercial street no 11, phase 7, DHA Karachi.



+92 21 35885870



www.thechemicalfactory.com



info@ dechemicalfactory.com