



THE CHEMICAL FACTORY

— Built to Dominate —

Chem Joint Lock

Elastomeric Fuel
Resistance Joint Sealant



STRONG
JOINT



EXCELLENT
ADHESION



UV & WEATHER
RESISTANT



DURABLE
FINISH



DESCRIPTION

Chem Joint Lock, a single component liquid polymer, is heated in an oil-jacketed extruder before being extruded into joints. Using Chem Joint Lock through an extruder might result in high daily application rates.

- ✓ Highly resistant to weathering, will not flow, bubble or blister to high temperatures.
- ✓ Maintain resilient, rubber like properties at sub-zero temperatures.
- ✓ Outstanding resistance to petrol, oil and jet fuel spillage.
- ✓ High productivity from extruder minimizes contract period.
- ✓ Resistant to jet blast and penetration from stones and hard debris.
- ✓ Self-leveling; produces uniform, neat joints.



RECOMMENDED USES

- Road Airfield Aprons
- Runway and Taxiways
- Cargo Terminals
- Warehouse
- Parking Areas



SERVICES



Admixtures



Surface Treatment



Concrete Repair



Water Proofings



Industrial Flooring System



Grouts & Anchors



Adhesives



Joint Sealants



Bitumin Products



Miscellaneous



SUPERIOR
WATERPROOFING



LONG LASTING
DURABILITY



ENHANCED SURFACE
PROTECTION



Office #1, building 99-c, jami commercial
street no 11, phase 7, DHA Karachi.



+92 21 35885870



www.thechemicalfactory.com



info@dechemicalfactory.com



TECHNICAL DATA

Property	Value
Type	Chem Joint Sealant, liquid polymer
Specific Gravity	1.26
Movement Accommodation Factor	25%
Resilience ASTM D3569	65 - 75%
ASTM D7116-05	>60%
Service Temperature range	-20°C to 70°C



CONSUMPTION

Coverage:

Chem Joint Lock: Number of liters required = join width (mm) x sealant dept (mm) x joint length (mm)

Priming:

Joints which have been sand/grit blasted, and which are perfectly clean and dry, can be sealed without the use of a primer.



STANDARDS

Chem Joint Lock complies with the performance requirements of: Us Federal Specification SS-S-1614, 167b, 1401b 164 ASTM D7116-05. ASTM D3406 85. ASTM D3569 85. BS2499 1973 Types A1 and B1. DTP sepecification for Highway works 1986 clause 1016.



IMPORTANT INFORMATION

Supplied in: 600 ml tube

Storage: Store dry, frost-free, out of direct sunlight

Shelf life: 1 year in original packaging

Hazard Class: Non-hazardous goods.



APPLICATION GUIDELINES



Joint Preparation

The substrate to which Chem Joint Lock is to be bonded must be clean and dry and the joint profile sound. Arris repair where required should be effected using a recommended Chem repair compound.



Priming

Joints which have been sand/gritblasted, and which are perfectly clean and dry, can be sealed without the use of a primer.



Heating / Application

It is essential that the correct heating and application equipment is used to ensure successful performance of the sealant. Chem Joint Lock should be poured directly into an approved oil jacketed heated / extruder.



Cleaning

Application equipment should be cleaned thoroughly using Chem Joint Lock flushing oil. Ignition sources associated with the heater / extruder must be extinguished prior to the use of flushing oil. Following application Chem Joint Lock can only be removed mechanically.



Technical Service

A trained Chem representative is available to assist in the preparation of specifications, and the resolution of concrete problem in the field.



Health and Safety

Chem Joint Lock should not come in contact with skin and eyes or be swallowed. Avoid inhalation of vapours and ensure adequate ventilation.



ENHANCED
DURABILITY



FASTER
PLACEMENT



BETTER FINISH
& PERFORMANCE

The information above reflects The Chemical Factory's current knowledge and is provided to assist specifiers and contractors. It does not replace project-specific trials to confirm suitability. Data are typical values under standard conditions; on-site results may vary. Recommendations are offered in good faith without warranty, as factors beyond our control can affect performance. The Chemical Factory may revise specifications without prior notice. Users are responsible for compliance with applicable standards and regulations. Technical assistance is available on request.



Office #1, building 99-c, jami commercial street no 11, phase 7, DHA Karachi.



+92 21 35885870



www.thechemicalfactory.com



info@ dechemicalfactory.com