THE CHEMICAL FACTORY

Built to Dominate

Chem Grout N-S

General Use Non-Shrink Cementitious Grout



HIGH FLOW | HIGH STRENGTH | EXCELLENT BOND | DURABLE FINISH

DESCRIPTION

Chem Grout N-S is delivered as a ready-to-use dry powder. A controlled amount of clean water is added to create a flowing, non-shrinking grout for gaps up to 100mm thick. Chem Grout N-S is a combination of Portland cement, graded fillers, and chemical additives that provide controlled expansion in the plastic state while reducing water use. The reduced water demand guarantees high early strengths. The graded filler is intended to aid in uniform mixing and yield a consistent grout.

- The gaseous expansion mechanism compensates for shrinkage and settlement in the plastic state.
- There is no metallic iron content to cause discolouration.
- Prepackaged materials eliminate any on-site batching differences.
- Increases early strength without the usage of chlorides.

RECOMMENDE USES

- Used for general purpose grouting
- Essential to eliminate shrinkage
- For completely filling the void between a base plate and a substrate
- Typical application: grouting of a stanchion base plate
- High early strength and durable load transfer



SERVICES

- Admixtures
- Surface Treatment
- Concrete Repair
- Water Proofings
- Industrial Flooring System
- Grouts & Anchors ✓
- Adhesives
- Joint Sealants
- Bitumin Products
- Miscellaneous

SUPERIOR WATERPROOFING | LONG LASTING DURABILITY | ENHANCED SURFACE PROTECTION

Office #1, building 99-c, jami commercial street no 11, phase 7, DHA Karachi.

+92 21 35885870

www.thechemicalfactory.com

info@dechemicalfactory.com

TECHNICAL DATA

Property	Value
Property	Value
Type	Grout N-S, Dry Powder
Compressive Strength @1 day	@ 25 MPa
7 days	@ 45 MPa
28 days	@ 66 MPa
Flexural Strength @1 day	@ 2.5 MPa
7 days	@ 10.0 MPa
28 days	@ 11.0 MPa
Viscosit	77°F (25°C):* 800–1000 cps
Time for expansion	Start: 5 minutes Finish: 2 hours
Fresh Wet Density	Approximately 2160 kg/m³
Young's Modulus	25 GPa
Expansion	An expansion of up to 1% overcomes plastic settlement in plastic material.
Setting Times	Initial: 165 minutes Final: 270 minutes

CONSUMPTION

Guidence:

Chem Grout NS is a specialized hydraulic cement material engineered with expansive additives to offset normal drying shrinkage and maintain full, continuous contact under structural load-bearing plates and machinery bases.

STANDARDS

- Tested in accordance with DIN 1048 Water Permeability Test.
- Complies with Water Research Council requirements for potable water contact.

IMPORTANT INFORMATION

Supplied in: 20 Kg Bag

Storage: Store dry, frost-free, out of direct sunlight

Shelf Life: 1 year in original packaging

Hazard Class: Non-hazardous goods.

APPLICATION GUIDELINES

Surface Preparation

The substrate surface must be free from oil, grease or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes or fixing pockets must be blown clean of any dirt or debris.

Mixing

To achieve optimal results, a mechanically powered grout mixer is recommended for quantities of up to 50kg; a slow-speed drill equipped with a high shear mixer is appropriate. Greater amounts will necessitate a high shear vane mixer. Avoid utilizing a colloidal impeller mixer.

Application

Chem Grout NS is applied to fill structural gaps under baseplates, anchor heavy machinery, and repair concrete without losing volume during the curing process.

Curing & Protection

On completion of the grouting operation, exposed areas should be thoroughly cured. This should be done by the use of Cure con curing membrane, continuous application of water and/or wet hessian.

Cleaning of Equipment

Chem Grout N-S should be removed from tools and equipment immediately after use. Cured material can only be removed mechanically.

Storage & Handling

Chem Grout N-S has a shelf life of 12 months if kept in a dry store in sealed bags . If store in a high temperature and high humidity locations, the self life may be reduced.



ENHANCED DURABILITY

FASTER PLACEMENT

BETTER FINISH & PERFORMANCE

The information above reflects The Chemical Factory's current knowledge and is provided to assist specifiers and contractors. It does not replace project-specific trials to confirm suitability. Data are typical values under standard conditions; on-site results may vary. Recommendations are offered in good faith without warranty, as factors beyond our control can affect performance. The Chemical Factory may revise specifications without prior notice. Users are responsible for compliance with applicable standards and regulations. Technical assistance is available on request.



Office #1, building 99-c, jami commercial street no 11, phase 7, DHA Karachi.

+92 21 35885870

www.thechemicalfactory.com

info@ dechemicalfactory.com