THE CHEMICAL FACTORY

Built to Dominate

Chem PU Elasto Pro

Pure polyurethane, liquid-applied roof waterproofing membrane with Superior Elastic and Durability



FAST DRYING | EXCELLENT ADHESION | CORROSION RESISTANT | EASY APPLICATION

DESCRIPTION

CHEM PU ELASTO PRO is a high performance, single-component, cold-applied, moisture-triggered aliphatic-aromatic polyurethane liquid waterproofing membrane. It forms seamless , elastic and durable coating that provides Long-term protection to concrete and mental surfaces. Designed for superior flexibility, weather resistance and chemical stability, it is ideal for both new and existing structure.

- Waterprooing for roofs, terraces and podiums.
- Protecttion for concrete and mental surafce.
- Ideal for new construction and refurbishment projects.
- Suitable for residenral, commercial and industrial building.
- long-lasting proctection against harsh weather condition and UV exposure.

RECOMMENDE USES

- Exposed and non-exposed flat roof waterproofing.
- Pitched roof and roof-deck waterproofing.
- Protective waterproofing layer beneath compatible subsequent finishes.
- Waterproofing of concrete and cementitious substrates.
- Concrete surface before coating.



SERVICES

- Admixtures
- Surface Treatment
- Concrete Repair
- Water Proofings ✓
- Industrial Flooring System
- Grouts & Anchors
- Adhesives
- Joint Sealants
- Bitumin Products
- Miscellaneous

STRONG WATERPROOFING | FAST & EFFECTIVE INJECTION | LONG LASTING PROTECTION

Office #1, building 99-c, jami commercial street no 11, phase 7, DHA Karachi.

+92 21 35885870

www.thechemicalfactory.com

info@dechemicalfactory.com

TECHNICAL DATA

Property	Value
Chemical Base	Two-component polyurethane (Polyurethane resin + Hardner
Form	Liquid
Typical Appearance	Smooth coating; standard colour as supplied
Density	Approx. 1.35 kg/L
Solids Content	Approx. 95% by weight
Flash Point	Flash Point Approx. 80 °C (closed-cup method)
Crack Bridging	Up to 3 mm, no cracking reported (ASTM C836)*
Elongation at Break	Approx. 700% (ASTM D412)*
Tear Strength	Approx. 16.5 N/mm (ASTM D624)*
Tensile Strength	Approx. 6 N/mm² (ASTM D412)*
Pull-Off Adhesion	< 2 N/mm² (ASTM D4541)*
VOC	< 250 g/L (ASTM D2369)*

* Performance varies with substrate, film build, temperature and application method.

CONSUMPTION

Coverage: Approximately 1.5–2.0 kg/m² per mm of thickness, depending on surface condition, porosity and application method.

Guidence: Clean all tools and application equipments with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

STANDARDS

- Solid Content: ~95% by weight (+23°C/50%r.h.
- Flash Point: 80 °C (Closed cup method)
- Density: ~2.0 kg/L

IMPORTANT INFORMATION

Supplied in: 20 Kg Bucket

Storage: Store dry, frost-free, out of direct sunlight

Self Life: 1 years in original packaging

Hazard Class: Non-hazardous goods.

APPLICATION GUIDELINES

DISPENSING

Use Brush or roller for even application.

MIXING

Adheres to various subatance including concrete, cementitious substrates and bitumen sheets.

USES

Waterproofing Membrane on exposed flat and pitched roofs both for new construction and refurbish-ment of old roofs.

APPLICATION

Ensure surface and clean, dry and free from dust oil or loose particles. Apply in 2-3 coats for best performance.

STORAGE & HANDLING

Store in a cool, dry and well-ventilated area, away from direct sunlight and heat sources.
Keep the product in its original, tightly closed container until ready for use.

SAFETY

Use gloves, goggles and protectiveclothing. Avoid skin and eye
contact.



ENHANCED DURABILITY

FASTER PLACEMENT

BETTER FINISH & PERFORMANCE

The information above reflects The Chemical Factory's current knowledge and is provided to assist specifiers and contractors.
It does not replace project-specific trials to confirm suitability. Data are typical values under standard conditions; on-site results may vary.
Recommendations are offered in good faith without warranty, as factors beyond our control can affect performance. The Chemical Factory may revise specifications without prior notice. Users are responsible for compliance with applicable standards and regulations.
Technical assistance is available on request.



Office #1, building 99-c, jami commercial street no 11, phase 7, DHA Karachi.

+92 21 35885870

www.thechemicalfactory.com

info@ dechemicalfactory.com