
THE CHEMICAL FACTORY

Built to Dominate

ChemAdd SP Pro

High-Range Water-Reducing Superplasticizer (HRWR)



WATER REDUCTION | HIGHER STRENGTH | IMPROVED WORKABILITY | DURABLE CONCRETE

DESCRIPTION

ChemAdd SP Pro is a high-performance polycarboxylate superplasticizer that gives superior flow with less water. Achieve stronger, denser concrete with better slump retention, easy pumping, and smooth finish No segregation. No bleeding. Perfect for precast and ready-mix concrete where speed and quality matter.

- Major water reduction with maintained workability.
- Higher early and ultimate strengths; reduced permeability.
- Smooth, defect-free finishes; improved compaction around congested steel.
- Compatible with most cements and supplementary cementitious materials.
- Chloride-free; suitable for reinforced and prestressed concrete.

RECOMMENDED USES

- High-strength columns, beams and slabs
- Precast elements and SCC/flowing concrete
- Dense reinforcement / complex formwork
- Fair-faced and architectural concrete
- Pumped concrete and long lines

SERVICES

- Admixtures
- Surface Treatment
- Concrete Repair
- Water Proofings
- Industrial Flooring System
- Grouts & Anchors
- Adhesives
- Joint Sealants
- Bitumin Products
- Miscellaneous



ENHANCED DURABILITY | FASTER PLACEMENT | BETTER FINISH & PERFORMANCE

Office #1, building 99-c, jami commercial street no 11, phase 2, DHA Karachi.

+92 21 35885870

www.thechemicalfactory.com

info@dechemicalfactory.com

TECHNICAL DATA

Property	Value
Appearance	Clear to pale amber liquid
Specific Gravity (25 °C)	1.02 ± 0.02
pH	7.0–9.0
Chloride Content	≤ 0.10% (chloride-free formulation)
Alkali Content (Na_2O-eq.)	≤ 1.5%
Dosage Range	0.20–0.80% by weight of cement (bwoc)
Typical Set Delay*	~1–4 hours depending on dose, cement and temperature
Effect on Strength	Maintains or improves 28-day strength at proper dose
Compatibility	Compatible with plasticizers, superplasticizers, air-entrainers & pozzolans
Packaging	**250 kg Drum**

*Actual set delay depends on temperature, cement chemistry, SCMs and total alkalies. Trial mixes are essential.

CONSUMPTION

Normal dosage: 0.20–0.60 litres per 100 kg of cement (bwoc)

High retardation / hot weather: up to 0.80 litres / long haul per 100 kg of cement (bwoc) — site trials recommended

Guidance: Add admixture to the mixing water or freshly mixed concrete. Do not add directly to dry cement. Adjust dosage according to temperature, cement type, and desired set delay.

STANDARDS

- Meets the requirements of ASTM C494 Type B (Retarding Admixture).
- Conforms to the intent of EN 934-2 (Set-retarding admixtures), when used as directed. **Sp**

IMPORTANT INFORMATION

Supplied in: 250 kg Drum

Storage: Store dry, frost-free, out of direct sunlight

Shelf Life: 1 year in original packaging

Hazard Class: Non-hazardous goods. Consult MSDS for details.

APPLICATION GUIDELINES

DISPENSING

ChemAdd SP Pro to the concrete mix at the recommended dosage. For best results, introduce the admixture into the mixing water or into freshly mixed concrete to ensure uniform dispersion. Do not add directly to dry cement.

MIXING

Add with the gauging water or directly into the mixer during batching. Allow a minimum of 60–90 seconds of mixing after the admixture addition to achieve complete and uniform distribution.

COMPATIBILITY

Compatible with most types of cement and supplementary cementitious materials. May be used with other admixtures; however, each admixture should be added separately to the mix. Conduct site trials when combining multiple admixtures.

PLACEMENT

Place, consolidate and finish the concrete using normal methods. Monitor setting time on site, as dosage and ambient conditions affect retardation.

STORAGE & HANDLING

Store in original, tightly closed containers in a cool, frost-free environment out of direct sunlight. Protect from freezing. If the product has been frozen, allow it to thaw and remix before use.

CLEANING OF EQUIPMENT

Clean spillage and equipment with clean water before the admixture hardens or dries.



ENHANCED DURABILITY

FASTER PLACEMENT

BETTER FINISH & PERFORMANCE

The information above reflects The Chemical Factory's current knowledge and is provided to assist specifiers and contractors. It does not replace project-specific trials to confirm suitability. Data are typical values under standard conditions; on-site results may vary. Recommendations are offered in good faith without warranty, as factors beyond our control can affect performance. The Chemical Factory may revise specifications without prior notice. Users are responsible for compliance with applicable standards and regulations. Technical assistance is available on request.



Office #1, building 99-c, jami commercial street no 11, phase 2, DHA Karachi.

+92 21 35885870

www.thechemicalfactory.com

info@dechemicalfactory.com