THE CHEMICAL FACTORY

Built to Dominate

Chem Epo Flow SL

Self-Leveling Epoxy Flooring System



FAST DRYING | EXCELLENT ADHESION | CORROSION RESISTANT | EASY APPLICATION

DESCRIPTION

Chem Epo Flow SL is a two-component, solvent-free, self-leveling epoxy flooring system developed to form a smooth, hard-wearing and hygienic floor finish over properly prepared concrete substrates. Its flowable formulation is designed to produce a uniform surface with good adhesion, durability and resistance to common industrial service conditions.

- Resists positive water pressure and helps control water ingress.
- Factories, warehouses, workshops and production areas
- Packing, processing and service areas where easy cleaning is important
- Areas exposed to regular foot traffic, wheeled traffic and mechanical wear
- Concrete floors requiring improved surface protection and a hygienic, low-maintenance finish

RECOMMENDE USES

- Solvent-free two-component epoxy system
- Self-leveling and flowable application characteristics
- Smooth, seamless and easy-to-clean finished surface
- Good adhesion to properly prepared concrete
- Designed for durable service under industrial traffic



SERVICES

- Admixtures
- Surface Treatment
- Concrete Repair
- Water Proofings
- Industrial Flooring System ✓
- Grouts & Anchors
- Adhesives
- Joint Sealants
- Bitumin Products
- Miscellaneous

STRONG WATERPROOFING | FAST & EFFECTIVE INJECTION | LONG LASTING PROTECTION

Office #1, building 99-c, jami commercial street no 11, phase 7, DHA Karachi.

+92 21 35885870

www.thechemicalfactory.com

info@dechemicalfactory.com

TECHNICAL DATA

Property	Value
Appearance	Two-component epoxy system
Finish	Smooth, seamless self-leveling finish
System	Two-component, solvent-free epoxy
Application substrate	Sound, clean and properly prepared concrete
Application method	Pour, spread and de-air using suitable tools/equipment
Curing	Dependent on site temperature and environmental conditions
Pot Life	65 minutes
Recoat time	18 Hours
Triffic Time	24 Hours
Light Vehicle	48 Hours
Full Cure	7 Days
Density / specific gravity	Grey. Other Colors to order in sufficient quantity

CONSUMPTION

Coverage: Approx is Supplied in preweighed 12 kg kits comprising Base , Hardner and Filler.

Guidence: Applying an epoxy floor topping requires strict adherence to system selection, deep surface profiling, and methodical application phases to prevent premature peeling, bubbling, or pinholes. Professional floor toppings generally range from 0.5 mm to over 3 mm in thickness, demanding distinct handling compared to thin, residential epoxy paint

STANDARDS

- Colour: Grey Grey. Other Colors to order in sufficient quantity
- Full Cure: 7 Days

IMPORTANT INFORMATION

Supplied in: 12 Kg Kit

Storage: Storage Condition Cool, covered and dry place; protect from direct sunlight and heat

Self Life: 1 years

Hazard Class: Non-hazardous goods.

APPLICATION GUIDELINES

DISPENSING

Concrete must be sound, clean and free from laitance, dust, oil, grease, curing compounds, loose material and other contaminants. Mechanically prepare the substrate as required to obtain a suitable open surface profile. Repair cracks, holes and weak areas before coating. The substrate must be sufficiently dry and suitable for epoxy application.

MIXING

Condition the components to suitable application temperature before mixing.
Mix the resin and hardener components in the manufacturer's specified proportion.
Use a clean, low-speed mechanical mixer and mix until a completely uniform blend is obtained.

USES

Protect the applied coating from premature drying. Where practical, fog-spray with clean water after initial set. Longer curing may be required under cold or humid conditions.

APPLICATION

Prime the prepared concrete where required by the system specification.
Pour the mixed material onto the prepared floor and distribute evenly using a suitable notched squeegee or gauge rake.
Back-roll the applied material with a suitable spiked roller to assist uniform leveling and release entrapped air

STORAGE & HANDLING

Store unopened components in a cool, dry and covered location, protected from direct sunlight, moisture, frost and excessive heat.

SAFETY

Use appropriate PPE including gloves, protective clothing and eye protection. Provide adequate ventilation during application. Avoid skin and eye contact and follow the current Safety Data Sheet (SDS) for detailed handling, first-aid, storage and disposal information.



ENHANCED DURABILITY

FASTER PLACEMENT

BETTER FINISH & PERFORMANCE

The information above reflects The Chemical Factory's current knowledge and is provided to assist specifiers and contractors.
It does not replace project-specific trials to confirm suitability. Data are typical values under standard conditions; on-site results may vary.
Recommendations are offered in good faith without warranty, as factors beyond our control can affect performance. The Chemical Factory may revise specifications without prior notice. Users are responsible for compliance with applicable standards and regulations.
Technical assistance is available on request.



Office #1, building 99-c, jami commercial street no 11, phase 7, DHA Karachi.

+92 21 35885870

www.thechemicalfactory.com

info@ dechemicalfactory.com