From a CIF File to a Crystal Shape

Every step from the numbers in a CIF file to the crystal shape, computed in your browser with the full working shown: lattice, metric tensor, centring and point group found from the atoms, structure factors, face spacings, the BFDH rule, the shape built plane by plane, and the map of every shape a cubic crystal can take.

Step 11 of 20 · next: **Morphology**

From a CIF File to a Crystal Shape, Step by Step

The panel asked whether a computer can start from the unit cell of an established MOF and produce the crystal shapes it can take. This page does the first, purely geometric version of that, in front of you: it reads a CIF file and computes every step from the six cell numbers to the finished shape, printing each intermediate number so the working can be checked by hand.

CIF file MOF-5 | **HKUST-1** | UiO-66 | ZIF-8

CIF	LATTICE	SYMMETRY	WIDEST PLANES	SHAPE
156 atoms, 18.59 Å, 60°	**cubic, a = 26.297 Å**	**Fm-3m**	**{111}, d_{eff} = 15.18 Å**	**truncated octahedron**

Computed in 31 ms in this browser by `mof_cif_shape.js`.

How to read this page

Each step has three parts. **In plain words** says what is being done and why. **The rule** gives the mathematics in general form. **With this file's numbers** applies the rule to the chosen CIF; everything in those boxes is computed when the page loads by `mof_cif_shape.js`, and nothing is typed in. For the four bundled files, a line marked **Python check** repeats the result of the independent Python implementation `code/morphology/run_cif_to_shape.py`, which also runs spglib. The test `website/tests/test_cif_to_shape.js` fails if the two disagree. The page prints in full from the browser, for reading on paper.

1 Read the File

IN PLAIN WORDS

A CIF is a plain text file. Two things in it matter here: the box that repeats to fill space (the unit cell, given by three edge lengths and three angles) and the list of atoms inside it. Each atom is given as an element and three **fractional coordinates**: how far along each edge of the box it sits, as a fraction of that edge.

THE RULE

Unit cell: a, b, c (Å) and α (between **b** and **c**), β (between **a** and **c**), γ (between **a** and **b**). An atom at fractional coordinates **x** = (x, y, z) sits at the point $\mathbf{r} = x\mathbf{a} + y\mathbf{b} + z\mathbf{c}$, and also at $\mathbf{r} + u\mathbf{a} + v\mathbf{b} + w\mathbf{c}$ for every whole number u, v, w.

WITH THIS FILE'S NUMBERS

```
_cell_length_a 18.59484
_cell_length_b 18.59490
_cell_length_c 18.59496
_cell_angle_alpha 59.99992
_cell_angle_beta 60.00001
_cell_angle_gamma 60.00034

loop_ (atoms)
O1 1.0 0.874414 0.020501 0.613727 Biso 1.000000 O
O2 1.0 0.020509 0.874415 0.491353 Biso 1.000000 O
O3 1.0 0.613724 0.491353 0.874415 Biso 1.000000 O
O4 1.0 0.491359 0.613727 0.020501 Biso 1.000000 O
… 152 more atom lines
```

The file lists **156 atoms** ($O_{48}\ C_{72}\ H_{24}\ Cu_{12}$), each by element and fractional coordinates (x, y, z), and the six cell numbers above. Its stated space group is `P 1`, that is, no symmetry is written down. Every symmetry used below is found from the numbers in the file.

2 The Lattice Vectors and the Metric Tensor

IN PLAIN WORDS

The six numbers are turned into three arrows, the cell edges **a**, **b**, **c**, written in ordinary x-y-z coordinates. From the arrows we build one 3×3 table, the metric tensor G, which holds every length and angle of the cell. Every later step that needs a distance or an angle reads it from G. G does not change when the crystal is turned, so it describes the lattice itself, not the way it happens to be drawn.

THE RULE

$\mathbf{a} = (a, 0, 0)$, $\mathbf{b} = (b\cos\gamma, b\sin\gamma, 0)$, $\mathbf{c} = (c\cos\beta, c(\cos\alpha - \cos\beta\cos\gamma)/\sin\gamma, c_z)$, with c_z fixed by $|\mathbf{c}| = c$.

Put the three edges as the rows of a matrix A. Then $G = A\,A^{\mathrm{T}}$, that is $G_{ij} = \mathbf{a}_i \cdot \mathbf{a}_j$: the diagonal holds a^2, b^2, c^2 and the off-diagonal entries $ab\cos\gamma$, $ac\cos\beta$, $bc\cos\alpha$.

Cell volume $V = \sqrt{(\det G)}$. The length of any lattice vector with integer or fractional components $\mathbf{u}$ is $|\mathbf{u}|^2 = \mathbf{u}^{\mathrm{T}}\, G\, \mathbf{u}$.

WITH THIS FILE'S NUMBERS

$\mathbf{a} = (a, 0, 0) = (18.5948, 0, 0)$

$\mathbf{b} = (b\cos\gamma, b\sin\gamma, 0) = (18.5949 \times 0.49999, 18.5949 \times 0.86603, 0) = (9.2974, 16.1037, 0.0000)$

$c_x = c\cos\beta = 18.5950 \times 0.50000 = 9.2975$

$c_y = c\,(\cos\alpha - \cos\beta\cos\gamma) / \sin\gamma = 18.5950 \times (0.50000 - 0.50000 \times 0.49999) / 0.86603 = 5.3680$

$c_z = \sqrt{(c^2 - c_x^2 - c_y^2)} = \sqrt{(345.773 - 86.443 - 28.815)} = 15.1827$

$$A = \begin{pmatrix} \mathbf{18.5948} & 0.0000 & 0.0000 \\ \mathbf{9.2974} & 16.1037 & 0.0000 \\ \mathbf{9.2975} & 5.3680 & 15.1827 \end{pmatrix} \text{ Å} \qquad G = A\,A^{\mathrm{T}} = \begin{pmatrix} \mathbf{345.768} & 172.883 & 172.885 \\ \mathbf{172.883} & 345.770 & 172.886 \\ \mathbf{172.885} & 172.886 & 345.773 \end{pmatrix} \text{ Å}^2$$

For example $G_{11} = \mathbf{a}\cdot\mathbf{a} = 18.5948^2 = 345.768$ and $G_{12} = \mathbf{a}\cdot\mathbf{b} = ab\cos\gamma = 18.5948 \times 18.5949 \times 0.49999 = 172.883$.

$\det G = G_{11}(G_{22}G_{33} - G_{23}^2) - G_{12}(G_{12}G_{33} - G_{23}G_{13}) + G_{13}(G_{12}G_{23} - G_{22}G_{13}) = 20669733\ \text{Å}^6$

Volume $V = \sqrt{(\det G)} =$ **4546.40 Å³**

3 Is the Lattice Cubic? The Conventional Cell

IN PLAIN WORDS

Files often store the smallest box that repeats, not the most symmetric one. A face-centred cube, for example, can be stored as a slanted box with 60° angles that is one quarter of the cube. To see the cube we look for whole-number combinations of the stored edges that are equal in length and at right angles.

THE RULE

The lattice is cubic exactly when there is an integer matrix M (its rows say how to combine the stored edges) such that $M\,G\,M^{\mathrm{T}} = a_c^2\,I$. The new edges $M\,A$ form the conventional cube of edge a_c, which contains $|\det M|$ lattice points. Three candidates cover every cubic lattice: $M = I$ (the file already holds the cube); the 60° rhombohedral cell of a face-centred cube ($\det M = 4$); the 109.47° rhombohedral cell of a body-centred cube ($\det M = 2$). Agreement is tested to a relative tolerance of 2×10^{-4}, which allows for the rounding of the numbers in the file.

WITH THIS FILE'S NUMBERS

The three edges are equal (18.5948 Å) but the angles are 60.000°, not 90°. Edges at 60° are exactly the three shortest lattice vectors of a **face-centred cube**: $\mathbf{a}_1 = \tfrac{1}{2}a_c(0, 1, 1)$, $\mathbf{a}_2 = \tfrac{1}{2}a_c(1, 0, 1)$, $\mathbf{a}_3 = \tfrac{1}{2}a_c(1, 1, 0)$, each of length $a_c/\sqrt{2}$ and at 60° to the others. The cube edges are then $\mathbf{c}_1 = -\mathbf{a}_1+\mathbf{a}_2+\mathbf{a}_3$, $\mathbf{c}_2 = \mathbf{a}_1-\mathbf{a}_2+\mathbf{a}_3$, $\mathbf{c}_3 = \mathbf{a}_1+\mathbf{a}_2-\mathbf{a}_3$, which is the matrix M below. Check with the numbers:

$$M = \begin{pmatrix} \mathbf{-1} & 1 & 1 \\ \mathbf{1} & -1 & 1 \\ \mathbf{1} & 1 & -1 \end{pmatrix} \qquad G_c = M\,G\,M^{\mathrm{T}} = \begin{pmatrix} \mathbf{691.547} & 0.000 & 0.000 \\ \mathbf{0.000} & 691.543 & -0.003 \\ \mathbf{0.000} & -0.003 & 691.534 \end{pmatrix} \text{ Å}^2$$


The diagonal entries agree and the off-diagonal entries vanish (largest relative deviation 1.1e-5, from the rounding in the file), so the lattice is cubic with

$a_c = \sqrt{G_{c,11}} = \sqrt{691.547} = \mathbf{26.2972}$ **Å**, and indeed 18.5948 × √2 = 26.2971 Å.

Volume check: $\det M = 4$, so the cube holds 4 lattice points and $V_c = 4 \times 4546.40 = 18185.6$ Å³ $= a_c^3 = 18185.6$ Å³.

Re-expressed in the cube, the 156 atoms of the file become 624 (each appears at its four lattice-equivalent positions).

Python check (`code/morphology/run_cif_to_shape.py`): conventional cell edge 26.2972 Å (transformation F); spglib standard cell 26.2972 Å.



Blue: the conventional cube, edge 26.297 Å. Orange dashed: the cell actually stored in the file (edges 18.595 Å at 60.0°), drawn from the same corner; four of them fill the cube. Red: metal atoms; grey: the other non-hydrogen atoms, all 624 atoms placed from the file's fractional coordinates. Drag to rotate.

4 Lattice Centring, Found from the Atoms

IN PLAIN WORDS

A cube of lattice points may have extra points that repeat the whole pattern: one at the centre of the body (a body-centred cube, I) or one at the centre of each face (a face-centred cube, F). We test this directly. Shift every atom by half a cell along a diagonal; if each one lands on an atom of the same element, that shift is a symmetry of the crystal.

THE RULE

A translation **t** is a symmetry when, for every atom *j*, some atom *k* of the same element satisfies $|(\mathbf{x}_j + \mathbf{t} - \mathbf{x}_k - \mathbf{m})\,A_c| < 0.02$ Å for some whole-number vector **m** (the wrap-around into the next cell). I-centring is **t** = (½, ½, ½); F-centring is the three vectors (0, ½, ½), (½, 0, ½), (½, ½, 0). The test is run with all atoms and again without hydrogen, because hydrogen positions in a CIF are often placed by software and can break a symmetry the framework has.

WITH THIS FILE'S NUMBERS

Atoms used	I: + (½, ½, ½)	F: + (0, ½, ½)	F: + (½, 0, ½)	F: + (½, ½, 0)
all 624	0 / 624	624 / 624	624 / 624	624 / 624
without H	0 / 528	528 / 528	528 / 528	528 / 528

Each entry counts the atoms *j* that have an atom of the same element within 0.02 Å of $\mathbf{x}_j + \mathbf{t}$. A translation is a symmetry only if every atom passes. Result: the lattice is **face-centred (F)**.

For this file the F translations hold for every atom automatically, because they are combinations of the file's own cell vectors (Step 3): the 60° cell already says the cube is face-centred.

Python check (`code/morphology/run_cif_to_shape.py`): centring F, found with hydrogen; spglib uses hydrogen: yes.

5 The Point Group, Found from the Atoms

IN PLAIN WORDS

Now we turn and reflect the crystal instead of shifting it. If the crystal looks exactly the same after a rotation (perhaps combined with a shift), that rotation is a symmetry. Which rotations survive decides which crystal faces are equivalent, and so which faces must grow at the same rate.

THE RULE

An operation (*R*, **t**) is a symmetry when every atom *j* is sent onto an atom of the same element: $R\mathbf{x}_j + \mathbf{t} \equiv \mathbf{x}_k$ (mod 1, within 0.02 Å). The shift **t** is not known in advance. However, a symmetry must send the first atom of the rarest element onto some atom of that element, so only that many values of **t** need to be tried. Four operations decide the cubic point group: inversion, a 3-fold axis along the body diagonal, a 4-fold axis along an edge, and a 4-fold rotoinversion along an edge.

WITH THIS FILE'S NUMBERS

Operation	Acts as	*R*	Atoms mapped (best t)	t found	Symmetry?
inversion	(x, y, z) → (−x, −y, −z)	$\begin{pmatrix} -1 & 0 & 0 \\ 0 & -1 & 0 \\ 0 & 0 & -1 \end{pmatrix}$	**624 / 624**	(0, 0, 0)	yes
3-fold axis along [111]	(x, y, z) → (z, x, y)	$\begin{pmatrix} 0 & 0 & 1 \\ 1 & 0 & 0 \\ 0 & 1 & 0 \end{pmatrix}$	**624 / 624**	(½, 0, ½)	yes
4-fold axis along [001]	(x, y, z) → (−y, x, z)	$\begin{pmatrix} 0 & -1 & 0 \\ 1 & 0 & 0 \\ 0 & 0 & 1 \end{pmatrix}$	**624 / 624**	(0, ½, ½)	yes
4-fold rotoinversion along [001]	(x, y, z) → (y, −x, −z)	$\begin{pmatrix} 0 & 1 & 0 \\ -1 & 0 & 0 \\ 0 & 0 & -1 \end{pmatrix}$	**624 / 624**	(0, ½, ½)	yes

Decision: a 3-fold axis is required for a cubic crystal. With inversion and a 4-fold axis the point group is **m-3m** (48 operations); with the 3-fold axis and the −4 axis but no inversion it is **-43m** (24 operations). Here: **m-3m**.

Python check (`code/morphology/run_cif_to_shape.py`): point group m-3m by the same search; spglib: Fm-3m (No. 225).

6 Which Planes Cancel: Structure Factors and the Space Group

IN PLAIN WORDS

A crystal face is a plane of atoms, and the face grows by adding the next identical layer. If the centring places an identical layer exactly half-way between two planes of a family, the true repeat distance of that family is half its nominal spacing. X-ray diffraction shows this directly: the waves scattered by the two layers are exactly out of step and cancel, so that reflection is missing. We compute this cancellation from the atoms in the file.

THE RULE

Structure factor: $F(hkl) = \Sigma_j Z_j \exp(2\pi i\,(hx_j + ky_j + lz_j))$, taking each atom's atomic number Z_j as its weight.

If the translations $\mathbf{t}_1, \ldots, \mathbf{t}_m$ are symmetries, the atoms come in sets $\{\mathbf{x}, \mathbf{x} + \mathbf{t}_1, \ldots\}$, and the sum factorises as $F(\mathbf{h}) = S(\mathbf{h}) \times \Sigma_{\text{one atom per set}} Z_j \exp(2\pi i\, \mathbf{h}\cdot\mathbf{x}_j)$, with $S(\mathbf{h}) = \Sigma_s \exp(2\pi i\, \mathbf{h}\cdot\mathbf{t}_s)$. When $S(\mathbf{h}) = 0$, the reflection vanishes whatever the atoms are. This is a **systematic absence**. The weights change the size of an allowed reflection but never make an absent one non-zero.

Glide planes (a reflection combined with a half-cell shift) forbid further reflections. Each possible glide group is checked against the one reflection it would remove.

WITH THIS FILE'S NUMBERS

For this lattice, $S(\mathbf{h}) = 1 + e^{i\pi(k+l)} + e^{i\pi(h+l)} + e^{i\pi(h+k)}$. Each term is +1 or −1, so S is 4 when h, k, l are all even or all odd, and 0 otherwise.

(*hkl*)	*S*(h), term by term	By centring	|*F*(*hkl*)| / Σ*Z*, from the 624 atoms
(100)	1 + 1 − 1 − 1 = 0	absent	**0.00000**
(200)	1 + 1 + 1 + 1 = 4	allowed	**0.30972**
(110)	1 − 1 − 1 + 1 = 0	absent	**0.00000**
(220)	1 + 1 + 1 + 1 = 4	allowed	**0.16606**
(111)	1 + 1 + 1 + 1 = 4	allowed	**0.03636**
(222)	1 + 1 + 1 + 1 = 4	allowed	**0.47520**
(210)	1 − 1 + 1 − 1 = 0	absent	**0.00000**
(420)	1 + 1 + 1 + 1 = 4	allowed	**0.02563**
(211)	1 + 1 − 1 − 1 = 0	absent	**0.00000**
(422)	1 + 1 + 1 + 1 = 4	allowed	**0.11037**
(311)	1 + 1 + 1 + 1 = 4	allowed	**0.06339**
(331)	1 + 1 + 1 + 1 = 4	allowed	**0.10718**

Every reflection the centring forbids comes out as exactly zero from the atoms; the allowed ones do not ($\Sigma Z = 4752$, with Z the atomic number of each atom as its weight).

Centring F with point group m-3m leaves 4 possible space groups. The others contain glide planes, and each glide forbids one more reflection:

- **Fm-3c** (No. 226): hhl: h, l = 2n, so (111) would vanish. From the atoms $|F(111)|/\Sigma Z = 0.0364$, not zero, so Fm-3c is ruled out.
- **Fd-3m** (No. 227): 0kl: k + l = 4n, so (200) would vanish. From the atoms $|F(200)|/\Sigma Z = 0.3097$, not zero, so Fd-3m is ruled out.
- **Fd-3c** (No. 228): 0kl: k + l = 4n, so (200) would vanish. From the atoms $|F(200)|/\Sigma Z = 0.3097$, not zero, so Fd-3c is ruled out.

Space group: Fm-3m (No. 225). For these groups the centring is the only rule that removes faces, so the first allowed order of (*hkl*) follows from the centring alone.

Python check (`code/morphology/run_cif_to_shape.py`): $|F|/\Sigma Z$ for (100), (110), (111), (200): 0.00000, 0.00000, 0.03636, 0.30972; spglib: **Fm-3m**.

7 Face Families, Spacings and Effective Spacings

IN PLAIN WORDS

Every set of parallel lattice planes is a possible crystal face, labelled by three whole numbers (*hkl*), its Miller indices. Planes related by the crystal's symmetry form a family, written {*hkl*}, and all members of a family behave identically. For each family we need one number, the distance between neighbouring identical layers. The picture shows why the centring can halve it.

THE RULE


Spacing: $1/d^2 = \mathbf{h}^{\mathrm{T}}\, G^{-1}\, \mathbf{h}$. For the cubic cell $G = a^2 I$, so $d_{hkl} = a / \sqrt{(h^2 + k^2 + l^2)}$.

First allowed order: the smallest n for which $n(hkl)$ is not absent (Step 6). Effective spacing $d_{\mathrm{eff}} = d_{hkl} / n$.

The members of a family are all signed permutations of (*hkl*) in point group m-3m. In -43m a family with no zero index splits into two halves of equal size, told apart by the sign of *hkl*. Every primitive (*hkl*) with indices up to 6 is listed.

Planes (100) (110)

(100) planes, viewed down [001]



Filled dots: lattice points at height 0; open dots: at height ½*a*. Two cells of edge *a* = 26.297 Å are shown. Blue lines: the planes (100) with spacing *d* = 26.297 Å. Red dashed lines: an identical layer of lattice points lies exactly half-way, so the true repeat is *d*/2 = **13.149 Å**. That is why (100) is absent and its first allowed order is (200).

WITH THIS FILE'S NUMBERS

#	Family	Planes	$h^2+k^2+l^2$	$d = a/\sqrt{(...)}$ (Å)	First allowed order	n	$d_{eff} = d/n$ (Å)
1	{111}	8	3	26.297 / √3 = 15.183	(111) allowed	1	15.183
2	{100}	6	1	26.297 / √1 = 26.297	(100) absent, (200) allowed	2	13.149
3	{110}	12	2	26.297 / √2 = 18.595	(110) absent, (220) allowed	2	9.297
4	{311}	24	11	26.297 / √11 = 7.929	(311) allowed	1	7.929
5	{331}	24	19	26.297 / √19 = 6.033	(331) allowed	1	6.033
6	{210}	24	5	26.297 / √5 = 11.760	(210) absent, (420) allowed	2	5.880
7	{211}	24	6	26.297 / √6 = 10.736	(211) absent, (422) allowed	2	5.368
8	{511}	24	27	26.297 / √27 = 5.061	(511) allowed	1	5.061
9	{531}	48	35	26.297 / √35 = 4.445	(531) allowed	1	4.445
10	{221}	24	9	26.297 / √9 = 8.766	(221) absent, (442) allowed	2	4.383
11	{310}	24	10	26.297 / √10 = 8.316	(310) absent, (620) allowed	2	4.158
12	{533}	24	43	26.297 / √43 = 4.010	(533) allowed	1	4.010

The 12 widest-spaced of 55 families with indices up to 6 are listed; show all 55 Every one of them is used in Step 9.

Python check (`code/morphology/run_cif_to_shape.py`): the widest families and d_{eff}: {111} 15.183, {100} 13.149, {110} 9.297, {311} 7.929, {331} 6.033, {210} 5.880 Å.

8 How Far Out Each Face Sits: the BFDH Rule

IN PLAIN WORDS

A face made of widely spaced planes is densely packed with atoms and is flat at the molecular scale, so new material sticks to it slowly. A slow face moves outward slowly and stays large on the finished crystal, while fast faces grow themselves out of existence. The simplest version of this idea says that each face's distance from the centre is inversely proportional to its effective spacing.

THE RULE

BFDH rule (Bravais 1866, Friedel 1907, Donnay and Harker 1937): the distance of face family f from the centre is $R_f \propto 1/d_{eff,f}$. Scale it so the widest-spaced family is at distance 1: $R_f = d_{eff,max} / d_{eff,f}$. Only ratios of distances matter, because the shape does not depend on its size.

WITH THIS FILE'S NUMBERS

The widest spacing is $d_{eff,max}$ = 15.183 Å, for {111}. Dividing by it puts that family at distance 1:

Family	$d_{\mathrm{eff,max}}$ / d_{eff}	R_f	Exact value
{111}	**15.183 / 15.183**	**1.0000**	1
{100}	**15.183 / 13.149**	**1.1547**	2/√3
{110}	**15.183 / 9.297**	**1.6330**	2√2/√3
{311}	**15.183 / 7.929**	**1.9149**	√11/√3
{331}	**15.183 / 6.033**	**2.5166**	√19/√3
{210}	**15.183 / 5.880**	**2.5820**	2√5/√3
{211}	**15.183 / 5.368**	**2.8284**	2√2
{511}	**15.183 / 5.061**	**3.0000**	3

The exact values follow because every d_{eff} is $a/(n\sqrt{(h^2+k^2+l^2)})$: the cell edge a cancels, so R_f^2 is a ratio of whole numbers, $R_f^2 = n_f^2(h^2+k^2+l^2)_f \,/\, n_0^2(h^2+k^2+l^2)_0$. So the BFDH shape depends only on the centring and the point group, not on the size of the cell or on the atoms.

Python check (`code/morphology/run_cif_to_shape.py`): BFDH distances {111} 1.0000, {100} 1.1547, {110} 1.6330, {311} 1.9148.

9 Building the Shape, Plane by Plane

IN PLAIN WORDS


Every member of every family becomes a flat wall at its distance R from the centre, facing outward. The crystal is everything that lies inside all the walls. We build it as a sculptor would: start from a large block and cut it with one wall at a time, nearest walls first. Most walls end up outside the shape and cut nothing. The animation shows only the cuts that change it.

THE RULE

The shape is the convex polytope $P = \{\mathbf{x} : \mathbf{n}_p \cdot \mathbf{x} \le R_p$ for every plane $p\}$, with outward unit normal $\mathbf{n} = \mathbf{h}/|\mathbf{h}|$. In a cubic cell the normal of (hkl) points along (h, k, l), and the wall is the plane $hx + ky + lz = R|\mathbf{h}|$.

One cut: every face polygon is clipped to the inner side of the new plane (each edge that crosses the plane is cut at the crossing point $\mathbf{A} + (\mathbf{B} - \mathbf{A})\, s_A/(s_A - s_B)$, with $s = \mathbf{n}\cdot\mathbf{x} - R$). The crossing points, ordered around their centre, form the new face.

A corner of the shape is a point on three planes with independent normals: the 3×3 linear system $N\mathbf{x} = \mathbf{r}$, solved by Cramer's rule.



Start. The 8 planes of the nearest family, {111} at R = 1.0000, already enclose a closed shape: **octahedron**, 8 faces.

Face colours: blue {100}, red {111} (dark red: the second half {111}_ where the point group splits it), green {110}. Drag to rotate.

WITH THIS FILE'S NUMBERS

One corner of the final shape, worked by hand. It lies on the three planes

(100): $x = R|\mathbf{h}| = 1.1547 \times 1.0000 = 1.1547$

(111): $x + y + z = R|\mathbf{h}| = 1.0000 \times 1.7321 = 1.7321$

(11$\bar{1}$): $x + y - z = R|\mathbf{h}| = 1.0000 \times 1.7321 = 1.7321$

$$N = \begin{pmatrix} 1 & 0 & 0 \\ 1 & 1 & 1 \\ 1 & 1 & -1 \end{pmatrix}, \quad \mathbf{r} = \begin{pmatrix} 1.1547 \\ 1.7321 \\ 1.7321 \end{pmatrix}, \quad \det N = -2$$

$x = \det N_x / \det N = -2.3094 / -2 =$ **1.1547** (N_x is N with column 1 replaced by **r**)

$y = \det N_y / \det N = -1.1547 / -2 =$ **0.5774** (N_y is N with column 2 replaced by **r**)

$z = \det N_z / \det N = 0.0000 / -2 =$ **0.0000** (N_z is N with column 3 replaced by **r**)

So the corner is at (1.1547, 0.5774, 0.0000). It must also satisfy every other plane: of all 1730 planes, the largest value of $\mathbf{n}\cdot\mathbf{x} - R$ at this point is 0.000000 (zero or below means inside), and 3 planes pass exactly through it.

10 Which Faces Survive, and by How Much the Others Miss

IN PLAIN WORDS

For each family we compare two distances: how far out its wall sits, and how far the finished shape reaches in that direction. If the wall is farther out than the shape reaches, it never touches the crystal and that face does not appear.

THE RULE

Reach of the shape along a direction **n** (the support function): $h_P(\mathbf{n})$ = max over the corners **v** of $\mathbf{n}\cdot\mathbf{v}$. On the finished shape every wall satisfies $R_f \geq h_P(\mathbf{n}_f)$. A family carries faces when equality holds and the wall meets the shape in a polygon of positive area; it is absent when $R_f > h_P(\mathbf{n}_f)$, and the difference is the margin by which it misses. When $R_f = h_P(\mathbf{n}_f)$ but the face has zero area, the wall touches the shape only at a corner or along an edge.

WITH THIS FILE'S NUMBERS

Family	Its distance R_f	Reach of the shape $h_P(n_f)$	Result
{111}	**1.0000**	**1.0000**	**face**, 8 polygons, 77.6% of the area
{100}	**1.1547**	**1.1547**	**face**, 6 polygons, 22.4% of the area
{110}	**1.6330**	**1.2247**	misses by 0.4082
{311}	**1.9149**	**1.2185**	misses by 0.6963
{331}	**2.5166**	**1.1921**	misses by 1.3245
{210}	**2.5820**	**1.2910**	misses by 1.2910
{211}	**2.8284**	**1.1785**	misses by 1.6499
{511}	**3.0000**	**1.2222**	misses by 1.7778
{531}	**3.4157**	**1.2687**	misses by 2.1470
{221}	**3.4641**	**1.1547**	misses by 2.3094
{310}	**3.6515**	**1.2780**	misses by 2.3735
{533}	**3.7859**	**1.1446**	misses by 2.6414
{551}	**4.1231**	**1.2127**	misses by 2.9104
{320}	**4.1633**	**1.2810**	misses by 2.8823

Of the 55 families, 2 carry faces. For the other 53, the smallest gap between the plane and the shape is 0.4082.

Python check (`code/morphology/run_cif_to_shape.py`): 55 families with SciPy half-space intersection on the ten widest; the narrower 45 miss that shape by at least 2.3735.

11 Measuring and Naming the Shape

IN PLAIN WORDS


The finished shape is reduced to a few numbers: how much of its surface each family covers, its volume, and how close it is to a sphere. The name follows from which families are present and from the outline of their faces.

THE RULE

Area of a face with corners $\mathbf{v}_1, \ldots, \mathbf{v}_m$ in order: $A = \tfrac{1}{2}\,|\Sigma_{t=2}^{m-1}\,(\mathbf{v}_t - \mathbf{v}_1) \times (\mathbf{v}_{t+1} - \mathbf{v}_1)|$.

Volume: the shape is a union of pyramids from the centre to each face, of height R_f, so $V = \tfrac{1}{3}\,\Sigma_f\, R_f\, A_f$.

Sphericity: $\Psi = \pi^{1/3}\,(6V)^{2/3} / A$, the area of the sphere of the same volume divided by the actual area (1 for a sphere).



The finished BFDH shape for this file, with Miller indices on the front faces. Drag to rotate.

WITH THIS FILE'S NUMBERS

A {111} face, (111), is a polygon with 6 corners:

> $\mathbf{v}_1$ = (0.0000, 1.1547, 0.5774)
>
> $\mathbf{v}_2$ = (0.0000, 0.5774, 1.1547)
>
> $\mathbf{v}_3$ = (0.5774, 0.0000, 1.1547)
>
> $\mathbf{v}_4$ = (1.1547, 0.0000, 0.5774)
>
> $\mathbf{v}_5$ = (1.1547, 0.5774, 0.0000)
>
> $\mathbf{v}_6$ = (0.5774, 1.1547, 0.0000)
>
> Area = ½|Σ_t ($\mathbf{v}_t$ − $\mathbf{v}_1$) × ($\mathbf{v}_{t+1}$ − $\mathbf{v}_1$)| = ½|(2.0000, 2.0000, 2.0000)| = **1.7321**, and 8 such faces give 13.8564.

A {100} face, (100), is a polygon with 4 corners:

> $\mathbf{v}_1$ = (1.1547, 0.5774, 0.0000)
>
> $\mathbf{v}_2$ = (1.1547, 0.0000, 0.5774)
>
> $\mathbf{v}_3$ = (1.1547, −0.5774, 0.0000)
>
> $\mathbf{v}_4$ = (1.1547, 0.0000, −0.5774)
>
> Area = ½|Σ_t ($\mathbf{v}_t$ − $\mathbf{v}_1$) × ($\mathbf{v}_{t+1}$ − $\mathbf{v}_1$)| = ½|(1.3333, 0.0000, 0.0000)| = **0.6667**, and 6 such faces give 4.0000.

> Total area A = 13.8564 + 4.0000 = **17.8564**; area fractions {111} 0.7760, {100} 0.2240.
>
> Volume V = ⅓ $\Sigma_f R_f A_f$ (a pyramid from the centre to each face) = ⅓ × 1.0000 × 13.8564 + ⅓ × 1.1547 × 4.0000 = **6.1584**
>
> Sphericity $\Psi = \pi^{1/3}(6V)^{2/3}/A$ = 1.4646 × $(6 \times 6.1584)^{2/3}$ / 17.8564 = **0.9099** (a sphere has 1, a cube 0.806).
>
> Counts: 14 faces, 24 corners, 36 edges (Euler: $F + V - E = 2$).

Name: **truncated octahedron**. Only {100} and {111} faces are present. The {111} faces are hexagons, so the corners of an **octahedron** have been cut off by small {100} squares. A closed-form check by hand: with $R_{100}/R_{111} = 2/\sqrt{3}$ every edge has the same length, e = 0.8165, so this is the regular (Archimedean) truncated octahedron. Its six squares have area $6e^2$ and its eight hexagons $8 \times (3\sqrt{3}/2)e^2 = 12\sqrt{3}\,e^2$, so the {100} fraction is $6/(6 + 12\sqrt{3})$ = 0.2240 and the total area is $(6 + 12\sqrt{3}) \times 0.6667$ = 17.8564, the same as the sums above. Its volume is $8\sqrt{2}\,e^3$ = 6.1584.

Python check (`code/morphology/run_cif_to_shape.py`): truncated octahedron, 14 faces, 24 corners, Ψ = 0.9099, area fractions {100} 0.2240, {111} 0.7760.

12 Beyond BFDH: Every Shape a Cubic Crystal Can Take

IN PLAIN WORDS


BFDH fixes one set of distances from the geometry alone. Real growth conditions (solvent, temperature, added modulators) change how fast each face grows, which moves the distances. For a cubic crystal bounded by {100}, {110} and {111}, two ratios decide the shape completely, so all possible shapes fit on one map. Click or drag on the map to see the shape at any point. The diamond marks where BFDH puts this file.


THE RULE

Set $R_{100} = 1$, $x = R_{110}/R_{100}$, $y = R_{111}/R_{100}$. Each boundary follows from the reach of one simple shape (Step 10):

- **Cube** (six {100} walls at 1, corners (±1, ±1, ±1)): its reach along (111)/√3 is 3/√3 = √3, and along (110)/√2 it is 2/√2 = √2. No other face cuts it when $y \geq \sqrt{3}$ and $x \geq \sqrt{2}$.
- **Octahedron** (eight {111} walls at y, corners ($\pm\sqrt{3}\,y$, 0, 0) and permutations): its reach along (100) is $\sqrt{3}\,y$, and along (110)/√2 it reaches the edge midpoint ($\sqrt{3}y/2$, $\sqrt{3}y/2$, 0), which gives $\sqrt{(3/2)}\,y$. It is pure when $y \leq 1/\sqrt{3}$ and $x \geq \sqrt{(3/2)}\,y$.
- **Rhombic dodecahedron** (twelve {110} walls at x, corners ($\pm\sqrt{2}\,x$, 0, 0) and $(\pm x/\sqrt{2})(1, 1, 1)$): its reach along (100) is $\sqrt{2}\,x$ and along (111)/√3 it is $\sqrt{(3/2)}\,x$. It is pure when $x \leq 1/\sqrt{2}$ and $y \geq \sqrt{(3/2)}\,x$.
- **Cuboctahedron**: the {111} triangles and {100} squares share corners at (1, 1, 0), where (1,1,1)·(1,1,0)/√3 = 2/√3. So it occurs only on the line $y = 2/\sqrt{3}$, and only for $x \geq \sqrt{2}$. Above the line the shape is a truncated cube, below it a truncated octahedron.

The map is coloured by the area fraction of each family (blue {100}, red {111}, green {110}); the black lines are the exact boundaries above. It treats the two halves of {111} as equal. The tetrahedral shapes that -43m allows when they differ are on the Morphology page.





x = 1.414, y = 0.866: **truncated octahedron**; area {100} 0.224, {110} 0.000, {111} 0.776.

13 What This Shows, and What It Does Not

- **Steps 1 to 7 are exact crystallography of the file.** The cell, the cubic lattice, the centring, the point group, the space group and the effective spacings follow from the numbers in the CIF, and for the four bundled files they agree with spglib.
- **Step 8 is a rule, not a physical model of growth.** BFDH ignores the chemistry of the faces, the solvent, the temperature and any modulator. Step 8 also shows that the BFDH shape depends only on the centring and the point group, so MOF-5, HKUST-1 and UiO-66, all face-centred cubic, receive the same truncated octahedron. Laboratories grow these three MOFs in different shapes, so BFDH cannot by itself tell them apart. How the project's other models (graph attachment numbers, force-field and CHGNet surface energies) move each MOF to a different point of the map in Step 12, and how those points compare with laboratory crystals, is on the Morphology, Surface Energy and Experiment pages.
- **Only equilibrium-like shapes are produced.** Every shape here is a convex polytope with flat faces. Rods, plates and spheres grown under kinetic control or with additives that block particular faces are not produced by this construction.
- **Cubic crystals only.** A file whose lattice is not cubic stops at Step 3 with a message. The Python package handles any lattice, and the Cell Deform page uses it on stretched cells.

> **Where every number comes from**

> Browser: `website/mof_cif_shape.js` (all steps) and `website/cif_shape_page.js` (this page), with `website/mof_morphology.js` for the shape descriptors and names. Python reference: `code/morphology/run_cif_to_shape.py`, which writes `code/morphology/results/cif_to_shape.json`; `website/_build/build_cif_shape_data.py` copies the Python numbers into `website/cif_shape_data.js`. Check: `website/tests/test_cif_to_shape.js`.
