

Structural Descriptors for Metal–Organic Frameworks: Multifractal Analysis of Framework Connectivity for Simulation-Free Screening

23CSE498 – Project Phase 2 (Panel Review 1) | Team Number: [XX]

S.No	Register Number	Student Name
1	CB.SC.U4CSE23134	P. M. Radha Krishna
2	CB.SC.U4CSE23122	P. Kshitij Varma
3	CB.SC.U4CSE23141	G. Rohith Abhinav
4	CB.SC.U4CSE23031	J. Keerthi Sree
5	CB.SC.U4CSE23029	Isha Sri Prakash

Guide: **Dr. T. Ramraj**, M.E, Ph.D — Assistant Professor (Sl. Gd.),
Department of Computer Science and Engineering, School of Computing, Coimbatore

September 7, 2026

0. Problem Context — Why This Project Exists

The gap between the number of candidate materials and our ability to evaluate them

The materials-science problem

- **Metal–organic frameworks (MOFs)** are crystalline solids built by joining metal clusters (*nodes*) to organic molecules (*linkers*).
- They are extremely porous — internal surface areas above 3,000 m²/g — making them candidates for gas storage, carbon capture and separation.
- **Hundreds of thousands** of MOFs are known or hypothesised.

The computational bottleneck

- Evaluating one MOF by molecular simulation (GCMC) takes **hours**.
- Exhaustive screening of the design space is **not feasible**.

Research Question

Can a **purely structural, simulation-free descriptor** — computed from a framework's *connectivity* in seconds — group MOFs into meaningful families, so a new candidate can be triaged **without** expensive calculation?

Value Proposition

Not a *replacement* for simulation — a **filter** that decides **what to simulate**. Reducing 10⁵ candidates to 10² is the contribution.

1. Methodology & Solution Design


Rubric: Workflow, Architecture, Algorithms/Mathematical Model & Evaluation Metrics (5 Marks)

Theoretical foundation. A MOF is a **periodic graph**. Collapse each building block to a vertex and each inter-block bond to an edge; the chemistry reduces to pure connectivity, which the properties follow.

Core algorithms

- **Decomposition:** MOFid metal-oxo algorithm [1] — PBC-aware bond perception, connected-component block extraction.
- **Graph construction:** *labelled quotient graph* — edges carry a lattice translation t , so the infinite crystal is represented exactly.
- **Descriptor:** influential-node multifractal analysis (iNMFA) [2].

Dataset. 77 frameworks queried live from MOFX-DB [7], with published PLD/LCD pore diameters. Supercells of 3,400–6,100 atoms.



Validation metric: published coordination numbers — an independent ground truth the graph must reproduce.

1b. Mathematical Model

The descriptor, defined

Step 1 — the measure. For each influential node i (top 10% by degree) and box radius r , let $M_i(r)$ be the number of vertices within r steps:

$$p_i(r) = M_i(r)/N$$

Step 2 — the partition function, reweighted by a distortion factor q :

$$\mathcal{P}_q(r) = \sum_{i \in I} p_i(r)^q$$

Step 3 — the mass exponent.

$$\tau(q) = \frac{\ln \mathcal{P}_q(r)}{\ln(r/r_N)}$$

Step 4 — Legendre transform.

$$\alpha(q) = \frac{d\tau}{dq}, \quad f(\alpha) = q\alpha(q) - \tau(q)$$

Interpreting the spectrum

Quantity	Physical meaning
α	local growth rate around one block
$f(\alpha)$	how much of the framework shares it
α_0	the <i>typical</i> dimension (apex)
$\Delta\alpha$	heterogeneity of the pore network
A	asymmetry — dense-vs-open dominance

Structural constraint used as a correctness test

$f(\alpha)$ must be an inverted parabola peaking at $q = 0$, where $f(\alpha_0) = D_0$. Any implementation not producing this shape is wrong — we used it as a test, and it caught a real defect (Slide 3).

Evaluation metrics: coordination-number agreement with published crystallography; spectrum shape (% peaking at $q = 0$); seed reproducibility; partial correlation against pore diameter.

2. Implementation Progress & Module Functionality

Rubric: Core Modules Implemented, Functional & Integrated (8 Marks)

Module / Component	Current Implementation State	Status
Data ingestion (code_01-02)	ClF parsing, symmetry expansion, PBC bond perception over 27 cell images	Functional
Decomposition (code_03-04)	is_metal() classification; metal-oxo, single-node, all-node splits	Functional
Topology export (code_05-07)	Centroid simplification, Systre .cgd writer, MOFid/MOFkey assembly	Functional
Network analysis (code_09)	Labelled quotient graph, degree/eigenvector/ betweenness centrality, Laplacian	Functional
Spectrum (code_10-11)	iNMFA (box-covering) and NMFA (box-growing); τ , α , $f(\alpha)$, $\Delta\alpha$, A	Functional
77-framework study	Live MOFX-DB query, spectra for all 77, band + confound analysis	Functional
Interactive web platform	9-page documentation portal; full pipeline runs live in-browser on any uploaded ClF; 5 headless test suites gate publication	Integrated
Size-matched comparison	61 synthesised MOFs expanded under the identical 48 Å rule and compared against the 77	Functional
Dataset release	138 frameworks, CC BY 4.0, with schema, provenance and both withdrawn claims documented	Functional
Experimental-set validation at scale	Done: 61 CoRE MOF frameworks via Zenodo DOI, no API dependency	Functional

Two axes, because “built” and “established” are different claims. Engineering $\approx 96\%$: 14 Python modules, an independent browser implementation that cross-checks them, a 10-page platform, 6 Cl-gating test suites, the 138-framework study end to end, a released dataset. Validation $\approx 73\%$: the descriptor is provably correct, its failure modes are documented, and it now transfers to experimentally synthesised structures — 61 of them, size-matched. Not established: that $\Delta\alpha$ predicts any measured property. The two engines are also not yet reconciled at supercell size. Weighted $\approx 85\%$ (rubric asks $\approx 60\%$). Verification: Python and JavaScript agree at unit-cell size ($\tau(0) = -2.6551$, HKUST-1).

2b. Results Obtained So Far

Every number computed from the live pipeline — nothing transcribed

Validation — the graph is correct

	Node c.n.	Published	Net
HKUST-1	4	(4, 3)	tbo
MOF-5	6	(6, 2)	pcu
ZIF-8	4	(4, 2)	sod
UiO-66	12	(12, 2)	fcu

All four match. A naive construction gives UiO-66 = 1.

Defects make influence measurable

In a perfect crystal every block is symmetry-equivalent $\Rightarrow$ only 2 distinct centrality values $\Rightarrow$ “top- k ” is a **tie**. Remove one linker: $2 \rightarrow 4$ distinct values, and $\lambda_2 : 1.44 \rightarrow 1.19$ — the weakening, quantified.

The band — and it transfers to real MOFs

	Hypothetical 77 hMOF	Synthesised 61 CoRE MOF
Valid spectra	77 / 77	61 / 61
$\Delta\alpha$ range	1.02 – 1.41	0.95 – 1.47
Mean $\Delta\alpha$	1.180	1.198
Mean asymmetry A	–1.31	–1.31

Means differ by **0.018** (Welch $p = 0.38$). Same band, same shape — calibrated on generated structures, valid on ones that exist.

What the band does *not* yet mean

$\Delta\alpha$ vs pore diameter, raw	–0.497
controlling for graph size	+0.101
$\Delta\alpha$ vs graph size, ctrl. pore	+0.621

R^2 : size alone / +pore 0.533 / 0.538

3. Technical Knowledge & Design Decisions

Rubric: Understanding of Methodology, Implementation & Design Choices (5 Marks)

Why a graph representation? MOF properties follow *connectivity*: gas moves through the pore network, and the pore network is the void left by the wiring. An **unweighted** graph deliberately discards element identity — what survives is **pure architecture**, which transfers across chemistries.

Key design decisions

- **Labelled quotient graph over a naive graph.** Without translation labels, UiO-66's 12-connected cluster reports as **1** — or degenerates into a star.
- **Supercell expansion.** A primitive cell has diameter ~ 2 , too small for a power-law fit. Expansion is *exact* because edges carry translations.
- **Box-growing (deterministic) validated against box-covering (stochastic).**
- **Defect simulation** to break symmetry — physically justified by [15].

Defect found by our own shape test

The spectra were not parabolic. Cause: $\tau(q)$ was extracted with a **free-intercept** least-squares slope, but [2] defines it as a **ratio** $\ln \mathcal{P}_q / \ln(r/r_N)$ — a fit **through the origin**. At $q = 0$: every term is $p_i^0 = 1$, so $\mathcal{P}_0 = |I|$ is **constant in r** . A flat line has slope $0 \Rightarrow \tau(0) = 0 \Rightarrow f(\alpha_0) = 0$ — **the peak is deleted**.

τ definition	$\tau(0)$	$f(\alpha_0)$	parabola
free intercept	0.0000	0.0000	no
paper (ratio)	-2.5669	+2.5669	yes

Trade-offs. MIN_CELL_LENGTH/MAX_ATOMS trade scaling range against $O(N^2)$ memory — and are the source of the size confound we identified.

Influential-node selection is ambiguous in a perfect crystal (all degrees tie); we report the ambiguity rather than hide it.

3b. Deliverable — Interactive Analysis Platform

An 18-section technical site; the full pipeline executes in-browser

What it does


- Runs the **complete decomposition live** on any uploaded `.cif` — no server, no installation.
- Steps through all nine pipeline modules with the **real source code beside a live 3D model** of the structure at that stage.
- Computes the network analysis and the multifractal spectrum **in the browser**, cross-validated against the Python reference.

Built for a mixed audience

- A **graph-theory primer** (Section 10) defines every term — vertex, degree, quotient graph, Laplacian, λ_2 , defect — *before* it is used.
- Every source file is readable by clicking its name anywhere on the page.
- Automated test suites cover the decomposition, the network layer, the band analysis and the site structure itself.

3c. Principal Result — All 77 Spectra and the Band


Computed live from the pipeline; nothing transcribed



(a) all 77 spectra are proper inverted parabolas, $q = 0$ at the apex (b) a tight band, $\Delta\alpha = 1.11\text{--}1.25$ (c–e) the apparent pore correlation (-0.50) collapses to $+0.10$ controlling for graph size; size survives at $+0.62$.

3d. Does It Transfer? 61 Frameworks That Actually Exist

The band was calibrated on structures nobody has ever made



(a) 61 synthesised frameworks land *on* the hypothetical band: 0.95–1.47 vs 1.02–1.41, means differing by 0.018 (Welch $p = 0.38$). (b) **We withdrew our own result to get [here](#)**. The four MOFs we previously reported at 1.66–2.26 are the gold diamonds — 256–972 atoms, off the size range of both clouds. $\Delta\alpha$ rises with atom count ($r = +0.73$), so that comparison measured graph size. (c) Same centre; the real set is significantly **more** variable (Levene $p = 0.010$).

4. Technical Enrichment Activity Choices

Professional Online Certification Details (Individual Mandatory: 10–20 Hours)

S.No	Student Name	Chosen MOOC / Course Title	Platform	Hours
1	P. M. Radha Krishna	Algorithms on Graphs (BFS, shortest paths, connected components)	Coursera (UC San Diego)	20 Hrs
2	P. Kshitij Varma	Introduction to Complex Network Analysis	NPTEL	20 Hrs
3	G. Rohith Abhinav	Chemoinformatics / Computational Materials Science	NPTEL	16 Hrs
4	J. Keerthi Sree	Data Visualization with Python	Coursera (IBM)	15 Hrs
5	Isha Sri Prakash	Machine Learning for Materials Informatics	edX / Coursera	15 Hrs

Rationale for these selections. Each maps to a component this project actually uses: **network analysis** (the graph representation and centrality measures), **complex networks** (fractal and multifractal characterisation), **chemoinformatics** (CIF handling, bond perception, MOF structure), **data visualisation** (the interactive platform), and **materials informatics** (descriptor-based screening — the project's stated goal).

Requirement: each student completes one approved 10–20 hour certification from a recognised platform relevant to the project.

5. Remaining Work & Timeline

Concrete engineering tasks, not open research questions

Priority 1 — 61 synthesised frameworks

done

- Structures now come from the **Zenodo archive** of CoRE MOF 2019 (DOI 10.5281/zenodo.3370236), not a live API — an immutable record is a stronger provenance guarantee than any query.
- It settled the question and settled it **against our own earlier claim**: the two bands coincide.

Priority 2 — Confirm the size control at scale

confirmed

- The partial-correlation check reproduces on real data: pore-size correlation $-0.20 \rightarrow +0.10$ once graph size is held constant.
- It also exposed the flaw in our four-structure comparison — see right.

Priority 3 — Validate against measured properties

blocking

- This is the only substantive item left. $\Delta\alpha$ is reproducible, size-controlled and transferable, and still not shown to predict any property a chemist would ask for.
- Regress against measured adsorption on this same 61-structure set

now

Position of the work

The **machinery is complete and verified**: the decomposition, the periodic graph, the centrality analysis and the spectrum all work, are cross-validated across two implementations, and reproduce published crystallography.

New: 61 *synthesised* CoRE MOF frameworks land *on* the hypothetical band, not beside it —

$\Delta\alpha = 0.95\text{--}1.47$ vs $1.02\text{--}1.41$; means differ by 0.018 (Welch $p = 0.38$), mean asymmetry -1.31 in both.

The descriptor **transfers** from generated structures to real ones.

We withdrew our own headline result

Our previous claim — four synthesised MOFs at $\Delta\alpha = 1.66\text{--}2.26$, “clear of the hMOF band, no overlap” — is **withdrawn**. Those four were expanded to 256–972 atoms while the 77 hMOFs occupy 3024–6592: not one hMOF is as small as the largest of the four. Since $\Delta\alpha$ rises with atom count

References (1 of 2)

Every entry is a source the project actually uses

- [1] B. J. Bucior *et al.*, "Identification Schemes for Metal–Organic Frameworks to Enable Rapid Search and Cheminformatics Analysis," *Cryst. Growth Des.*, 19(11), 6682–6697, 2019. [the decomposition we visualise](#)
- [2] J. Xiao, B. Wang, X. Li, "Deciphering the Generating Rules and Functionalities of Complex Networks," *Sci. Rep.*, 11, 22964, 2021. [the method we implement](#)
- [3] C. Song, S. Havlin, H. A. Makse, "Self-Similarity of Complex Networks," *Nature*, 433, 392–395, 2005.
- [4] O. Delgado-Friedrichs, M. O'Keeffe, "Identification of and Symmetry Computation for Crystal Nets," *Acta Cryst. A*, 59(4), 351–360, 2003. (Systre)
- [5] M. O'Keeffe *et al.*, "The Reticular Chemistry Structure Resource (RCSR)," *Acc. Chem. Res.*, 41(12), 1782–1789, 2008. (net symbols)
- [6] M. Eddaoudi *et al.*, "Modular Chemistry: Secondary Building Units. . .," *Acc. Chem. Res.*, 34(4), 319–330, 2001. (the SBU concept)
- [7] N. S. Bobbitt, J. Chen, R. Q. Snurr, "MOFX-DB," *J. Chem. Eng. Data*, 68(2), 483–498, 2023. [our data source](#)
- [8] C. E. Wilmer *et al.*, "Large-Scale Screening of Hypothetical MOFs," *Nature Chem.*, 4(2), 83–89, 2012. [our 77 are hMOF = hypothetical](#)
- [9] Y. G. Chung *et al.*, "CoRE MOF 2019," *J. Chem. Eng. Data*, 64(12), 5985–5998, 2019. [the set we still need](#)
- [10] B. Cordero *et al.*, "Covalent Radii Revisited," *Dalton Trans.*, 2832–2838, 2008. (bond-perception cutoffs)

References (2 of 2)

- S. S.-Y. Chui *et al.*, *Science*, 283, 1148–1150, 1999. (HKUST-1 — test structure)
- H. Li, M. Eddaoudi, M. O’Keeffe, O. M. Yaghi, *Nature*, 402, 276–279, 1999. (MOF-5 / IRMOF-1)
- K. S. Park *et al.*, *PNAS*, 103(27), 10186–10191, 2006. (ZIF-8 — our chemical control)
- J. H. Cavka *et al.*, *JACS*, 130(42), 13850–13851, 2008. UiO-66 — the 12-connected test
- G. C. Shearer *et al.*, “Defect Engineering: Tuning the Porosity and Composition of UiO-66,” *Chem. Mater.*, 28(11), 3749–3761, 2016. defects are real chemistry
- M. Fiedler, “Algebraic Connectivity of Graphs,” *Czech. Math. J.*, 23(2), 298–305, 1973. (λ_2)
- U. Brandes, “A Faster Algorithm for Betweenness Centrality,” *J. Math. Sociol.*, 25(2), 163–177, 2001.
- A. H. Larsen *et al.*, “The Atomic Simulation Environment,” *J. Phys. Condens. Matter*, 29(27), 273002, 2017. (ASE)
- A. A. Hagberg, D. A. Schult, P. J. Swart, “Exploring Network Structure... using NetworkX,” *SciPy2008*, 11–15. (NetworkX)

Full annotated list — what each reference is *for* — in 6_references/README.md.

Thank You

Interactive platform, source code and full documentation:
github.com/Radha-Krishna-19/fyp