

CARACTERISTQUES TECHNIQUES / ANALYSES SPECTRALES. ALUMINIUM

Alloy	Al_000	Mode	Element Concentration					15.02.2024 18:22:46
	Al [%]	Si [%]	Fe [%]	Cu [%]	Mn [%]	Mg [%]	Zn [%]	
1	96.30	0.5428	0.6502	1.543	0.0039	0.1038	0.6843	
2	96.64	0.5734	0.5780	1.369	0.0042	0.1109	0.5476	
3	96.19	0.5777	0.6917	1.659	0.0042	0.0564	0.6803	
4	96.50	0.6102	0.5275	1.481	0.0040	0.1146	0.5782	
Ø	96.41	0.5760	0.6118	1.513	0.0041	0.0964	0.6226	
	Cr [%]	Ni [%]	Ti [%]	Be [%]	Ca [%]	Li [%]	Pb [%]	
1	0.0011	0.0054	0.0148	<0.0001	>0.0250	<0.0001	0.0489	
2	0.0021	0.0056	0.0180	<0.0001	>0.0250	<0.0001	0.0395	
3	0.0016	0.0053	0.0086	<0.0001	0.0106	<0.0001	0.0472	
4	0.0024	0.0070	0.0179	<0.0001	>0.0250	<0.0001	0.0427	
Ø	0.0018	0.0058	0.0148	<0.0001	0.0214	<0.0001	0.0446	
	Sn [%]	Sr [%]	V [%]	Na [%]	Bi [%]	Zr [%]	B [%]	
1	0.0015	0.0008	0.0061	0.0106	<0.0005	0.0036	0.0035	
2	0.0013	0.0016	0.0074	0.0175	<0.0005	0.0038	0.0041	
3	0.0015	0.0004	0.0048	0.0106	<0.0005	0.0034	0.0019	
4	0.0012	0.0016	0.0069	0.0173	<0.0005	0.0033	0.0073	
Ø	0.0014	0.0011	0.0063	0.0140	<0.0005	0.0035	0.0042	
	Ga [%]	Cd [%]	Co [%]	Ag [%]	Hg [%]	In [%]	Sb [%]	
1	0.0199	<0.0002	0.0012	0.0002	<0.0005	0.0005	0.0132	
2	0.0176	<0.0002	0.0015	0.0002	<0.0005	0.0030	0.0127	
3	0.0186	<0.0002	0.0009	0.0002	<0.0005	0.0009	0.0155	
4	0.0169	<0.0002	0.0010	0.0002	<0.0005	0.0001	0.0141	
Ø	0.0182	<0.0002	0.0012	0.0002	<0.0005	0.0011	0.0139	
	P [%]	As [%]	Ce [%]	La [%]	Mo [%]	Sc [%]	Ba [%]	
1	0.0022	0.0064	0.0014	0.0006	0.0011	0.0003	0.0004	
2	0.0043	0.0065	0.0015	0.0014	0.0016	0.0004	0.0006	
3	0.0029	0.0048	0.0019	0.0001	0.0009	0.0003	0.0003	
4	0.0049	0.0055	0.0024	0.0008	0.0010	0.0004	0.0005	
Ø	0.0036	0.0058	0.0018	0.0007	0.0011	0.0004	0.0004	
	Tl [%]							

- مؤسسة ذات الشخص الوحيد و المسؤولية المحدودة - سامي بيزنس - Eurl SAMY BUSINESS

قطعة 108 - ع 06A ، رقم 01 - سعيد حمدين - بنر مراد رايس 10678 - ولاية بجاية

Capital 250.000.000,00 DA | RC: 07B0977512-00/16 | NIF: 000716097751278 | Art. 16098906013 | NIS: 000716090133849.