ORAGUARD® 293F

Laminating Film

Short description

Ultra flexible, transparent Premium Cast PVC Film with highly effective UV protection. Surface glossy.

Front material

Cast PVC film, cast film, 0.03 mm

Liner

PET film, single-side silicone coated, 0.036 mm

Adhesive

Solvent-polyacrylate, permanent, Transparent, 0.028 mm

Technical properties

RESISTANCE

Durability	with vertical outdoor exposure, normal Central European climate 8 Year(s)	
Shelf Life	2 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Resistance to solvents and chemicals	Water, Weak acids, Salts and alkalis, Isopropyl alcohol, Washing suds (0.5 % household cleaner)	At room temperature
Maximum shrinkage	Maximum shrinkage along 0.1 mm Maximum shrinkage across 0.1 mm	bonded to steel | FINAT TM 14
Elongation at break	Minimum elongation at break along 120 % Minimum elongation at break across 120 %	DIN EN ISO 527
Tensile strength	Minimum tensile strength along 19 N/mm^2 Minimum tensile strength across 19 N/mm^2	DIN EN ISO 527
Temperature resistance	Minimum temperature -40 °C Maximum temperature 60 °C	Short-term exposure up to 80 °C

ORAFOL Europe GmbH
Orafolstrasse 1
D-16515 Oranienburg
Germany

Tel: +49 (0)3301 864-0
graphic.solutions@orafol.de
www.orafol.com

ORAGUARD® 293F

Laminating Film

ADHESIVE PROPERTIES

Adhesive power	12 N/25 mm	after 24 h, on stainless steel | FINAT TM 1, average value

PROCESSING

Application temperature	Minimum temperature 10 °C

PRODUCT NOTE

Due to the diversity of prints and printing techniques, the user should test the suitability of ORAGUARD® laminating films for the specific print purpose, prior to use. Furthermore the application information published by ORAFOL must be followed. number of print images to be protected and the different printing methods used to produce them, it is essential for the processor to check the suitability of ORAGUARD® protective laminates for the respective print image.

IMPORTANT NOTES

All ORAGUARD® products are subject to careful quality control during the entire manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORAGUARD® products is based on research results which the company believes to be reliable, but which do not constitute a guarantee. Due to the wide variety of uses of ORAGUARD® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice.

ORAFOL Europe GmbH
Orafolstrasse 1
D-16515 Oranienburg
Germany

Tel: +49 (0)3301 864-0
graphic.solutions@orafol.de
www.orafol.com