ORAJET®3440 E

Technical Datasheet

Description

Soft PVC film, available in white with a glossy or matt surface or transparent with a glossy or matt surface

Release Paper

One side PE & Silicon coated Paper, 140 g/m²

Adhesive

Permanent, Transparent

Features

1. Stable ink absorption, bright colors, vivid images.
2. Good dimensional stability after application.
3. Easy application to a wide variety of substrates.

Applications

1. Applicable to Vehicle Wrapping Media, Glass curtain, indoor and outdoor graphics.
2. Suitable for various solvent ink, Eco-solvent ink and UV ink.

Technical Data

Testing condition: Indoor temperature 23±2°C;Relative humidity 50±5%;Use aluminum, glass, steel plate as the base material for testing.

Test Items	Units	Test method	Average value
Thickness PVC*(Without paper and adhesive)	80 Micron	GB/T6672-2001	80±10
Weight-Liner			
Weight -finished product	g/m²	GB4669-1995	140±10
Gloss Rate 60°	g/m²	GB4669-1995	270±20
Initial Adhesion	%	GB8807-88	≤20
24h, 180°peel	N/25mm	FTM 9	≥7
Dimensional stability MD	N/25mm	FTM 1	≥9
Dimensional stability CD	mm	FTM 14	≤1.2
Tensile strength MD	mm	FTM 14	≤1.0
Tensile strength CD	N/25 mm	GB/T1040.1-2006	≥40
Construction Temperature	N/25 mm	GB/T1040.1-2006	≥35
Applicable Temperature	°C		20±10°C
Shelf life**	°C		-20 ~ +70
Service life		1 Year	
(Under Vertical Outdoor Exposer)		1 Year	

Note

All ORAFOL products always need to be stored in the original packaging and with the original protection materials, preferably stored hermetically, not more than 4 layers if stored horizontally. Do not be exposed to direct sunlight or heat sources. Shelf life will be one year with a temperature of 25°C±5°C and relative humidity of 50±15%. After printing, the ink must be allowed to thoroughly dry, in order to avoid any issues when later combined with the laminate. Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of the selected lacquers and paints should be tested by the user, prior to the application of the material. Furthermore, the application information published by ORAFOL is to be considered.

One year shelf life: stored in suitable conditions, preferably use within six months.

IMPORTANT NOTICE

All ORAJET® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORAJET® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORAJET® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

ORAJET® is a registered trademark of ORAFOL Europe GmbH.