



## WB67M MIG WELDING WIRE

|                                              |                                                                                                                                                                                                                                            |         |      |         |      |                   |      |          |      |      |
|----------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------|------|---------|------|-------------------|------|----------|------|------|
| Classifications                              | AWS A5.7: ERCuNi      BS EN ISO 24373: SCu 7158                                                                                                                                                                                            |         |      |         |      |                   |      |          |      |      |
| Product Description                          | Copper-Nickel, solid MIG wire.                                                                                                                                                                                                             |         |      |         |      |                   |      |          |      |      |
| Applications                                 | WB67M is suitable for the repair and welding of CN103-CN107, CA 715UNS C71500 and similar cupronickel alloys.<br><br>Used extensively for offshore pipe and cladding systems, desalination plants and similar applications / environments. |         |      |         |      |                   |      |          |      |      |
| Wire Composition (Wt. %)                     |                                                                                                                                                                                                                                            |         |      |         |      |                   |      |          |      |      |
| min.                                         | Cu bal.                                                                                                                                                                                                                                    | Ni 29.0 | Mn - | Ti 0.20 | Al - | Fe 0.40           | Si - | Pb -     | P -  | S -  |
| max.                                         | -                                                                                                                                                                                                                                          | 32.0    | 1.0  | 0.50    | 0.03 | 0.70              | 0.25 | 0.02     | 0.02 | 0.01 |
| Typical All-Weld Metal Mechanical Properties | Ultimate Tensile Strength                                                                                                                                                                                                                  |         |      |         |      | N/mm <sup>2</sup> |      | 345 Min. |      |      |
|                                              | Yield Stress/0.2% Proof Stress                                                                                                                                                                                                             |         |      |         |      | N/mm <sup>2</sup> |      | -        |      |      |
|                                              | Elongation on 5D                                                                                                                                                                                                                           |         |      |         |      | %                 |      | -        |      |      |
|                                              | Impact Energy CV @                                                                                                                                                                                                                         |         |      |         |      | Joules            |      | -        |      |      |
|                                              | As welded                                                                                                                                                                                                                                  |         |      |         |      |                   |      |          |      |      |
|                                              | Hardness Vickers                                                                                                                                                                                                                           |         |      |         |      | HV                |      | 64 - 94  |      |      |

| <b>Wire Dia. (mm)</b>                    |             | 0.6mm                                                                                                                                                                     | 0.8mm | 1.0mm | 1.2mm | 1.6mm | 2.4mm | 3.2mm |
|------------------------------------------|-------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------|-------|-------|-------|-------|-------|
| <b>Current Range (Amps)</b>              | <b>min.</b> | -                                                                                                                                                                         | 60    | 75    | 130   | -     | -     | -     |
|                                          | <b>max.</b> | -                                                                                                                                                                         | 170   | 230   | 280   | -     | -     | -     |
| <b>Volt Range (Volts)</b>                | <b>min.</b> | -                                                                                                                                                                         | 18    | 18    | 18    | -     | -     | -     |
|                                          | <b>max.</b> | -                                                                                                                                                                         | 26    | 28    | 28    | -     | -     | -     |
| <b>Packaging Information Kg Per Reel</b> |             | -                                                                                                                                                                         | 15.0  | 15.0  | 15.0  | -     | -     | -     |
| <b>Storage</b>                           |             | <b>Storage</b><br>It is recommended that the WB range of wires are stored in a dry heated store at a minimum temperature of 18°C, and a maximum relative humidity of 60%. |       |       |       |       |       |       |
| <b>Gases</b>                             |             | <b>Gas</b><br>100% Argon or 95% Argon / 5% H <sub>2</sub><br><br><b>Flow Rate</b><br>15-20 L/min                                                                          |       |       |       |       |       |       |

### Current Conditions DC+ and Welding Positions

