



WB22-9-3LM MIG WELDING WIRE

Classifications	AWS A5.9: ER2209BS EN ISO 14343-A: G 22 9 3 N L									
Product Description	Standard duplex stainless steel, solid MIG wire.									
Applications	WB22-9-3LM finds use in the fabrication and repair of offshore installations and pipework by virtue of its high strength and corrosion resistance, can be used for welding SAF2205, UR45N & AF22. WB22-9-3LM is extensively used for the repair of super duplex castings and yields excellent mechanical properties in the as-welded condition. Duplex structure of 30-50 ferrite gives a pitting resistance equivalent of >35. H2<3ppm									
Wire Composition (Wt. %)	C	Mn	Si	S	P	Cr	Ni	Mo	Cu	N
min.	-	0.5	-	-	-	21.5	7.5	2.5	-	0.10
max.	0.03	2.0	0.90	0.020	0.030	23.5	9.5	3.5	0.5	0.20
Typical All-Weld Metal Mechanical Properties	Ultimate Tensile Strength Yield Stress/0.2% Proof Stress Elongation on 5D Impact Energy CV @ -50°C As welded					N/mm²690 min. N/mm²450 min. %20 min. Joules>120				

Wire Dia. (mm)		0.6mm	0.8mm	1.0mm	1.2mm	1.6mm	2.4mm	3.2mm
Current Range (Amps)	min.	-	80	120	160	180	-	-
	max.	-	180	240	280	340	-	-
Volt Range (Volts)	min.	-	17	17	18	20	-	-
	max.	-	20	22	28	29	-	-
Packaging Information								
Kg Per Reel		-	0.7/15	15	15	15	-	-
Storage	Storage It is recommended that the WB range of wires are stored in a dry heated store at a minimum temperature of 18°C, and a maximum relative humidity of 60%.							
Gases	Gas Pure Argon or Argon + 2% O ₂				Flow Rate 15-20 L/min			

Current Conditions DC+ and Welding Positions

