



WB22-9-3LT TIG WELDING WIRE

Classifications	AWS A5.9: ER 2209BS EN ISO 14343-A: W 22 9 3 N L									
Product Description	Standard duplex stainless steel TIG wire.									
Applications	WB22-9-3LT finds use in the fabrication and repair of offshore installations and pipework by virtue of its high strength and corrosion resistance, can be used for welding SAF2205, UR45N & AF22. WB22-9-3LT is extensively used for the repair of 22Cr duplex castings and yields excellent mechanical properties in the as-welded condition. Duplex structure of 30-50 ferrite gives a pitting resistance equivalent of >35.									
Wire Composition (Wt. %)	C	Mn	Si	S	P	Cr	Ni	Mo	Cu	N
min.	-	0.5	-	-	-	21.5	7.5	2.5	-	0.10
max.	0.03	2.0	0.90	0.020	0.030	23.5	9.5	3.5	0.5	0.20
Typical All-Weld Metal Mechanical Properties	Ultimate Tensile Strength					N/mm ²	690 min.			
	Yield Stress/0.2% Proof Stress					N/mm ²	450 min.			
	Elongation on 5D					%	20 min.			
	Impact Energy CV @ -50°C					Joules	>120			
	As welded									

Wire dia. (mm)		0.6mm	0.8mm	1.0mm	1.2mm	1.6mm	2.4mm	3.2mm
Current Range (Amps)	min.	-	-	-	-	60	70	80
	max.	-	-	-	-	120	200	240
Volt Range (Volts)	min.	-	-	-	-	-	-	-
	max.	-	-	-	-	-	-	-
Packaging Information								
Kg Per Tube		-	-	-	-	5.0	5.0	5.0
Storage	Storage It is recommended that the WB range of wires are stored in a dry heated store at a minimum temperature of 18°C, and a maximum relative humidity of 60%.							
Gases	Gas Pure Argon							
	Flow Rate 12-14 L/min							

Current Conditions DC- and Welding Positions

