Analysis of Titanium Alloy in Hip Replacement – Materials and Manufacturing II

Flory L. Mendez Merida and Raphael E. Lemus Solis

[1]

***Abstract*— Titanium alloys are among the most commonly used metals in biomedical applications due to their excellent mechanical properties and corrosion resistance. In particular, Ti-6Al-4V titanium alloy is widely used in hip replacement implants due to its high strength, fatigue resistance, biocompatibility, and resistance to corrosive body environments. These properties are critical because hip implants experience cyclic loading and stress concentrations during daily activities such as walking and running. This paper explores and analyzes the structure, processing, mechanical behavior, and long-term performance of Ti-6Al-4V titanium alloy in hip replacement applications.**

***Index Terms*—Diffusion, fatigue resistance, hip implants, strengthening mechanism, Ti-6Al-4V, titanium alloy**

I. INTRODUCTION

Titanium alloys are used in biomedical applications due to their high strength, corrosion resistance, and biocompatibility. Among these, Ti-6Al-4V (Grade 5) is the most commonly used alloy for load-bearing implants such as hip replacements. It can withstand cyclic mechanical loading while remaining chemically stable in the human body, making it an ideal material for long-term implantation.

The lifecycle of Ti-6Al-4V begins deep in the Earth's crust, with the extraction of titanium from mineral ores such as ilmenite (FeTiO3) and rutile (TiO2), which occurs in Australia, South Africa, and Canada. The raw ore is refined using the energy-intensive Kroll process[2], resulting in titanium tetrachloride ($TiCl_4$), which is reduced by magnesium at high temperature under an inert argon atmosphere, producing a titanium sponge. This sponge is then crushed, mixed with aluminum (5.5-6.75 wt%) and vanadium (3.5-4.5 wt%), and vacuum arc remelted multiple times to produce a chemically homogeneous ingot. From there, the alloy is hot-worked by forging and rolling in the α + β region below the β-transus temperature (995°C), refining the grain structure and establishing the dual-phase microstructure that defines the alloy's mechanical performance. The resulting billet is precision-forged into hip implant stems, CNC-machined to tight tolerances, and surface-treated to promote osseointegration with surrounding bone tissue. After sterilization, the implant is ready for surgical implantation, where it must perform reliably under cyclic stresses of 100-400 MPa for 15 to 25 years or more. At the end of life, explanted implants are classified as biohazardous medical waste and are predominantly incinerated, with titanium recycling rates remaining low due to contamination and traceability requirements.

The performance of Ti-6Al-4V is strongly influenced by its dual-phase α + β microstructure and by strengthening mechanisms that balance strength, ductility, and fatigue resistance.

This paper examines the full cradle-to-grave lifecycle of Ti-6Al-4V in hip replacement applications, tracing the relationships between processing, microstructure, mechanical properties, failure mechanisms, and environmental considerations.

II. Extraction and Processing

Titanium does not occur in nature in a pure metallic form and must be extracted from mineral ores through a multi-stage refining process. The two primary sources are ilmenite ($FeTiO_3$) and rutile (TiO_2), which are mined through large-scale operations, including beach-sand dredging and hard-rock mining. Rutile is the preferred feedstock due to its higher titanium dioxide content, though ilmenite is more commonly used in practice.

The extracted ore is converted to usable titanium metal through the Kroll Process, which remains the dominant industrial method for titanium production. Rutile or ilmenite is first chlorinated at high temperature to produce titanium tetrachloride ($TiCl_4$), which is then purified by distillation and reduced with magnesium to produce titanium sponge. The sponge is crushed, separated from byproduct magnesium chloride ($MgCl_2$), and blended with aluminum (5.5-6.75 wt%) and vanadium (3.5-4.5wt%), along with rightly controlled levels of interstitial impurities including oxygen (max 0.2 wt%), nitrogen (max 0.05 wt%), carbon (max 0.08 wt%), and hydrogen (max 0.015 wt%). These impurities distort the titanium lattice and create local strain fields that resist dislocation motion, strengthening the alloy but reducing ductility if present in excess. The mixture is then vacuum arc remelted (VAR) multiple times to ensure chemical homogeneity throughout the ingot.

III. Manufacturing the Hip Implant

Once the Ti-6Al-4V billet has been processed to its final microstructural condition, it must be shaped into a functional

[1]Raphael E. Lemus Solis is with Tufts University, Medford, MA 02155 USA. (raphael.lemus_solis@tufts.)

,Flory L. Mendez Merida is with Tufts University, Medford, MA 02155 USA. (e-mail: flory.mendez_merida@tufts.edu)

[2] The Kroll process is the primary industrial method used to extract titanium metal from titanium tetrachloride (TiCl4) through magnesium reduction, producing porous titanium spongethese phases play.

hip implant system. It is here that Ti-6Al-4V is most commonly used due to its combination of high strength, low density, and biocompatibility.

Forging is the preferred manufacturing method for femoral stems because it produces the best mechanical properties compared to casting. During forging, the billet is pressed into a near-net shape under high compressive force, aligning the grain flow with the geometry of the implant and further refining the microstructure. This results in improved fatigue resistance and fracture toughness relative to cast components, both of which are critical given the cyclic stresses of 100-400 MPa that the implant must endure during walking and running. Following forging, the component is CNC-machined to achieve the tight dimensional tolerances required for proper fit during surgery.

Surface treatment is the final manufacturing step before sterilization and represents a critical interface between the implant and the patient's biology. The femoral stem surface is typically grit-blasted or acid-etched to increase surface roughness, which promotes mechanical interlocking with surrounding bone tissue known as osseointegration. In many modern implants, a hydroxyapatite (HA) coating is applied by plasma spraying onto the porous surface, providing a bioactive layer that chemically bonds with bone and accelerates long-term fixation. Once surface treatment is complete, the implant is cleaned, sterilized through gamma irradiation or ethylene oxide treatment, and sealed for surgical use.

IV. Atomic Bonding, Crystal Structure, and Strengthening Mechanisms

Ti-6AI-4V titanium alloy exhibits metallic bonding, in which valence electrons are shared collectively throughout the crystal lattice rather than between specific atoms. This creates positively charged ion cores surrounded by delocalizing electrons that are free to move throughout the materials. Because metallic bonding is non-directional, the alloy can withstand loading conditions without immediate fracture, providing high ductility and toughness. These properties are especially important for hip replacement implants because they experience repeated cyclic loading during daily activities such as walking.




Fig. 1. Comparison of the hexagonal close-packed (HCP) α phase and body-centered cubic (BCC) β phase crystal structures in Ti-6Al-4V titanium alloy.

Source: Lütjering & Williams, Fig. 1.

The alloying elements aluminum and vanadium further influence the mechanical behavior of Ti-6Al-4V. Aluminum acts as an α-phase stabilizer, strengthening the alloy through solid-solution hardening by distorting the titanium lattice. In contrast, vanadium acts as a β-phase stabilizer, improving toughness and ductility

As shown in Fig. 1, the α phase has a hexagonal close-packed (HCP) crystal structure with fewer independent slip systems, which restricts dislocation motion and increases strength and fatigue resistance. In contrast, the β phase has a body-centered cubic (BCC) crystal structure with more available slip systems, allowing easier dislocation movement and improving ductility and toughness. The combination of α and β phases allows Ti-6Al-4V to maintain a balance between strength, stiffness, and ductility. This balance is critical for hip replacement implants because the material must withstand long-term cyclic loading without cracking, excessive deformation, or brittle failure.

Since the HCP α phase has a more closely packed structure than the BCC β phase, diffusion occurs more slowly in α-Ti than in β-Ti, contributing to the alloy's stability and resistance to degradation under physiological conditions.




Fig. 2. Temperature dependence of diffusion coefficient for self-diffusion and alloying elements in Titanium.

Several strengthening mechanisms contribute to the high strength of Ti-6Al-4V. Solid solution strengthening occurs when aluminum and vanadium atoms distort the titanium lattice, creating local strain fields that hinder dislocation motion. Grain boundary strengthening is achieved through thermomechanical processing, in which smaller grain sizes increase resistance to dislocation motion according to the Hall-Petch relationship.

$$\sigma_y = \sigma_0 + kd^{-\frac{1}{2}} \qquad (1)$$

Dislocation strengthening also occurs during plastic deformation, as increased dislocation density creates interactions that impede further movement. Additionally, the dual-phase α + β microstructure itself acts as a strengthening mechanism because the phase interfaces impede dislocation motion. Together, these mechanisms provide Ti-6Al-4V with the high yield strength, fatigue resistance, and durability required for long-term hip implant applications.

V. Phase Diagrams, Heat Treatment, and Failure Mechanisms

Phase transformations and heat treatment processes strongly influence the mechanical properties and microstructure of Ti-6Al-4V. Titanium exhibits allotropic behavior, meaning its crystal structure changes with temperature. At room temperature, pure titanium exists in the α phase, which has an HCP structure. When heated above approximately 882°C, titanium transforms into the β phase, which has a BCC structure. Alloying elements such as aluminum and vanadium modify the stability of these phases and shift the transformation temperatures.

$$Ti_{\alpha\,(HCP)} \rightarrow 882°C \rightarrow Ti_{\beta\,(BCC)} \quad (2)$$

The titanium phase diagram is important for understanding how temperature and alloy composition determine the resulting microstructure. Aluminum acts as an α stabilizer, while vanadium stabilizes the β phase. As a result, Ti-6Al-4V forms a dual-phase α + β microstructure at room temperature, providing a balance among strength, fatigue resistance, ductility, and toughness.

Thermomechanical processing and heat treatment are used to control the amounts, sizes, and distributions of the α and β phases. During hot working operations such as forging and rolling, the alloy is typically processed in the α + β region below the β-transus temperature (995°C). Processing in this region refines the grain structure and improves fatigue performance. Solution treatment followed by aging then controls the precipitation and redistribution of phases, increasing strength while maintaining adequate ductility and toughness.

The long-term performance of Ti-6Al-4V hip implants is strongly influenced by several failure mechanisms that develop under repeated loading conditions within the human body. Fatigue failure is one of the most common causes of implant degradation because hip replacement experiences continuous cyclic tensile and compressive stresses during activities such as walking and running. These repeated stresses can initiate microscopic cracks that gradually propagate over time, eventually leading to mechanical failure of the implant. In addition to fatigue, fretting corrosion may occur at modular implant junctions, where repeated micro-motion exposes bare-metal surfaces to chloride-rich body fluids. The resulting corrosion pits act as stress concentrators, accelerating crack initiation and fatigue damage. Another important failure mechanism is stress shielding, which occurs because Ti-6Al-4V is stiffer than natural bone. As a result, the implant bears a disproportionate share of the applied load, reducing stress in the surrounding bone tissue and weakening the bone-implant interface over time. Understanding these failure mechanisms is critical for improving implant lifespan, minimizing revision surgeries, and ensuring the long-term safety and reliability of hip replacement applications.

VI. Environmental and Societal Consideration

The production of Ti-6Al-4V carries significant environmental consequences that begin at the extraction stage. Titanium mining through beach-sand dredging and hard-rock operations disturbs coastal and terrestrial ecosystems, generating large volumes of waste slurry that can contaminate local water sources. The Kroll process is among the most energy-intensive metal production processes in industry, requiring 36 MJ/kg compared to approximately 20 MJ/kg for steel. This high energy demand results in a substantial carbon footprint relative to other structural metals, and because the process requires magnesium reduction under an inert argon atmosphere, it cannot be easily simplified or made more efficient with current technology.

From a societal standpoint, the high cost of Ti-6Al-4V hip implants raises concerns about healthcare equity. Ti-6Al-4V implants cost significantly more than alternative materials such as cobalt-chromium or stainless steel, which limits access to titanium-based implants in lower-income healthcare systems. Additionally, vanadium is cytotoxic at elevated concentrations. Ion release from fretting corrosion at modular implant junctions can introduce vanadium and aluminum ions into the surrounding tissue and bloodstream over time, raising concerns about long-term biological safety. This has motivated ongoing research into vanadium-free alternatives such as Ti-6Al-7Nb, which replaces vanadium with niobium to reduce cytotoxicity, while maintaining similar mechanical properties.

At the end of life, Ti-6Al-4V hip implants present additional environmental and logistical challenges. Implants are classified as biohazardous medical waste in most jurisdictions, so they are typically incinerated rather than recycled. As a result, titanium recycling rates for explanted implants remain low, representing a significant waste of a resource that required substantial energy to produce.

Despite these concerns, Ti-6Al-4V hip implants offer an important environmental and societal benefit that partially offsets their production impact. This extended service life directly reduces long-term material and energy consumption, offering a meaningful environmental offset despite production costs.

VII. Conclusion

Ti-6Al-4V remains one of the most widely used titanium alloys for hip replacement implants because it combines high strength, corrosion resistance, fatigue performance, and biocompatibility across a demanding cradle-to-grave lifecycle. Although failure mechanisms such as fatigue, fretting corrosion, and stress shielding remain important challenges in implant applications, understanding these relationships between processing, microstructure, and properties is essential for improving future implant materials and extending the lifespan and safety of biomedical devices.

Acknowledgment

The authors would like to thank the Tufts University Department of Mechanical Engineering for supporting this project and providing the educational resources used throughout the study of materials and manufacturing principles.

References

[1] “As-Level Bonding,” ChemistryStudent. [Online]. Available: www.chemistrystudent.com/metallicbonding.html

[2] J. Tjandra et al., “Corrosion, Fatigue, and Wear of Additively Manufactured Ti Alloys for Orthopedic Implants,” [Online]. Available: https://www.tandfonline.com/doi/full/10.1080/02670836.2023.2230417
[3] G. Lütjering and J. C. Williams, Titanium. Berlin, Germany: Springer, 2007.
[4] “Titanium Grade 5 (Ti-6Al-4V) Technical Data Sheet,” [Online].
[5] X. Xu et al., “Ti-6Al-4V Alloy Strengthening via Instantaneous Phase Transformation Induced by Electropulsing,” Mater. Sci. Eng., [Online]. Available: https://www.sciencedirect.com/science/article/pii/S0925838821047137
[6] A. Yang, “Titanium Grades Guide: Detailed Comparison Chart,” [Online].
[7] C. Leyens and M. Peters, *Titanium and Titanium Alloys*. Weinheim, Germany: Wiley-VCH, 2003.
[8] U.S. Geological Survey, “Mineral commodity summaries: Titanium,” [Online]. Available:https://www.usgs.gov/centers/national-minerals-information-center/titanium-statistics-and-information
[9] H. J. Rack and J.I. Qazi, “Titanium alloys for biomedical applications,” *Mater. Sci. Eng. C,* vol. 26, no.8, pp.1269-1277, 2006.

[10] M. Niinomi, “Mechanical biocompatibilities of titanium alloys for biomedical applications,” *J. Mech. Behav. Biomed. Mater.,* vol.1, no.1, pp. 30-42, 2008. [Online]. Available: https://www.sciencedirect.com/science/article/pii/S0079642508001126