

**GORECHA METAL TECH PVT. LTD.**

Address : Survey No. 55 / P7, Plot No. 1, Shreej Industrial Area 2,
Rajkot Gondal NH-27, Pipaliya Sadak, Dist. Rajkot - 360 311 (Gujarat, India)

Telefax : +91 85111 55652

Email : inquiry@gorechametal.com, Web : www.gorechametal.com

GSTIN : 24AAICG4703F1ZY, State Code : 24 - Gujarat

TEST CERTIFICATE

AS PER EN - 10204 TYPE 3.1

M/s. GMT CORPORATION PRIVATE LIMITED

TC No. : 404 - 01/06/2026

DC No. : 404/26-27 - 01/06/2026

Invoice No. : 26/27-410 - 01/06/2026

PO No. : 2025-26/GCPL/2490-I

Specification : ASTM A351/351M Gr.CF8M

SPECTRO CHEMICAL ANALYSIS

Heat No.	C %	Si %	Mn %	P %	S %	Cr %	Mo %	Ni %									Heat Code
Min.						18.000	2.800	9.000									
Max.	0.080	1.500	1.500	0.040	0.040	21.000	3.000	12.000									
FD-256	0.062	1.340	1.260	0.039	0.004	18.320	2.080	9.480									
FE-024	0.065	1.240	1.100	0.038	0.007	18.480	2.120	9.420									
FE-025	0.074	1.400	1.200	0.036	0.006	18.550	2.160	9.280									
FE-058	0.065	1.110	1.190	0.032	0.004	18.580	2.120	9.500									
FE-176	0.065	1.160	1.160	0.037	0.010	18.350	2.110	9.670									

MECHANICAL PROPERTIES

Heat No.	TS MPa	YS MPa By 0.2% Offset	Elgn. %	R.A. %	Hardness	Impact Test at Test Temp. °C				Die No.	Description	Qty.
Min.	485	205	30.00	-	-							
Max.	-	-	-	-	-	1	2	3	Avg			
FD-256	535	348	50.32	-	152	-	-	-	-	G-250103	007156-001	27
FE-024	542	334	51.40	-	158	-	-	-	-	G-250103	007156-001	88
FE-025	546	331	51.36	-	153	-	-	-	-	G-250103	007156-001	60
FE-058	532	336	51.56	-	152	-	-	-	-	G-250103	007156-001	64
FE-176	567	279	50.76	-	151	-	-	-	-	G-250103	007156-001	9

Casting Process : Lost Wax Investment Casting


Supply Condition : Solution Annealing at 1050° C ± 20° C for 1hr, then Water Quenched.

Dimensional Inspection : Accepted

Material Identification : Casting are Identified with Heat No. / Grade / Foundry Logo etc.

We hereby certify that the items mentioned above conforms to PO
Specification : ASTM A351/351M Gr.CF8M

QUALITY ASSURANCE SYSTEM IN ACCORDANCE WITH THE
PRESSURE EQUIPMENT DIRECTIVE 2014/68/EU, ANNEX I,
SECTION 4.3, AD 2000-MERKBLATT W-0 AS WELL AS EN
764-5, PARA. 4.2



Tested By

For, Gorecha Metal Tech Pvt. Ltd.

