



GORECHA METAL TECH PVT. LTD.

Address : Survey No. 55 / P7, Plot No. 1, Shreeji Industrial Area 2,
Rajkot Gondal NH-27, Pipaliya Sadak, Dist. Rajkot - 360 311 (Gujarat, India)
Telefax : +91 85111 55652
Email : inquiry@gorechametals.com, Web : www.gorechametal.com
GSTIN : 24AAICG4703F1ZY, State Code : 24 - Gujarat

TEST CERTIFICATE

AS PER EN - 10204 TYPE 3.1

M/s. GMT CORPORATION PRIVATE LIMITED

TC No. : 147 - 18/04/2026
DC No. : 146/26-27 - 18/04/2026
Invoice No. : 26/27-151 - 18/04/2026
PO No. : 00-02-26

Specification : ASTM A351/351M Gr:CF8M

SPECTRO CHEMICAL ANALYSIS

Heat No.	C %	SI %	Mn %	P %	S %	Cr %	Mo %	Ni %										
Min.						18.000	2.000	9.000										
Max.	0.080	1.500	1.500	0.040	0.040	21.000	3.000	12.000										Heat Code
EO-016	0.022	1.210	1.070	0.036	0.002	18.520	2.140	9.590										
EO-037	0.039	1.400	1.080	0.040	0.002	18.650	2.160	9.590										
EO-077	0.049	1.320	1.050	0.036	0.005	18.600	2.230	9.440										

MECHANICAL PROPERTIES

Heat No.	TS MPa	YS MPa By 0.2% Offset	Elgn. %	R.A. %	Hardness	Impact Test at Test Temp. °C				Die No.	Description	Qty.
Min.	485	205	30.00	--	--							
Max.	--	--	--	--	--	1	2	3	Avg			
EO-016	524	335	51.56	--	159	--	--	--	--	G-250103	007156-001 Cust Part ID : 00716-001	119
EO-037	555	334	50.32	--	151	--	--	--	--	G-250103	007156-001 Cust Part ID : 00716-001	85
EO-077	530	349	50.08	--	155	--	--	--	--	G-250103	007156-001 Cust Part ID : 00716-001	84

Casting Process : Lost Wax Investment Casting
Supply Condition : Solution Annealing at 1060° C ± 20° C for 1hr/inch, then Water Quenched.
Dimensional Inspection : Accepted
Material Identification : Casting are identified with Heat No. / Grade / Foundry Logo etc.

We hereby certify that the items mentioned above confirms to PO
Specification : ASTM A351/351M Gr:CF8M

QUALITY ASSURANCE SYSTEM IN ACCORDANCE WITH THE
PRESSURE EQUIPMENT DIRECTIVE 2014/68/EU, ANNEX I,
SECTION 4.3, AD 2000-MERKBLATT W-0 AS WELL AS EN
764-5, PARA. 4.2

Tested By

For, Gorecha Metal Tech Pvt. Ltd.

Quality Control Dept.

**GORECHA METAL TECH PVT. LTD.**

Address : Survey No. 55 / P7, Plot No. 1, Shreeji Industrial Area 2,
Rajkot Gondal NH-27, Pipaliya Sadak, Dist. Rajkot - 360 311 (Gujarat, India)
Telefax : +91 85111 55652
Email : inquiry@gorechametals.com, **Web** : www.gorechametal.com
GSTIN : 24AAICG4703F1ZY, **State Code** : 24 - Gujarat

TEST CERTIFICATE

AS PER EN - 10204 TYPE 3.1

M/s. GMT CORPORATION PRIVATE LIMITED

TC No. : 191 - 24/04/2026
DC No. : 190/26-27 - 24/04/2026
Invoice No. : 26/27-190 - 24/04/2026
PO No. : 00-01-26, 00-02-26

Specification : ASTM A351/351M Gr:CF8M

SPECTRO CHEMICAL ANALYSIS

Heat No.	C %	Si %	Mn %	P %	S %	Cr %	Mo %	Ni %								Heat Code
Min.						18.000	2.000	9.000								
Max.	0.080	1.500	1.500	0.040	0.040	21.000	3.000	12.000								
EN-189	0.033	1.120	1.100	0.037	0.001	18.320	2.110	9.430								
EO-176	0.076	1.210	1.240	0.038	0.002	18.830	2.060	9.310								
EO-258	0.072	1.270	1.160	0.038	0.030	18.590	2.090	9.440								
EO-259	0.065	1.170	1.210	0.039	0.004	18.520	2.090	9.660								

MECHANICAL PROPERTIES

Heat No.	TS MPa	YS MPa By 0.2% Offset	Elign. %	R.A. %	Hardness	Impact Test at Test Temp. °C				Die No.	Description	Qty.
Min.	485	205	30.00	--	--							
Max.	--	--	--	--	--	1	2	3	Avg			
EN-189	566	341	50.08	--	157	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	6
EO-176	564	332	51.84	--	152	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	2
EO-258	530	339	51.36	--	150	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	94
EO-259	559	333	49.12	--	151	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	114

Casting Process : Lost Wax Investment Casting
Supply Condition : Solution Annealing at 1060° C ± 20° C for 1hr/inch, then Water Quenched.
Dimensional Inspection : Accepted
Material Identification : Casting are Identified with Heat No. / Grade / Foundry Logo etc.

We hereby certify that the Items mentioned above confirms to PO
Specification : ASTM A351/351M Gr:CF8M

QUALITY ASSURANCE SYSTEM IN ACCORDANCE WITH THE
PRESSURE EQUIPMENT DIRECTIVE 2014/68/EU, ANNEX I,
SECTION 4.3, AD 2000-MERKBLATT W-0 AS WELL AS EN
764-5, PARA. 4.2.

Tested By

Quality Control Dept.



For Gorecha Metal Tech Pvt. Ltd.



GMT Corporation Pvt. Ltd.

Pre-Dispatch Inspection Report

Format No.: GMT/CQA/F/04
Rev. No.: 00
Rev. Date: 01/04/2025
Page No.: 01 of 01

Part Name: FLANGED HEAD	Customer Name: DESSIMATE LLC	Date: 05-06-2026
Part No.: 007157-001	Challan / Invoice No.: - GMT/CX/2627/0286	Sample Size: 03
Rev. No: N	Control Plan No.: GMT/C/DSS/CP/007157-001	Dispatch Qty.: 300


Sr. No.	Parameter	Specification	Instrument / Gauge	Special Characteristics	Sample No. (All Dimensions are in Inch)			Remark
					1	2	3	
1	Outer Diameter	3.3750 + 0.0000 / - 0.0017	Air Ring Gauge	(X)	3.3743	3.3742	3.374	Accepted
2	Distance	0.655 ± 0.005	Ht. Gauge	(X)	0.655	0.654	0.654	Accepted
3	Pocket Diameter	0.800 ± 0.005	CMM	(X)	0.8019	0.801	0.8012	Accepted
4	Bore Size	1.540 ± 0.005	Plain Plug Gauge	(X)	OK	OK	OK	Accepted
5	Bore Size	1.255 + 0.000 / - 0.003	Inside Vernier Caliper / Plain Plug Gauge	(X)	1.254	1.254	1.253	Accepted
6	Bore Deep	0.042 + 0.002 / - 0.000	Ht. Gauge	(X)	0.0432	0.0430	0.0433	Accepted
7	Distance	0.200 ± 0.005	CMM	(X)	0.2015	0.2026	0.201	Accepted
8	Hole Size	0.125 + 0.005 / - 0.001	Plain Plug Gauge	(X)	OK	OK	OK	Accepted
9	Distance	R 0.718 ± 0.005	CMM	(X)	0.7185	0.7192	0.7184	Accepted
10	Pocket Width	0.400 ± 0.005	Width Gauge	(X)	OK	OK	OK	Accepted
11	Chamfer Length	0.050 ± 0.005	Contracer	(X)	0.0504	0.0505	0.0500	Accepted
12	Chamfer Angle	30° ± 1°	Contracer	(X)	30°12'34"	30°27'45"	30°10'55"	Accepted
13	3 x Drill Depth To Point	0.500 Max.	Special Point Pin with Dial	(X)	0.462	0.465	0.468	Accepted
14	2 x Drill Depth To Point	0.320 Max.	Special Point Pin with Dial	(X)	0.468	0.462	0.470	Accepted
15	Bore Size	2.430 ± 0.005	Plain Plug Gauge	(X)	0.471	0.462	0.465	Accepted
16	Groove Width	0.081 ± 0.005	Plain Plug Gauge	(X)	0.309	0.308	0.308	Accepted
17	4 x Hole Size	0.250 ± 0.005	Plain Plug Gauge	(X)	0.309	0.309	0.308	Accepted
18	2 x Tap	10-32 UNF - 2B	Thread Plug Gauge	(X)	OK	OK	OK	Accepted
19	5 x Tap	4-40 UNC - 2B	Thread Plug Gauge	(X)	OK	OK	OK	Accepted
20	Hole	0.625 ± 0.005	Plain Plug Gauge	(X)	OK	OK	OK	Accepted
21	Hole	0.500 ± 0.005	Plain Plug Gauge	(X)	OK	OK	OK	Accepted
22	Groove Width	0.140 ± 0.005	Width Gauge	(X)	OK	OK	OK	Accepted

Legend: Critical- (X)	Safety Critical- (S)	Major - (M)	Minor - (No Symbol)	Key Instructions- (K)	Pass Through Characteristic- (P)
Lot: ☒ Accepted ☐ Rejected	Approved By: Dhiraj Patil				
Checked By: Shreejyot Vharate					





INDACO METAL COATS PVT LTD
Sr. No. 430/2, Bhutaramanahatti, Honaga, Belgaum, Karnataka, India - 591156



CERTIFICATE OF CONFORMANCE

Report No.:IMC/COC/E+P/2026/044		Customer:	GMT CORPORATION PVT. LTD.	Date:	13/05/2026
Part Name:	FLANGED HEAD	Part No.:	007157-001	Rev No.:	-
Drawing No.:	NA	FAI No.:	-		
Material	CF8M SS	WO/DC No.:	2627/000138	PO No.:	-
Job Card No.:	IMC/P/E+P/JC/2026/044	Traveler No.:	IMC/P/E+P/PT/2026/044		
Quantity:	53 No's	Part Serial No.:	-		
ected Quantity (No's):	53 No's	Accepted Quantity (No's):	53 No's	Rejected Quantity (No's):	0

Customer Specification: Electropolish as per (ASTM B912)

Process Specification:Electropolish as per (ASTM B912)

Sl. No.	Parameter	Control Limits	Observation	Result	Quantity Accepted	Quantity Rejected
1	Visual Inspection	After completion of processing, there shall be no evidence of etching, pitting, smutting, frosting, dimensional changes, or other chemical attack on the parts when visually examined without aid of magnification. However, loss of temper color	After completion of processing, there is no evidence of etching, pitting, smutting, frosting, dimensional changes, and other chemical attack on the parts when visually examined without aid of magnification. No loss of temper color	Satisfactory	53 No's	Nil



Customer Deviation If Any: Nil

This is to certify that all the above mentioned parts are processed, Inspected and unless otherwise satisfactory to the above mentioned Type / Class / Method / Drawing / Specification and / Contract.

Prepared By: Pooja K.


Approved By: Poonam Kutre

Format No.: QC-IMC-003

Rev No.: K & Date: 13-03-2025



INDACO METAL COATS PVT LTD
Sr. No. 430/2, Bhutaramanahatti, Honaga, Belgaum, Karnataka, India -
591156




CERTIFICATE OF CONFORMANCE

Report No.:IMC/COC/E+P/2026/045		Customer:	GMT CORPORATION PVT. LTD.	Date:	14/05/2026
Part Name:	FLANGED HEAD	Part No.:	007157-001	Rev No.:	-
Drawing No.:	NA	FAI No.:	-		
Material	CF8M SS	WO/DC No.:	2627/000194	PO No.:	-
Job Card No.:	IMC/P/E+P/JC/2026/045	Traveler No.:	IMC/P/E+P/PT/2026/045		
Quantity:	36 No's	Part Serial No.:	-		
Inspected Quantity (No's):	36 No's	Accepted Quantity (No's):	36 No's	Rejected Quantity (No's):	0

Customer Specification: Electropolish as per (ASTM B912)

Process Specification:Electropolish as per (ASTM B912)

Sl. No.	Parameter	Control Limits	Observation	Result	Quantity Accepted	Quantity Rejected
1	Visual Inspection	After completion of processing, there shall be no evidence of etching, pitting, smutting, frosting, dimensional changes, or other chemical attack on the parts when visually examined without aid of magnification. However, loss of temper color	After completion of processing, there is no evidence of etching, pitting, smutting, frosting, dimensional changes, and other chemical attack on the parts when visually examined without aid of magnification. No loss of temper color	Satisfactory	36 No's	Nil



Customer Deviation If Any: Nil


This is to certify that all the above mentioned parts are processed, Inspected and unless otherwise satisfactory to the above mentioned Type / Class / Method / Drawing / Specification and / Contract.


Prepared By: Pooja K.

Approved By: Poonam Kutre

Format No.: QC-IMC-003

Rev No.: K & Date: 13-03-2025

		INDACO METAL COATS PVT LTD Sr. No. 430/2, Bhutaramanahatti, Honaga, Belgaum, Karnataka, India - 591156				
CERTIFICATE OF CONFORMANCE						
Report No.:IMC/COC/E+P/2026/046		Customer:	GMT CORPORATION PVT. LTD.	Date:	15/05/2026	
Part Name:	FLANGED HEAD	Part No.:	007157-001	Rev No.:	-	
Drawing No.:	NA	FAI No.:	-			
Material	CF8M SS	WO/DC No.:	264	PO No.:	-	
Job Card No.:	IMC/P/E+P/JC/2026/046	Traveler No.:	IMC/P/E+P/PT/2026/046			
Quantity:	40 No's	Part Serial No.:	-			
Inspected Quantity (No's):	40 No's	Accepted Quantity (No's):	40 No's	Rejected Quantity (No's):	0	
Customer Specification: Electropolish as per (ASTM B912)						
Process Specification:Electropolish as per (ASTM B912)						
Sl. No.	Parameter	Control Limits	Observation	Result	Quantity Accepted	Quantity Rejected
1	Visual Inspection	After completion of processing, there shall be no evidence of etching, pitting, smutting, frosting, dimensional changes, or other chemical attack on the parts when visually examined without aid of magnification. However, loss of temper color	After completion of processing, there is no evidence of etching, pitting, smutting, frosting, dimensional changes, and other chemical attack on the parts when visually examined without aid of magnification. No loss of temper color	Satisfactory	40 No's	Nil
 						
Customer Deviation If Any: Nil						
This is to certify that all the above mentioned parts are processed, Inspected and unless otherwise satisfactory to the above mentioned Type / Class / Method / Drawing / Specification and / Contract.						
Prepared By: Pooja K. 			Approved By: Poonam Kutre 			

	INDACO METAL COATS PVT LTD Sr. No. 430/2, Bhutaramanahatti, Honaga, Belgaum, Karnataka, India - 591156	
--	--	---

CERTIFICATE OF CONFORMANCE

Report No.:IMC/COC/E+P/2026/047	Customer:	GMT CORPORATION PVT. LTD.	Date:	20/05/2026
Part Name:	FLANGED HEAD	Part No.:	007157-001	Rev No.:
Drawing No.:	NA	FAI No.:		
Material	CF8M SS	WO/DC No.:	2627/000235	PO No.:
Job Card No.:	IMC/P/E+P/JC/2026/047	Traveler No.:	IMC/P/E+P/PT/2026/047	
Quantity:	44 No's	Part Serial No.:		
Inspected Quantity (No's):	44 No's	Accepted Quantity (No's):	44 No's	Rejected Quantity (No's):
				0

Customer Specification: Electropolish as per (ASTM B912)

Process Specification:Electropolish as per (ASTM B912)

Sl. No.	Parameter	Control Limits	Observation	Result	Quantity Accepted	Quantity Rejected
1	Visual Inspection	After completion of processing, there shall be no evidence of etching, pitting, smutting, frosting, dimensional changes, or other chemical attack on the parts when visually examined without aid of magnification. However, loss of temper color	After completion of processing, there is no evidence of etching, pitting, smutting, frosting, dimensional changes, and other chemical attack on the parts when visually examined without aid of magnification. No loss of temper color	Satisfactory	44 No's	Nil



Customer Deviation If Any: Nil

This is to certify that all the above mentioned parts are processed, Inspected and unless otherwise satisfactory to the above mentioned Type / Class / Method / Drawing / Specification and / Contract.

Prepared By: Pooja K.



Pooja K. 20/05/26

Approved By: Nagesh Metri

Nagesh Metri 20/5/26


Format No.: QC-IMC-003

Rev No.: K & Date: 13-03-2025

		INDACO METAL COATS PVT LTD Sr. No. 430/2, Bhutaramanahatti, Honaga, Belgaum, Karnataka, India - 591156				
CERTIFICATE OF CONFORMANCE						
Report No.:IMC/COC/E+P/2026/048		Customer:	GMT CORPORATION PVT. LTD.	Date:	25/05/2026	
Part Name:	FLANGED HEAD	Part No.:	007157-001	Rev No.:	-	
Drawing No.:	NA	FAI No.:	-			
Material	CF8M SS	WO/DC No.:	2627/000294	PO No.:	-	
Job Card No.:	IMC/P/E+P/JC/2026/048	Traveler No.:	IMC/P/E+P/PT/2026/048			
Quantity:	96 No's	Part Serial No.:	-			
Inspected Quantity (No's):	96 No's	Accepted Quantity (No's):	96 No's	Rejected Quantity (No's):	0	
Customer Specification: Electropolish as per (ASTM B912)						
Process Specification:Electropolish as per (ASTM B912)						
Sl. No.	Parameter	Control Limits	Observation	Result	Quantity Accepted	Quantity Rejected
1	Visual Inspection	After completion of processing, there shall be no evidence of etching, pitting, smutting, frosting, dimensional changes, or other chemical attack on the parts when visually examined without aid of magnification. However, loss of temper color	After completion of processing, there is no evidence of etching, pitting, smutting, frosting, dimensional changes, and other chemical attack on the parts when visually examined without aid of magnification. No loss of temper color	Satisfactory	96 No's	Nil
 						
Customer Deviation If Any: Nil						
This is to certify that all the above mentioned parts are processed, Inspected and unless otherwise satisfactory to the above mentioned Type / Class / Method / Drawing / Specification and / Contract.						
Prepared By: Pooja K. 		Approved By: Poonam Kutre 				

Format No.: QC-IMC-003

Rev No.: K & Date: 13-03-2025

	INDACO METAL COATS PVT LTD Sr. No. 430/2, Bhutaramanahatti, Honaga, Belgaum, Karnataka, India - 591156	 Administered by PRI ACCREDITED Chemical Processing				
CERTIFICATE OF CONFORMANCE						
Report No.:IMC/COC/E+P/2026/050	Customer:	GMT CORPORATION PVT. LTD.	Date:	30/05/2026		
Part Name:	FLANGED HEAD	Part No.:	007157-001	Rev No.:	-	
Drawing No.:	NA	FAI No.:				
Material	CF8M SS	WO/DC No.:	2627/000376	PO No.:	-	
Job Card No.:	IMC/P/E+P/JC/2026/050	Traveler No.:	IMC/P/E+P/PT/2026/050			
Quantity:	40 No's	Part Serial No.:	-			
Inspected Quantity (No's):	40 No's	Accepted Quantity (No's):	40 No's	Rejected Quantity (No's):	0	
Customer Specification: Electropolish as per (ASTM B912)						
Process Specification:Electropolish as per (ASTM B912)						
Sl. No.	Parameter	Control Limits	Observation	Result	Quantity Accepted	Quantity Rejected
1	Visual Inspection	After completion of processing, there shall be no evidence of etching, pitting, smutting, frosting, dimensional changes, or other chemical attack on the parts when visually examined without aid of magnification. However, loss of temper color	After completion of processing, there is no evidence of etching, pitting, smutting, frosting, dimensional changes, and other chemical attack on the parts when visually examined without aid of magnification. No loss of temper color	Satisfactory	40 No's	Nil
 						
Customer Deviation If Any: Nil						
This is to certify that all the above mentioned parts are processed, Inspected and unless otherwise satisfactory to the above mentioned Type / Class / Method / Drawing / Specification and / Contract.						
Prepared By: Pooja K. 			Approved By: Poonam Kutre 			