

**GORECHA METAL TECH PVT. LTD.**

Address : Survey No. 55 / P7, Plot No. 1, Shreeji Industrial Area 2,
Rajkot Gondal NH-27, Pipaliya Sadak, Dist. Rajkot - 360 311 (Gujarat, India)
Telefax : +91 85111 55652
Email : inquiry@gorechametals.com, Web : www.gorechametal.com
GSTIN : 24AAICG4703F1ZY, State Code : 24 - Gujarat

TEST CERTIFICATE

AS PER EN - 10204 TYPE 3.1

M/s. GMT CORPORATION PRIVATE LIMITED

TC No. : 1662 - 13/01/2026
DC No. : 1662/25-26 - 13/01/2026
PO No. : 11-11-25

Specification : ASTM A351/351M Gr:CF8M

SPECTRO CHEMICAL ANALYSIS

Heat No.	C %	Si %	Mn %	P %	S %	Cr %	Mo %	Ni %								
Min.						18.000	2.000	9.000								Heat Code
Max.	0.080	1.500	1.500	0.040	0.040	21.000	3.000	12.000								
EL-031	0.037	1.070	1.010	0.028	0.002	18.410	2.090	9.810								
EL-032	0.036	0.820	1.150	0.030	0.006	18.300	2.080	9.800								
EL-096	0.040	1.090	1.050	0.032	0.004	19.030	2.090	9.660								
EL-097	0.039	1.300	0.970	0.032	0.004	18.360	2.170	9.620								

MECHANICAL PROPERTIES


Heat No.	TS MPa	YS MPa By 0.2% Offset	Elgn. %	R.A. %	Hardness	Impact Test at Test Temp. °C				Die No.	Description	Qty.
Min.	485	205	30.00	--	--							
Max.	--	--	--	--	--	1	2	3	Avg			
EL-031	535	355	50.16	--	151	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	144
EL-032	540	325	50.08	--	155	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	92
EL-096	560	334	48.88	--	155	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	124
EL-097	549	333	48.40	--	153	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	140

Casting Process : Lost Wax Investment Casting
Supply Condition : Solution Annealing at 1060° C ± 20° C for 1hr/inch, then Water Quenched.
Dimensional Inspection : Accepted
Material Identification : Casting are Identified with Heat No. / Grade / Foundry Logo etc.

We hereby certify that the Items mentioned above confirms to PO
Specification : ASTM A351/351M Gr:CF8M

QUALITY ASSURANCE SYSTEM IN ACCORDANCE WITH THE
PRESSURE EQUIPMENT DIRECTIVE 2014/68/EU, ANNEX I,
SECTION 4.3, AD 2000-MERKBLATT W-0 AS WELL AS EN
764-5, PARA. 4.2.

Tested By



For, Gorecha Metal Tech Pvt. Ltd.

Quality Control Dept.