

**GORECHA METAL TECH PVT. LTD.**

Address : Survey No. 55 / P7, Plot No. 1, Shreeji Industrial Area 2,
Rajkot Gondal NH-27, Pipalyan, Sadak, Dist. Rajkot - 360 311 (Gujarat, India)
Telefax : +91 85111 55652
Email : inquiry@gorechametals.com, Web : www.gorechametal.com
GSTIN : 24AAICG4703F1ZY, State Code : 24 - Gujarat

TEST CERTIFICATE

AS PER EN - 10204 TYPE 3.1

M/s GMT CORPORATION PRIVATE LIMITED

TC No. : 219 - 28/04/2026
DC No. : 218/26-27 - 28/04/2026
Invoice No. : 26/27-213 - 30/04/2026
PO No. : 00-02-26, 00-04-26

Specification : ASTM A351/351M Gr:CF8M

SPECTRO CHEMICAL ANALYSIS

Heat No.	C %	SI %	Mn %	P %	S %	Cr %	Mo %	NI %									Heat Code
Min.						18.000	2.000	9.000									
Max.	0.080	1.500	1.500	0.040	0.040	21.000	3.000	12.000									
EO-259	0.065	1.170	1.210	0.039	0.004	18.520	2.090	9.660									
EO-260	0.054	1.160	1.210	0.039	0.002	18.320	2.090	9.680									
FD-065	0.053	1.090	1.340	0.038	0.004	18.400	2.100	9.510									
FD-108	0.063	1.120	1.320	0.038	0.004	18.490	2.100	9.420									

MECHANICAL PROPERTIES

Heat No.	TS MPa	YS MPa By 0.2% Offset	Elgn. %	R.A. %	Hardness	Impact Test at Test Temp. °C				Die No.	Description	Qty.
Min.	485	205	30.00	--	--							
Max.	--	--	--	--	--	1	2	3	Avg			
EO-259	559	333	49.12	--	152	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	2
EO-260	549	339	51.40	--	158	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	124
FD-065	560	338	51.56	--	151	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	80
FD-108	528	309	50.32	--	155	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	10

Casting Process : Lost Wax Investment Casting
Supply Condition : Solution Annealing at 1060° C ± 20° C for 1hr/inch, then Water Quenched
Dimensional Inspection : Accepted
Material Identification : Casting are Identified with Heat No. / Grade / Foundry Logo etc.

We hereby certify that the Items mentioned above confirms to PO
Specification : ASTM A351/351M Gr.CF8M

QUALITY ASSURANCE SYSTEM IN ACCORDANCE WITH THE
PRESSURE EQUIPMENT DIRECTIVE 2014/68/EU, ANNEX I,
SECTION 4.3, AD 2000-MERKBLATT W-0 AS WELL AS EN
764-5, PARA. 4.2.

Tested By

For, Gorecha Metal Tech Pvt. Ltd.

Quality Control Dept.