

**GORECHA METAL TECH PVT. LTD.**

Add : Survey No. 55 / PT, Plot No. 1, Shreej Industrial Area 2,
Rajkot Gondal NH-27, Pipaliya Sadak, Dist. Rajkot - 360 311 (Gujarat, India)
Telefax : +91 85111 55652
Email : inquiry@gorechametals.com, Web : www.gorechametal.com
GSTIN : 24AAICG4703F1ZY, State Code : 24 - Gujarat

TEST CERTIFICATE

AS PER EN - 10204 TYPE 3.1

M/s. GMT CORPORATION PRIVATE LIMITED

TC No. : 391 - 26/05/2026
DC No. : 391/26-27 - 26/05/2026
Invoice No. : 26/27-384 - 26/05/2026
PO No. : 2025-26/GCPL/2490-I

Specification : ASTM A351/351M Gr:CF8M

SPECTRO CHEMICAL ANALYSIS

Heat No.	C %	Si %	Mn %	P %	S %	Cr %	Mo %	Ni %										Heat Code
Min						18.000	2.000	9.000										
Max	0.080	1.500	1.500	0.040	0.040	21.000	3.000	12.000										
FD-105	0.085	1.220	1.310	0.039	0.004	18.640	2.090	9.440										
FD-185	0.060	1.380	1.150	0.037	0.005	18.380	2.090	9.330										
FD-186	0.061	1.380	1.230	0.036	0.005	18.630	2.150	9.320										
FD-256	0.062	1.340	1.280	0.039	0.004	18.320	2.090	9.480										

MECHANICAL PROPERTIES

Heat No.	TS MPa	YS MPa By 0.2% Offset	Elgn. %	R.A. %	Hardness	Impact Test at Test Temp. °C				Die No.	Description	Qty.
Min	485	205	30.00	--	--							
Max	--	--	--	--	--	1	2	3	Avg			
FD-105	533	341	49.00	--	158	--	--	--	--	G-250103	007156001 Cust. Part ID	20
FD-185	529	334	50.32	--	155	--	--	--	--	G-250103	007156001 Cust. Part ID	54
FD-186	571	334	51.84	--	152	--	--	--	--	G-250103	007156001 Cust. Part ID	55
FD-256	535	348	50.32	--	155	--	--	--	--	G-250103	007156001 Cust. Part ID	57

Casting Process : Lost Wax Investment Casting
Supply Condition : Solution Annealing at 1060° C ± 20° C for 1hr/inch, then Water Quenched.
Dimensional Inspection : Accepted
Material Identification : Casting are Identified with Heat No. / Grade / Foundry Logo etc.

We hereby certify that the items mentioned above conforms to PO
Specification : ASTM A351/351M Gr:CF8M

QUALITY ASSURANCE SYSTEM IN ACCORDANCE WITH THE
PRESSURE EQUIPMENT DIRECTIVE 2014/68/EU, ANNEX I,
SECTION 4.3, AD 2000-MERKBLATT W-0 AS WELL AS EN
754-5, PARA 4.2

Tested By

For, Gorecha Metal Tech Pvt. Ltd.

