



GORECHA METAL TECH PVT. LTD.

Address : Survey No. 55/P7, Plot No. 1, Shreeji Industrial Area 2,
Rajkot Gondal NH-27, Pipaliya Sadak, Dist. Rajkot - 360 311 (Gujarat, India)
Telefax : +91 85111 55652
Email : inquiry@gorechametals.com, Web : www.gorechametal.com
GSTIN : 24AAICG4703F1ZY, State Code : 24 - Gujarat

TEST CERTIFICATE

AS PER EN - 10204 TYPE 3.1

M/s. GMT CORPORATION PRIVATE LIMITED

TC No. : 671 - 06/07/2026
DC No. : 677/26-27 - 06/07/2026
Invoice No. : 26/27-662 - 06/07/2026
PO No. : 2025-26/GCPL/2490-1

Specification : ASTM A351/351M Gr:CF8M

SPECTRO CHEMICAL ANALYSIS

Heat No.	C %	Si %	Mn %	P %	S %	Cr %	Mo %	Ni %									Heat Code
Min.						18.000	2.000	9.000									
Max.	0.030	1.500	1.500	0.040	0.040	21.000	3.000	12.000									
FD-320	0.059	1.340	1.240	0.036	0.004	18.920	2.130	9.160									
FE-246	0.045	1.020	1.240	0.036	0.001	18.290	2.040	9.610									
FE-301	0.056	1.210	1.250	0.035	0.001	18.450	2.100	9.670									
FE-212	0.057	1.420	1.080	0.038	0.001	18.540	2.140	9.570									
FE-233	0.056	1.370	1.250	0.035	0.003	18.290	2.070	9.390									

MECHANICAL PROPERTIES

Heat No.	TS MPa	YS MPa By 0.2% Offset	Elgn. %	R.A. %	Hardness	Impact Test at Test Temp. °C				Die No.	Description	Qty.
Min.	485	205	30.00	--	--							
Max.	--	--	--	--	--	1	2	3	Avg			
FD-320	535	333	50.32	--	152	--	--	--	--	G-250103	007156001	54
FE-246	532	300	50.36	--	158	--	--	--	--	G-250103	007156-001	66
FE-301	526	306	48.92	--	151	--	--	--	--	G-250103	007156-001	40
FE-212	530	296	50.32	--	155	--	--	--	--	G-250103	007156-001	76
FE-233	538	300	49.88	--	151	--	--	--	--	G-250103	007156-001	30

Casting Process : Lost Wax Investment Casting
Supply Condition : Solution Annealing at 1060° C ± 20° C for 1hr/inch, then Water Quenched
Dimensional Inspection : Accepted
Material Identification : Casting are Identified with Heat No. / Grade / Foundry Logo etc.

We hereby certify that the items mentioned above conforms to PO
Specification : ASTM A351/351M Gr CF8M

QUALITY ASSURANCE SYSTEM IN ACCORDANCE WITH THE
PRESSURE EQUIPMENT DIRECTIVE 2014/68/EU, ANNEX I,
SECTION A.3, AD 2000-MERKBLATT W.O AS WELL AS EN
704-5, PARA 4.2

Tested By

For, Gorecha Metal Tech Pvt. Ltd.

