

**GORECHA METAL TECH PVT. LTD.**

Address : Survey No. 55 / P7, Plot No. 1, Shreeji Industrial Area 2,
Rajkot Gondal NH-27, Pipaliya Sadak, Dist. Rajkot - 360 311 (Gujarat, India)
Telefax : +91 85111 55652
Email : inquiry@gorechametals.com, **Web** : www.gorechametal.com
GSTIN : 24AAICG4703F1ZY, **State Code** : 24 - Gujarat

TEST CERTIFICATE

AS PER EN - 10204 TYPE 3.1

M/s. GMT CORPORATION PRIVATE LIMITED

TC No. : 1361 - 27/02/2026
DC No. : 1358/25-26 - 27/02/2026
Invoice No. : 25/26-1994 - 27/02/2026
PO No. : 00-01-26

Specification : **ASTM A351/351M Gr:CF8M****SPECTRO CHEMICAL ANALYSIS**

Heat No.	C %	Si %	Mn %	P %	S %	Cr %	Mo %	Ni %								
Min.						18.000	2.000	9.000								Heat Code
Max.	0.080	1.500	1.500	0.040	0.040	21.000	3.000	12.000								
EN-189	0.033	1.120	1.100	0.037	0.001	18.320	2.110	9.430								
EN-190	0.038	1.340	1.060	0.037	0.001	18.720	2.160	9.420								
EN-213	0.043	1.230	1.080	0.034	0.001	18.710	2.140	9.500								
EN-214	0.032	1.180	1.110	0.033	0.001	18.450	2.050	9.520								

MECHANICAL PROPERTIES


Heat No.	TS MPa	YS MPa By 0.2% Offset	Elgn. %	R.A. %	Hardness	Impact Test at Test Temp. °C				Die No.	Description	Qty.
Min.	485	205	30.00	--	--							
Max.	--	--	--	--	--	1	2	3	Avg			
EN-189	566	341	50.08	--	155	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	84
EN-190	533	328	50.08	--	152	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	48
EN-213	556	334	50.08	--	155	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	144
EN-214	525	351	50.16	--	158	--	--	--	--	G-250103	007156-001 Cust. Part ID : 00716-001	30

Casting Process : Lost Wax Investment Casting
Supply Condition : Solution Annealing at 1060° C ± 20° C for 1hr/inch, then Water Quenched.
Dimensional Inspection : Accepted
Material Identification : Casting are Identified with Heat No. / Grade / Foundry Logo etc.

We hereby certify that the items mentioned above confirms to PO
Specification : ASTM A351/351M Gr:CF8M

QUALITY ASSURANCE SYSTEM IN ACCORDANCE WITH THE
PRESSURE EQUIPMENT DIRECTIVE 2014/68/EU, ANNEX I,
SECTION 4.3, AD 2000-MERKBLATT W-0 AS WELL AS EN
764-5, PARA. 4.2.

Tested By



For, Gorecha Metal Tech Pvt. Ltd.

Quality Control Dept.