PM-40 reinforced bitumen membrane

PM-40 is an elastomeric bitumen membrane with a polyester reinforcement, used as the cap sheet of two-layer roofing systems on flat and low-slope roofs. The upper face is covered with grey mineral granules; the lower face has a thin film that is melted with a torch during installation.

Applications

Cap sheet on concrete, timber and metal decks; renovation of existing bitumen roofs after the surface has been cleaned and primed; detailing around roof lights, upstands and outlets.

Storage and handling

Store rolls upright on a flat, dry surface, away from direct sunlight and sources of heat. Do not stack pallets. Rolls taken from a cold store must be kept at room temperature for one day before they are unrolled.

Packaging

Rolls are wrapped in a printed sleeve and delivered on returnable pallets of twenty-five rolls. Each sleeve shows the production batch and the date of manufacture.

Technical data

Property	Typical value
Thickness	4.0 mm
Mass per unit area	4.8 kg/m²
Reinforcement	polyester fleece, 160 g/m²
Tensile strength, length / width	900 / 700 N per 50 mm
Elongation at break	45 %
Cold flexibility	−25 °C
Heat resistance	+110 °C
Roll size	1 m × 7.5 m

The membrane stays flexible at low temperatures and can be installed when the air temperature is above freezing. Below that, rolls must be warmed before use and the substrate must be free of frost and condensation.

Values are typical results from factory production control and are given for guidance only. They do not form a specification.

Installation notes

Side laps are at least 80 mm wide and end laps at least 150 mm wide. Laps are sealed by heating both surfaces until the bitumen flows and pressing them together with a roller, leaving a small bead of bitumen along the edge.

Install the cap sheet on the same day as the underlayer where possible. Joints in the cap sheet are offset from the joints of the underlayer by at least a third of the roll width.

Disposal

Offcuts and damaged rolls are collected separately and returned to a recycling scheme for bitumen products. Empty sleeves and pallets are taken back by the supplier.