From Molecular Redox Screening to Polymer Grafts: Benchmarking and Matched Thermodynamic Comparisons

Working draft: authorship and affiliations to be confirmed

JCIM Article draft; evidence updated: 3 November 2026

Abstract

Selecting redox groups for attachment to a preformed polymer requires connecting molecular electrochemistry to a defined installation reaction and a local polymer environment. We examine these connections using a 39-endpoint acetonitrile benchmark and an experimentally supported viologen attachment class, with TEMPO and diimide controls. The unfitted redox protocol gives a mean absolute error of 0.247 V; all nine paired redox-step spacings are overestimated, identifying an error component that cannot be removed by a ferrocene reference shift. Matched oligomer cycles distinguish a polymer contribution to attachment from neighboring-graft nonadditivity, while four illustrative ionic viologen frames show that favorable whole-chain electronic nonadditivity can coexist with repulsive capped motif pairs. These comparisons establish which molecular, reaction and polymer quantities can inform the same assessment, while their predictive scope remains limited by molecular redox error, salt speciation and incomplete occupied-polymer sampling.

Keywords: computational electrochemistry; redox-active polymers; polymer grafting; density functional theory; thermodynamic cycles; conformer sampling.

1 Introduction

Nonaqueous flow batteries can store charge in redox groups attached to insoluble polymer beads while soluble mediators exchange charge with those groups. This architecture separates the circulating electrolyte from the charge-storage material and makes the electrochemistry of the pendant group a central design choice.[1] Related polymer and colloidal systems illustrate the broader use of macromolecular supports to retain redox-active material.[2, 3] Post-functionalization of a preformed support allows the polymer and redox group to be prepared separately; attachment to chloromethylated polystyrene has been demonstrated for viologen, TEMPO and phenothiazine groups.[1, 4–6]

A molecular screening result addresses only part of this choice. The installed group has a specific attachment bond and linker, its preparation requires a suitable precursor and reaction conditions, and its surroundings depend on graft occupancy and polymer conformation. Molecular potential, installation free energy and neighboring-group response therefore answer different questions. For a redox-matched battery, the potential of the installed group must also be considered in relation to its soluble mediator, while useful capacity depends on the amount of polymer and the fraction of accessible redox sites.[1]

High-throughput screening and redox databases provide molecular structures and electrochemical descriptors across broad chemical spaces.[7–9] Multistep screening has also been developed for radical-polymer anodes and flow-battery anolytes.[10] Computational electrochemistry establishes the roles of reference choice, solvation and charge-state treatment,[11–13] while studies of

diimide association and charge transport in polymers motivate explicit treatment of neighboring groups and backbone structure.[14–16] These approaches make it useful to ask which molecular conclusions survive a change from a soluble compound to an installed group and then to a polymer model.

Here we address that question through a benchmark and matched thermodynamic comparisons. First, we examine the accuracy and redox-step dependence of an unfitted molecular protocol. We then follow an exact viologen graft from a source-supported attachment class through its molecular states, local quaternization reaction and finite oligomer models. Balanced differences distinguish the polymer contribution to first attachment from the effect of an occupied neighboring site. Finally, frozen motif calculations test whether whole-chain nonadditivity can be interpreted as direct motif attraction. TEMPO, pyromellitic diimide (PMDI) and phthalimide supply focused supporting comparisons. The contribution is a reproducible way to formulate and test these links, with quantitative examples rather than a completed ranking of polymer materials.

2 Computational Methods

2.1 Structures, reaction models and calculation levels

The synthesis modeled here is post-functionalization of a polymer bearing benzyl chloride handles. A 4-methylbenzyl chloride site and its substituted product define the local graft model. Five-repeat open oligomers contain three reactive sites and two unfunctionalized styrene padding units; an unoccupied reactive site retains benzyl chloride. Precursor/product graphs, attachment bonds and the connectivity of the saved coordinates are checked explicitly. Free parents, capped grafts and oligomers are treated as distinct structures. The design registry and route evidence, including the distinction between an exact-support demonstration and a molecular analogue, are provided in the Supporting Information (SI).

Molecular geometries and solution Hessians use r^{2}SCAN-D4/SMD acetonitrile (MeCN), with def2-SVP for neutral/cationic species and def2-SVPD for anions.[17–21] Molecular single-point electronic energies use ωB97M-V/def2-TZVPD uniformly for every target charge state and both ferrocene (Fc) states.[22] Calculations use PySCF 2.14.0, GPU4PySCF 1.8.1 and geomeTRIC, with density fitting of Coulomb and exact-exchange contributions.[23–25] Supporting electrolyte ions are absent except in explicitly identified contact models.

At 298.15 K, the molecular composite free energy is

$$G = E_{\mathrm{SMD}}^{\omega\mathrm{B97M-V}} + G_{\mathrm{nuclear}}^{\mathrm{qRRHO}} - RT\ln(2S+1). \tag{1}$$

The quasi-rigid-rotor/harmonic-oscillator (qRRHO) nuclear partition uses projected internal modes from the solution DFT Hessian, unscaled frequencies, a geometry-specific symmetry number and the xTB 6.7.1 thermodynamic integrator.[26, 27] The integrator supplies no xTB Hessian. The primary rotor cutoff is 50 cm^{-1}; 25 and 100 cm^{-1} test sensitivity. The spin term assumes an unsplit ground multiplet.

Each reported minimum must satisfy a maximum Cartesian gradient of 4.5×10^{-4} hartree bohr^{-1}, Hessian asymmetry no greater than 10^{-6} in atomic units, a lowest projected internal frequency of at least -5 cm^{-1} and spin contamination no greater than 0.1. Frequencies between -5 and 0 cm^{-1} enter the partition by absolute value. At least two complete Hessian columns are checked against displaced gradients at 0.0005 and 0.001 bohr with a 1% relative-norm tolerance. Checks also bind the electronic energy to the accepted geometry and verify finite data and full grid response. The SI gives derivative-selection, implementation-repeat and independent reconstruction

details. These numerical checks establish the stated local calculations; experimental accuracy and conformer sampling are assessed separately.

The ionic viologen oligomer cycles and expanded sampling controls use a separate r^{2}SCAN-D4/def2-SVP smooth-surface MeCN model. All components within each such cycle share that model. Their energies are not added to the primary composite molecular reaction energies. Table 1 summarizes the distinction.

Table 1: Calculation levels and quantities used in the comparisons. The SI specifies the separate smooth-surface implementation and the scope of its derivative checks.

Comparison	Electronic energy	Nuclear treatment / scope
Parent benchmark, capped grafts and local reactions	ωB97M-V/def2-TZVPD/SMD	Geometry-level DFT qRRHO; Eq. 1
Primary PMDI and phthalimide oligomer controls	Same composite protocol	One or two minima per graph
Ionic viologen oligomers	r^{2}SCAN-D4/def2-SVP, smooth-surface MeCN	Matched graph-specific qRRHO; one minimum per graph
Frozen viologen motif pairs	Same electronic model as ionic parent frames	Electronic differences only; fixed motif coordinates

2.2 Molecular redox benchmark

For a one-electron couple $\mathrm{O} + \mathrm{e}^- \rightarrow \mathrm{R}$, the potential relative to the computed $\mathrm{Fc/Fc^+}$ reference is

$$E_{\mathrm{O/R}}^{\mathrm{vs\ Fc}} = \frac{G_{\mathrm{O}} - G_{\mathrm{R}} - [G_{\mathrm{Fc^+}} - G_{\mathrm{Fc}}]}{F}. \tag{2}$$

All four states use matched electronic and thermal conventions. Equation 2 uses molar energies; a one-electron energy difference in eV per molecule gives the voltage directly.

The fixed retrospective panel contains 39 MeCN endpoints from 30 molecules and seven studies: 22 quinone, nine aromatic-imide, five phenothiazine, two viologen and one nitroxide endpoints. Experimental potentials retain the source-reported reference calibration and measurement conditions. No endpoint is removed and no offset is fitted in the primary analysis. Molecule- and study-cluster percentile bootstrap intervals use 2,000 replicates and seed 20261021. Grouped held-out offset analyses are post hoc diagnostics; each training fold excludes every endpoint of the held-out molecule or study. They are not prospective external validation. Source locations, state assignments and individual errors are supplied in the SI and accompanying benchmark data.

2.3 Local attachment and balanced polymer comparisons

Viologen installation is modeled as quaternization of a mono-N-methyl bipyridinium precursor with the local RCl site:

$$\mathrm{V^+_{prec}} + \mathrm{RCl} \rightarrow \mathrm{RV^{2+}} + \mathrm{Cl^-}. \tag{3}$$

Atoms and charge balance, and this reaction has no HCl or base-capture term. Three fixed precursor starts are checked; the lowest precursor G at the primary cutoff is used. The separated-ion convention treats chloride and the dicationic graft as distinct solutes. Explicit graft/chloride contacts are tested separately using

$$\Delta G_{\mathrm{assoc}} = G(\mathrm{RVCl^+}) - G(\mathrm{RV^{2+}}) - G(\mathrm{Cl^-}). \tag{4}$$

The contact is a +1 singlet, chemically distinct from the isolated +1 doublet redox state. Duplicate review uses proper-rotation, symmetry-aware heavy-atom alignment and an electronic-energy tolerance; starting counts do not define populations.

The nuclear translation convention is 1 atm. Conversion to a 1 M solute standard state adds $\Delta nRT\ln(RTc^\circ/p^\circ)$. It cancels in separated-ion quaternization and contributes approximately $-7.93\ \mathrm{kJ\,mol^{-1}}$ to a two-solute-to-one-solute contact association at 298.15 K. The SI defines the separate N–H/O–H substitution cycles and base-capture controls used for the supporting neutral grafts. Those reaction definitions are not transferred to viologen quaternization.

For an empty oligomer P_0, a singly grafted oligomer P_i, local site RCl and capped graft RM, the polymer-minus-local first-attachment difference is

$$\delta G_{i,\mathrm{poly-local}} = G(P_i) + G(\mathrm{RCl}) - G(P_0) - G(\mathrm{RM}). \tag{5}$$

The neighboring-graft response uses the empty, singly occupied and doubly occupied graphs:

$$\Delta\Delta G_{ij} = G(P_{ij}) + G(P_0) - G(P_i) - G(P_j). \tag{6}$$

Common precursor, base and byproduct terms cancel in these balanced differences. The first measures a polymer contribution relative to the capped reaction; the second measures how occupation of i changes attachment at j. Both include chain relaxation and solvent response. Neither is an isolated pair-binding free energy.




Figure 1: The three comparisons addressed in the study. Measured soluble parents test the molecular protocol. A capped graft specifies the installed chemical group and its local reaction. Balanced oligomer cycles test additional environmental responses. Each comparison retains its own structure, method and reference; arrows indicate the assessment sequence.

2.4 Sampling and local interaction controls

Graph-specific finite conformer sets use

$$G_{\mathrm{set}} = -RT\ln\sum_k \exp[-G_k/(RT)]. \tag{7}$$

Duplicate review precedes summation. One retained minimum per graph is used for the PMDI and ionic viologen cycles, and two for the original phthalimide control. Expanded occupied-phthalimide sampling supplies a separate ten-to-twenty-start diagnostic under the smooth-surface model. It cannot establish convergence for a different graph or replace a primary-model component.

Frozen motif interactions are defined as $\Delta E_{\mathrm{motif}} = E_{AB} - E_A - E_B$ at unchanged parent-relative motif coordinates, using the same electronic and solvent model as the parent frame. For viologen, the benzyl carbon is retained and its aryl bond is replaced by C–H, giving methyl-capped +2 singlet motifs and a +4 singlet pair. Four frames and three C–H lengths (1.07, 1.09 and 1.11 Å) give twelve fragment triplets. These electronic interactions include capping and continuum response but no counterpoise correction or thermal association term. The SI reports the fragment construction and the separate TEMPO directional-relaxation calculation.[28]

3 Results and Discussion

3.1 Redox-step errors cannot be removed by a common reference shift

The unfitted protocol gives MAE 0.247 V, RMSE 0.279 V and bias +0.190 V (Figure 2). Molecule-cluster 95% intervals are [0.213,0.286], [0.245,0.313] and [0.128,0.257] V, respectively. The panel covers several relevant families but is dominated by quinones; the five phenothiazine endpoints and single TEMPO endpoint do not establish broad family accuracy. The two viologen endpoints belong to one molecule, and naphthalene diimide (NDI) is absent.




Figure 2: Unfitted comparison of 39 sourced soluble-parent potentials in MeCN. All endpoints are retained. Family and redox-step labels expose uneven coverage and distinguish first- from second-step errors. Bootstrap intervals describe this retrospective panel rather than prospective errors for exact polymer grafts.

Table 2 makes the comparisons most directly related to the graft examples explicit. TEMPO and N-ethylphenothiazine first oxidations are too positive by 0.253 and 0.259 V. For benzyl–methyl viologen, the first-reduction error is +0.190 V, whereas the second is −0.003 V. These are measurements and calculations for matched soluble-parent identities. They are already included in the 39-endpoint panel and supply no additional independent test.

Across the full panel, all 30 first-step errors are positive, with mean +0.266 V, while the nine second-step errors have mean −0.064 V. More decisively, all nine paired step spacings are overestimated in magnitude. Subtracting two potentials calculated against the same Fc couple cancels its contribution exactly. A common reference shift therefore cannot correct the spacing errors, even if it improves a mean potential offset. The near agreement of an individual second step can reflect cancellation of errors.

The computed Fc absolute potential is 4.379 V. Recent solution photoemission work reports a ferrocene adiabatic ionisation energy of 4.94 ± 0.05 eV in MeCN.[31] This comparison motivates further investigation of the reference and its physical conventions; it does not justify substituting an experimental constant for one term of an otherwise unchanged DFT cycle. The opposite

Table 2: Selected matched parent comparisons from the fixed benchmark. Potentials and signed errors ($E_{\mathrm{calc}} - E_{\mathrm{exp}}$) are V versus Fc in MeCN. Each source defines its own electrolyte and experimental uncertainty. These parent measurements are distinct from the capped graft models.

Parent and event	Experiment	Calculation	Error
TEMPO, first oxidation[29]	+0.249	+0.502	+0.253
N-Ethylphenothiazine, first oxidation[30]	+0.278	+0.537	+0.259
Benzyl–methyl viologen, first reduction[1]	−0.785	−0.595	+0.190
Benzyl–methyl viologen, second reduction[1]	−1.204	−1.207	−0.003

first-/second-step residual patterns and the Fc-independent spacing errors require charge-state and solvation contributions to be considered as well. The SI separates this scale comparison from fixed-geometry reference-functional controls.

Post hoc molecule-held-out offsets reduce MAE to 0.158 V with one constant and 0.106 V with separate step constants; the corresponding study-held-out values are 0.182 and 0.124 V. These diagnostics confirm residual structure within this panel and are not adopted as corrections for new grafts. Five neutral-partner diffuse-basis controls shift first potentials by 11.7–35.1 mV, and changing the rotor cutoff gives a largest endpoint span of 25.4 mV. Those limited sensitivities are smaller than the observed molecular error but do not identify its unique cause.[13]

3.2 Viologen connects a demonstrated attachment class to an exact local model

The viologen example is motivated by a nonaqueous redox-matched battery in which methylbipyridinium groups were attached to preformed Merrifield beads.[1] The source reports precursor preparation, grafting in refluxing MeCN and subsequent counterion exchange. Our capped product, registered as `search_viologen_b7a4dca7a5e1`, retains the specified local bond but replaces the rest of the polymer by the 4-methylbenzyl model. The experimental soluble benzyl–methyl mediator in Table 2 and this capped product are therefore different structures.

The computed graft reductions are −0.608 and −1.208 V versus the matched Fc couple. The states are a dicationic singlet, radical-cation doublet and neutral singlet; their calculated spacing is 0.600 V. These values describe the exact capped model. Its correspondence to a demonstrated attachment class provides a practical reason to study it, while the parent errors in Table 2 show why its absolute potentials require experimental testing.

The local quaternization in Eq. 3 gives $\Delta G = -11.49\ \mathrm{kJ\,mol^{-1}}$ at the primary cutoff. The three precursor starts span 1.50 $\mathrm{kJ\,mol^{-1}}$, and rotor settings give −13.30 to −11.49 $\mathrm{kJ\,mol^{-1}}$. This favorable value refers to separated ions at 298.15 K. The source synthesis uses reflux, and the calculation supplies neither an activation barrier nor a conversion or yield prediction.

Seven optimized chloride-contact outcomes give 1-M association free energies of 5.33 to 22.36 $\mathrm{kJ\,mol^{-1}}$. Duplicate review reduces them to five numerical groups without assigning statistical weights. The tested contacts are unfavorable under this finite association model; they do not exhaust the dication's counterions, iodide exchange, concentration dependence or salt speciation. Their role is to expose a condition of the local reaction model rather than validate its absolute free energy.

3.3 Balanced differences separate polymer attachment from neighboring-site response

Equations 5 and 6 compare different physical effects. PMDI supplies a primary-model illustration: attaching at two sites of a five-repeat chain incurs polymer-minus-local penalties of +5.34 and +6.11 kJ mol^{-1} at the primary cutoff, whereas its neighboring-graft response is −1.86 kJ mol^{-1}. A positive first-site penalty and a negative neighboring-site response can therefore occur in the same finite model. All six site/cutoff penalties are positive, but the small preference between sites changes sign. Full component tables and figures are in the SI. Each graph contributes one minimum, and the exact PMDI installation route remains incompletely established.[32, 33]

For viologen, four matched ionic oligomer cycles test adjacent and one-spacer grafts in all-same and alternating backbone configurations (Figure 3 and Table 3). The method is the separate r^{2}SCAN-D4/SVP smooth-surface MeCN model, and each component contributes one retained minimum. Both spacings change sign when the backbone configuration changes. These results illustrate configuration sensitivity within the sampled structures; they do not establish an equilibrium spacing preference. The models have total charge +4 when doubly grafted and contain no explicit counterions. The molecular chloride-contact calculations above do not complete a counterion test of these oligomer cycles.




Figure 3: Connectivity of the adjacent and one-spacer viologen occupancy models. The open backbone contains five repeats: 1 and 5 are unfunctionalized styrene padding, while the unoccupied reactive site retains benzyl chloride. The drawings define graft positions and the drawn backbone configuration; both configurations in Table 3 have the same site identities. Graph spacing does not prescribe spatial separation. Doubly grafted models have bare charge +4 and omit counterions.

Table 3: Illustrative ionic viologen neighboring-graft responses, $\Delta\Delta G$ in kJ mol^{-1}. Each entry is a balanced four-graph cycle with one retained minimum per graph. The primary cutoff is 50 cm^{-1}; the ranges span the tested 25/50/100 cm^{-1} settings and are not uncertainty intervals.

Backbone	Graft spacing	Primary	Cutoff range
All-same	Adjacent	−3.94	−5.85 to −3.94
All-same	One spacer	22.58	19.75 to 22.58
Alternating	Adjacent	8.28	8.28 to 8.37
Alternating	One spacer	−5.30	−5.79 to −4.28

An explicit sampling test explains the restriction to retained structures. In the separate occupied-phthalimide control, increasing ten starts to twenty lowers the finite-set free energy by 2.40 kJ mol^{-1} at the primary cutoff, exceeding its 2.00 kJ mol^{-1} diagnostic. Twenty inputs remain twenty numerical minima; the failure persists across duplicate and rotor settings, and eleven other cohort cells are incomplete. This control does not measure the error of the viologen cycles. It shows why successful minimum checks and rotor sensitivity alone cannot establish an occupied ensemble. The geometric spacing control also finds close-contact poses for both adjacent and one-spacer graphs, so sequence separation does not by itself exclude spatial contact (SI).

3.4 Whole-chain nonadditivity differs from direct motif interaction

The ionic viologen frames permit a second, electronically matched comparison (Figure 4). Frozen methyl-capped pairs are repulsive in all four MeCN frames, with electronic interactions of +7.618 to +9.631 kJ mol^{-1}. Yet two of the same parent frames have favorable whole-chain electronic nonadditivity. For the adjacent all-same frame, the chain value is −3.46 kJ mol^{-1} and the capped motif interaction is +9.029 kJ mol^{-1}. Thus a favorable whole-chain cycle does not, by itself, demonstrate attractive local motifs in this cap model.

The distinction follows from what each quantity compares. The whole-chain cycle contains four separately optimized occupancy graphs. The fragment interaction retains one parent's motif coordinates, removes the aryl linker and backbone and introduces methyl caps. Their opposite signs are a result for those operational definitions. The difference is not a unique decomposition into backbone, deformation and solvent contributions. The tested cap-length span is below 0.003 kJ mol^{-1}, while chemical-cap choice, basis convergence and counterpoise sensitivity remain untested. Both comparisons here are electronic energies at matched model settings, rather than a mixture of the molecular composite G and oligomer E.

3.5 Implications for selecting grafted redox groups

The comparisons suggest a practical assessment sequence. Molecular redox predictions should first be tested on matched experimental identities and the relevant redox steps. An installed group should then be specified by its precursor, attachment bond and demonstrated or proposed conditions. Polymer comparisons should use balanced states and report first-site, neighboring-site and local-interaction quantities separately. This sequence keeps a favorable molecular descriptor connected to the chemical question it actually addresses.

Supporting examples show why additional descriptors require their own interpretation. The exact O-linked TEMPO graft, whose attachment class has NaH/DMF or THF precedent, has a computed oxidation potential of +0.579 V versus Fc.[4] Its directional solution-relaxation costs are 1.477 and 1.639 eV, differing by 10.4%; this exceeds the declared 5% diagnostic for a symmetric




Figure 4: Whole-chain and local electronic responses for four retained ionic viologen frames. The chain cycle is $E(P_{ij}) + E(P_0) - E(P_i) - E(P_j)$; the local quantity is $E_{AB} - E_A - E_B$ for frozen methyl-capped motifs. Both use r^{2}SCAN-D4/SVP with the same smooth-surface MeCN model. The opposite signs in two frames concern different quantities and do not define a unique backbone contribution, an association free energy or an electronic coupling.

approximation. These quantities retain their directional definitions and are not transfer rates. For PMDI, a nominal two-electron molecular capacity of 153.9 mAh g^{-1} becomes a dry-fragment ceiling of 61.2, 98.9 or 124.5 mAh g^{-1} for the specified one-, two- or three-graft models. Those composition bounds retain scaffold and residual chloride mass but omit unspecified crosslinker, electrolyte and charging counterions. Neither example supplies an experimental accessibility or loading distribution.

Reaction bookkeeping has a similarly specific role. Adding a common base-capture term shifts compatible substitution reactions by the same amount and preserves their order; that invariance is an identity. External acid/base controls reveal a DBU/HCl capture discrepancy of 22.81 kJ mol^{-1}, so favorable base-assisted sums cannot be used alone as evidence that a graft will form. The complete reaction panel and its source qualifications are reported in the SI. A demonstrated attachment class and thermodynamic calculations provide complementary evidence; kinetics, selectivity and polymer accessibility remain distinct questions.

The principal limits are molecular prediction error, restricted chemical coverage, incomplete ion speciation and unconverged occupied-polymer sampling. The finite oligomer responses use a different method from the molecular benchmark and do not establish a material ranking, coupling or transport rate. Operating potential windows, accessible electron counts, graft conversion, swelling and cycling stability must be specified and measured for an application. In a redox-matched flow battery, mediator exchange and access to tethered sites are especially relevant.[1] Polymer hopping and backbone-dependent transport provide further reasons to avoid equating an isolated pair interaction with device performance.[15, 16, 34] The maintained design inventory records structures and available evidence; an incomplete assessment is not a demonstrated failure of every candidate.

4 Conclusions

The molecular benchmark identifies a systematic redox-step error: all nine paired step spacings are overestimated, and a common Fc shift cancels from those differences. Explicit matched-parent comparisons also expose first-step errors of approximately 0.19–0.26 V for viologen, TEMPO and phenothiazine examples. These observations define a concrete accuracy problem for molecular screening and motivate validation across the charge states used in a proposed application.

Following an exact viologen graft through its local reaction and oligomer models shows how balanced comparisons add information beyond a molecular potential. Polymer-minus-local attachment, neighboring-graft nonadditivity and frozen motif interaction answer different questions. In the retained ionic frames, favorable whole-chain electronic nonadditivity coexists with repulsive capped motifs, demonstrating why chain-level energetics alone cannot establish local attraction. The present oligomer results are finite-model illustrations whose equilibrium interpretation requires further sampling and ion treatment. Together, the benchmark and matched cycles provide a reproducible basis for evaluating proposed polymer grafts while preserving the distinction between a computed descriptor and a synthesis or material-performance decision.

Supporting Information

Experimental benchmark sources, individual endpoints, reference handling and post hoc diagnostics; basis and rotor sensitivity; exact design and route inventory; local reaction components and base-capture controls; PMDI attachment and occupancy comparisons; phthalimide geometry and sampling controls; TEMPO directional relaxation; ionic viologen states and frozen fragments; numerical implementation, restart and portable replay details (PDF). Exact structures and parent-benchmark endpoints are also supplied as CSV, with model context and source records in JSON/TXT.

Data and Software Availability

The project repository contains development code. A commit-pinned source snapshot preserves the code and evidence context used for this revision. Its corrected-primary CPU example reconstructs the molecular redox and local quaternization cycles from ten cached states using NumPy, including nine Hessians and saved-gradient panels. The SI describes raw-state inventories, environments and additional replays. A tagged public release, full raw-data archival deposition and a permanent deposition identifier remain outstanding.

Author Information

Authorship, affiliations, corresponding-author details, contributions, funding and competing-interest statements require confirmation by the authors.

Acknowledgments

AI tools, including OpenAI Codex and Claude Code, were used during the project to assist with code development, analysis, literature retrieval and manuscript preparation. Computational statements are supported by the recorded calculations and checks described in the Methods and SI. The authors are responsible for reviewing the scientific content, references and this disclosure before submission.

References

[1] Dukhan Kim, Melanie S. Sanford, Thomas P. Vaid, and Anne J. McNeil. A nonaqueous redox-matched flow battery with charge storage in insoluble polymer beads. *Chemistry—A European Journal*, 28:e202200149, 2022. doi: 10.1002/chem.202200149.

[2] Tobias Janoschka, Norbert Martin, Udo Martin, Christian Friebe, Sabine Morgenstern, Hannes Hiller, Martin D. Hager, and Ulrich S. Schubert. An aqueous, polymer-based redox-flow battery using non-corrosive, safe, and low-cost materials. *Nature*, 527:78–81, 2015. doi: 10.1038/nature15746.

[3] Elena C. Montoto, Gavvalapalli Nagarjuna, Jingshu Hui, Mark Burgess, Nina M. Sekerak, Kenneth Hernández-Burgos, Teng-Sing Wei, Marissa Kneer, Joshua Grolman, Kevin J. Cheng, Jennifer A. Lewis, Jeffrey S. Moore, and Joaquín Rodríguez-López. Redox Active Colloids as Discrete Energy Storage Carriers. *Journal of the American Chemical Society*, 138:13230–13237, 2016. doi: 10.1021/jacs.6b06365.

[4] Reinhard Sommerlade, Hansjörg Grützmacher, and Souâd Boulmaâz. Process for the selective oxidation of alcohols using readily removable nitroxyl radicals. U.S. Patent 6,441,243 B1, Example A4, 2002. URL https://patents.google.com/patent/US6441243B1/en.

[5] Michael E. Wright and Myung Jong Jin. Polymer-supported cation radicals. *The Journal of Organic Chemistry*, 54(4):965–968, 1989. doi: 10.1021/jo00265a043.

[6] Algin Oh Biying, Sabrina Trano, Yi Jie Eng, Gabriele Lingua, Haritz Sardon, David Mecerreyes, and Julian M. W. Chan. Upcycling commodity styrofoam into redox polymer-based electrodes. *ChemSusChem*, 18(11):e202500092, 2025. doi: 10.1002/cssc.202500092.

[7] Süleyman Er, Changwon Suh, Michael P. Marshak, and Alán Aspuru-Guzik. Computational design of molecules for an all-quinone redox flow battery. *Chemical Science*, 6:885–893, 2015. doi: 10.1039/c4sc03030c.

[8] Rebekah Duke, Vinayak Bhat, Parker Sornberger, Susan A. Odom, and Chad Risko. Towards a comprehensive data infrastructure for redox-active organic molecules targeting non-aqueous redox flow batteries. *Digital Discovery*, 2:1152–1162, 2023. doi: 10.1039/d3dd00081h.

[9] Elif Sorkun, Qi Zhang, Abhishek Khetan, Murat Cihan Sorkun, and Süleyman Er. RedDB, a computational database of electroactive molecules for aqueous redox flow batteries. *Scientific Data*, 9:718, 2022. doi: 10.1038/s41597-022-01832-2.

[10] Andreas J. Achazi, Xhesilda Fataj, Philip Rohland, Martin D. Hager, Ulrich S. Schubert, and Doreen Mollenhauer. Development of a multi-step screening procedure for redox active molecules in organic radical polymer anodes and as redox flow anolytes. *Journal of Computational Chemistry*, 45(14):1112–1129, 2024. doi: 10.1002/jcc.27299.

[11] Aleksandr V. Marenich, Junming Ho, Michelle L. Coote, Christopher J. Cramer, and Donald G. Truhlar. Computational electrochemistry: prediction of liquid-phase reduction potentials. *Phys. Chem. Chem. Phys.*, 16:15068–15106, 2014. doi: 10.1039/c4cp01572j.

[12] Mansoor Namazian, Ching Yeh Lin, and Michelle L. Coote. Benchmark Calculations of Absolute Reduction Potential of Ferricinium/Ferrocene Couple in Nonaqueous Solutions. *Journal of Chemical Theory and Computation*, 6:2721–2725, 2010. doi: 10.1021/ct1003252.

[13] Sarah Elhajj and Samer Gozem. First and Second Reductions in an Aprotic Solvent: Comparing Computational and Experimental One-Electron Reduction Potentials for 345 Quinones. *Journal of Chemical Theory and Computation*, 20:6227–6240, 2024. doi: 10.1021/acs.jctc.4c00602.

[14] Cedrik Wiberg, Lars Evenäs, Michael Busch, and Elisabet Ahlberg. Naphthalene diimides (NDI) in highly stable ph-neutral aqueous organic redox flow batteries. *Journal of Electroanalytical Chemistry*, 896:115224, 2021. doi: 10.1016/j.jelechem.2021.115224.

[15] Abhinav Akhoury, Lev Bromberg, and T. Alan Hatton. Interplay of Electron Hopping and Bounded Diffusion during Charge Transport in Redox Polymer Electrodes. *The Journal of Physical Chemistry B*, 117:333–342, 2013. doi: 10.1021/jp302157g.

[16] Khirabdhi Tannaya Mohanty, Sheila Keating, Kha Trinh, Riccardo Alessandri, Daniel P. Tabor, Stuart J. Rowan, Juan J. de Pablo, and Jodie L. Lutkenhaus. Deciphering concentration and backbone identity effects on the redox properties of phthalimide-based polymers. *Chemistry of Materials*, 38(18):9530–9541, 2026. doi: 10.1021/acs.chemmater.6c01965.

[17] James W. Furness, Aaron D. Kaplan, Jinliang Ning, John P. Perdew, and Jianwei Sun. Accurate and numerically efficient r2SCAN meta-generalized gradient approximation. *The Journal of Physical Chemistry Letters*, 11:8208–8215, 2020. doi: 10.1021/acs.jpclett.0c02405.

[18] Eike Caldeweyher, Sebastian Ehlert, Andreas Hansen, Hagen Neugebauer, Sebastian Spicher, Christoph Bannwarth, and Stefan Grimme. A generally applicable atomic-charge dependent London dispersion correction. *The Journal of Chemical Physics*, 150:154122, 2019. doi: 10.1063/1.5090222.

[19] Aleksandr V. Marenich, Christopher J. Cramer, and Donald G. Truhlar. Universal solvation model based on solute electron density and on a continuum model of the solvent defined by the bulk dielectric constant and atomic surface tensions. *The Journal of Physical Chemistry B*, 113:6378–6396, 2009. doi: 10.1021/jp810292n.

[20] Florian Weigend and Reinhart Ahlrichs. Balanced basis sets of split valence, triple zeta valence and quadruple zeta valence quality for H to Rn: Design and assessment of accuracy. *Physical Chemistry Chemical Physics*, 7:3297–3305, 2005. doi: 10.1039/B508541A.

[21] Dmitrij Rappoport and Filipp Furche. Property-optimized Gaussian basis sets for molecular response calculations. *The Journal of Chemical Physics*, 133:134105, 2010. doi: 10.1063/1.3484283.

[22] Narbe Mardirossian and Martin Head-Gordon. ωB97M-V: A combinatorially optimized, range-separated hybrid, meta-GGA density functional with VV10 nonlocal correlation. *The Journal of Chemical Physics*, 144:214110, 2016. doi: 10.1063/1.4952647.

[23] Qiming Sun et al. Recent developments in the PySCF program package. *The Journal of Chemical Physics*, 153:024109, 2020. doi: 10.1063/5.0006074.

[24] Rui Li, Qiming Sun, Xing Zhang, and Garnet Kin-Lic Chan. Introducing GPU-acceleration into the Python-based simulations of chemistry framework, 2024. Preprint.

[25] Lee-Ping Wang and Chenchen Song. Geometry optimization made simple with translation and rotation coordinates. *The Journal of Chemical Physics*, 144:214108, 2016. doi: 10.1063/1.4952956.

[26] Stefan Grimme. Supramolecular Binding Thermodynamics by Dispersion-Corrected Density Functional Theory. *Chemistry – A European Journal*, 18:9955–9964, 2012. doi: 10.1002/chem.201200497.

[27] Christoph Bannwarth, Eike Caldeweyher, Sebastian Ehlert, Andreas Hansen, Philipp Pracht, Jakob Seibert, Sebastian Spicher, and Stefan Grimme. Extended tight-binding quantum chemistry methods. *WIREs Computational Molecular Science*, 11:e1493, 2021. doi: 10.1002/wcms.1493.

[28] Zhi-Qiang You, Jan-Michael Mewes, Andreas Dreuw, and John M. Herbert. Comparison of the marcus and pekar partitions in the context of non-equilibrium, polarizable-continuum solvation models. *The Journal of Chemical Physics*, 143(20):204104, 2015. doi: 10.1063/1.4936357.

[29] James B. Gerken and Shannon S. Stahl. High-Potential Electrocatalytic O_2 Reduction with Nitroxyl/NO_x Mediators: Implications for Fuel Cells and Aerobic Oxidation Catalysis. *ACS Central Science*, 1:234–243, 2015. doi: 10.1021/acscentsci.5b00163.

[30] N. Harsha Attanayake, Jeffrey A. Kowalski, Katharine V. Greco, Matthew D. Casselman, Jarrod D. Milshtein, Steven J. Chapman, Sean R. Parkin, Fikile R. Brushett, and Susan A. Odom. Tailoring Two-Electron-Donating Phenothiazines To Enable High-Concentration Redox Electrolytes for Use in Nonaqueous Redox Flow Batteries. *Chemistry of Materials*, 31:4353–4363, 2019. doi: 10.1021/acs.chemmater.8b04770.

[31] Tomi K. Baikie, Jonathon R. Harwell, Iain D. Baikie, Eli Zysman-Colman, Ifor D. W. Samuel, and Graham A. Turnbull. Absolute calibration for cyclic voltammetry from the solution-phase ionisation of ferrocene. *ACS Electrochemistry*, 2(2):297–304, 2026. doi: 10.1021/acselectrochem.5c00382.


[32] Richard J. Bochis, Michael H. Fisher, and Bruce O. Linn. Pyromellitic diimides, processes for their preparation, these compounds in orally administrable form for use in increasing the feed efficiency of a ruminant animal and compositions for this purpose containing them. European patent EP0010440B1, published January 26, 1983, 1983. URL https://patents.google.com/patent/EP0010440B1/en. Example 19, printed p. 10; precursor identity only.

[33] Darren G. Hamilton, Daniel E. Lynch, Karl A. Byriel, Colin H. L. Kennard, and Jeremy K. M. Sanders. N-alkylation of pyromellitic diimide: Solid-state structure of the 1 : 1 N,N′-diethylpyromellitic diimide/2,6-dimethoxynaphthalene cocrystal. *Australian Journal of Chemistry*, 51(5):441–444, 1998. doi: 10.1071/C97214.

[34] Kenichi Oyaizu, Yuko Ando, Hiroaki Konishi, and Hiroyuki Nishide. Nernstian Adsorbate-like Bulk Layer of Organic Radical Polymers for High-Density Charge Storage Purposes. *Journal of the American Chemical Society*, 130:14459–14461, 2008. doi: 10.1021/ja803742b.

For Table of Contents Only

From molecules to polymer grafts



Fc cancels from paired redox-step spacings.

Whole-chain response differs from motif interaction.

Molecular validation and finite polymer comparisons