TANZANIA BUREAU OF STANDARDS

P O Box 9524, Dar es Salaam

Tel: +255222450206/+255222450949/+255222450298

Fax: +255222450959

E-mail: info@tbs.go.tz- Physical Address: Junction Morogoro/Sam Nujoma Rds, Ubungo

International Organization for Standardization (ISO), Codex Alimentarius Commission (WHO/FAO), Agent for ISO and other National Standards Bodies

Page 1 of 3

TBS Code No.

QCL/EZ 12834

80 HT

TEST REPORT BCL/05503/2024



This report is issued in accordance with Section 4 (1) (c) of the Standards Act No. 2 of 209. The report shall not be published, other than in full, without prior written approval of the Director General, TBS.

"A SADCAS ACCREDITED TESTING LABORATORY

DATE

2024-06-07

TEST-3 0003

Client: LAKE CEMENT LIMITED

Client address: PLOT NO. 265, KIMBIJI KIGAMBONI PO BOX- 40707, DAR ES SALAAM, DAR-ES-SALAAM

Sample: 1 BAG 50KG OF NYATI CEM II A-L 42.5N

Site and position sampled: STORAGE AREA

Sampling plan: **RANDOM**

Date of sampling: 2024-05-06

Date received: 2024-05-08

Date started: 2024-05-08

Date finished: 2024-06-07

Specification: TZS 727 (PART 1): 2018 (2ND ED)

Test method: AS INDICATED IN THE TABLE OF RESULTS ACCORDING TO THE STANDARD

BL Number:

1.0 INTRODUCTION

A sample of 50Kgs of cement (NYATI CEMENT II A-L 42.5N) was submitted to TBS Building and Construction Laboratory for testing whether it conforms to TZS 727:2018. The sample was given TBS Code No. QCL/EZ 12834.

Page 2 of 3

Tel: +255222450206/+255222450949/+255222450298

Fax: +255222450959

E-mail: info@tbs.go.tz- Physical Address: Junction Morogoro/Sam Nujoma Rds, Ubungo

the International Organization for Standardization (ISO), Codex Alimentarius Commission (WHO/FAO), Agent for ISO and other National Standards Bodies

TEST REPORT BCL/05503/2024

2.0 TEST RESULTS

The sample was analyzed as per specified method and the given results pertain only to the sample submitted to the TBS BUILDING AND CONSTRUCTION LABORATORY for testing.

TABLE: Results of Cement

	ON Testification Control Province Contro						
S/N	Test/Characteristic	Test	Requirements	Results and	Pass/Fail		
		Method		uncertainty			
1	■ *Standard consistence, %	EN 196-3	-	28.2 ± 1.7	Pass		
2	■ * Initial setting time, Minutes	EN 196-3	60 (Minimum)	198 ± 17.0	Pass		
3	■ * Soundness (Expansion), mm	EN 196-3	10 (Maximum)	0.7 ± 0.3	Pass		
4	■ * Early strength (2 days), N/mm²	EN 196-1	10 (Minimum)	23.2 ± 2.9	Pass		
5	■ * Standard strength (28 days), N/mm²	EN 196-1	Between 42.5 and 62.5	45.9 ± 5.7	Pass		
6	■ Loss of Ignition, %	EN 196-2	5(Maximum)	0.8	Pass		

- 1) The reported uncertainty is an expanded uncertainty, calculated using a coverage factor of 2 which gives a level of confidence of approximately 95%.
- 2) Results with black dot () indicates decision rule applied.
- 3) Results with asterisk (*) indicate accredited parameters.
- 4) DECISION RULE "pass" when results and its uncertainty range is within limits or results uncertainty range overlap the limit, "fail" when results and its uncertainty range is outside the limits.

MARKING AS PER TZS 727:2018

The manufacturer's name, address (factory physical address) and/or trademark	-Marked
Standard designation of cement	-Marked
Net weight	-Marked
Date of packing and /or batch number	-Marked



TANZANIA BUREAU OF STANDARDS

P O Box 9524, **Dar es Salaam**

Tel: +255222450206/+255222450949/+255222450298

Fax: +255222450959

E-mail: info@tbs.go.tz- Physical Address: Junction Morogoro/Sam Nujoma Rds, Ubungo

DATE **2024-06-07** TH 08 TBS Code No. QCL/EZ 12834

Page 3 of 3

TEST REPORT BCL/05503/2024

the International Organization for Standardization (ISO), Codex Alimentarius Commission (WHO/FAO), Agent for ISO and other National Standards Bodies

3.0 REMARK

The sample conforms to **TZS 727:2018** "Composition, specification and conformity criteria for common cement specification" for the tested parameters. The test of this sample was destructive.

Reported by: Verified by: Approved by:

Justinianius Kampuni Saidi Ayoub Eng. Mahona William

Analyst Technical Signatory Head of Laboratory