

Product Data Sheet



Aesthetic Description

Solarban® 70 glass (formerly *Solarban® 70XL* glass) is a solar control, low-e glass that brilliantly combines the clear appearance of transparent, color-neutral glass with an exceptional combination of solar control and visible light transmittance (VLT).

The world's first triple-silver, magnetron sputter vacuum deposition (MSVD) coating, *Solarban® 70* glass expands the design possibilities for buildings in two important ways. First, *Solarban® 70* glass enables architects to incorporate vast areas of vision glass into their designs without a corresponding increase in cooling equipment capacity.

Second, architects can specify a clear aesthetic while achieving solar control performance that was once attainable only through the use of tinted glass and a solar control, low-e coating in an insulating glass unit (IGU).

Performance Options

When coupled with conventional clear glass in a one-inch IGU, *Solarban® 70* glass achieves a VLT of 64 percent and a Solar Heat Gain Coefficient (SHGC) of 0.27 to produce a Light to Solar Gain (LSG) ratio of 2.37, making it one of the industry's highest-performing glasses.

The clear aesthetic of *Solarban® 70* glass also makes the product exceptionally versatile, offering architects an extensive array of performance and appearance options. For instance, for projects that require advanced solar control performance, *Solarban® 70* glass can be coated on the second (#2) surface of nearly all of



The Cirque

Location: Dallas, TX | Product: *Solarban® 70* Glass | Architect of Record: PageSouthernlandPage | Design Architect: Gromatzky Dupree & Associates | Glass Fabricator: Trulite Glass and Aluminum Solutions | Glazing Contractor: Haley-Greer

Vitre Architectural Glass's (formerly PPG Glass) wide range of tinted glasses to produce SHGCs as low as 0.19 and LSG ratios ranging from 1.68 to 2.15.

For more color and reflectivity choices, *Solarban® 70* glass may be specified on the third (#3) surface of an IGU behind a tinted lite or in combination with *Solarcool®* reflective or *Vistacool®* subtly reflective color-enhanced glasses.

Supporting Sustainable Design

Vitre Architectural Glass provides abundant opportunities for architects and building owners to realize their sustainability objectives.

Energy Use & Operating Cost Reduction: High-performance glasses by Vitre are engineered to facilitate downsized mechanical equipment costs, leading to reduced long-term energy costs. Visit tools.vitroglazings.com for glass comparison and configuration tools for analyzing glass products.

Sustainability Documentation: Vitre Architectural Glass is the first U.S. float glass manufacturer to have its entire selection of products recognized by the *Cradle to Cradle Certified™* program, and the first in North America to publish third-party verified Environmental Product Declarations (EPDs) for its Flat Glass and Processed Glass products.

For additional credit opportunities and supporting documentation, visit tools.vitroglazings.com/LEED

LEED® Credit Opportunities

Possible Points	LEED Credit	<i>Solarban® 70</i> Feature	Path/Option Satisfied
18	Energy & Atmosphere (EA) Optimize Energy Performance	Excellent SHGC, U-value and Tvis performance	Whole Building Energy Simulation (Option 1) or Prescriptive Compliance: ASHRAE Advanced Energy Design Guide (Option 2)
5	Innovation (IN) Innovation in Design	Exceeds minimum performance mandated by local energy codes	Innovation (Option 1), Pilot (Option 2) and Exemplary Performance (Option 3)
3	Indoor Environmental Quality (EQ) Daylight	Exhibits high light transmission	Simulation: Spatial Daylight Autonomy and Annual Sunlight Exposure (Option 1), Simulation: Illuminance Calculations (Option 2) or Measurement (Option 3)

Solarban® 70 Glass

Insulating Glass Unit Performance Comparisons 1-inch (25 mm) units with 1/2-inch (13 mm) airspace and two 1/4-inch (6 mm) lites								
Outdoor Lite: Coating if Any (Surface) Glass	Glass Type + Indoor Lite: Coating if Any (Surface) Glass	Visible Light Transmittance (VLT%)	Visible Light Reflectance		(BTU/hr ² ft ²⁰ *F) NFRC U-Value		Solar Heat Gain Coefficient (SHGC)	Light to Solar Gain (LSG)
			Exterior %	Interior %	Winter Nighttime	Winter Argon		

Solarban® 70 Solar Control Low-E Glass

Solarban® 70 (2) + Clear	64	13	14	0.28	0.24	0.27	2.37
Solarban® 70 (2) Solexia® + Clear	56	11	14	0.28	0.24	0.26	2.15
Solarban® 70 (2) Atlantica® + Clear	49	10	13	0.28	0.24	0.23	2.13
Solarban® 70 (2) Azuria® + Clear	50	10	13	0.28	0.24	0.24	2.08
Solarban® 70 (2) Solarblue® + Clear	41	8	13	0.28	0.24	0.22	1.86
Solarban® 70 (2) Pacifica® + Clear	31	7	13	0.28	0.24	0.19	1.63
Solarban® 70 (2) Solarbronze® + Clear	39	8	13	0.28	0.24	0.20	1.95
Solarban® 70 (2) Optigray® + Clear	46	9	13	0.28	0.24	0.23	2.00
Solarban® 70 (2) Solargray® + Clear	32	7	13	0.28	0.24	0.19	1.68
Solexia® + Solarban® 70 (3) Clear	56	11	12	0.28	0.24	0.32	1.75
Atlantica® + Solarban® 70 (3) Clear	48	9	11	0.28	0.24	0.28	1.71
Azuria® + Solarban® 70 (3) Clear	49	9	11	0.28	0.24	0.29	1.69
Solarblue® + Solarban® 70 (3) Clear	41	8	12	0.28	0.24	0.27	1.52
Pacifica® + Solarban® 70 (3) Clear	31	6	10	0.28	0.24	0.22	1.41
Solarbronze® + Solarban® 70 (3) Clear	38	8	11	0.28	0.24	0.26	1.46
Optigray® + Solarban® 70 (3) Clear	46	9	12	0.28	0.24	0.28	1.64
Solargray® + Solarban® 70 (3) Clear	32	7	11	0.28	0.24	0.24	1.33
Graylite® II + Solarban® 70 (3) Clear	6	4	10	0.28	0.24	0.11	0.55

Vistacool® and Solarcool® with Solarban® 70 Solar Control Low-E (3)*

Vistacool® (2) Azuria® + Solarban® 70 (3)	38	21	23	0.28	0.24	0.24	1.58
Vistacool® (2) Pacifica® + Solarban® 70 (3)	24	11	22	0.28	0.24	0.19	1.26
Solarcool® (2) Azuria® + Solarban® 70 (3)	19	19	27	0.28	0.24	0.16	1.19
Solarcool® (2) Solarblue® + Solarban® 70 (3)	17	14	28	0.28	0.23	0.15	1.07
Solarcool® (2) Pacifica® + Solarban® 70 (3)	12	10	27	0.28	0.24	0.13	0.92
Solarcool® (2) Solarbronze® + Solarban® 70 (3)	15	14	27	0.28	0.24	0.15	1.00
Solarcool® (2) Solargray® + Solarban® 70 (3)	13	11	27	0.28	0.24	0.14	0.93

*Solarban® 70 glass for annealed applications is applied to Starphire® glass, heat treated applications will require either clear or Starphire® glass depending on manufacturing process.

All performance data calculated using LBNL Window 7.3 software and represents center of glass performance data. For detailed information on the methodologies used to calculate the aesthetic and performance values in this table, please visit vitroglazings.com or request our Architectural Glass Catalog.

Fabrication and Availability

Solarban® 70 glass is available exclusively through the Vitro Certified™ Network. Vitro Certified™ Fabricators can meet tight construction deadlines and accelerate the delivery of replacement glass before, during and after construction. Solarban® 70 glass is manufactured using the sputter-coating process and is available for annealed, heat-strengthened and tempered applications.

Additional Resources

To obtain samples of any Vitro Glass product, call **1-855-VTRO-GLS (877-6457)** or visit samples.vitroglazings.com. For videos, design insights and technical education, visit the Vitro Glass Education Center at glassed.vitroglazings.com. For glass comparison and configuration tools, visit tools.vitroglazings.com.

For more information about Solarban® low-e glass and other Cradle to Cradle Certified™ architectural glasses by Vitro Glass, visit vitroglazings.com, or call **1-855-VTRO-GLS (887-6457)**.

©2020 Vitro Architectural Glass. All rights reserved. Atlantica®, Azuria®, Graylite®, Optigray®, Pacifica®, Solarban®, the Solarban® logo, Solarblue®, Solarbronze®, Solarcool®, Solargray®, Solexia®, Starphire® and Vistacool® are registered trademarks owned by Vitro. Vitro Certified™ is a trademark owned by Vitro. Cradle to Cradle Certified™ is a trademark licensed by the Cradle to Cradle Products Innovation Institute. LEED®—an acronym for Leadership in Energy and Environmental Design—is a registered trademark of the U.S. Green Building Council. 10/2020

