DEPARTMENT OF WORKS & HIGHWAY

MATERIAL SCIENCE & TECHNOLOGY BRANCH

Materials Testing Laboratory

☑ Port Moresby, ☐ Mt. Hagen, ☐ Lae, ☐ Annex Lab:

Date:

Page of

FLAKINESS INDEX - AS 1141. 15

Client : _____ Asset No. _____

Project: _____ Job No: _____

Location: _____ Material Source / Pit No. _____

Material Description: _____ Depth: _____

Nominal Size: _____ (mm) Aggregate

Thickness Gauges Passing	Total Mass (g) (ml)	Mass Passing (m2)	Mass Retained (m3)	Check (m3+m2=m1)	Percent Flaky (F)	Mass of sample (kg)
63.0mm						25 - 30
53.0mm						20 - 25
37.5mm						10 - 15
31.5mm						8 - 10
26.5mm						4 - 6
19.0mm						1.5 - 2
16.0mm						1.2 - 1.5
13.2mm						0.7 - 1.0
9.50mm						0.3 - 0.5
6.70mm						0.2 - 0.4
TOTAL						

FLAKINESS INDEX (FI) =

Calculation Details

F = (m3) / (m1) x (100)

FI = (m5) / (m4) x (100) Σm1 = m4 Σm2 = m5

NOTE

(From PSD analysis worksheets) any fraction retained less than 20% should **not** be tested.

Tested by: _____ Checked by: _____

Date: _____ Date: _____

Authorised by: AS(Material Science & Technology Branch)

FORM No. A-15

Revised Worksheet: 05/05/2022 lhb