DEPARTMENT OF WORKS & HIGHWAYS

MATERIAL SCIENCE & TECHNOLOGY BRANCH

Materials Testing Laboratory

☑ **Port Moresby,** ☐ **Mt. Hagen,** ☐ **Lae,** ☐ **Annex Lab.**

Date:

Page of

LOS ANGELES VALUE - AS 1141. 23

Client : ---------- Asset No.: ----------

Project: ---------- Job No: ----------

Location: ---------- Material Source / Pit No.: ----------

Material Description: ---------- Depth: ----------

Drying Temperature ---------- No. of Steel Balls ----------

Cooling Temperature ---------- Total Mass ----------

	Prefered Test Grading		Alternative Test Grading			B - 25 % Flaky Particle (For Spalls & Drill cores only)
Selected Test Grading	B	K	A	H	J	
M1 Total Mass of washed & dried material before test g						
Mp Mass of Material passing 1.70mm sieve after abrasion g						
MR Mass of Material retained 1.70mm sieve after abrasion g						
CHECK Mp + MR = M1 ± 25 g						
Mw Mass of Material retained 1.70mm sieve after wash, dried & sieved g						
LA Los Angeles Value (M1 - Mw) / M1 * 100 %						

2. Details of Grading B - 25 Percent Flaky Particle

Sieve Sizes (mm)	37.5 - 26.5	26.5 - 19.0	19.0 - 13.2	13.2 - 9.5	9.5 - 6.70
Percent Flaky Particle					

Notes: Where flaky particles are not to be removed, these must be seperated, weighed and removed.

Tested by: ---------- Checked by: ----------

Date: ---------- Date: ----------

Authorised by: AS(Material Science & Technology Branch)

FORM No. A-23

Revised Worksheet: 091/05/2022 lhb