DEPARTMENT OF WORKS & HIGHWAYS

MATERIAL SCIENCE & TECHNOLOGY BRANCH

Materials Testing Laboratory

☑ **Port Moresby,** ☐ **Mt. Hagen,** ☐ **Lae,** ☐ **Annex Lab.**

Date

Page of

FRACTURED FACES - QT215 & DOW SPEC, 6.2.4(e)

Client : _

Project:_ _

Location: _

Material Description: _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _

Asset No. _ _ _ _ _ _ _ _ _ _ _ _ _ _ _

Job No: _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _

Material Source / Pit No. _ _ _ _ _ _

Depth: _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _

Sieve Sizes	**mm**	**37.5 -26.5**	**26.5-19.0**	**19.0-13.2**	**13.2-9.5**	**9.5-4.75**
Mass of Fraction (M_1)						
Mass of Test Portion * (M_2)	**g**					
Mass of Crushed Particles (CP) (M_3)	**g**					
Percentage of CP in each test Portion, P**	**g**					
Percentage of CP in Test Portion x Mass of Size Fraction ($P \times M_1$)	**%**					
Sum of % of CP x Mass of fraction $\sum(P \times M_1)$	**%**					
Total sum of mass of size fraction $\sum M_1$	**g**					
Total % of Crushed Particle in the sample, . Ps***	**%**					

Note:

Any fractions with <5% of the sample mass and material passing 4.75 mm AS sieve shall not be included in the test.

*** The test portion for the predominant fraction shall be at least 200 pieces and for each other fraction the test portion shall be at least 100 pieces**

**** P = (M3 X 100)/M2**

***** $Ps = \sum(P \times M_1)/\sum M_1$**

Crushed faces is a mechanically fractured face which is rough in texture with sharp edges

Crushed Particle (CP) is a particle having two or more cruched faces

Tested by: _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _

Date: _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _

Checked by: _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _

Date: _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _ _

Authorised by: AS(Material Science & Technology Branch)

FORM No. A-G6.2.4(e)