DEPARTMENT OF WORKS & HIGHWAYS

MATERIAL SCIENCE & TECHNOLOGY BRANCH

Materials Testing Laboratory

[√] **Port Moresby,** [ ] **Mt. Hagen,** [ ] **Lae,** [ ] **Annex Lab.**

Date:

Page of

COMPRESSIVE STRENGTH OF CONCRETE MASONRY UNITS (BLOCKS) -AS/NZS 4456.4
(NET AREA BY DIRECT MEASUREMENT METHOD) - ASNZS - 4456.3

Client: ---------- TYPE OF MASONARY UNIT: ---------- LAB. CURING/ IMMERSION ----------

Project: ---------- SAMPLED BY: ---------- CAPPING MATERIAL: ----------

Location: ---------- SUBMITTED BY: ---------- OPERATOR ----------

Part of Structure: TEST DATE ----------

Lab. No.	I.D No.	Date Cast	Age (Days)	OVERALL DIMENSIONS: Length (mm) Top / Bott. = L	width (mm) Top / Bott. = B	Height (mm) Face1 / Face2 / Head1 / Head2 = H	GROSS AREA A_G=BL (mm^2)	CORE 1: X Top / Bott	CORE 1: Y Top / Bott	CORE 1 AREA $A_1=X_1,Y_1$ (mm^2)	CORE 2: X Top / Bott	CORE 2: Y Top / Bott	CORE 2 AREA $A_2=X_2,Y_2$ (mm^2)	TOTAL CORE AREA $A_C=A_1+A_2$ (mm^2)	NETT AREA A_{Nett} = A_G - A_C (mm^2)	Aspect Ratio Height to Thickn's Ratio	Aspect Factor (K_a)	Mass M (g)	Density kN/m^3	Max LOAD W (kN)	Compr've Strength C = W/A_N (MPa)	Rem'ks

Notes

1. Compressive strength determination in accordance with AS/NZS4456.4
2. Dimension is determined in accordance with AS/NZS4456.3
3. Laboratory Curing: Standard Moist Tropical Zone (unless stated otherwise).
4. Measurement reference Y
5. Capping with plywood

Tested By: _____ **Date:** _____

Checked By: _____ **Date:** _____

Authorised by: AS(Material Science & Technology Branch)

FORM M-4

Revised Worksheet: 11/05/2022 lhb