

ZeAll Standard FRP Molded Grating Specifications & Size (Part)

Serial Number	Height(mm)	Mesh size(mm)	Panel Size(mm)	Open Area
1	13	38x38	1220x3660	78%
2	15	38x38	1220x3660	78%
3	20	38x38	1220x3660	65%
4	25	38x38	1220x3660	68%
5	30	38x38	1220x3660	68%
6	35	38x38	1220x3660	56%
7	38	38x38	1220x3660	68%
8	50	38x38	1220x3660	56%
9	60	38x38	1220x3660	56%
10	25	40x40	1007x4047	67%
11	30	40x40	1247x4047	67%
12	40	40x40	1247x4047	67%
13	13	50x50	1220x4000	82%
14	13	50.8x50.8	1220x4000	82%
15	25	50x50	1220x3660	78%
16	40	50x50	1220x3660	80%
17	50	50x50	1220x3660	78%
18	63	50x50	1220x3660	78%
19	25	83x83	1007x4047	84%
20	40	83x83	1007x4047	84%
21	30	12.7x12.7/40x40	1220x3660	30%
22	25	19x19/38x38	1220x3660	40%
23	38	19x19/38x38	1220x3660	40%
24	14	20x20/40x40	1247x4047	42%
25	30	20x20/40x40	1007x4047	42%
26	40	20x20/40x40	1007x4047	42%
27	50	25x25/50x50	1524x4000	55%
28	38	26x26/52x52	1220x3660	60%
29	38	25x50	1220x3660	48%
30	50	25x50	1220x3660	48%
31	25	25x100	1007x3007	67%
32	30	25x100	1007x3007	67%
33	38	25x100	1220x3660	62%
34	38	38x100	1220x3660	65%
35	38	25x152	1220x3660	63%
36	38	38x152	1220x3660	67%
37	50	38x100	1220x3660	62%

ZeAll uses different resins to achieve different environments. Covering all resin application ranges, our professional sales team will recommend different resin substrates according to customer needs.

Resin System

Resin Type	Resin Base	Description	Corrosion Resistance	Flame Spread Rating ASTM E84	Available colors	Max. Oper. Temp.
VEFR-20	Vinyl Ester	Superior Corrosion Resistance and Fire Retardant	Excellent	Class 1, 20 or less	Dark Gray, Orange	230°F
IFR-25	Isophthalic Polyester	Industrial Grade Corrosion Resistance and Fire Retardant	Very Good	Class 1, 25 or less	Dark Gray, Green	221°F
FG-20	Isophthalic Polyester	Food Grade Corrosion Resistance and Fire Retardant	Very Good	Class 1, 20 or less	Light Gray, Light Green	221°F
CFR-25	Orthophthalic Polyester	Moderate Corrosion Resistance and Fire Retardant	Moderate	Class 1, 25 or less	Green Yellow Light Gray Dark Gray	212°F
MP-4	Phenolic	Low Smoke and Superior Fire Resistance	Very Good	Class 1, 5 or less	Reddish-Brown	356°F
IFR-10	Isophthalic Polyester	Industrial Grade Corrosion Resistance and Extra Fire Retardant	Very Good	Class 1, 10 or less	Custom	221°F