

CHEMICAL COMPOSITION

TYPE GRADE	C	Mn	P	S	Si	Cr	Ni	Cu	Mo	N	Ti	Others
	Max%	Max%	Max%	Max%	Max%	%	%	%	Max	Max	%	%
400	409	0.08	1.00	0.045	0.030	1.00	10.50-12.50	—	—	—	6X%C	—
	409Cb	0.06	1.00	0.045	0.040	1.00	10.50-11.75	0.50 max.	—	—	—	Cb 10XNi-0.75Max
	410	0.15	1.00	0.040	0.030	1.00	11.5-13.5	—	—	—	—	—
	416	0.15	1.00	0.040	0.15-0.30	1.00	12.0-14.0	—	—	—	—	—
	420A	0.15-0.25	1.00	0.040	0.030	1.00	12.0-14.0	—	—	—	—	—
	420B	0.30-0.37	1.00	0.030	0.015	1.00	12.0-14.0	—	—	—	—	—
	420C	0.43-0.50	1.00	0.040	0.030	1.00	12.0-14.0	—	—	—	—	—
	Er420	0.30-0.37	1.00	0.030	0.015	1.00	12.0-14.0	—	—	—	—	—
	430	0.10	1.00	0.040	0.030	0.75	16.0-18.0	0.60	—	—	—	—
	430L	0.030	1.00	0.040	0.030	1.00	16.0-18.0	—	—	—	—	—
	430LNb	0.020	0.80	0.030	0.020	0.50	17.8-18.8	0.30	0.30	0.30	—	No 0.05+7(C+N)0.50
	430Cu	0.12	0.30-0.50	0.040	0.010	0.30-0.50	16.0-18.0	0.50 max.	0.85-1.00	—	—	—
	430F	0.12	1.25	0.060	0.150	1.00	16.0-18.0	—	—	—	—	—
	430F DIN	0.12	1.25	0.060	0.150	1.00	16.0-18.0	—	—	0.20-0.60	—	—
	430Nb	0.08	1.00	0.045	0.030	1.00	16.0-18.0	—	—	—	—	Nb12X%C
	431	0.12-0.22	1.50	0.040	0.015	1.00	15.0-17.0	1.50-2.50	—	—	—	—
	434	0.12	1.00	0.040	0.030	1.00	16.0-18.0	0.50 max.	0.75 max.	0.75-1.25	—	—
	439Ti	0.15	1.00	0.040	0.015	1.00	16.0-18.0	—	—	—	0.15-0.80	—
	441	0.03	1.00	0.040	0.015	1.00	17.5-18.5	—	—	—	0.10-0.60	Nb 0.35-1.00
Duplex Steel	2101	0.040	4.00-6.00	0.040	0.030	1.00	21.00-22.00	1.35-1.70	0.10-0.80	0.10-0.80	0.20-0.25	—
	2205	0.030	2.00	0.030	0.20	1.00	21.00-23.00	4.50-6.50	0.10-0.60	2.50-3.50	0.10-0.22	—
	2209	0.030	0.50-2.00	0.030	0.030	0.90	21.50-23.50	7.50-9.50	0.75	2.50-3.50	0.08-0.20	—
	2304	0.030	2.00	0.030	0.020	1.00	22.0-24.0	3.50-5.50	0.10-0.60	0.10-0.60	0.05-0.22	—
	2553	0.040	1.50	0.040	0.030	1.00	24.0-27.0	4.50-6.50	1.50-2.50	2.90-3.90	0.10-0.25	—
	2594	0.030	2.50	0.030	0.020	1.00	24.0-27.0	8.0-10.50	1.50	2.50-4.50	0.20-0.30	W-1.0

TYPE GRADE	C	Mn	P	S	Si	Cr	Ni	Cu	Mo	N	Ti	Others
	Max%	Max%	Max%	Max%	Max%	%	%	%	Max	Max	%	%
Other Grades	Alloy 82 (ERNiCr-3)	0.05	—	—	—	20.0	67.0min	—	—	—	—	—
	904L	0.025	1.00-2.50	0.020	0.030	0.50	19.5-21.5	24.0-26.0	1.20-2.00	4.20-5.20	—	—
	X 750	0.08	0.30	—	0.010	0.50	14.0-17.0	Ni+Co 70min	0.50	—	2.25-2.75	—
	Nickel 200	0.15	0.35	—	0.010	0.35	—	99.0 min	0.25	—	—	—
	Nickel 600	0.15	1.00	—	0.015	0.50	14.0-17.0	72.0min	0.50	—	0.50	—
	Inconel 625	0.10	0.50	0.015	0.015	0.50	20.0-23.0	58.0min	—	8.0-10.0	0.40 max	—
	C-276	0.01	1.00	0.040	0.030	0.08	14.5-16.5	Bal.	—	15.0-17.0	—	—
	Alloy 020	0.07	2.00	0.045	0.035	1.00	19.0-21.0	32.0-38.0	3.00-4.00	2.00-3.00	—	—
	Incoloy 825	0.05	1.00	—	0.030	0.50	19.5-23.5	38.0-46.0	1.50-3.00	2.50-3.50	0.60-1.20	—
	631 (17-7PH)	0.09	1.00	0.040	0.030	1.00	16.0-18.0	6.50-7.80	—	—	—	Al0.75-1.50
	Monel 400	0.30	2.00	—	0.024	0.50	—	63.0min	28.0-34.0	—	—	—
	A 286	0.080	2.00	—	0.030	1.00	13.5-16.0	24.0-27.0	---	1.00-1.50	1.90-2.35	B.0.001-0.010