

CHEMICAL COMPOSITION

	TYPE	C	Mn	P	S	Si	Cr	Ni	Cu	Mo	N	Ti	Others
	GRADE	Max%	Max%	Max%	Max%	Max%	%	%	%	Max	Max	%	%
200	201 (0.9% Ni)	0.15	7.00-9.00	0.100	0.030	1.00	14.0-16.0	0.90-1.20	1.50-2.50	0.30	0.25	—	-
	201 (3%Ni)	0.15	7.00-9.00	0.100	0.030	1.00	14.0-17.0	3.00-4.00	1.50-2.50	0.30	0.25	—	-
	AISI 201	0.15	5.50-7.50	0.060	0.030	0.75	16.0-18.0	3.50-5.50	0.75	—	0.25	—	-
	204 Cu	0.08	6.50-8.50	0.060	0.030	2.00	16.0-17.0	1.50-3.00	2.00-3.00	0.30	0.25	—	-
300	301	0.12	2.00	0.045	0.030	1.00	16.0-18.0	6.0-8.0	—	—	0.10	—	-
	302	0.12	2.00	0.045	0.030	1.00	17.0-19.0	8.0-10.0	—	—	0.10	—	-
	302HQ	0.03	2.00	0.045	0.030	1.00	17.0-19.0	9.0-11.0	3.0-4.0	—	—	—	-
	Xm7	0.03	2.00	0.045	0.030	1.00	17.0-19.0	8.0-10.0	3.0-4.0	0.10	—	—	-
	303	0.08	2.00	0.045	0.15-0.35	1.00	17.0-19.0	8.0-10.0	—	—	—	—	-
	303Cu	0.08	2.50	0.045	0.15-0.35	1.00	17.0-19.0	8.0-10.0	1.4-3.0	—	0.10	—	-
	304	0.08	2.00	0.045	0.030	1.00	18.0-20.0	8.0-10.0	—	—	—	—	-
	304HC	0.08	2.00	0.045	0.030	1.00	18.0-20.0	8.0-10.0	2.0-3.0	—	—	—	-
	304L	0.03	2.00	0.045	0.030	1.00	18.0-20.0	10.0-12.0	---	—	—	—	-
	304L	0.03	2.00	0.045	0.030	1.00	17.5-19.5	8.0-10.5	—	—	—	—	-
	305	0.06	2.00	0.045	0.030	1.00	17.0-19.0	11.0-13.0	—	—	—	—	-
	310S	0.08	2.00	0.045	0.030	1.50	24.0-26.0	19.0-22.0	—	—	0.14-0.20	—	Ce0.030-0.080
	253MA	0.05-0.10	0.80	0.040	0.030	1.10-2.00	20.0-22.0	10.0-12.0	—	—	—	—	-
	314	0.25	2.00	0.045	0.030	1.50-3.00	23.0-26.0	19.0-22.0	—	—	—	—	-
	316	0.08	2.00	0.040	0.030	1.00	16.0-18.0	10.0-14.0	—	2.00-3.00	—	—	-
	316 (2.5Mo)	0.05	2.00	0.045	0.030	1.00	16.5-18.5	10.5-13.0	—	2.50-3.00	0.11	—	-
	316L	0.03	2.00	0.045	0.030	1.00	16.0-18.0	10.0-14.0	—	2.00-3.00	—	—	-
	316LYM	0.03	2.00	0.025	0.010	0.75	17.0-19.0	13.0-15.0	—	2.50-3.00	0.10	—	-
	316Ti	0.08	2.00	0.045	0.030	1.00	16.0-18.0	10.0-12.0	—	2.00-3.00	—	5X%Cupto0.8	-
	ER317L	0.03	1.00-2.50	0.030	0.030	0.30-0.65	18.0-20.50	13.0-15.0	0.75	3.00-4.00	—	—	-
	ER318Si	0.08	1.00-2.50	0.030	0.030	0.65-1.00	18.0-20.0	11.0-14.0	0.75	2.00-3.00	—	—	Nb=8XCmin-1.00% max
	321	0.08	2.00	0.045	0.030	1.00	17.0-19.0	9.0-13.0	—	—	—	5X%Cminimum	-
	321H	0.04-0.08	2.00	0.045	0.030	1.00	17.0-19.0	9.0-13.0	—	—	—	5X%Cminimum	-
	347	0.08	2.00	0.045	0.030	1.00	17.0-19.0	9.0-13.0	—	—	—	—	Nb>=10xC
	347H	0.04-0.08	2.00	0.045	0.030	1.00	17.0-19.0	9.0-13.0	—	—	—	—	Nb>=10xC
	Er347	0.08	2.50	0.030	0.030	0.30-0.65	19.0-21.5	9.0-11.0	0.75	—	—	—	Nb=10xCmin-1.0%max
	ER307S	0.12	6.00/7.50	0.030	0.020	0.65-0.95	17.2-19.8	8.0-9.4	0.30	0.30	—	—	-
	Er308	0.04-0.08	2.00	0.020	0.020	0.30-0.65	19.0-21.0	9.5-11.0	—	—	—	—	-
	Er308L	0.03	1.00-2.50	0.030	0.030	0.30-0.65	19.5-22.0	9.0-11.0	—	—	—	—	-
	ER308Ls	0.03	1.00-2.50	0.030	0.030	0.65-1.00	19.5-22.0	9.0-11.0	—	—	—	—	-
	ER30L(Low%Si)	0.02	1.00-2.50	0.020	0.010	0.15	19.5-22.0	9.5-11.5	—	—	—	—	-
	ER309L	0.03	1.00-2.50	0.030	0.010	0.30-0.65	23.0-25.0	12.0-14.0	—	—	—	—	-
	Er309Lsi	0.03	1.00-2.50	0.030	0.030	0.65-1.00	23.0-25.0	12.0-14.0	—	—	—	—	-
	Er310	0.08-0.15	1.50/2.50	0.030	0.025	0.30-0.65	25.0-28.0	20.0-22.0	—	—	—	—	-
	Er312	0.15	2.00	0.025	0.025	0.30-0.65	29.0-32.0	8.0-10.0	—	—	—	—	-
	ER316L	0.03	1.00-2.50	0.030	0.030	0.30-0.65	18.0-20.0	11.0-14.0	—	2.20-2.75	—	—	-
ER316Lsi	0.03	1.00-2.50	0.030	0.030	0.65-1.00	18.0-20.0	11.0-14.0	—	2.00-3.00	—	—	-	
ER316L(Low %Si)	0.02	1.00-2.50	0.020	0.010	0.15	18.0-20.0	11.0-14.0	—	2.50-3.00	—	—	-	
2340	0.10	2.00	0.040	0.030	1.00	16.0-18.0	8.0-10.0	—	1.30-1.80	—	—	-	