

Beckry® Fluor 630

AAMA 2605-13 PVDF Test Certificate



Adding Value Beyond the Surface

Customer: EUROCON BUILDING INDUSTRIES FZE

Tests	AAMA 2605-13 Requirements	RESULT
Dry Film Thickness (ASTM D 7091)	38 ± 2µm	40
Colour Uniformity (ASTM D2244)	Light Color	0.32
Specular Gloss (ASTM D523 @ 60°)	15 - 35	32.2 units
Pencil Hardness (ASTM D3363)	HB minimum hardness	2H Pass
Film Adhesion (11 x 1 mm cross hatch / ASTM D 3359)		
1) Dry Adhesion (18°C - 27°C)	100% Adhesion	Excellent - No Removal
2) Wet Adhesion (38°C @ 24 hours)	100% Adhesion	Excellent - No Removal
3) Boiling Water Test (99°C - 100°C @ 20 mins)	100% Adhesion	Excellent - No Removal
Reverse Impact Resistance : (ASTM D 2794)	Load = 1.5 * metal thickness	Excellent - No Removal
Coating Flexibility : T-Bend (ASTM 4145)	2T NR, Minute cracking permissible	1T Pass
Abrasion Resistance (ASTM D968)	40 liters /mil minimum	57
Chemical Resistance (ASTM 1308)		
1) Muriatic Acid Resistance (15mins Spot Test)	No blister and visual change	Pass: No Blister
2) Mortar Resistance (24 hours Pat Test)	No adhesion loss or visual change	Pass: No Visual Change
3) Nitric Acid Resistance (30 min Vapour Test)	Delta E ≤ 5.0 (Hunterlab)	Pass: DE 0.4
4) Detergent Resistance (72 hours Test) (ASTMD2248)	No adhesion loss or visual change	Pass: No Visual Change
Corrosion Resistance		
1) Humidity 4000 hours (ASTM D2247)	"Few" blisters size No. 8; Fig. No. 4 (D714)	Pass; No Blister
2) Salt Spray 4000 hours (ASTM B117)	Min. rating of 7 on cut edges, 8 of blistering rating (ASTM D1654)	Pass; No Blister
Weathering (10 years – 45°South Florida) as per AAMA 2605-13		
1) Colour Retention (ASTM D2244)	Delta E ≤ 5.0	Pass; DE 1.8
2) Chalk Resistance (ASTM D4214)	Max. No. 8 for color, No. 6 on White	Chalking Rating; 8
3) Gloss Retention (ASTM D523)	Min 50% @ 60°	GR % 96
4) Erosion (ASTM B244)	<10% Dry Film Thickness Loss	Pass < 1.46%
The above-mentioned test results are under the standard test conditions on Al substrate as per 2605-13 test method		
Prepared by	Saravanan Natarajan (R & D Manager – Beckers RAK)	Date 24.June.2025

Becker Industrial Coatings L.L.C
P.O.Box 12795, RAK, U.A.E,
Tel: +971-7-2278843,
Fax: +971-4-2278863,
Email:info-uae@beckers-group.com



KYNAR500FSF
BY ARKEMA