



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

SURFACE PREPARATION & PRIMER PAINT INSPECTION REPORT

CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2
WO/PO NO	9558569010	PROCEDURE NO.	PRS/4	OFFER DATE	08/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32

SURFACE CONDITION

ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST	METAL RUST GRADE	B
PAINT SYSTEM NO.	BUILDING STR			BLASTING DATE	08/03/2025

SURFACE PREPARATION

BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2	ABRASIVE TYPE	MIXTURE OF GRIT & SHOT
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns		
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m2	SALT TEST READING	28 mg/m2

PRIMER COATING

PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY	PRIMER DATE	08/03/2025
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns	TIME	12:40 PM
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025	SHELF LIFE	6 MONTH
PAINT BATCH NO. (HARDNER)	Q0D4561				

SR. NO.	DRAWING NO.	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
					PRIMER	
1	TCE-13282A-CV-3066-ST-31020-ASS-FR4	FR4	FR4	1	78 - 90	ACC
2	TCE-13282A-CV-3066-ST-31020-ASS-FR5	FR5	FR5	1	70 - 90	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	SHIVANG DIWAKAR				
DATE	08/03/2025				



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

SURFACE PREPARATION & PRIMER PAINT INSPECTION REPORT

CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2
WO/PO NO	9558569010	PROCEDURE NO.	PRS/4	OFFER DATE	08/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32

SURFACE CONDITION

ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST	METAL RUST GRADE	B
PAINT SYSTEM NO.	BUILDING STR			BLASTING DATE	08/03/2025

SURFACE PREPARATION

BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2	ABRASIVE TYPE	MIXTURE OF GRIT & SHOT
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns		
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m ²	SALT TEST READING	28 mg/m ²



PRIMER COATING

PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY	PRIMER DATE	08/03/2025
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns	TIME	12:40 PM
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025	SHELF LIFE	6 MONTH
PAINT BATCH NO. (HARDNER)	Q0D4561				



SR. NO.	DRAWING NO.	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
					PRIMER	
3	TCE-13282A-CV-3066-ST-31020-ASS-FR6	FR6	FR6	1	75 - 90	ACC
4	TCE-13282A-CV-3066-ST-31020-ASS-FR8	FR8	FR8	1	70 - 80	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	SHIVANG DIWAKAR				

DATE	08/03/2025	
VE-STR-16		

  <div style="text-align: center;"> VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES </div>									
SURFACE PREPARATION & PRIMER PAINT INSPECTION REPORT									
CLIENT	PIYUSH ENTERPRISE		PROJECT	PIYUSH BUILDING		REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2		
WO/PO NO	9558569010		PROCEDURE NO.	PRS/4		OFFER DATE	08/03/2025		
WEATHER CONDITION									
ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32
SURFACE CONDITION									
ORIGINAL STATUS		NON COATED	METAL CONDITION		SURFACE BEGUN TO RUST	METAL RUST GRADE		B	
PAINT SYSTEM NO.		BUILDING STR				BLASTING DATE		08/03/2025	
SURFACE PREPARATION									
BLASTING METHOD		AUTO BLAST	PREP. STANDARD		SA 2 1/2	ABRASIVE TYPE		MIXTURE OF GRIT & SHOT	
SURFACE PROFILE REQUIREMENT		40 - 75 microns	ACTUAL SURFACE PROFILE		50 - 60 microns				
DUST LEVEL		01	SALT TEST REQUIRED		Maximum 50 kg/m2	SALT TEST READING		28 mg/m2	
PRIMER COATING									
PRIMER PAINT/SHADE		APCOSIL 605	APP. METHOD		SPRAY	PRIMER DATE		08/03/2025	
PAINT MANUFACTURER		ASIAN PPG	DFT RANGE		75 - 100 microns	TIME		12:40 PM	
PAINT BATCH NO. (BASE)		Q0D4567	MANUFACTURE DATE		14/01/2025	SHELF LIFE		6 MONTH	
PAINT BATCH NO. (HARDNER)		Q0D4561							
SR. NO.	DRAWING NO.	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT		ACC/REJ		
					PRIMER				
5	TCE-13282A-CV-3066-ST-31020-ASS-FR9	FR9	FR9	1	75 - 90		ACC		
6	TCE-13282A-CV-3066-ST-31020-ASS-FR10	FR10	FR10	1	80 - 90		ACC		
NOTE									
VISHAL QC				CLIENT / TPIA					
SIGN									



NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	
VE-STR-16		

 		<h2 style="text-align: center;">VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES</h2>							
SURFACE PREPARATION & PRIMER PAINT INSPECTION REPORT									
CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING		REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2			
WO/PO NO	9558569010	PROCEDURE NO.	PRS/4		OFFER DATE	08/03/2025			
WEATHER CONDITION									
ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32
SURFACE CONDITION									
ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST		METAL RUST GRADE	B			
PAINT SYSTEM NO.	BUILDING STR					BLASTING DATE	08/03/2025		
SURFACE PREPARATION									
BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2		ABRASIVE TYPE	MIXTURE OF GRIT & SHOT			
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns						
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m2		SALT TEST READING	28 mg/m2			
PRIMER COATING									
PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY		PRIMER DATE	08/03/2025			
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns		TIME	12:40 PM			
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025		SHELF LIFE	6 MONTH			
PAINT BATCH NO. (HARDNER)	Q0D4561								
SR. NO.	DRAWING NO.	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ			
					PRIMER				
7	TCE-13282A-CV-3066-ST-31020-ASS-FR11	FR11	FR11	1	96 -100	ACC			
8	TCE-13282A-CV-3066-ST-31020-ASS-FR12	FR12	FR12	1	90 - 98	ACC			
NOTE	--								
VISHAL QC					CLIENT / TPJA				

SIGN		
NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	
VE-STR-16		

<div style="display: flex; align-items: center; justify-content: space-between;"> <div style="display: flex; align-items: center;"> </div> <div style="text-align: center;"> <h2 style="margin: 0;">VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED</h2> <h3 style="margin: 0;">GROUP OF COMPANIES</h3> </div> </div>									
SURFACE PREPARATION & PRIMER PAINT INSPECTION REPORT									
CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2				
WO/PO NO	9558569010	PROCEDURE NO.	PRS/4	OFFER DATE	08/03/2025				
WEATHER CONDITION									
ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32
SURFACE CONDITION									
ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST		METAL RUST GRADE	B			
PAINT SYSTEM NO.	BUILDING STR				BLASTING DATE	08/03/2025			
SURFACE PREPARATION									
BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2		ABRASIVE TYPE	MIXTURE OF GRIT & SHOT			
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns						
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m2		SALT TEST READING	28 mg/m2			
PRIMER COATING									
PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY		PRIMER DATE	08/03/2025			
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns		TIME	12:40 PM			
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025		SHELF LIFE	6 MONTH			
PAINT BATCH NO. (HARDNER)	Q0D4561								
SR. NO.	DRAWING NO.	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ			
					PRIMER				
9	TCE-13282A-CV-3066-ST-31020-ASS-FR13	FR13	FR13	1	79 - 90	ACC			
10	TCE-13282A-CV-3066-ST-31020-ASS-FR14	FR14	FR14	1	86 - 96	ACC			
NOTE	--								

	VISHAL QC	CLIENT / TPIA
SIGN		
NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	
VE-STR-16		

  <div style="text-align: center;"> VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES </div>									
SURFACE PREPARATION & PRIMER PAINT INSPECTION REPORT									
CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2				
WO/PO NO	9558569010	PROCEDURE NO.	PRS/4	OFFER DATE	08/03/2025				
WEATHER CONDITION									
ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32
SURFACE CONDITION									
ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST		METAL RUST GRADE	B			
PAINT SYSTEM NO.	BUILDING STR				BLASTING DATE	08/03/2025			
SURFACE PREPARATION									
BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2		ABRASIVE TYPE	MIXTURE OF GRIT & SHOT			
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns						
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m2		SALT TEST READING	28 mg/m2			
PRIMER COATING									
PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY		PRIMER DATE	08/03/2025			
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns		TIME	12:40 PM			
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025		SHELF LIFE	6 MONTH			
PAINT BATCH NO. (HARDNER)	Q0D4561								
SR. NO.	DRAWING NO.	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ			
					PRIMER				
11	TCE-13282A-CV-3066-ST-31020-ASS-FR15	FR15	FR15	1	90 - 96	ACC			
NOTE	--								

	VISHAL QC	CLIENT / TPIA
SIGN		
NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	
VE-STR-16		