



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT	SURAJ ROSHNI	PROJECT	SURYA-25	REPORT NO.	VE/SURYA-25/STR/MIO/6
WO/PO NO	898989890000	PROCEDURE NO.	VEPL/DCM/ITP/001	OFFER DATE	25/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 22:10				FINISH TIME- 23:10			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	24/03/2025	28	22	61	29	30	24	67	31

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	SIGMA 620	APP. METHOD	SPRAY	MIO DATE	24/03/2025
PAINT MANUFACTURER	SIGMA PPG	DFT RANGE	200 microns (Including Primer : 300 microns)	HARD DRY TIME	4 HOUR
PAINT BATCH NO. (BASE)	Q089256	MANUFACTURE DATE	16/01/2025	SHELF LIFE	1 YEAR
PAINT BATCH NO. (HARDNER)	Q089255				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
1	TCE-13282A-CV-2026-ST-30306-ASS-B1	0	B1	B1-1	5	309 - 319	ACC
2	TCE-13282A-CV-2026-ST-30306-ASS-B1	0	B1	B1-2	5	305 - 324	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPJA	
SIGN					
NAME	SHIVANG DIWAKAR				
DATE	25/03/2025				

VE-STR-16C