



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT	SURAJ ROSHNI	PROJECT	SURYA-25	REPORT NO.	VE/SURYA-25/STR/MIO/2
WO/PO NO	898989890000	PROCEDURE NO.	VEPL/DCM/ITP/001	OFFER DATE	20/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START				FINISH			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	20/03/2025	33	28	62	32	34	28	66	34

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	Intergard 475HS / Light gray	APP. METHOD	SPRAY	MIO DATE	20/03/2025
PAINT MANUFACTURER	AKZONOBEL INDIA	DFT RANGE	200 microns (Including Primer : 300 microns)	TIME	01:40 PM
PAINT BATCH NO. (BASE)	Q089256	MANUFACTURE DATE	09/01/2025	SHELF LIFE	1 YEAR
PAINT BATCH NO. (HARDNER)	Q089255				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
1	TCE-13282A-CV-2026-ST-30306-ASS-B44	1	B44	B44	1	310 - 328	ACC
2	TCE-13282A-CV-2026-ST-30306-ASS-B43	1	B43	B43	1	307 - 317	ACC
3	TCE-13282A-CV-2026-ST-30306-ASS-B23	1	B23	B23	2	318 - 325	ACC
4	TCE-13282A-CV-2026-ST-30306-ASS-B21	1	B21	B21-1	5	308 - 319	ACC
5	TCE-13282A-CV-2026-ST-30306-ASS-B21	1	B21	B21-2	6	302 - 316	ACC
6	TCE-13282A-CV-2026-ST-30306-ASS-B14	2	B14	B14-2	1	306 - 317	ACC
7	TCE-13282A-CV-2026-ST-30306-ASS-B14	2	B14	B14-1	4	302 - 320	ACC
8	TCE-13282A-CV-2026-ST-30306-ASS-B14	2	B14	B14-3	3	305 - 322	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	SHIVANG DIWAKAR				
DATE	20/03/2025				

VE-STR-16C



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT	SURAJ ROSHNI	PROJECT	SURYA-25	REPORT NO.	VE/SURYA-25/STR/MIO/2
WO/PO NO	898989890000	PROCEDURE NO.	VEPL/DCM/ITP/001	OFFER DATE	20/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START				FINISH			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	20/03/2025	33	28	62	32	34	28	66	34

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	Intergard 475HS / Light gray	APP. METHOD	SPRAY	MIO DATE	20/03/2025
PAINT MANUFACTURER	AKZONOBEL INDIA	DFT RANGE	200 microns (Including Primer : 300 microns)	TIME	01:40 PM
PAINT BATCH NO. (BASE)	Q089256	MANUFACTURE DATE	09/01/2025	SHELF LIFE	1 YEAR
PAINT BATCH NO. (HARDNER)	Q089255				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
9	TCE-13282A-CV-2026-ST-30306-ASS-B13	2	B13	B13	1	308 - 320	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	SHIVANG DIWAKAR				
DATE	20/03/2025				

VE-STR-16C