



# VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

## SURFACE PREPARATION & PRIMER PAINT INSPECTION REPORT

CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2
WO/PO NO	9558569010	PROCEDURE NO.	VEPL/NFASL/EPCM/QSI-002	OFFER DATE	08/03/2025

### WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32

### SURFACE CONDITION

ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST	METAL RUST GRADE	B
PAINT SYSTEM NO.	BUILDING STR			BLASTING DATE	08/03/2025

### SURFACE PREPARATION

BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2	ABRASIVE TYPE	MIXTURE OF GRIT & SHOT
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns		
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m2	SALT TEST READING	28 mg/m2

### PRIMER COATING

PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY	PRIMER DATE	08/03/2025
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns	HARD DRY TIME	12:40 PM
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025	SHELF LIFE	6 MONTH
PAINT BATCH NO. (HARDNER)	Q0D4561				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						PRIMER	
1	TCE-13282A-CV-3066-ST-31020-ASS-FR4	0	FR4	FR4	1	78 - 90	ACC
2	TCE-13282A-CV-3066-ST-31020-ASS-FR5	0	FR5	FR5	1	70 - 90	ACC
NOTE	--						
	VISHAL QC			CLIENT / TPIA			
SIGN							
NAME	SHIVANG DIWAKAR						
DATE	08/03/2025						



## VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

### SURFACE PREPARATION & PRIMER PAINT INSPECTION REPORT

CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2
WO/PO NO	9558569010	PROCEDURE NO.	VEPL/NFASL/EPCM/QSI-002	OFFER DATE	08/03/2025

#### WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32

#### SURFACE CONDITION

ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST	METAL RUST GRADE	B
PAINT SYSTEM NO.	BUILDING STR			BLASTING DATE	08/03/2025

#### SURFACE PREPARATION

BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2	ABRASIVE TYPE	MIXTURE OF GRIT & SHOT
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns		
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m2	SALT TEST READING	28 mg/m2



#### PRIMER COATING

PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY	PRIMER DATE	08/03/2025
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns	HARD DRY TIME	12:40 PM
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025	SHELF LIFE	6 MONTH
PAINT BATCH NO. (HARDNER)	Q0D4561				



SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						PRIMER	
3	TCE-13282A-CV-3066-ST-31020-ASS-FR6	0	FR6	FR6	1	75 - 90	ACC
4	TCE-13282A-CV-3066-ST-31020-ASS-FR8	0	FR8	FR8	1	70 - 80	ACC

NOTE	--	
	VISHAL QC	CLIENT / TPIA
SIGN		
NAME	SHIVANG DIWAKAR	



DATE	08/03/2025	
VE-STR-16		

 		<b>VISHAL ENTERPRISE &amp; VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES</b>							
SURFACE PREPARATION & PRIMER PAINT INSPECTION REPORT									
CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2				
WO/PO NO	9558569010	PROCEDURE NO.	VEPL/NFASL/EPCM/QSI-002	OFFER DATE	08/03/2025				
WEATHER CONDITION									
ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32
SURFACE CONDITION									
ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST		METAL RUST GRADE	B			
PAINT SYSTEM NO.	BUILDING STR				BLASTING DATE	08/03/2025			
SURFACE PREPARATION									
BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2		ABRASIVE TYPE	MIXTURE OF GRIT & SHOT			
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns						
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m2		SALT TEST READING	28 mg/m2			
PRIMER COATING									
PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY		PRIMER DATE	08/03/2025			
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns		HARD DRY TIME	12:40 PM			
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025		SHELF LIFE	6 MONTH			
PAINT BATCH NO. (HARDNER)	Q0D4561								
SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT		ACC/REJ	
						PRIMER			
5	TCE-13282A-CV-3066-ST-31020-ASS-FR9	0	FR9	FR9	1	75 - 90		ACC	
6	TCE-13282A-CV-3066-ST-31020-ASS-FR10	0	FR10	FR10	1	80 - 90		ACC	
NOTE	--								
VISHAL QC				CLIENT / TPIA					
SIGN									



NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	
VE-STR-16		

  <div style="text-align: center;"> <b>VISHAL ENTERPRISE &amp; VRISHAL ENGINEERING PRIVATE LIMITED</b>  <b>GROUP OF COMPANIES</b> </div>									
<b>SURFACE PREPARATION &amp; PRIMER PAINT INSPECTION REPORT</b>									
CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2				
WO/PO NO	9558569010	PROCEDURE NO.	VEPL/NFASL/EPCM/QSI-002	OFFER DATE	08/03/2025				
<b>WEATHER CONDITION</b>									
ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32
<b>SURFACE CONDITION</b>									
ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST		METAL RUST GRADE	B			
PAINT SYSTEM NO.	BUILDING STR				BLASTING DATE	08/03/2025			
<b>SURFACE PREPARATION</b>									
BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2		ABRASIVE TYPE	MIXTURE OF GRIT & SHOT			
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns						
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m2		SALT TEST READING	28 mg/m2			
<b>PRIMER COATING</b>									
PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY		PRIMER DATE	08/03/2025			
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns		HARD DRY TIME	12:40 PM			
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025		SHELF LIFE	6 MONTH			
PAINT BATCH NO. (HARDNER)	Q0D4561								
SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ		
						PRIMER			
7	TCE-13282A-CV-3066-ST-31020-ASS-FR11	0	FR11	FR11	1	96 -100	ACC		
8	TCE-13282A-CV-3066-ST-31020-ASS-FR12	0	FR12	FR12	1	90 - 98	ACC		
NOTE	--								
VISHAL QC				CLIENT / TPIA					

SIGN		
NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	
VE-STR-16		

  <div style="text-align: center;"> <b>VISHAL ENTERPRISE &amp; VRISHAL ENGINEERING PRIVATE LIMITED</b>  <b>GROUP OF COMPANIES</b> </div>									
<b>SURFACE PREPARATION &amp; PRIMER PAINT INSPECTION REPORT</b>									
CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2				
WO/PO NO	9558569010	PROCEDURE NO.	VEPL/NFASL/EPCM/QSI-002	OFFER DATE	08/03/2025				
<b>WEATHER CONDITION</b>									
ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32
<b>SURFACE CONDITION</b>									
ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST	METAL RUST GRADE	B				
PAINT SYSTEM NO.	BUILDING STR				BLASTING DATE	08/03/2025			
<b>SURFACE PREPARATION</b>									
BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2	ABRASIVE TYPE	MIXTURE OF GRIT & SHOT				
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns						
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m2	SALT TEST READING	28 mg/m2				
<b>PRIMER COATING</b>									
PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY	PRIMER DATE	08/03/2025				
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns	HARD DRY TIME	12:40 PM				
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025	SHELF LIFE	6 MONTH				
PAINT BATCH NO. (HARDNER)	Q0D4561								
SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT		ACC/REJ	
						PRIMER			
9	TCE-13282A-CV-3066-ST-31020-ASS-FR13	0	FR13	FR13	1	79 - 90		ACC	
10	TCE-13282A-CV-3066-ST-31020-ASS-FR14	0	FR14	FR14	1	86 - 96		ACC	
NOTE	--								

	VISHAL QC	CLIENT / TPIA
SIGN		
NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	
VE-STR-16		

  <div style="text-align: center;"> <b>VISHAL ENTERPRISE &amp; VRISHAL ENGINEERING PRIVATE LIMITED</b>  <b>GROUP OF COMPANIES</b> </div>									
<b>SURFACE PREPARATION &amp; PRIMER PAINT INSPECTION REPORT</b>									
CLIENT	PIYUSH ENTERPRISE		PROJECT	PIYUSH BUILDING		REPORT NO.	VE/PIYUSH BUILDING/STR/SP/2		
WO/PO NO	9558569010		PROCEDURE NO.	VEPL/NFASL/EPCM/QSI-002		OFFER DATE	08/03/2025		
<b>WEATHER CONDITION</b>									
ACTIVITY	DATE PERFORMED	START TIME - 10:26				FINISH TIME- 12:26			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
Blasting / Surf. Prep.	08/03/2025	28	25	67	29	29	25	69	30
Primer Application	08/03/2025	27	23	74	30	30	24	70	32
<b>SURFACE CONDITION</b>									
ORIGINAL STATUS	NON COATED	METAL CONDITION	SURFACE BEGUN TO RUST		METAL RUST GRADE	B			
PAINT SYSTEM NO.	BUILDING STR					BLASTING DATE	08/03/2025		
<b>SURFACE PREPARATION</b>									
BLASTING METHOD	AUTO BLAST	PREP. STANDARD	SA 2 1/2		ABRASIVE TYPE	MIXTURE OF GRIT & SHOT			
SURFACE PROFILE REQUIREMENT	40 - 75 microns	ACTUAL SURFACE PROFILE	50 - 60 microns						
DUST LEVEL	01	SALT TEST REQUIRED	Maximum 50 kg/m2		SALT TEST READING	28 mg/m2			
<b>PRIMER COATING</b>									
PRIMER PAINT/SHADE	APCOSIL 605	APP. METHOD	SPRAY		PRIMER DATE	08/03/2025			
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	75 - 100 microns		HARD DRY TIME	12:40 PM			
PAINT BATCH NO. (BASE)	Q0D4567	MANUFACTURE DATE	14/01/2025		SHELF LIFE	6 MONTH			
PAINT BATCH NO. (HARDNER)	Q0D4561								
SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT		ACC/REJ	
						PRIMER			
11	TCE-13282A-CV-3066-ST-31020-ASS-FR15	0	FR15	FR15	1	90 - 96		ACC	
NOTE	--								

	VISHAL QC	CLIENT / TPIA
SIGN		
NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	
VE-STR-16		