



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/MIO/3
WO/PO NO	9558569010	PROCEDURE NO.	VEPL/NFASL/EPCM/QSI-002	OFFER DATE	08/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 17:10				FINISH TIME- 18:10			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	08/03/2025	29	23	66	30	30	24	70	31

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	APCODUR MIO 400	APP. METHOD	SPRAY	MIO DATE	08/03/2025
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	200 microns (Including Primer : 300 microns)	HARD DRY TIME	5:10 PM
PAINT BATCH NO. (BASE)	Q089256	MANUFACTURE DATE	08/01/2025	SHELF LIFE	1 YEAR
PAINT BATCH NO. (HARDNER)	Q089255				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
1	TCE-13282A-CV-3066-ST-31020-ASS-FR2	0	FR2	FR2-3	1	310 - 350	ACC
2	TCE-13282A-CV-3066-ST-31020-ASS-FR2	0	FR2	FR2-4	1	315 - 330	ACC
3	TCE-13282A-CV-3066-ST-31020-ASS-FR2	0	FR2	FR2-1	1	318 - 330	ACC
4	TCE-13282A-CV-3066-ST-31020-ASS-FR2	0	FR2	FR2-5	1	320 - 350	ACC
5	TCE-13282A-CV-3066-ST-31020-ASS-FR2	0	FR2	FR2-2	1	310 - 330	ACC
6	TCE-13282A-CV-3066-ST-31020-ASS-FR3	0	FR3	FR3-3	1	315 - 330	ACC
7	TCE-13282A-CV-3066-ST-31020-ASS-FR3	0	FR3	FR3-2	1	312 - 330	ACC
8	TCE-13282A-CV-3066-ST-31020-ASS-FR3	0	FR3	FR3-1	1	310 - 340	ACC

NOTE	--
------	----

	VISHAL QC	CLIENT / TPIA
SIGN		
NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	

VE-STR-16C



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/MIO/3
WO/PO NO	9558569010	PROCEDURE NO.	VEPL/NFASL/EPCM/QSI-002	OFFER DATE	08/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 17:10				FINISH TIME- 18:10			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	08/03/2025	29	23	66	30	30	24	70	31

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	APCODUR MIO 400	APP. METHOD	SPRAY	MIO DATE	08/03/2025
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	200 microns (Including Primer : 300 microns)	HARD DRY TIME	5:10 PM
PAINT BATCH NO. (BASE)	Q089256	MANUFACTURE DATE	08/01/2025	SHELF LIFE	1 YEAR
PAINT BATCH NO. (HARDNER)	Q089255				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
9	TCE-13282A-CV-3066-ST-31020-ASS-FR3	0	FR3	FR3-4	1	310 - 350	ACC
10	TCE-13282A-CV-3066-ST-31020-ASS-FR3	0	FR3	FR3-5	1	315 - 340	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	SHIVANG DIWAKAR				
DATE	08/03/2025				

VE-STR-16C