



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT	SURAJ ROSHNI	PROJECT	SURYA-25	REPORT NO.	VE/SURYA-25/STR/MIO/1
WO/PO NO	898989890000	PROCEDURE NO.	VEPL/DCM/ITP/001	OFFER DATE	20/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START				FINISH			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	20/03/2025	33	29	62	32	34	28	63	32

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	Intergard 475HS / Light gray	APP. METHOD	SPRAY	MIO DATE	20/03/2025
PAINT MANUFACTURER	AKZONOBEL INDIA	DFT RANGE	200 microns (Including Primer : 300 microns)	TIME	12:34 PM
PAINT BATCH NO. (BASE)	Q089256	MANUFACTURE DATE	28/02/2025	SHELF LIFE	1 YEAR
PAINT BATCH NO. (HARDNER)	Q089255				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
1	TCE-13282A-CV-2026-ST-30306-ASS-B4	0	B4	B4	2	300 - 320	ACC
2	TCE-13282A-CV-2026-ST-30306-ASS-B5	0	B5	B5	1	310 - 330	ACC
3	TCE-13282A-CV-2026-ST-30306-ASS-B7	0	B7	B7	1	305 - 332	ACC
4	TCE-13282A-CV-2026-ST-30306-ASS-B6	0	B6	B6	1	302 - 323	ACC
5	TCE-13282A-CV-2026-ST-30306-ASS-B9	1	B9	B9-1	1	305 - 320	ACC
6	TCE-13282A-CV-2026-ST-30306-ASS-B9	1	B9	B9-2	1	310 - 320	ACC
7	TCE-13282A-CV-2026-ST-30306-ASS-B10	0	B10	B10-2	1	305 - 315	ACC
8	TCE-13282A-CV-2026-ST-30306-ASS-B10	0	B10	B10-1	8	300 - 310	ACC

NOTE	--
------	----

	VISHAL QC	CLIENT / TPIA
--	-----------	---------------

SIGN	
------	--

NAME	SHIVANG DIWAKAR
------	-----------------

DATE	20/03/2025
------	------------

VE-STR-16C



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT	SURAJ ROSHNI	PROJECT	SURYA-25	REPORT NO.	VE/SURYA-25/STR/MIO/1
WO/PO NO	898989890000	PROCEDURE NO.	VEPL/DCM/ITP/001	OFFER DATE	20/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START				FINISH			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	20/03/2025	33	29	62	32	34	28	63	32

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	Intergard 475HS / Light gray	APP. METHOD	SPRAY	MIO DATE	20/03/2025
PAINT MANUFACTURER	AKZONOBEL INDIA	DFT RANGE	200 microns (Including Primer : 300 microns)	TIME	12:34 PM
PAINT BATCH NO. (BASE)	Q089256	MANUFACTURE DATE	28/02/2025	SHELF LIFE	1 YEAR
PAINT BATCH NO. (HARDNER)	Q089255				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
9	TCE-13282A-CV-2026-ST-30306-ASS-B8	0	B8	B8	1	309 - 312	ACC
10	TCE-13282A-CV-2026-ST-30306-ASS-B11	2	B11	B11	1	310 - 312	ACC
11	TCE-13282A-CV-2026-ST-30306-ASS-B12	2	B12	B12	1	314 - 320	ACC

NOTE	--	CLIENT / TPIA
SIGN		
NAME	SHIVANG DIWAKAR	
DATE	20/03/2025	

VE-STR-16C