



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/150
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	23/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:45				FINISH TIME- 11:50			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	22/09/2025	35	26.6	72.4	32.2	34.4	25.1	73.4	30.4

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	21/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
1	PIN-084-TPT-PM1-CS11-006_0-HB12	0	HB12	D-E/4-5	2	225-230	ACC
2	PIN-084-TPT-PM1-CS11-006_0-HB4	0	HB4	D-E/6-7	2	235-240	ACC
3	PIN-084-TPT-PM1-CS11-006_0-HB4	0	HB4	D-E/7-8	2	230-235	ACC
4	PIN-084-TPT-PM1-CS11-006_0-HB6	0	HB6	D-E/6-7	2	225-237	ACC
5	PIN-084-TPT-PM1-CS11-006_0-HB8	0	HB8	D-E/4-5	2	232-236	ACC
6	PIN-084-TPT-PM1-CS11-006_0-HB9	0	HB9	D-E/7-8	2	225-236	ACC
7	PIN-084-TPT-PM1-CS11-006_0-HB14	0	HB14	D-E/1-2	2	231-236	ACC
8	PIN-084-TPT-CM1-CS11-004-FAB-FR1	1	FAB-FR1	FAB-FR1	1	225-235	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	23/09/2025				

VE-DOC-26 REV.00



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/150
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	23/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:45				FINISH TIME- 11:50			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	22/09/2025	35	26.6	72.4	32.2	34.4	25.1	73.4	30.4

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	21/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
9	PIN-084-TPT-CM1-CS11-004-FAB-FR4	1	FAB-FR4	FAB-FR4	1	232-237	ACC
10	PIN-084-TPT-CM1-CS11-004-FAB-FR18	0	FAB-FR18	FAB-FR18	1	227-230	ACC
11	PIN-084-TPT-CM1-CS11-004-FAB-FR20	0	FAB-FR20	FAB-FR20	1	223-235	ACC
12	PIN-084-TPT-CM1-CS11-004-FAB-FR27	0	FAB-FR27	FAB-FR27	1	225-237	ACC
13	PIN-084-TPT-CM1-CS11-004-FAB-FR28	0	FAB-FR28	FAB-FR28	1	231-235	ACC
14	PIN-084-TPT-CM1-CS11-004-FAB-FR29	0	FAB-FR29	FAB-FR29	1	225-237	ACC
15	PIN-084-TPT-CM1-CS11-004-FAB-FR30	0	FAB-FR30	FAB-FR30	1	222-238	ACC
16	PIN-084-TPT-CM1-CS11-004-FAB-FR31	0	FAB-FR31	FAB-FR31	1	222-235	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	23/09/2025				

VE-DOC-26 REV.00



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/150
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	23/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:45				FINISH TIME- 11:50			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	22/09/2025	35	26.6	72.4	32.2	34.4	25.1	73.4	30.4

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	21/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
17	PIN-084-TPT-CM1-CS11-004-FAB-FR32	0	FAB-FR32	FAB-FR32	4	235-234	ACC
18	PIN-084-TPT-CM1-CS11-004-FAB-FR34	0	FAB-FR34	FAB-FR34	1	237-240	ACC
19	PIN-084-TPT-CM1-CS11-004-FAB-FR35	0	FAB-FR35	FAB-FR35	1	221-236	ACC
20	PIN-084-TPT-CM1-CS11-004-FAB-FR36	0	FAB-FR36	FAB-FR36	3	215-235	ACC
21	PIN-084-TPT-CM1-CS11-004-FAB-FR40	0	FAB-FR40	FAB-FR40	1	231-236	ACC
22	PIN-084-TPT-CM1-CS11-004-FAB-FR41	0	FAB-FR41	FAB-FR41	1	217-230	ACC
23	PIN-084-TPT-CM1-CS11-004-FAB-FR42	0	FAB-FR42	FAB-FR42	1	231-236	ACC
24	PIN-084-TPT-CM1-CS11-004-FAB-FR43	0	FAB-FR43	FAB-FR43	1	231-238	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	23/09/2025				

VE-DOC-26 REV.00



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/150
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	23/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:45				FINISH TIME- 11:50			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	22/09/2025	35	26.6	72.4	32.2	34.4	25.1	73.4	30.4

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	21/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
25	PIN-084-TPT-CM1-CS11-004-FAB-FR44	0	FAB-FR44	FAB-FR44	1	231-236	ACC
26	PIN-084-TPT-CM1-CS11-004-FAB-FR47	0	FAB-FR47	FAB-FR47	1	232-235	ACC
27	PIN-084-TPT-CM1-CS11-004-FAB-FR51	0	FAB-FR51	FAB-FR51	1	225-236	ACC
28	PIN-084-TPT-CM1-CS11-004-FAB-FR52	0	FAB-FR52	FAB-FR52	1	221-236	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	23/09/2025				

VE-DOC-26 REV.00