



# VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

## MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/151
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	27/09/2025

### WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:15				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	27/09/2025	33.2	24.5	71.3	31.4	35.1	23.1	65.8	32.6

### INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	27/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
1	PIN-084-TPT-CM1-CS11-006-FAB-B1	0	FAB-B1	FAB-B1	16	225-229	ACC
2	PIN-084-TPT-CM1-CS11-006-FAB-B2	0	FAB-B2	FAB-B2	8	227-231	ACC
3	PIN-084-TPT-CM1-CS11-006-FAB-B3	0	FAB-B3	FAB-B3	4	229-233	ACC
4	PIN-084-TPT-CM1-CS11-006-FAB-C1	0	FAB-C1	FAB-C1	1	231-235	ACC
5	PIN-084-TPT-CM1-CS11-006-FAB-C2	0	FAB-C2	FAB-C2	1	233-237	ACC
6	PIN-084-TPT-CM1-CS11-006-FAB-HB1	0	FAB-HB1	FAB-HB1	1	235-239	ACC
7	PIN-084-TPT-CM1-CS11-006-FAB-HB2	0	FAB-HB2	FAB-HB2	1	226-230	ACC
8	PIN-084-TPT-CM1-CS11-006-FAB-HB3	0	FAB-HB3	FAB-HB3	6	228-232	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	27/09/2025				

VE-DOC-26 REV.00



# VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

## MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/151
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	27/09/2025

### WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:15				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	27/09/2025	33.2	24.5	71.3	31.4	35.1	23.1	65.8	32.6

### INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	27/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
9	PIN-084-TPT-CM1-CS11-006-FAB-HB4	0	FAB-HB4	FAB-HB4	1	230-234	ACC
10	PIN-084-TPT-CM1-CS11-006-FAB-HB5	0	FAB-HB5	FAB-HB5	1	232-236	ACC
11	PIN-084-TPT-CM1-CS11-006-FAB-SC1	0	FAB-SC1	FAB-SC1	1	234-238	ACC
12	PIN-084-TPT-CM1-CS11-006-FAB-SC4	0	FAB-SC4	FAB-SC4	1	236-240	ACC
13	PIN-084-TPT-CM1-CS11-006-FAB-VB1	0	FAB-VB1	FAB-VB1	2	225-229	ACC
14	PIN-084-TPT-CM1-CS11-008-FAB-C1	0	FAB-C1	FAB-C1	1	227-231	ACC
15	PIN-084-TPT-CM1-CS11-008-FAB-C2	0	FAB-C2	FAB-C2	1	229-233	ACC
16	PIN-084-TPT-CM1-CS11-008-FAB-C3	0	FAB-C3	FAB-C3	1	231-235	ACC

NOTE					
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	27/09/2025				

VE-DOC-26 REV.00



# VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

## MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/151
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	27/09/2025

### WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:15				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	27/09/2025	33.2	24.5	71.3	31.4	35.1	23.1	65.8	32.6

### INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	27/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
17	PIN-084-TPT-CM1-CS11-008-FAB-C5	0	FAB-C5	FAB-C5	1	233-237	ACC
18	PIN-084-TPT-CM1-CS11-008-FAB-C6	0	FAB-C6	FAB-C6	1	235-239	ACC
19	PIN-084-TPT-CM1-CS11-008-FAB-C7	0	FAB-C7	FAB-C7	1	226-230	ACC
20	PIN-084-TPT-CM1-CS11-008-FAB-C8	0	FAB-C8	FAB-C8	1	228-232	ACC
21	PIN-084-TPT-CM1-CS11-008-FAB-C9	0	FAB-C9	FAB-C9	1	230-234	ACC
22	PIN-084-TPT-PM1-CS11-008 FAB-B1	0	FAB-B1	FAB-B1	6	232-236	ACC
23	PIN-084-TPT-PM1-CS11-008- FAB-B6	0	FAB-B6	FAB-B6	1	234-238	ACC
24	PIN-084-TPT-PM1-CS11-008- FAB-B7	0	FAB-B7	FAB-B7	1	236-240	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	27/09/2025				

VE-DOC-26 REV.00



# VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

## MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/151
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	27/09/2025

### WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:15				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	27/09/2025	33.2	24.5	71.3	31.4	35.1	23.1	65.8	32.6

### INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	27/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
25	PIN-084-TPT-PM1-CS11-008- FAB-B8	0	FAB-B8	FAB-B8	1	225-229	ACC
26	PIN-084-TPT-PM1-CS11-008- FAB-B14	0	FAB-B14	FAB-B14	1	227-231	ACC
27	PIN-084-TPT-PM1-CS11-008- FAB-B15	0	FAB-B15	FAB-B15	1	229-233	ACC
28	PIN-084-TPT-PM1-CS11-008- FAB-B18	0	FAB-B18	FAB-B18	1	231-235	ACC
29	PIN-084-TPT-PM1-CS11-008- FAB-C3	0	FAB-C3	FAB-C3	4	233-237	ACC
30	PIN-084-TPT-PM1-CS11-008- FAB-C7	0	FAB-C7	FAB-C7	1	235-239	ACC
31	PIN-084-TPT-PM1-CS11-008- FAB-C18	0	FAB-C18	FAB-C18	1	226-230	ACC
32	PIN-084-TPT-PM1-CS11-008- FAB-C20	0	FAB-C20	FAB-C20	1	228-232	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	27/09/2025				

VE-DOC-26 REV.00



# VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

## MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/151
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	27/09/2025

### WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:15				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	27/09/2025	33.2	24.5	71.3	31.4	35.1	23.1	65.8	32.6

### INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	27/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
33	PIN-084-TPT-PM1-CS11-008- FAB-HB1	0	FAB-HB1	FAB-HB1	2	230-234	ACC
34	PIN-084-TPT-PM1-CS11-008- FAB-HB2	0	FAB-HB2	FAB-HB2	2	232-236	ACC
35	PIN-084-TPT-PM1-CS11-008- FAB-HB3	0	FAB-HB3	FAB-HB3	2	234-238	ACC
36	PIN-084-TPT-PM1-CS11-008- FAB-LP1	0	FAB-LP1	FAB-LP1	41	236-240	ACC
37	PIN-084-TPT-PM1-CS11-008- FAB-LP3	0	FAB-LP3	FAB-LP3	3	225-229	ACC
38	PIN-084-TPT-PM1-CS11-008- FAB-LP4	0	FAB-LP4	FAB-LP4	12	227-231	ACC
39	PIN-084-TPT-PM1-CS11-008- FAB-LP6	0	FAB-LP6	FAB-LP6	14	229-233	ACC
40	PIN-084-TPT-PM1-CS11-008- FAB-LP7	0	FAB-LP7	FAB-LP7	32	231-235	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	27/09/2025				

VE-DOC-26 REV.00



# VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

## MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/151
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	27/09/2025

### WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:15				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	27/09/2025	33.2	24.5	71.3	31.4	35.1	23.1	65.8	32.6

### INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	27/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
41	PIN-084-TPT-PM1-CS11-008- FAB-LP8	0	FAB-LP8	FAB-LP8	34	233-237	ACC
42	PIN-084-TPT-PM1-CS11-008- FAB-RF1	0	FAB-RF1	FAB-RF1	2	235-239	ACC
43	PIN-084-TPT-PM1-CS11-008- FAB-RF2	0	FAB-RF2	FAB-RF2	2	226-230	ACC
44	PIN-084-TPT-PM1-CS11-008- FAB-RF3	0	FAB-RF3	FAB-RF3	1	228-232	ACC
45	PIN-084-TPT-PM1-CS11-008- FAB-RF4	0	FAB-RF4	FAB-RF4	1	230-234	ACC
46	PIN-084-TPT-PM1-CS11-008- FAB-RF5	0	FAB-RF5	FAB-RF5	1	232-236	ACC
47	PIN-084-TPT-PM1-CS11-008- FAB-RF6	0	FAB-RF6	FAB-RF6	1	234-238	ACC
48	PIN-084-TPT-PM1-CS11-008- FAB-RF7	0	FAB-RF7	FAB-RF7	1	236-240	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	27/09/2025				

VE-DOC-26 REV.00



# VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

## MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/151
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	27/09/2025

### WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:15				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	27/09/2025	33.2	24.5	71.3	31.4	35.1	23.1	65.8	32.6

### INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	27/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
49	PIN-084-TPT-PM1-CS11-008- FAB-RF8	0	FAB-RF8	FAB-RF8	1	225-229	ACC
50	PIN-084-TPT-PM1-CS11-008- FAB-RF9	0	FAB-RF9	FAB-RF9	1	227-231	ACC
51	PIN-084-TPT-PM1-CS11-010-FAB-B12	0	FAB-B12	FAB-B12	20	229-233	ACC
52	PIN-084-TPT-PM1-CS11-010-FAB-B21	0	FAB-B21	FAB-B21	3	231-235	ACC
53	PIN-084-TPT-PM1-CS11-010-FAB-B22	0	FAB-B22	FAB-B22	1	233-237	ACC
54	PIN-084-TPT-PM1-CS11-010-FAB-B23	0	FAB-B23	FAB-B23	1	235-239	ACC
55	PIN-084-TPT-PM1-CS11-010-FAB-B25	0	FAB-B25	FAB-B25	4	232-236	ACC
56	PIN-084-TPT-PM1-CS11-010-FAB-B26	0	FAB-B26	FAB-B26	1	234-238	ACC

NOTE					
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	27/09/2025				

VE-DOC-26 REV.00



# VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

## MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/151
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	27/09/2025

### WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:15				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	27/09/2025	33.2	24.5	71.3	31.4	35.1	23.1	65.8	32.6

### INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	27/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
57	PIN-084-TPT-PM1-CS11-010-FAB-B27	0	FAB-B27	FAB-B27	1	236-240	ACC

NOTE	--					
	VISHAL QC			CLIENT / TPIA		
SIGN						
NAME	BIRENDRA KUMAR					
DATE	27/09/2025					

VE-DOC-26 REV.00