



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/154
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	29/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:20				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	29/09/2025	33.1	24.2	68.6	31.3	34.2	23.1	65.4	32.3

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	29/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
1	PIN-084-TPT-CM1-CS11-006-FAB-B4	0	FAB-B4	FAB-B4	1	225-229	ACC
2	PIN-084-TPT-CM1-CS11-006-FAB-B5	0	FAB-B5	FAB-B5	1	227-231	ACC
3	PIN-084-TPT-CM1-CS11-006-FAB-B7	0	FAB-B7	FAB-B7	1	229-233	ACC
4	PIN-084-TPT-CM1-CS11-006-FAB-B6	0	FAB-B6	FAB-B6	1	231-235	ACC
5	PIN-084-TPT-CM1-CS11-006-FAB-FR1	0	FAB-FR1	FAB-FR1	1	233-237	ACC
6	PIN-084-TPT-CM1-CS11-006-FAB-FR2	0	FAB-FR2	FAB-FR2	1	235-239	ACC
7	PIN-084-TPT-CM1-CS11-006-FAB-FR3	0	FAB-FR3	FAB-FR3	1	226-230	ACC
8	PIN-084-TPT-CM1-CS11-006-FAB-FR4	0	FAB-FR4	FAB-FR4	1	228-232	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	29/09/2025				

VE-DOC-26 REV.00



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/154
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	29/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:20				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	29/09/2025	33.1	24.2	68.6	31.3	34.2	23.1	65.4	32.3

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	29/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
9	PIN-084-TPT-CM1-CS11-006-FAB-SC2	0	FAB-SC2	FAB-SC2	1	230-234	ACC
10	PIN-084-TPT-CM1-CS11-006-FAB-SC3	0	FAB-SC3	FAB-SC3	1	232-236	ACC
11	PIN-084-TPT-CM1-CS11-008-FAB-B1	0	FAB-B1	FAB-B1	2	234-238	ACC
12	PIN-084-TPT-CM1-CS11-008-FAB-B2	0	FAB-B2	FAB-B2	5	236-240	ACC
13	PIN-084-TPT-CM1-CS11-008-FAB-B3	0	FAB-B3	FAB-B3	11	225-229	ACC
14	PIN-084-TPT-CM1-CS11-008-FAB-B4	0	FAB-B4	FAB-B4	1	227-231	ACC
15	PIN-084-TPT-CM1-CS11-008-FAB-B5	0	FAB-B5	FAB-B5	1	229-233	ACC
16	PIN-084-TPT-CM1-CS11-008-FAB-B6	0	FAB-B6	FAB-B6	2	231-235	ACC

NOTE	---				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	29/09/2025				

VE-DOC-26 REV.00



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/154
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	29/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:20				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	29/09/2025	33.1	24.2	68.6	31.3	34.2	23.1	65.4	32.3

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	29/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
17	PIN-084-TPT-CM1-CS11-008-FAB-B7	0	FAB-B7	FAB-B7	1	233-237	ACC
18	PIN-084-TPT-CM1-CS11-008-FAB-B8	0	FAB-B8	FAB-B8	2	235-239	ACC
19	PIN-084-TPT-CM1-CS11-008-FAB-B9	0	FAB-B9	FAB-B9	1	226-230	ACC
20	PIN-084-TPT-CM1-CS11-008-FAB-B10	0	FAB-B10	FAB-B10	2	228-232	ACC
21	PIN-084-TPT-CM1-CS11-008-FAB-B11	0	FAB-B11	FAB-B11	4	230-234	ACC
22	PIN-084-TPT-CM1-CS11-008-FAB-B12	0	FAB-B12	FAB-B12	2	232-236	ACC
23	PIN-084-TPT-CM1-CS11-008-FAB-B13	0	FAB-B13	FAB-B13	1	234-238	ACC
24	PIN-084-TPT-CM1-CS11-008-FAB-B14	0	FAB-B14	FAB-B14	1	236-240	ACC

NOTE	---				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	29/09/2025				

VE-DOC-26 REV.00



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/154
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	29/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:20				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	29/09/2025	33.1	24.2	68.6	31.3	34.2	23.1	65.4	32.3

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	29/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
25	PIN-084-TPT-CM1-CS11-008-FAB-B15	0	FAB-B15	FAB-B15	1	225-229	ACC
26	PIN-084-TPT-CM1-CS11-008-FAB-B16	0	FAB-B16	FAB-B16	1	227-231	ACC
27	PIN-084-TPT-CM1-CS11-008-FAB-C4	0	FAB-C4	FAB-C4	2	229-233	ACC
28	PIN-084-TPT-CM1-CS11-008-FAB-VB1	0	FAB-VB1	FAB-VB1	5	231-235	ACC
29	PIN-084-TPT-CM1-CS11-008-FAB-VB2	0	FAB-VB2	FAB-VB2	1	233-237	ACC
30	PIN-084-TPT-PM1-CS11-008- FAB-C2	0	FAB-C2	FAB-C2	1	235-239	ACC
31	PIN-084-TPT-PM1-CS11-008- FAB-C4	0	FAB-C4	FAB-C4	1	237-241	ACC
32	PIN-084-TPT-PM1-CS11-008- FAB-C5	0	FAB-C5	FAB-C5	1	226-230	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	29/09/2025				

VE-DOC-26 REV.00



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/154
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	29/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:20				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	29/09/2025	33.1	24.2	68.6	31.3	34.2	23.1	65.4	32.3

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	29/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
33	PIN-084-TPT-PM1-CS11-008- FAB-C6	0	FAB-C6	FAB-C6	3	228-232	ACC
34	PIN-084-TPT-PM1-CS11-008- FAB-C8	0	FAB-C8	FAB-C8	1	230-234	ACC
35	PIN-084-TPT-PM1-CS11-008- FAB-C11	0	FAB-C11	FAB-C11	1	232-236	ACC
36	PIN-084-TPT-PM1-CS11-008- FAB-C12	0	FAB-C12	FAB-C12	1	234-238	ACC
37	PIN-084-TPT-PM1-CS11-008- FAB-C13	0	FAB-C13	FAB-C13	1	236-240	ACC
38	PIN-084-TPT-PM1-CS11-008- FAB-C14	0	FAB-C14	FAB-C14	1	225-229	ACC
39	PIN-084-TPT-PM1-CS11-008- FAB-C15	0	FAB-C15	FAB-C15	1	227-231	ACC
40	PIN-084-TPT-PM1-CS11-008- FAB-C16	0	FAB-C16	FAB-C16	1	229-233	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	29/09/2025				

VE-DOC-26 REV.00



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/154
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	29/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:20				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	29/09/2025	33.1	24.2	68.6	31.3	34.2	23.1	65.4	32.3

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	29/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
41	PIN-084-TPT-PM1-CS11-008- FAB-C17	0	FAB-C17	FAB-C17	1	231-235	ACC
42	PIN-084-TPT-PM1-CS11-008- FAB-C21	0	FAB-C21	FAB-C21	1	233-237	ACC
43	PIN-084-TPT-PM1-CS11-008- FAB-LU2	0	FAB-LU2	FAB-LU2	24	235-239	ACC
44	PIN-084-TPT-PM1-CS11-008- FAB-LU3	0	FAB-LU3	FAB-LU3	8	237-241	ACC
45	PIN-084-TPT-PM1-CS11-008- FAB-LU4	0	FAB-LU4	FAB-LU4	17	226-230	ACC
46	PIN-084-TPT-PM1-CS11-008- FAB-LU5	0	FAB-LU5	FAB-LU5	1	228-232	ACC
47	PIN-084-TPT-PM1-CS11-008- FAB-LU7	0	FAB-LU7	FAB-LU7	8	230-234	ACC
48	PIN-084-TPT-PM1-CS11-008- FAB-LU11	0	FAB-LU11	FAB-LU11	25	232-236	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	29/09/2025				

VE-DOC-26 REV.00



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT		PROJECT	CORAL-2	REPORT NO.	VE/CORAL-2/STR/MIO/OFFER/154
WO/PO NO	4580584722	PROCEDURE NO.	VEPL/AIL-J/CORAL-2/QSI-002	OFFER DATE	29/09/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START TIME - 09:20				FINISH TIME- 11:55			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	29/09/2025	33.1	24.2	68.6	31.3	34.2	23.1	65.4	32.3

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	INTERGUARD 475HS	APP. METHOD	SPRAY	MIO DATE	29/09/2025
PAINT MANUFACTURER	AKZONOBEL	DFT RANGE	150 Microns	HARD DRY TIME	8 HOURS
PAINT BATCH NO. (BASE)	'Q0D5107009	MANUFACTURE DATE	18/04/2025	SHELF LIFE	18 MONTHS
PAINT BATCH NO. (HARDNER)	'Q0D5164082				

SR. NO.	DRAWING NO.	REV	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
						MIO	
49	PIN-084-TPT-PM1-CS11-008- FAB-LU12	0	FAB-LU12	FAB-LU12	5	234-238	ACC
50	PIN-084-TPT-PM1-CS11-010-FAB-B1	0	FAB-B1	FAB-B1	1	236-240	ACC
51	PIN-084-TPT-PM1-CS11-010-FAB-B9	0	FAB-B9	FAB-B9	1	238-242	ACC
52	PIN-084-TPT-PM1-CS11-010-FAB-B17	0	FAB-B17	FAB-B17	1	227-231	ACC
53	PIN-084-TPT-PM1-CS11-010-FAB-B19	0	FAB-B19	FAB-B19	1	229-233	ACC
54	PIN-084-TPT-PM1-CS11-010-FAB-B20	0	FAB-B20	FAB-B20	1	231-235	ACC
55	PIN-084-TPT-PM1-CS11-010-FAB-B24	0	FAB-B24	FAB-B24	1	233-237	ACC
56	PIN-084-TPT-PM1-CS11-010-FAB-C1	0	FAB-C1	FAB-C1	1	235-239	ACC

NOTE	--				
	VISHAL QC			CLIENT / TPIA	
SIGN					
NAME	BIRENDRA KUMAR				
DATE	29/09/2025				

VE-DOC-26 REV.00