



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/MIO/2
WO/PO NO	9558569010	PROCEDURE NO.	PRS/4	OFFER DATE	08/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START				FINISH			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	08/03/2025	29	22	68	29	30	23	69	30

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	APCODUR MIO 400	APP. METHOD	SPRAY	MIO DATE	08/03/2025
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	200 microns (Including Primer : 300 microns)	TIME	4:45 PM
PAINT BATCH NO. (BASE)	Q089256	MANUFACTURE DATE	08/01/2025	SHELF LIFE	1 YEAR
PAINT BATCH NO. (HARDNER)	Q089255				

SR. NO.	DRAWING NO.	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
					MIO	
1	TCE-13282A-CV-3066-ST-31020-ASS-FR4	FR4	FR4	1	310 - 325	ACC
2	TCE-13282A-CV-3066-ST-31020-ASS-FR5	FR5	FR5	1	310 - 325	ACC
3	TCE-13282A-CV-3066-ST-31020-ASS-FR6	FR6	FR6	1	310 - 325	ACC
4	TCE-13282A-CV-3066-ST-31020-ASS-FR8	FR8	FR8	1	310 - 325	ACC
5	TCE-13282A-CV-3066-ST-31020-ASS-FR9	FR9	FR9	1	310 - 325	ACC
6	TCE-13282A-CV-3066-ST-31020-ASS-FR10	FR10	FR10	1	310 - 325	ACC
7	TCE-13282A-CV-3066-ST-31020-ASS-FR11	FR11	FR11	1	310 - 325	ACC
8	TCE-13282A-CV-3066-ST-31020-ASS-FR12	FR12	FR12	1	310 - 325	ACC

NOTE	--
------	----

	VISHAL QC	CLIENT / TPIA
SIGN		
NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	

VE-STR-16C



VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE LIMITED GROUP OF COMPANIES

MIO PAINT INSPECTION REPORT

CLIENT	PIYUSH ENTERPRISE	PROJECT	PIYUSH BUILDING	REPORT NO.	VE/PIYUSH BUILDING/STR/MIO/2
WO/PO NO	9558569010	PROCEDURE NO.	PRS/4	OFFER DATE	08/03/2025

WEATHER CONDITION

ACTIVITY	DATE PERFORMED	START				FINISH			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	08/03/2025	29	22	68	29	30	23	69	30

INTERMEDIATE / MIO COATING

MIO PAINT/SHADE	APCODUR MIO 400	APP. METHOD	SPRAY	MIO DATE	08/03/2025
PAINT MANUFACTURER	ASIAN PPG	DFT RANGE	200 microns (Including Primer : 300 microns)	TIME	4:45 PM
PAINT BATCH NO. (BASE)	Q089256	MANUFACTURE DATE	08/01/2025	SHELF LIFE	1 YEAR
PAINT BATCH NO. (HARDNER)	Q089255				

SR. NO.	DRAWING NO.	ASSEMBLY NUMBER	GRID NUMBER	GRID QTY	Average DFT	ACC/REJ
					MIO	
9	TCE-13282A-CV-3066-ST-31020-ASS-FR13	FR13	FR13	1	310 - 325	ACC
10	TCE-13282A-CV-3066-ST-31020-ASS-FR14	FR14	FR14	1	310 - 325	ACC
11	TCE-13282A-CV-3066-ST-31020-ASS-FR15	FR15	FR15	1	310 - 325	ACC

NOTE	--
------	----

	VISHAL QC	CLIENT / TPIA
SIGN		
NAME	SHIVANG DIWAKAR	
DATE	08/03/2025	

VE-STR-16C