



**VISHAL ENTERPRISE & VRISHAL ENGINEERING PRIVATE  
LIMITED  
GROUP OF COMPANIES**

**MIO PAINT INSPECTION REPORT**

<b>CLIENT</b>	AARTI INDUSTRIES LTD	<b>PROJECT</b>	CORAL-2	<b>REPORT NO.</b>	VE/CORAL-2/STR/MIO/OFFER/158
<b>WO/PO NO</b>	4580584722	<b>PROCEDURE NO.</b>	VEPL/AI-L-J/CORAL-2/QSI-002	<b>OFFER DATE</b>	11/10/2025

**WEATHER CONDITION**

<b>ACTIVITY</b>	<b>DATE PERFORMED</b>	START TIME - 09:10				FINISH TIME- 11:10			
		SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C	SURFACE OR METAL TEMP °C	DEW POINT °C	RELATIVE HUMIDITY %	AMBIENT TEMP °C
MIO Coat	11/10/2025	34.2	25.2	70.4	31.2	35	26.6	72.4	32.2

**INTERMEDIATE / MIO COATING**

<b>MIO PAINT/SHADE</b>	INTERGUARD 475HS	<b>APP. METHOD</b>	SPRAY	<b>MIO DATE</b>	11/10/2025
<b>PAINT MANUFACTURER</b>	AKZONOBEL	<b>DFT RANGE</b>	150 Microns	<b>HARD DRY TIME</b>	8 HOURS
<b>PAINT BATCH NO. (BASE)</b>	'Q0D5107009	<b>MANUFACTURE DATE</b>	18/04/2025	<b>SHELF LIFE</b>	18 MONTHS
<b>PAINT BATCH NO. (HARDNER)</b>	'Q0D5164082				

<b>SR. NO.</b>	<b>DRAWING NO.</b>	<b>REV</b>	<b>ASSEMBLY NUMBER</b>	<b>GRID NUMBER</b>	<b>GRID QTY</b>	<b>Average DFT</b>	<b>ACC/REJ</b>
						<b>MIO</b>	
1	PIN-084-TPT-CM1-CS11-004-FAB-LD1	0	FAB-LD1	FAB-LD1	1	225-230	ACC
2	PIN-084-TPT-CM1-CS11-004-FAB-LD2	0	FAB-LD2	FAB-LD2	1	232-235	ACC

<b>NOTE</b>	--	
	<b>VISHAL QC</b>	<b>CLIENT / TPIA</b>
<b>SIGN</b>		
<b>NAME</b>	BIRENDRA KUMAR	
<b>DATE</b>	11/10/2025	

VE-DOC-26 REV.00