



PT. SALIPI NAGARI PERKASA

Komp. Pejaten Mas Blok E No. 3 Kramat Watu Serang - Banten 42161

Telp. : 0254 - 231363 Fax.: 0254 - 231183

LAPORAN UJI MINYAK TRAFO

di

UNIT JASA PEMBANGKIT

JERANJANG



Yang dilakukan pada tanggal 17 SEPTEMBER 2019

Untuk keadaan trafo periode 16 September ~ 11 Oktober 2019

<u>1.0 Table of Contents</u>	<u>Page</u>
1.0 Specific Information	3
2.0 Our Comments and Recommendations of the Test Results Analysis	
- Transformer Unit MAIN TRAFO UNIT 1 (S/N: 100691) Test Certificate 4	5
- Transformer Unit TRAFO 1 ESP UNIT 1 (S/N: 10937) Test Certificate 5	6
- Transformer Unit TRAFO 2 ESP UNIT 1 (S/N: 10035) Test Certificate 6	7
- Transformer Unit TRAFO 3 ESP UNIT 1 (S/N: 10031) Test Certificate 7	8
- Transformer Unit TRAFO 4 ESP UNIT 1 (S/N: 10034) Test Certificate 8	9
- Transformer Unit MAIN TRAFO UNIT 3 (S/N: 3011160192) Test Certificate 23	10
- Transformer Unit UAT 3 (S/N: PX18-0082) Test Certificate 22	11
- Transformer Unit TRAFO 1 ESP UNIT 3 (S/N: 0073084208) Test Certificate 11	12
- Transformer Unit TRAFO 2 ESP UNIT 3 (S/N: 0070084208) Test Certificate 12	13
- Transformer Unit TRAFO 3 ESP UNIT 3 (S/N: 0072084208) Test Certificate 13	14
- Transformer Unit TRAFO 4 UNIT 3 (S/N: 0071084208) Test Certificate 14	15
- Transformer Unit ASH HANDLING-1 (S/N: 10820108) Test Certificate 15	16
- Transformer Unit ASH HANDLING-2 (S/N: 10820107) Test Certificate 16	17
- Transformer Unit TRAFO 1 ESP UNIT 2 (S/N: 10037) Test Certificate 17	18
- Transformer Unit TRAFO 2 ESP UNIT 2 (S/N: 10036) Test Certificate 18	19

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

-	Transformer Unit TRAFO 3 ESP UNIT 2 (S/N: 10033)	20
	Test Certificate 19	
-	Transformer Unit TRAFO 4 ESP UNIT 2 (S/N: 10032)	21
	Test Certificate 20	
-	Transformer Unit MAIN TRAFO UNIT 2 (S/N: 1006902)	22
	Test Certificate 21	
3.0	Summary of Recommendation	23

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

1.0 Specific Information:

No.	Unit No.	Serial Number	TC	Test Requested
1.	MAIN TRAFO UNIT 1	100691	4	Acidity, Dielectric, Color, Visualization and Water Content
2.	TRAFO 1 ESP UNIT 1	10937	5	Acidity, Dielectric, Color, Visualization and Water Content
3.	TRAFO 2 ESP UNIT 1	10035	6	Acidity, Dielectric, Color, Visualization and Water Content
4.	TRAFO 3 ESP UNIT 1	10031	7	Acidity, Dielectric, Color, Visualization and Water Content
5.	TRAFO 4 ESP UNIT 1	10034	8	Acidity, Dielectric, Color, Visualization and Water Content
6.	MAIN TRAFO UNIT 3	3011160192	23	Acidity, Dielectric, Color, Visualization and Water Content
7.	UAT 3	PX18-0082	22	Acidity, Dielectric, Color, Visualization and Water Content
8.	TRAFO 1 ESP UNIT 3	0073084208	11	Acidity, Dielectric, Color, Visualization and Water Content
9.	TRAFO 2 ESP UNIT 3	0070084208	12	Acidity, Dielectric, Color, Visualization and Water Content
10.	TRAFO 3 ESP UNIT 3	0072084208	13	Acidity, Dielectric, Color, Visualization and Water Content
11.	TRAFO 4 UNIT 3	0071084208	14	Acidity, Dielectric, Color, Visualization and Water Content
12.	ASH HANDLING-1	10820108	15	Acidity, Dielectric, Color, Visualization and Water Content
13.	ASH HANDLING-2	10820107	16	Acidity, Dielectric, Color, Visualization and Water Content
14.	TRAFO 1 ESP UNIT 2	10037	17	Acidity, Dielectric, Color, Visualization and Water Content
15.	TRAFO 2 ESP UNIT 2	10036	18	Acidity, Dielectric, Color, Visualization and Water Content
16.	TRAFO 3 ESP UNIT 2	10033	19	Acidity, Dielectric, Color, Visualization and Water Content
17.	TRAFO 4 ESP UNIT 2	10032	20	Acidity, Dielectric, Color, Visualization and Water Content

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

No.	Unit No.	Serial Number	TC	Test Requested
18.	MAIN TRAFO UNIT 2	1006902	21	Acidity, Dielectric, Color, Visualization and Water Content

Note:

* OLTT+ consists of Liquid Screen Tests, Dissolved Gas Analysis (DGA), Water Content, Furan Analysis, Metals-in-Oil Analysis, Liquid Power Factors, and Inhibitor Content (DBPC).

** Liquid Screen Test consists of Acidity, Interfacial Tension (IFT), Dielectric, Colour, Specific Gravity, Visualization, and Sediment.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

2.0 Our Comments and Recommendations of The Test Results Analysis:

We had reviewed each laboratory test result against respective benchmark parameter and following are our comments and recommendations.

No.	Unit No.	Serial Number	TC
1.	MAIN TRAFO UNIT 1	100691	4

A) Analysis

- **Acidity** of 0.017mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 73kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 6ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 0.43% M/dw is graded as **A**. For this transformer, it is recommended to maintain water content in oil at less than 20ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

CENNIX LABORATORY (M) SDN BHD

(Formerly known as Myers-Musteq Sdn Bhd)

4

DATE PRINTED 06/10/2019

ID# - 601669

**CUST - PT IP UJP PLTU
JERANJANG**

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **MAIN TRAFU UNIT 1**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	ONLINE						
23/10/2018	ONLINE						
22/11/2018	ONLINE						
08/12/2018	ONLINE						
21/05/2019	ONLINE						
20/06/2019	ONLINE						
25/07/2019	ONLINE						
20/08/2019	ONLINE						
17/09/2019	ONLINE						

NAMEPLATE DATA

MFG	- WOLONG
DATE MFG	- 2011
MAIN TANK S/N	- 100691
KVA	- 40000
PRI	- 165000 V
SEC	- 6300 V
KILOGRAMS	- 81000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- OFAF
IMPEDENCE	- 13.1%
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 30857
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.017 AC		90 AC	0.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.014 AC		96 AC	0.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.014 AC		83 AC	0.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.014 AC		73 AC	0.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.014 AC		75 AC	0.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.014 AC		71 AC	0.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.017 AC	41.3 AC	66 AC	0.5 AC	0.8789 AC	CLEAR AC	
25/07/2019	ROUTINE	0.014 AC		79 AC	0.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.014 AC		61 AC	0.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.017 AC		73 AC	0.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	147	9471	43278	32	655	2728	4	5	ND	843	56320
06/12/2017	183	12895	43794	39	715	3166	5	5	ND	947	60802
28/06/2018	176	11044	46776	41	758	3393	5	6	ND	986	62199
20/06/2019	18	19122	60738	26	756	3272	2	3	ND	805	83937

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- YES
H2O COOLED	- NO
OIL PUMPS	- YES
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- YES
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- YES

RECOMMENDATION:

GAS LEVELS HAVE REMAINED STABLE. PROCEED WITH ANNUAL MONITORING.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	30	6	0.63	A
25/09/2018	38	7	0.46	A
23/10/2018	44	8	0.36	A
22/11/2018	41	9	0.45	A
08/12/2018	41	8	0.40	A
21/05/2019	38	8	0.52	A
20/06/2019	39	7	0.38	A
25/07/2019	38	8	0.52	A
20/08/2019	38	7	0.46	A
17/09/2019	35	6	0.43	A

FIELD SERVICE

DATE SERVICE

No.	Unit No.	Serial Number	TC
2.	TRAFO 1 ESP UNIT 1	10937	5

A) Analysis

- **Acidity** of 0.020mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 60kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water content** in oil of 13ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 1.53% M/dw is graded as **C**. For this transformer, it is advisable to maintain the water content level below 20ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

CENNIX LABORATORY (M) SDN BHD

(Formerly known as Myers-Musteq Sdn Bhd)

5

DATE PRINTED 06/10/2019

ID# - 601669

**CUST - PT IP UJP PLTU
JERANJANG**

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 1 ESP UNIT 1**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	ONLINE						
23/10/2018	ONLINE						
22/11/2018	ONLINE						
08/12/2018	OFFLINE						
21/05/2019	ONLINE						
20/06/2019	ONLINE						
25/07/2019	OFFLINE						
20/08/2019	OFFLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- FUJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 10937
KVA	-
PRI	- 72000 V
SEC	- 380 V
KILOGRAMS	- 1000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 630
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.020 AC		71 AC	0.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.017 AC		63 AC	0.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.020 AC		49 AC	0.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.017 AC		30 AC	0.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.017 AC		41 AC	0.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.017 AC		40 AC	0.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.017 AC	38.7 AC	34 AC	0.5 AC	0.8747 AC	CLEAR AC	
25/07/2019	ROUTINE	0.017 AC		61 AC	0.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.017 AC		56 AC	0.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.020 AC		60	0.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	35	20494	67487	4	69	1143	ND	1	ND	109	89233
06/12/2017	39	19933	67198	4	83	1261	ND	1	ND	127	88519
28/06/2018	44	20039	64529	4	119	1696	ND	2	ND	169	86433
20/06/2019	22	27043	68613	5	36	689	ND	ND	ND	63	96408

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	32	12	1.14	B
25/09/2018	35	18	1.28	B
23/10/2018	40	24	1.32	B
22/11/2018	37	23	1.50	C
08/12/2018	32	18	1.71	D
21/05/2019	39	22	1.21	B
20/06/2019	38	23	1.50	C
25/07/2019	29	18	1.89	D
20/08/2019	29	16	1.68	C
17/09/2019	28	13	1.53	C

FIELD SERVICE

DATE SERVICE
01/08/2018 CHANGED OIL

No.	Unit No.	Serial Number	TC
3.	TRAFO 2 ESP UNIT 1	10035	6

A) Analysis

- **Acidity** of 0.022mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 47kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water content** in oil of 16ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 1.89% M/dw is graded as **D**. For this transformer, it is advisable to maintain the water content level below 20ppm.

B) Recommendation

- Based on previous oil analysis, the IFT of the oil is unfavorable. It is recommended to perform **Transformer Oil Regeneration** on this unit. Transformer oil regeneration at this stage of contamination will effectively remove unwanted oxidation byproducts from the insulating oil. This process will restore the oil back to its original quality, thus protecting the paper insulation and extending the transformer serviceable lifespan. Furthermore, oil inhibitor 2,6-DBPC and passivator will be added to preserve both the transformer oil and copper surfaces to enhance the service ability of the transformer.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

CENNIX LABORATORY (M) SDN BHD

(Formerly known as Myers-Musteq Sdn Bhd)

6

DATE PRINTED 06/10/2019

ID# - 601669

**CUST - PT IP UJP PLTU
JERANJANG**

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 2 ESP UNIT 1**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	OFFLINE						
23/10/2018	OFFLINE						
22/11/2018	OFFLINE						
08/12/2018	OFFLINE						
21/05/2019	OFFLINE						
20/06/2019	ONLINE						
25/07/2019	OFFLINE						
20/08/2019	OFFLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- FUJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 10035
KVA	-
PRI	- 72000 V
SEC	- 380 V
KILOGRAMS	- 1000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 630
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.022 AC		56 AC	0.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.020 AC		67 AC	0.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.020 AC		71 AC	0.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.020 AC		63 AC	0.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.020 AC		51 AC	0.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.020 AC		71 AC	0.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.020 AC	27.9 UN	68 AC	0.5 AC	0.8658 AC	CLEAR AC	
25/07/2019	ROUTINE	0.022 AC		67 AC	0.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.020 AC		51 AC	0.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.022 AC		47 AC	0.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	27	18639	66781	3	64	1106	ND	1	ND	95	86621
06/12/2017	20	19360	61590	3	45	728	ND	1	ND	69	81747
28/06/2018	22	22494	64443	4	57	789	ND	ND	ND	83	87809
20/06/2019	23	17710	61707	5	23	842	ND	ND	ND	51	80310

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	31	13	1.24	B
25/09/2018	31	11	1.04	B
23/10/2018	33	14	1.15	B
22/11/2018	34	18	1.48	C
08/12/2018	33	14	1.15	B
21/05/2019	37	15	0.98	B
20/06/2019	37	17	1.11	B
25/07/2019	30	15	1.58	C
20/08/2019	29	15	1.58	C
17/09/2019	28	16	1.89	D

FIELD SERVICE

DATE SERVICE
01/08/2018 CHANGED OIL

No.	Unit No.	Serial Number	TC
4.	TRAFO 3 ESP UNIT 1	10031	7

A) Analysis

- **Acidity** of 0.056mgKOH/gm is **QUESTIONABLE**. Although the level remained stable, the oil are containing oxidation by-products. These oxidation by-products are depositing and degrading the oil as well as the paper insulation. Therefore, removal of these contaminations are highly recommended.
- **Dielectric** of 48kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water content** in oil of 18ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 1.71% M/dw is graded as **D**. For this transformer, it is advisable to maintain the water content level below 20ppm.

B) Recommendation

- Based on previous oil analysis, the IFT of the oil is unfavorable. Together with the high level of Acidity, it is recommended to perform **Transformer Oil Regeneration** on this unit. Transformer oil regeneration at this stage of contamination will effectively remove unwanted oxidation byproducts from the insulating oil. This process will restore the oil back to its original quality, thus protecting the paper insulation and extending the transformer serviceable lifespan. Furthermore, oil inhibitor 2,6-DBPC and passivator will be added to preserve both the transformer oil and copper surfaces to enhance the service ability of the transformer.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019

ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 3 ESP UNIT 1**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	OFFLINE						
23/10/2018	ONLINE						
22/11/2018	OFFLINE						
08/12/2018	OFFLINE						
21/05/2019	ONLINE						
20/06/2019	ONLINE						
25/07/2019	ONLINE						
20/08/2019	ONLINE						
17/09/2019	ONLINE						

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.056 QU		57 AC	1.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.051 QU		46 AC	1.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.056 QU		44 AC	1.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.056 QU		39 AC	1.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.056 QU		39 AC	1.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.051 QU		33 AC	1.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.051 QU	29.6 QU	30 AC	1.5 AC	0.8689 AC	CLEAR AC	
25/07/2019	ROUTINE	0.056 QU		48 AC	1.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.051 QU		43 AC	1.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.056 QU		48 AC	1.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	32	15273	65111	5	95	1002	ND	2	ND	134	81520
06/12/2017	7	14730	65738	3	42	617	ND	ND	ND	52	81137
28/06/2018	9	17958	66007	4	46	781	ND	1	ND	60	84806
20/06/2019	16	17771	65478	6	73	829	ND	1	ND	96	84174

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	30	15	1.58	C
25/09/2018	32	21	2.00	D
23/10/2018	36	20	1.42	C
22/11/2018	36	22	1.56	C
08/12/2018	35	20	1.42	C
21/05/2019	36	19	1.35	B
20/06/2019	36	19	1.35	B
25/07/2019	31	15	1.42	C
20/08/2019	32	18	1.71	D
17/09/2019	32	18	1.71	D

NAMEPLATE DATA

MFG	- FUJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 10031
KVA	-
PRI	- 72000 V
SEC	- 380 V
KILOGRAMS	- 1000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 630

LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

FIELD SERVICE

DATE	SERVICE
------	---------

No.	Unit No.	Serial Number	TC
5.	TRAFO 4 ESP UNIT 1	10034	8

A) Analysis

- **Acidity** of 0.017mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 52kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water content** in oil of 16ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 1.31% M/dw is graded as **B**. For this transformer, it is advisable to maintain the water content level below 20ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

CENNIX LABORATORY (M) SDN BHD

(Formerly known as Myers-Musteq Sdn Bhd)

8

DATE PRINTED 06/10/2019

ID# - 601669

**CUST - PT IP UJP PLTU
JERANJANG**

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 4 ESP UNIT 1**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	OFFLINE						
23/10/2018	ONLINE						
22/11/2018	OFFLINE						
08/12/2018	OFFLINE						
21/05/2019	OFFLINE						
20/06/2019	ONLINE						
25/07/2019	ONLINE						
20/08/2019	OFFLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- FUJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 10034
KVA	-
PRI	- 72000 V
SEC	- 380 V
KILOGRAMS	- 1000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 630
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.017 AC		61 AC	0.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.014 AC		45 AC	0.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.014 AC		52 AC	0.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.014 AC		44 AC	0.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.014 AC		47 AC	0.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.014 AC		41 AC	0.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.014 AC	38.6 AC	45 AC	0.5 AC	0.8775 AC	CLEAR AC	
25/07/2019	ROUTINE	0.014 AC		67 AC	0.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.017 AC		45 AC	0.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.017 AC		52 AC	0.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	13	12265	66770	5	172	1206	ND	8	ND	198	80439
06/12/2017	8	13331	63527	3	70	720	ND	1	ND	82	77660
28/06/2018	9	17962	64248	4	75	1054	ND	2	ND	90	83354
20/06/2019	11	15056	64828	5	11	951	ND	ND	ND	27	80862

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	30	14	1.47	C
25/09/2018	30	20	2.10	D
23/10/2018	41	21	1.05	B
22/11/2018	38	21	1.37	C
08/12/2018	38	20	1.30	B
21/05/2019	36	19	1.35	B
20/06/2019	37	19	1.24	B
25/07/2019	32	16	1.52	C
20/08/2019	33	16	1.31	B
17/09/2019	33	16	1.31	B

FIELD SERVICE

DATE SERVICE
01/08/2018 CHANGED OIL

No.	Unit No.	Serial Number	TC
6.	MAIN TRAF0 UNIT 3	3011160192	23

A) Analysis

- **Acidity** of 0.014mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 81kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 6ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 0.39% M/dw is graded as **A**. For this transformer, it is recommended to maintain water content in oil at less than 20ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019
ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - MAIN TRAF0 UNIT 3

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
20/06/2019	ONLINE						
25/07/2019	ONLINE						
20/08/2019	ONLINE						
17/09/2019	ONLINE						

NAMEPLATE DATA

MFG	- PAUWES TRAF0
DATE MFG	- 2018
MAIN TANK S/N	- 3011160192
KVA	- 60000
PRI	- 157000 V
SEC	- 6300 V
KILOGRAMS	- 103500
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAF
IMPEDENCE	- 13.171%
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 30183

LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
21/05/2019	ROUTINE	0.011 AC		93 AC	0.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.011 AC	40.6 AC	83 AC	0.5 AC	0.8786 AC	CLEAR AC	
25/07/2019	ROUTINE	0.014 AC		87 AC	0.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.011 AC		78 AC	0.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.014 AC		81 AC	0.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
20/06/2019	3	9903	31346	6	156	369	ND	ND	ND	165	41783

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- YES
H2O COOLED	- NO
OIL PUMPS	- YES
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- YES
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- YES

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
21/05/2019	38	7	0.46	A
20/06/2019	38	8	0.52	A
25/07/2019	37	6	0.39	A
20/08/2019	39	6	0.33	A
17/09/2019	38	6	0.39	A

FIELD SERVICE

DATE	SERVICE
------	---------

No.	Unit No.	Serial Number	TC
7.	UAT 3	PX18-0082	22

A) Analysis

- **Acidity** of 0.014mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 88kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 4ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 0.28% M/dw is graded as **A**. For this transformer, it is recommended to maintain water content in oil at less than 30ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019
ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **UAT 3**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
20/06/2019	ONLINE						
25/07/2019	ONLINE						
20/08/2019	ONLINE						
17/09/2019	ONLINE						

NAMEPLATE DATA

MFG	- B & D
DATE MFG	- 2018
MAIN TANK S/N	- PX18-0082
KVA	- 6300
PRI	- 6300 V
SEC	- 6300 V
KILOGRAMS	- 52000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	- 5.78%
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 12000
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
21/05/2019	ROUTINE	0.014 AC		85 AC	0.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.014 AC	37.0 AC	89 AC	0.5 AC	0.8798 AC	CLEAR AC	
25/07/2019	ROUTINE	0.014 AC		83 AC	0.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.014 AC		78 AC	0.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.014 AC		88 AC	0.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
20/06/2019	4	10251	34223	16	39	232	26	2	ND	87	44793

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- YES

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
21/05/2019	35	5	0.35	A
20/06/2019	34	5	0.41	A
25/07/2019	32	5	0.47	A
20/08/2019	35	4	0.28	A
17/09/2019	36	4	0.28	A

FIELD SERVICE

DATE	SERVICE
------	---------

No.	Unit No.	Serial Number	TC
8.	TRAFO 1 ESP UNIT 3	0073084208	11

A) Analysis

- **Acidity** of 0.022mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 67kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water content** in oil of 8ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 1.04% M/dw is graded as **B**. For this transformer, it is advisable to maintain the water content level below 20ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019

ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 1 ESP UNIT 3**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	OFFLINE						
23/10/2018	ONLINE						
22/11/2018	OFFLINE						
08/12/2018	OFFLINE						
21/05/2019	OFFLINE						
20/06/2019	OFFLINE						
25/07/2019	OFFLINE						
20/08/2019	OFFLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- ZHEJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 0073084208
KVA	-
PRI	- 72000 V
SEC	- 416 V
KILOGRAMS	- 1350
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 731
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.022 AC		77 AC	0.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.020 AC		64 AC	0.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.020 AC		63 AC	0.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.020 AC		53 AC	0.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.020 AC		62 AC	0.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.022 AC		85 AC	0.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.022 AC	35.2 AC	65 AC	0.5 AC	0.8212 QU	CLEAR AC	
25/07/2019	ROUTINE	0.020 AC		51 AC	0.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.020 AC		69 AC	0.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.022 AC		67 AC	0.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	14	12943	68807	3	62	1243	ND	ND	ND	79	83072
06/12/2017	14	12739	65097	3	66	612	ND	ND	ND	83	78531
28/06/2018	19	15552	64448	3	57	1391	ND	ND	ND	79	81470
20/06/2019	11	19448	64974	6	15	1064	ND	ND	ND	32	85518

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- NO
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- YES

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	26	9	1.17	B
25/09/2018	30	10	1.05	B
23/10/2018	31	12	1.14	B
22/11/2018	32	9	0.86	B
08/12/2018	29	9	0.94	B
21/05/2019	25	9	1.17	B
20/06/2019	26	9	1.17	B
25/07/2019	25	9	1.17	B
20/08/2019	26	8	1.04	B
17/09/2019	26	8	1.04	B

FIELD SERVICE

DATE	SERVICE
------	---------

No.	Unit No.	Serial Number	TC
9.	TRAFO 2 ESP UNIT 3	0070084208	12

A) Analysis

- **Acidity** of 0.031mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 43kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 20ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 1.90% M/dw is graded as **D**. For this transformer, it is advisable to maintain the water content level below 20ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019

ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 2 ESP UNIT 3**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	ONLINE						
23/10/2018	OFFLINE						
22/11/2018	ONLINE						
08/12/2018	ONLINE						
21/05/2019	OFFLINE						
20/06/2019	ONLINE						
25/07/2019	ONLINE						
20/08/2019	OFFLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- ZHEJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 0070084208
KVA	-
PRI	- 72000 V
SEC	- 415 V
KILOGRAMS	- 1350
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 731
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.025 AC		67 AC	0.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.022 AC		31 AC	0.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.025 AC		54 AC	0.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.025 AC		33 AC	0.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.025 AC		30 AC	0.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.028 AC		40 AC	1.0 AC		CLEAR AC	
20/06/2019	ROUTINE	0.028 AC	31.3 QU	41 AC	1.0 AC	0.8163 QU	CLEAR AC	
25/07/2019	ROUTINE	0.031 AC		60 AC	1.0 AC		CLEAR AC	
20/08/2019	ROUTINE	0.028 AC		48 AC	1.0 AC		CLEAR AC	
17/09/2019	ROUTINE	0.031 AC		43 AC	1.0 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	38	16781	70523	5	129	2431	3	5	ND	180	89915
06/12/2017	42	19523	66059	3	102	912	ND	ND	ND	147	86641
28/06/2018	43	22272	68719	4	38	1226	ND	ND	ND	85	92302
20/06/2019	13	21221	65168	7	48	1870	ND	ND	ND	68	88327

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	26	11	1.43	C
25/09/2018	39	32	1.76	D
23/10/2018	32	13	1.24	B
22/11/2018	42	38	1.90	D
08/12/2018	43	32	1.44	C
21/05/2019	33	18	1.48	C
20/06/2019	32	18	1.71	D
25/07/2019	29	21	2.20	D
20/08/2019	31	19	1.80	D
17/09/2019	31	20	1.90	D

FIELD SERVICE

DATE SERVICE
01/07/2018 PURIFIED

No.	Unit No.	Serial Number	TC
10.	TRAFO 3 ESP UNIT 3	0072084208	13

A) Analysis

- **Acidity** of 0.020mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 43kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water content** in oil of 20ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 1.64% M/dw is graded as **C**. For this transformer, it is advisable to maintain the water content level below 20ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019

ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 3 ESP UNIT 3**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	ONLINE						
23/10/2018	ONLINE						
22/11/2018	ONLINE						
08/12/2018	ONLINE						
21/05/2019	ONLINE						
20/06/2019	ONLINE						
25/07/2019	ONLINE						
20/08/2019	ONLINE						
17/09/2019	ONLINE						

NAMEPLATE DATA

MFG	- ZHEJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 0072084208
KVA	-
PRI	- 72000 V
SEC	- 415 V
KILOGRAMS	- 1350
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 731
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.014 AC		76 AC	0.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.020 AC		47 AC	0.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.014 AC		49 AC	0.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.017 AC		39 AC	0.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.014 AC		34 AC	0.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.014 AC		41 AC	0.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.020 AC	38.5 AC	36 AC	0.5 AC	0.8215 QU	CLEAR AC	
25/07/2019	ROUTINE	0.020 AC		36 AC	0.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.017 AC		32 AC	0.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.020 AC		43 AC	0.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	21	16364	70694	3	38	1068	ND	ND	ND	62	88188
06/12/2017	15	14515	65277	2	40	559	ND	ND	ND	57	80408
28/06/2018	30	15202	64188	4	65	1833	ND	ND	ND	99	81322
20/06/2019	14	18302	64811	6	86	2181	ND	ND	ND	106	85400

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	25	11	1.43	C
25/09/2018	40	20	1.10	B
23/10/2018	39	15	0.82	A
22/11/2018	40	15	0.82	A
08/12/2018	43	18	0.81	A
21/05/2019	36	20	1.42	C
20/06/2019	35	23	1.63	C
25/07/2019	31	20	1.90	D
20/08/2019	33	19	1.56	C
17/09/2019	33	20	1.64	C

FIELD SERVICE

DATE SERVICE
01/07/2018 PURIFIED

No.	Unit No.	Serial Number	TC
11.	TRAFO 4 UNIT 3	0071084208	14

A) Analysis

- **Acidity** of 0.025mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 51kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water content** in oil of 12ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 1.42% M/dw is graded as **C**. For this transformer, it is advisable to maintain the water content level below 20ppm.

B) Recommendation

- Do carry-out *Liquid Screen, Liquid Power Factor, Inhibitor, Water Content, Metals-In-Oil, Furan Analysis & DGA periodically for **Condition Monitoring purposes**

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019
ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 4 UNIT 3**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
24/07/2018	OFFLINE						
25/08/2018	OFFLINE						
25/09/2018	ONLINE						
23/10/2018	OFFLINE						
08/12/2018	OFFLINE						
21/05/2019	OFFLINE						
20/06/2019	OFFLINE						
25/07/2019	OFFLINE						
20/08/2019	OFFLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- ZHEJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 0071084208
KVA	-
PRI	- 72000 V
SEC	- 415 V
KILOGRAMS	- 1350
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 731
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.025 AC		66 AC	1.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.022 AC		51 AC	1.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.022 AC		56 AC	1.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.022 AC		44 AC	1.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.022 AC		49 AC	1.0 AC		CLEAR AC	
21/05/2019	ROUTINE	0.022 AC		58 AC	1.0 AC		CLEAR AC	
20/06/2019	ROUTINE	0.022 AC	30.3 QU	51 AC	1.0 AC	0.8451 AC	CLEAR AC	
25/07/2019	ROUTINE	0.020 AC		75 AC	1.0 AC		CLEAR AC	
20/08/2019	ROUTINE	0.022 AC		49 AC	1.0 AC		CLEAR AC	
17/09/2019	ROUTINE	0.025 AC		51 AC	1.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	10	18669	66036	3	24	665	ND	ND	ND	37	85407
06/12/2017	14	15414	63712	2	22	675	ND	ND	ND	38	79839
28/06/2018	20	14690	67822	2	22	683	ND	ND	ND	44	83239
20/06/2019	19	16312	66417	4	37	732	ND	ND	ND	60	83521

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	27	11	1.30	B
25/09/2018	30	11	1.15	B
23/10/2018	30	12	1.26	B
22/11/2018	30	11	1.15	B
08/12/2018	29	13	1.37	C
21/05/2019	26	11	1.43	C
20/06/2019	27	12	1.42	C
25/07/2019	26	11	1.43	C
20/08/2019	27	11	1.30	B
17/09/2019	27	12	1.42	C

FIELD SERVICE

DATE	SERVICE
------	---------

No.	Unit No.	Serial Number	TC
12.	ASH HANDLING-1	10820108	15

A) Analysis

- **Acidity** of 0.025mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 52kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 21ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 1.49% M/dw is graded as **B**. For this transformer, it is recommended to maintain water content in oil at less than 30ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019
ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - ASH HANDLING-1

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
24/07/2018	ONLINE						
25/08/2018	OFFLINE						
23/10/2018	ONLINE						
22/11/2018	ONLINE						
08/12/2018	ONLINE						
21/05/2019	ONLINE						
20/06/2019	ONLINE						
25/07/2019	ONLINE						
20/08/2019	ONLINE						
17/09/2019	ONLINE						

NAMEPLATE DATA

MFG	- WOLONG
DATE MFG	- 2011
MAIN TANK S/N	- 10820108
KVA	- 1600
PRI	- 6300 V
SEC	- 400 V
KILOGRAMS	- 4505
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	- 5.56%
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 1023
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.025 AC		60 AC	1.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.025 AC		43 AC	1.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.022 AC		28 QU	1.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.022 AC		25 QU	1.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.022 AC		20 UN	1.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.022 AC		28 QU	1.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.022 AC	36.6 AC	27 QU	1.5 AC	0.8890 AC	CLEAR AC	
25/07/2019	ROUTINE	0.025 AC		49 AC	1.0 AC		CLEAR AC	
20/08/2019	ROUTINE	0.022 AC		30 AC	1.0 AC		CLEAR AC	
17/09/2019	ROUTINE	0.025 AC		52 AC	1.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	35	10984	71058	20	441	5037	7	8	ND	511	87590
06/12/2017	49	12034	67124	20	558	5440	8	8	ND	643	85241
28/06/2018	53	10939	69394	20	557	5425	9	8	ND	647	86405
20/06/2019	53	14032	65585	13	487	5360	ND	11	ND	564	85541

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- YES

RECOMMENDATION:

GAS LEVELS HAVE REMAINED STABLE. PROCEED WITH ANNUAL MONITORING.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	30	16	1.68	B
25/09/2018	35	17	1.21	A
23/10/2018	36	29	2.06	C
22/11/2018	36	28	1.99	B
08/12/2018	35	28	1.99	B
21/05/2019	34	29	2.38	C
20/06/2019	34	29	2.38	C
25/07/2019	35	21	1.49	B
20/08/2019	38	20	1.30	B
17/09/2019	35	21	1.49	B

FIELD SERVICE

DATE	SERVICE
------	---------

No.	Unit No.	Serial Number	TC
13.	ASH HANDLING-2	10820107	16

A) Analysis

- **Acidity** of 0.028mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 37kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 26ppm is **ACCEPTABLE**. Meanwhile Water Content in solid insulation of 2.13% M/dw is graded as **C**. For this transformer, it is recommended to maintain water content in oil at less than 30ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019
ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - ASH HANDLING-2

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
28/06/2018	OFFLINE						
24/07/2018	ONLINE						
25/08/2018	OFFLINE						
25/09/2018	OFFLINE						
08/12/2018	ONLINE						
21/05/2019	OFFLINE						
20/06/2019	ONLINE						
25/07/2019	ONLINE						
20/08/2019	ONLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- WOLONG
DATE MFG	- 2011
MAIN TANK S/N	- 10820107
KVA	- 1600
PRI	- 6300 V
SEC	- 400 V
KILOGRAMS	- 4505
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	- 5.6%
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 1023
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.022 AC		45 AC	1.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.022 AC		36 AC	1.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.022 AC		36 AC	1.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.022 AC		30 AC	1.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.022 AC		32 AC	1.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.022 AC		32 AC	1.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.022 AC	36.8 AC	37 AC	1.5 AC	0.8889 AC	CLEAR AC	
25/07/2019	ROUTINE	0.025 AC		42 AC	1.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.025 AC		36 AC	1.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.028 AC		37 AC	1.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
04/07/2017	18	21157	64224	4	129	1676	ND	1	ND	152	87209
06/12/2017	20	15791	63530	5	275	2783	ND	4	ND	304	82408
28/06/2018	32	22904	67139	4	249	3112	ND	5	ND	290	93445
20/06/2019	39	11205	66397	21	439	5998	11	9	ND	519	84119

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- NO
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- NO
HOSE LENGTH	-
POWER AVAILABLE	- YES

RECOMMENDATION:
CARBON MONOXIDE AND CARBON DIOXIDE LEVEL ARE HIGH. OTHER GASES LEVELS ARE ASSESSED AS ACCEPTABLE.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	28	16	1.89	B
25/09/2018	30	19	2.00	B
23/10/2018	37	23	1.50	B
22/11/2018	36	25	1.77	B
08/12/2018	37	24	1.56	B
21/05/2019	35	23	1.63	B
20/06/2019	34	24	1.97	B
25/07/2019	35	27	1.92	B
20/08/2019	38	29	1.88	B
17/09/2019	34	26	2.13	C

FIELD SERVICE

DATE SERVICE
01/07/2018 PURIFIED

No.	Unit No.	Serial Number	TC
14.	TRAFO 1 ESP UNIT 2	10037	17

A) Analysis

- **Acidity** of 0.036mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 19kV is **UNACCEPTABLE**. This is reflected from the high water content detected in the transformer oil
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 62ppm is **UNACCEPTABLE** while moisture in solid insulation of 7.32% M/dw is graded as **E**. For this transformer, it is recommended to maintain the water content less than 20ppm. This indicates the high presence of water content in the oil. The presence of high water content could cause dielectric failure.

B) Recommendation

- Recommend to retest for Dielectric and Water Content immediately in order to verify the results. If the result confirmed that the oil is high in water content, we recommend to perform **OIL PURIFICATION**. The transformer oil is not conducive for normal operation of a transformer. This transformer unit is operating on low dielectric value and high water content. Operating a transformer on these conditions is prone to tripping. Oil purification will remove excessive moisture detected in the transformer oil and thus improving dielectric breakdown voltage of the mineral oil.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019

ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 1 ESP UNIT 2**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	OFFLINE						
23/10/2018	OFFLINE						
22/11/2018	OFFLINE						
08/12/2018	OFFLINE						
21/05/2019	OFFLINE						
20/06/2019	OFFLINE						
25/07/2019	OFFLINE						
20/08/2019	ONLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- FUJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 10037
KVA	-
PRI	- 72000 V
SEC	- 380 V
KILOGRAMS	- 1000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 630
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.031 AC		74 AC	1.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.028 AC		74 AC	1.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.028 AC		54 AC	1.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.028 AC		54 AC	1.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.028 AC		46 AC	1.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.031 AC		67 AC	1.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.031 AC	31.0 QU	62 AC	1.0 AC	0.8776 AC	CLEAR AC	
25/07/2019	ROUTINE	0.031 AC		64 AC	1.0 AC		CLEAR AC	
20/08/2019	ROUTINE	0.034 AC		63 AC	1.0 AC		CLEAR AC	
17/09/2019	ROUTINE	0.036 AC		19 UN	1.0 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
28/06/2018	93	17225	43231	5	57	775	ND	2	ND	157	61388
20/06/2019	62	18560	46166	5	50	839	ND	ND	ND	117	65682

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	29	12	1.26	B
25/09/2018	30	10	1.05	B
23/10/2018	31	11	1.04	B
22/11/2018	32	10	0.95	B
08/12/2018	30	10	1.05	B
21/05/2019	30	12	1.26	B
20/06/2019	30	13	1.37	C
25/07/2019	29	11	1.15	B
20/08/2019	29	11	1.15	B
17/09/2019	28	62	7.32	E

FIELD SERVICE

DATE SERVICE

No.	Unit No.	Serial Number	TC
15.	TRAFO 2 ESP UNIT 2	10036	18

A) Analysis

- **Acidity** of 0.067mgKOH/gm is **QUESTIONABLE**. Although the level remained stable, the oil are containing oxidation by-products. These oxidation by-products are depositing and degrading the oil as well as the paper insulation. Therefore, removal of these contaminations are highly recommended.
- **Dielectric** of 59kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 11ppm is **ACCEPTABLE** while moisture in solid insulation of 1.30% M/dw is graded as **B**. For this transformer, it is recommended to maintain the water content less than 20ppm.

B) Recommendation

- Based on previous oil analysis, the IFT of the oil is unfavorable, it is recommended to perform **Transformer Oil Regeneration** on this unit. Transformer oil regeneration at this stage of contamination will effectively remove unwanted oxidation byproducts from the insulating oil. This process will restore the oil back to its original quality, thus protecting the paper insulation and extending the transformer serviceable lifespan. Furthermore, oil inhibitor 2,6-DBPC and passivator will be added to preserve both the transformer oil and copper surfaces to enhance the service ability of the transformer.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019

ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 2 ESP UNIT 2**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	OFFLINE						
23/10/2018	OFFLINE						
22/11/2018	OFFLINE						
08/12/2018	OFFLINE						
21/05/2019	OFFLINE						
20/06/2019	OFFLINE						
25/07/2019	OFFLINE						
20/08/2019	ONLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- FUJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 10036
KVA	-
PRI	- 72000 V
SEC	- 380 V
KILOGRAMS	- 1000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 630

LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.062 QU		67 AC	1.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.056 QU		51 AC	1.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.062 QU		67 AC	1.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.062 QU		61 AC	1.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.062 QU		59 AC	1.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.065 QU		77 AC	1.0 AC		CLEAR AC	
20/06/2019	ROUTINE	0.065 QU	29.7 QU	76 AC	1.0 AC	0.8655 AC	CLEAR AC	
25/07/2019	ROUTINE	0.062 QU		47 AC	1.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.065 QU		41 AC	1.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.067 QU		59 AC	1.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
28/06/2018	8	22714	64906	5	67	879	ND	ND	ND	80	88579
20/06/2019	5	29439	65338	5	25	977	ND	ND	ND	35	95789

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	31	10	0.95	B
25/09/2018	29	9	0.94	B
23/10/2018	31	13	1.24	B
22/11/2018	33	8	0.66	A
08/12/2018	30	8	0.84	A
21/05/2019	30	11	1.15	B
20/06/2019	31	12	1.14	B
25/07/2019	28	11	1.30	B
20/08/2019	30	12	1.26	B
17/09/2019	27	11	1.30	B

FIELD SERVICE

DATE	SERVICE
------	---------

No.	Unit No.	Serial Number	TC
16.	TRAFO 3 ESP UNIT 2	10033	19

A) Analysis

- **Acidity** of 0.062mgKOH/g is **QUESTIONABLE**. Although the level remained stable, the oil are containing oxidation by-products. These oxidation by-products are depositing and degrading the oil as well as the paper insulation. Therefore, removal of these contaminations are highly recommended.
- **Dielectric** of 84kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 10ppm is **ACCEPTABLE** while moisture in solid insulation of 1.05% M/dw is graded as **B**. For this transformer, it is recommended to maintain the water content less than 20ppm.

B) Recommendation

- Based on previous oil analysis, the IFT of the oil is unfavorable. It is recommended to perform **Transformer Oil Regeneration** on this unit. Transformer oil regeneration at this stage of contamination will effectively remove unwanted oxidation byproducts from the insulating oil. This process will restore the oil back to its original quality, thus protecting the paper insulation and extending the transformer serviceable lifespan. Furthermore, oil inhibitor 2,6-DBPC and passivator will be added to preserve both the transformer oil and copper surfaces to enhance the service ability of the transformer.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019
ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 3 ESP UNIT 2**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
25/08/2018	OFFLINE						
25/09/2018	OFFLINE						
23/10/2018	OFFLINE						
22/11/2018	OFFLINE						
08/12/2018	OFFLINE						
21/05/2019	OFFLINE						
20/06/2019	OFFLINE						
25/07/2019	OFFLINE						
20/08/2019	ONLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- FUJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 10033
KVA	-
PRI	- 72000 V
SEC	- 380 V
KILOGRAMS	- 1000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 630
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.067 QU		73 AC	1.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.067 QU		59 AC	1.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.070 QU		86 AC	1.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.070 QU		13 UN	1.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.070 QU		8 UN	1.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.073 QU		50 AC	1.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.073 QU	26.5 UN	53 AC	1.5 AC	0.8687 AC	CLEAR AC	
25/07/2019	ROUTINE	0.070 QU		48 AC	1.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.067 QU		58 AC	1.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.062 QU		84 AC	1.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
28/06/2018	14	17627	48672	4	47	935	ND	ND	ND	65	67299
20/06/2019	16	17449	51923	5	58	1049	ND	ND	ND	79	70500

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	30	13	1.37	C
25/09/2018	30	12	1.26	B
23/10/2018	32	13	1.24	B
22/11/2018	33	84	6.89	E
08/12/2018	31	84	7.98	E
21/05/2019	30	13	1.37	C
20/06/2019	30	13	1.37	C
25/07/2019	29	13	1.37	C
20/08/2019	31	14	1.33	B
17/09/2019	30	10	1.05	B

FIELD SERVICE

DATE	SERVICE
------	---------

No.	Unit No.	Serial Number	TC
17.	TRAFO 4 ESP UNIT 2	10032	20

A) Analysis

- **Acidity** of 0.034mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 50kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 12ppm is **ACCEPTABLE** while moisture in solid insulation of 1.26% M/dw is graded as **B**. For this transformer, it is recommended to maintain the water content less than 20ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019
ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - **TRAFO 4 ESP UNIT 2**

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
24/07/2018	OFFLINE						
25/08/2018	OFFLINE						
23/10/2018	OFFLINE						
22/11/2018	OFFLINE						
08/12/2018	OFFLINE						
21/05/2019	OFFLINE						
20/06/2019	OFFLINE						
25/07/2019	OFFLINE						
20/08/2019	ONLINE						
17/09/2019	OFFLINE						

NAMEPLATE DATA

MFG	- FUJIAN
DATE MFG	- 2010
MAIN TANK S/N	- 10032
KVA	-
PRI	- 72000 V
SEC	- 380 V
KILOGRAMS	- 1000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- ONAN
IMPEDENCE	-
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 630
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.031 AC		68 AC	1.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.031 AC		51 AC	1.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.034 AC		57 AC	1.0 AC		CLEAR AC	
22/11/2018	ROUTINE	0.034 AC		69 AC	1.0 AC		CLEAR AC	
08/12/2018	ROUTINE	0.034 AC		61 AC	1.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.036 AC		60 AC	1.0 AC		CLEAR AC	
20/06/2019	ROUTINE	0.036 AC	30.3 QU	61 AC	1.0 AC	0.8732 AC	CLEAR AC	
25/07/2019	ROUTINE	0.034 AC		59 AC	1.0 AC		CLEAR AC	
20/08/2019	ROUTINE	0.036 AC		45 AC	1.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.034 AC		50 AC	1.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
28/06/2018	22	25201	74464	5	85	823	ND	ND	ND	112	100600
20/06/2019	33	25208	70145	4	35	853	ND	ND	ND	72	96278

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- NO
H2O COOLED	- NO
OIL PUMPS	- NO
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- NO
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- NO

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	31	10	0.95	B
25/09/2018	29	11	1.15	B
23/10/2018	32	15	1.42	C
22/11/2018	33	14	1.15	B
08/12/2018	31	18	1.71	D
21/05/2019	31	14	1.33	B
20/06/2019	30	14	1.47	C
25/07/2019	29	12	1.26	B
20/08/2019	32	12	1.14	B
17/09/2019	30	12	1.26	B

FIELD SERVICE

DATE	SERVICE
------	---------

No.	Unit No.	Serial Number	TC
18.	MAIN TRAFO UNIT 2	1006902	21

A) Analysis

- **Acidity** of 0.014mgKOH/g is **ACCEPTABLE**.
- **Dielectric** of 63kV is **ACCEPTABLE**.
- **Colour** and **Visualization** of oil is in the **ACCEPTABLE** range.
- **Water Content** in oil of 8ppm is **ACCEPTABLE** while moisture in solid insulation of 0.66% M/dw is graded as **A**. For this transformer, it is recommended to maintain the water content less than 20ppm.

B) Recommendation

- Do carry out *Liquid Screen Tests, Water Content, Furan Analysis, Metals-In-Oil, Liquid Power Factor and Inhibitor Content tests **annually for Condition Monitoring purposes**.

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein

DATE PRINTED 06/10/2019
ID# - 601669

CUST - PT IP UJP PLTU
JERANJANG

SUB NAME -
CITY - MATARAM LOMBOK
UNIT# - MAIN TRAFU UNIT 2

LOCATION - OUTDOOR
OTHER -

VISUAL INSPECTION

DATE	STATUS	OIL TEMP °C	W. TEMP °C	OIL LEVEL	PAINT	S. GEL	LEAKS
24/07/2018	ONLINE					GOOD	
25/08/2018	ONLINE						
25/09/2018	ONLINE						
23/10/2018	OFFLINE						
08/12/2018	OFFLINE						
21/05/2019	ONLINE						
20/06/2019	ONLINE						
25/07/2019	ONLINE						
20/08/2019	ONLINE						
17/09/2019	ONLINE						

NAMEPLATE DATA

MFG	- WOLONG
DATE MFG	- 2011
MAIN TANK S/N	- 1006902
KVA	- 33000
PRI	- 170000 V
SEC	- 6300 V
KILOGRAMS	- 81000
EQUIP TYPE	- TRANSFORMER
TRANS CLASS	- OFAF
IMPEDENCE	- 13.03%
PHASE/CYCLE	- 3/50 Hz
LIQUID TYPE	- OIL
LITRES LIQUID	- 30857
LTC MFG	-
LTC S/N	-
LTC FAB NO	-
LTC MODEL	-
LTC LITRES LIQUID	-
LTC ENERGIZED	-

LIQUID SCREEN TEST DATA

DATE	SERVICES	ASTM D974 ACID (mgKOH/gm)	ASTM D971 IFT (mN/m)	IEC 156 DIEL (kV)	ASTM D1500 COLOUR	ASTM D4052 SP. GR.	ASTM D1524 VISUAL	ASTM D1698 ® SEDIMENT
25/08/2018	ROUTINE	0.011 AC		83 AC	0.5 AC		CLEAR AC	
25/09/2018	ROUTINE	0.011 AC		90 AC	0.5 AC		CLEAR AC	
23/10/2018	ROUTINE	0.011 AC		64 AC	0.5 AC		CLEAR AC	
22/11/2018	ROUTINE	0.011 AC		61 AC	0.5 AC		CLEAR AC	
08/12/2018	ROUTINE	0.011 AC		57 AC	0.5 AC		CLEAR AC	
21/05/2019	ROUTINE	0.011 AC		63 AC	0.5 AC		CLEAR AC	
20/06/2019	ROUTINE	0.011 AC	39.3 AC	58 AC	0.5 AC	0.8745 AC	CLEAR AC	
25/07/2019	ROUTINE	0.011 AC		49 AC	0.5 AC		CLEAR AC	
20/08/2019	ROUTINE	0.014 AC		36 AC	0.5 AC		CLEAR AC	
17/09/2019	ROUTINE	0.014 AC		63 AC	0.5 AC		CLEAR AC	

DISSOLVED GAS ANALYSIS (ASTM D3612C), EXPRESSED IN PPM

DATE	HYDROGEN	OXYGEN	NITROGEN	METHANE	CARBON MONOXIDE	CARBON DIOXIDE	ETHANE	ETHYLENE	ACETYLENE	TOTAL COMBUSTIBLE	TOTAL GAS
28/06/2018	19	12733	53386	10	193	2448	ND	2	ND	224	68791
20/06/2019	10	17382	50681	8	107	712	ND	2	ND	127	68902

ADDITIONAL EQUIPMENT

RADIATORS	- YES
FANS	- YES
H2O COOLED	- NO
OIL PUMPS	- YES
TOP FPV	-
BOTTOM FPV	-
BUCHOLZ	- YES
CONSERVATOR	- YES
LTC COMPARTMENT	- YES
BUSHING LOC	- TOP
FREE BREATHER	- YES
HOSE LENGTH	-
POWER AVAILABLE	- YES

RECOMMENDATION:
RETEST 12 MONTHS:
TEST RESULT INDICATES NORMAL OPERATION.

WATER CONTENT (ASTM D1533), EXPRESSED IN PPM

DATE	TEMP°C	PPM	%M/dw	GRADE
25/08/2018	34	9	0.74	A
25/09/2018	32	7	0.67	A
23/10/2018	29	7	0.74	A
22/11/2018	32	7	0.67	A
08/12/2018	30	6	0.63	A
21/05/2019	35	7	0.50	A
20/06/2019	35	11	0.78	A
25/07/2019	32	7	0.67	A
20/08/2019	34	8	0.66	A
17/09/2019	34	8	0.66	A

FIELD SERVICE

DATE	SERVICE
------	---------

3.0 Summary of Our Comments & Recommendations:

No.	Sub Name	Unit No.	TC	Recommendation
1.	MAIN TRAF0 UNIT 1	100691	4	• Periodic condition monitoring
2.	TRAF0 1 ESP UNIT 1	10937	5	• Periodic condition monitoring
3.	TRAF0 2 ESP UNIT 1	10035	6	• Perform OIL REGENERATION
4.	TRAF0 3 ESP UNIT 1	10031	7	• Perform OIL REGENERATION
5.	TRAF0 4 ESP UNIT 1	10034	8	• Periodic condition monitoring
6.	MAIN TRAF0 UNIT 3	3011160192	23	• Periodic condition monitoring
7.	UAT 3	PX18-0082	22	• Periodic condition monitoring
8.	TRAF0 1 ESP UNIT 3	0073084208	11	• Periodic condition monitoring
9.	TRAF0 2 ESP UNIT 3	0070084208	12	• Periodic condition monitoring
10.	TRAF0 3 ESP UNIT 3	0072084208	13	• Periodic condition monitoring
11.	TRAF0 4 UNIT 3	0071084208	14	• Periodic condition monitoring
12.	ASH HANDLING-1	10820108	15	• Periodic condition monitoring
13.	ASH HANDLING-2	10820107	16	• Periodic condition monitoring
14.	TRAF0 1 ESP UNIT 2	10037	17	• Perform OIL PURIFICATION
15.	TRAF0 2 ESP UNIT 2	10036	18	• Perform OIL REGENERATION
16.	TRAF0 3 ESP UNIT 2	10033	19	• Perform OIL REGENERATION

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein


No.	Sub Name	Unit No.	TC	Recommendation
17.	TRAFO 4 ESP UNIT 2	10032	20	• Periodic condition monitoring
18.	MAIN TRAFO UNIT 2	1006902	21	• Periodic condition monitoring

Page Disclaimer :

All information provided is deemed reliable but is not guaranteed. The interpretation, comments and recommendations are derived based on International Standards and are the personal opinion of the Analyst of TxM Services Sdn. Bhd. The customer is advised to independently verify the information herein



no	Test Cer.	Date Test	nama unit	Serial number	thn opr	Jumlah minyak, liter	Buatan	hasil test laboratorium														
								acid	ift	diel.	color	spec. Graf.	visual	sedi.	moisture		dga ASTM D3612					
															ppm	grade	H ₂	O ₂	N ₂	CH ₄	CO	CO ₂
Standard yang dipakai								ASTM D974	ASTM D971	IEC 156	ASTM D1500	ASTM D4052	ASTM D1524	ASTM D1698	ASTM D1533	hydrogen	oksigen	nitrogen	methane	carbon monoksida	carbon dioksida	
			BATASAN OPERASI					< 0,06	> 32	> 30	< 3,5	> 0,84	C		< 20		< 100			< 120	< 350	< 2.500
	4	21/05/2018						0,011		77	0,5		C		10	B						
	4	28/06/2018						0,014	41,9	69	0,5	0,8716	C		7	A	176	11.044	46.776	41	758	3.393
	4	24/07/2018						0,014		86	0,5		C		6	A						
	4	25/08/2018						0,017		90	0,5		C		6	A						
	4	25/09/2018						0,014		96	0,5		C		7	A						
	4	23/10/2018						0,014		83	0,5		C		8	A						
	4	22/11/2018						0,014		73	0,5		C		9	A						
	4	08/12/2018						0,014		75	0,5		C		8	A						
	4	21/05/2019						0,014		71	0,5		C		8	A						
	4	20/06/2019						0,017	41,3	66	0,5	0,8789	C		7	A		19.122	60.738	26	756	3.272
	4	25/07/2019						0,014		79	0,5		C		8	A						
	4	20/08/2019						0,014		61	0,5		C		7	A						
	4	17/09/2019						0,017		73	0,5		C		6	A						
2	5	21/05/2018	Trafo 1 ESP	1	10937	2010	1.143	Fujia	0,065		38	1,5	C		33	E						
	5	28/06/2018						0,067	25,9	32	1,5	0,8560	C		30	E	44	20.039	64.529	4	119	1.696
	5	24/07/2018						0,073		38	1,5		C		19	D						
	5	25/08/2018						0,020		71	0,5		C		12	B						
	5	25/09/2018						0,017		63	0,5		C		18	B						
	5	23/10/2018						0,020		49	0,5		C		24	B						
	5	22/11/2018						0,017		30	0,5		C		23	C						
	5	08/12/2018						0,017		41	0,5		C		18	D						
	5	21/05/2019						0,017		40	0,5		C		22	C						
	5	20/06/2019						0,017	38,7	34	0,5	0,8747	C		23	C	22	27.043	68.613	5		689
	5	25/07/2019						0,017		61	0,5		C		18	D						
	5	20/08/2019						0,017		56	0,5		C		16	C						
	5	17/09/2019						0,020		60	0,5		C		13	C						
3	6	21/05/2018	Trafo 2 ESP	1	10035	2010	1.143	Fujia	0,056		45	1,5	C		20	D						
	6	28/06/2018						0,059	27,6	55	1,5	0,8570	C		17	C	22	22.494	64.443	4	57	789
	6	24/07/2018						0,062		47	1,5		C		15	C						
	6	25/08/2018						0,022		56	0,5		C		13	B						
	6	25/09/2018						0,020		67	0,5		C		11	B						
	6	23/10/2018						0,020		71	0,5		C		14	B						
	6	22/11/2018						0,020		63	0,5		C		18	C						
	6	08/12/2018						0,020		51	0,5		C		14	B						
	6	21/05/2019						0,020		71	0,5		C		15	B						
	6	20/06/2019						0,020	27,9	68	0,5	0,8658	C		17	B	23	17.710	61.707	5	23	842
	6	25/07/2019						0,022		67	0,5		C		15	C						
	6	20/08/2019						0,020		51	0,5		C		15	C						
	6	17/09/2019						0,022		47	0,5		C		16	D						
4	7	21/05/2018	Trafo 3 ESP	1	10031	2010	1.143	Fujia	0,056		48	1,5	C		21	D						
	7	28/06/2018						0,053	29,7	62	1,5	0,8605	C		17	D	9	17.958	66.007	4	46	781
	7	24/07/2018						0,510		64	1,5		C		17	D						
	7	25/08/2018						0,056		57	1,5		C		15	C						
	7	25/09/2018						0,051		46	1,5		C		21	D						
	7	23/10/2018						0,056		44	1,5		C		20	C						
	7	22/11/2018						0,056		39	1,5		C		22	C						
	7	08/12/2018						0,056		39	1,5		C		20	C						
	7	21/05/2019						0,051		33	1,5		C		19	B						
	7	20/06/2019						0,051	29,6	30	1,5	0,8689	C		19	B	16	17.771	65.478	6	73	829
	7	25/07/2019						0,056		48	1,5		C		15	C						
	7	20/08/2019						0,051		43	1,5		C		18	D						
	7	17/09/2019						0,056		48	1,5		C		18	D						
5	8	21/05/2018	Trafo 4 ESP	1	10034	2010	1.143	Fujia	0,034		37	1,5	C		23	D						





no	Test Cer.	Date Test	nama unit		PAK SOETJAHJONO (TXM ADVISOR) RECOMMENDATION
Standar					
	4	21/05/2018			For Test 17 September 2019 Pada dasarnya masih sama seperti bulan sebelumnya, KECUALI trafo ESP 1 Unit 2 , terjadi kenaikan Water Content dan penurunan BDV yang sangat mencolok, Perlu dilakukan pemeriksaan kemungkinan terjadi kebocoran trafo sehingga mencemari kondisi oli. Akan kita lihat trend pada bulan mendatang. Perlu persiapan dilakukan PURIFIKASI Kami tetap meyarankan untuk ESP 2 dan 3 Unit 3 dilakukan PURIFIKASI dengan temperatur sekitar 700 GANTI MINYAK pada trafo ESP 2 dan 3 Unit 1 dan ESP 2 dan 3 Unit 2 For Test 25 July 2019 Kondisi trafo masih seperti bulan yang lalu Kami tetap meyarankan untuk ESP 1 Unit 1 dan ESP 2 dan 3 Unit 3 dilakukan PURIFIKASI dengan temperatur sekitar 70 ⁰ GANTI MINYAK pada trafo ESP 3 Unit 1 dan ESP 2 dan 3 Unit 2 For Test 25 July 2019 Trend penurunan kondisi trafo ESP Jadi kami sarankan untuk ESP 1 Unit 1 dan ESP 2 dan 3 Unit 3 segera dilakukan PURIFIKASI dengan temperatur sekitar 70 ⁰ GANTI MINYAK pada trafo ESP 3 Unit 1 dan ESP 2 dan 3 Unit 2 For Test 20 Juni 2019 Ada penurunan kondisi trafo ESP terutama Unit 1 dan 2 Jadi kami sarankan untuk ESP 1 Unit 1 dan Ash Handling 1 segera dilakukan PURIFIKASI dengan temperatur sekitar 70 ⁰ GANTI MINYAK pada trafo ESP 3 Unit 1 dan ESP 2 dan 3 Unit 2 Monitoring kualitas minyak untuk ESP 1 dan 4 Unit 2 For TEST 21 Mei 2019 Ada beberapa perubahan kondisi trafo seperti, Main Trafo dan UAT Unit 3 yang ganti Trafo baru serta perbaikan oli diESP 3 Unit 2
	4	28/06/2018			
	4	24/07/2018			
	4	25/08/2018			
	4	25/09/2018			
	4	23/10/2018			
	4	22/11/2018			
	4	08/12/2018			
	4	21/05/2019			
	4	20/06/2019			
	4	25/07/2019			
	4	20/08/2019			
	4	17/09/2019			
2	5	21/05/2018	Trafo 1 ESP	1	
	5	28/06/2018			
	5	24/07/2018			
	5	25/08/2018			
	5	25/09/2018			
	5	23/10/2018			
	5	22/11/2018			
	5	08/12/2018			
	5	21/05/2019			
	5	20/06/2019			
	5	25/07/2019			
	5	20/08/2019			
	5	17/09/2019			
3	6	21/05/2018	Trafo 2 ESP	1	
	6	28/06/2018			
	6	24/07/2018			
	6	25/08/2018			
	6	25/09/2018			
	6	23/10/2018			
	6	22/11/2018			
	6	08/12/2018			
	6	21/05/2019			
	6	20/06/2019			
	6	25/07/2019			
	6	20/08/2019			
	6	17/09/2019			
4	7	21/05/2018	Trafo 3 ESP	1	
	7	28/06/2018			
	7	24/07/2018			
	7	25/08/2018			
	7	25/09/2018			
	7	23/10/2018			
	7	22/11/2018			
	7	08/12/2018			
	7	21/05/2019			
	7	20/06/2019			
	7	25/07/2019			
	7	20/08/2019			
	7	17/09/2019			
5	8	21/05/2018	Trafo 4 ESP	1	



no	Test Cer.	Date Test	nama unit	Serial number	thn opr	Jumlah minyak, liter	Buatan	hasil test laboratorium														
								acid	ift	diel.	color	spec. Graf.	visual	sedi.	moisture		dga ASTM D3612					
															ppm	grade	H ₂	O ₂	N ₂	CH ₄	CO	CO ₂
Standard yang dipakai								ASTM D974	ASTM D971	IEC 156	ASTM D1500	ASTM D4052	ASTM D1524	ASTM D1698	ASTM D1533	hydrogen	oksigen	nitrogen	methane	carbon monoksida	carbon dioksida	
		BATASAN OPERASI						< 0,06	> 32	> 30	< 3,5	> 0,84	C		< 20		< 100			< 120	< 350	< 2.500
	8	28/06/2018						0,037	27,5	55	1,5	0,8653	C		20	D	9	17.962	64.248	4	75	1.054
	8	24/07/2018						0,039		50	1,5		C		19	D						
	8	25/08/2018						0,017		61	0,5		C		14	C						
	8	25/09/2018						0,014		45	0,5		C		20	D						
	8	23/10/2018						0,014		52	0,5		C		21	B						
	8	22/11/2018						0,014		44	0,5		C		21	C						
	8	08/12/2018						0,014		47	0,5		C		20	B						
	8	21/05/2019						0,014		47	0,5		C		19	B						
	8	20/06/2019						0,014	38,6	45	0,5	0,8775	C		19	B	11	15.056	64.828	5	11	951
	8	25/07/2019						0,014		67	0,5		C		16	C						
	8	20/08/2019						0,017		45	0,5		C		16	B						
	8	17/09/2019						0,017		52	0,5		C		16	B						
6	9	21/05/2018	Main trafo	3	1122170	2010	26.706	Shandong			0,014		C		11	B						
	9	28/06/2018							41,0	85	0,5	0,8805	C		8	A	18	11.431	48.283	13	700	1.512
	9	24/07/2018								77	0,5		C		8	A						
	9	25/08/2018								82	0,5		C		7	A						
	9	25/09/2018								83	0,5		C		6	A						
	9	23/10/2018								78	0,5		C		8	A						
	9	22/11/2018								63	0,5		C		7	A						
	9	08/12/2018								83	0,5		C		7	A						
	23	21/05/2019		3011160192	2018	30.183	PAUWES TRAF			93	0,5		C		7	A						
	23	20/06/2019							40,6	83	0,5	0,8786	C		8	A	3	9.903	31.346	6	156	369
	23	25/07/2019								87	0,5		C		6	A						
	23	20/08/2019								78	0,5		C		6	A						
	23	17/09/2019								81	0,5		C		6	A						
7	10	21/05/2018	Trafo UAT	3	1035082	2010	4.749	Shandong			0,020		C		14	B						
	10	28/06/2018							37,5	79	0,5	0,8793	C		10	A	35	13.798	68.180	22	1.144	3.644
	10	24/07/2018								76	0,5		C		11	A						
	10	25/08/2018								78	0,5		C		8	A						
	10	25/09/2018								75	0,5		C		8	A						
	10	23/10/2018								69	0,5		C		8	A						
	10	22/11/2018								80	0,5		C		11	A						
	10	08/12/2018								61	0,5		C		8	A						
	22	21/05/2019		PX18-0082	2018	12.000	B & D			85	0,5		C		5	A						
	22	20/06/2019							37,0	89	0,5	0,8798	C		5	A	4	10.251	34.223	16	39	232
	22	25/07/2019								83	0,5		C		5	A						
	22	20/08/2019								78	0,5		C		4	A						
	22	17/09/2019								88	0,5		C		4	A						
8	11	21/05/2018	Trafo 1 ESP	3	007308428	2010	731	Zhejiang			0,022		C		27	D						
	11	28/06/2018							35,0	60	0,5	0,8154	C		10	B	19	15.552	64.448	3	57	1.391
	11	24/07/2018								53	0,5		C		9	B						
	11	25/08/2018								77	0,5		C		9	B						
	11	25/09/2018								64	0,5		C		10	B						
	11	23/10/2018								63	0,5		C		12	B						
	11	22/11/2018								53	0,5		C		9	B						
	11	08/12/2018								62	0,5		C		9	B						
	11	21/05/2019								85	0,5		C		9	B						
	11	20/06/2019							35,2	65	0,5	0,8212	C		9	B	11	19.448	64.974	6	15	1.064
	11	25/07/2019								51	0,5		C		9	B						
	11	20/08/2019								69	0,5		C		8	B						
	11	17/09/2019								67	0,5		C		8	B						



no	Test Cer.	Date Test	nama unit	m cennix											corr. sul	keterangan	MALAYSIAN LAB RECOMMENDATION	
								lpf (C)		dbpc	furan	metal in oil						
				C ₂ H ₆	C ₂ H ₄	C ₂ H ₂	TOT	25 ^o	100 ^o			Al	Fe	Cu				
Standar				ethane	ethylene	acethylene		ASTM D924		ASTM D2668	ASTM D5837	ASTM D3635			ASTM D1275B			
					< 65	<50	< 2	< 687	< 0.1	< 2.9	> .2	< 100	0,00	0,00	0,00		Non corrosive	
	8	28/06/2018			0	2	0	90	0,060	2,850	0,02	21	0,00	0,00	0,05	3 A	Suspec Corrosive	Perform OIL REGENERATION
	8	24/07/2018																Perform OIL REGENERATION
	8	25/08/2018																Periodic condition monitoring (change oil on beginning of August 2018)
	8	25/09/2018																Perform OIL PURIFICATION
	8	23/10/2018																Perform OIL PURIFIATION
	8	22/11/2018																Perform OIL PURIFIATION
	8	08/12/2018																Perform OIL PURIFIATION
	8	21/05/2019																Perform OIL PURIFIATION
	8	20/06/2019			0	0	0	27	0,010	1,120	0,00	0	0,00	0,00	0,02	3A	Suspec Corrosive	Periodic condition monitoring
	8	25/07/2019																Periodic condition monitoring
	8	20/08/2019																Periodic condition monitoring
	8	17/09/2019																Periodic condition monitoring
6	9	21/05/2018	Main trafo	3														Periodic condition monitoring
	9	28/06/2018			1	1	0	733	0,000	0,110	0,19	0	0,00	0,01	0,06	3 A	Suspec Corrosive	Add passivator
	9	24/07/2018																Periodic condition monitoring
	9	25/08/2018																Periodic condition monitoring
	9	25/09/2018																Periodic condition monitoring
	9	23/10/2018																Periodic condition monitoring
	9	22/11/2018																Periodic condition monitoring
	9	08/12/2018																Periodic condition monitoring
	23	21/05/2019																Periodic condition monitoring
	23	20/06/2019			0	0	0	165	0,000	0,000	0,00	0	0,00	0,00	0,02	3A	Non corrosive	Periodic condition monitoring
	23	25/07/2019																Periodic condition monitoring
	23	20/08/2019																Periodic condition monitoring
	23	17/09/2019																Periodic condition monitoring
7	10	21/05/2018	Trafo UAT	3														Periodic condition monitoring
	10	28/06/2018			5	7	1	1.214	0,000	0,140	0,21	0	0,00	0,01	0,11	3 A	Suspec Corrosive	Retest 6 months: DGA Add Passivator
	10	24/07/2018																Periodic condition monitoring
	10	25/08/2018																Periodic condition monitoring
	10	25/09/2018																Periodic condition monitoring
	10	23/10/2018																Periodic condition monitoring
	10	22/11/2018																Periodic condition monitoring
	10	08/12/2018																Periodic condition monitoring
	22	21/05/2019																Periodic condition monitoring
	22	20/06/2019			26	2	0	87	0,000	0,120	0,00	0	0,00	0,00	0,02			Periodic condition monitoring
	22	25/07/2019																Periodic condition monitoring
	22	20/08/2019																Periodic condition monitoring
	22	17/09/2019																Periodic condition monitoring
8	11	21/05/2018	Trafo 1 ESP	3														Perform OIL PURIFICATION
	11	28/06/2018			0	0	0	79	0,000	0,050	0,16	0	0,00	0,00	0,02	1 B	Non corrosive	Retest 12 months: Specific Gravity Add Passivator
	11	24/07/2018																Periodic condition monitoring
	11	25/08/2018																Periodic condition monitoring (Purifying on end of July 2018)
	11	25/09/2018																Periodic condition monitoring
	11	23/10/2018																Periodic condition monitoring
	11	22/11/2018																Periodic condition monitoring
	11	08/12/2018																Periodic condition monitoring
	11	21/05/2019																Periodic condition monitoring
	11	20/06/2019			0	0	0	32	0,000	0,060	0,16	0	0,00	0,00	0,02	2E	Non corrosive	Periodic condition monitoring
	11	25/07/2019																Periodic condition monitoring
	11	20/08/2019																Periodic condition monitoring
	11	17/09/2019																Periodic condition monitoring



no	Test Cer.	Date Test	nama unit		PAK SOETJAHJONO (TXM ADVISOR) RECOMMENDATION
Standar					
	8	28/06/2018			Jadi kami sarankan untuk ESP 1 dan 4 Unit 1, ESP 2 Unit 3 dan Ash Handling 1 segera dilakukan PURIFIKASI dengan temperatur sekitar 700 GANTI MINYAK pada trafo ESP 3 Unit 1 dan ESP 2 dan 3 Unit 2 For TEST 08 Desember 2018 Pada dasarnya kondisi masih sama dengan pada saat pengetesan bulan November 2018, <u>Untuk trafo ESP 3 Unit 2 kondisi BDV sudah sangat rendah sekali, harap menjadikan perhatian khusus</u> Kami sarankan untuk Untuk ESP 1 dan 4 Unit 1, ESP 2 Unit 3 dan Ash Handling 1 segera dilakukan PURIFIKASI dengan temperatur sekitar 70⁰ GANTI MINYAK pada trafo ESP 3 Unit 1 dan ESP 2 Unit 2 For TEST 22 November 2018 Meskipun hampir semua trafo dalam keadaan prima, beberapa sudah mulai mengalami penurunan kondisi. PURIFIKASI Untuk ESP 1 dan 4 Unit 1, ESP 2 Unit 3 dan Ash Handling 1 ditemukan telah mengalami trend penurunan fungsi BDV dan Water Content. Purifikasi sebaiknya dilakukan dengan temperatur sekitar 70⁰ agar mampu menghilangkan kandungan air dalam isolasi kertas. GANTI MINYAK Pada trafo ESP 3 Unit 1, ESP 2 dan 3 Unit 2 perlu dilakukan GANTI MINYAK, mengingat tingkat Acidity nya yang sudah tinggi.
	8	24/07/2018			
	8	25/08/2018			
	8	25/09/2018			
	8	23/10/2018			
	8	22/11/2018			
	8	08/12/2018			
	8	21/05/2019			
	8	20/06/2019			
	8	25/07/2019			
	8	20/08/2019			
	8	17/09/2019			
6	9	21/05/2018	Main trafo	3	
	9	28/06/2018			
	9	24/07/2018			
	9	25/08/2018			
	9	25/09/2018			
	9	23/10/2018			
	9	22/11/2018			
	9	08/12/2018			
	23	21/05/2019			
	23	20/06/2019			
	23	25/07/2019			
	23	20/08/2019			
	23	17/09/2019			
7	10	21/05/2018	Trafo UAT	3	
	10	28/06/2018			
	10	24/07/2018			
	10	25/08/2018			
	10	25/09/2018			
	10	23/10/2018			
	10	22/11/2018			
	10	08/12/2018			
	22	21/05/2019			
	22	20/06/2019			
	22	25/07/2019			
	22	20/08/2019			
	22	17/09/2019			
8	11	21/05/2018	Trafo 1 ESP	3	
	11	28/06/2018			
	11	24/07/2018			
	11	25/08/2018			
	11	25/09/2018			
	11	23/10/2018			
	11	22/11/2018			
	11	08/12/2018			
	11	21/05/2019			
	11	20/06/2019			
	11	25/07/2019			
	11	20/08/2019			
	11	17/09/2019			



no	Test Cer.	Date Test	nama unit	Serial number	thn opr	Jumlah minyak, liter	Buatan	hasil test laboratorium														
								acid	ift	diel.	color	spec. Graf.	visual	sedi.	moisture		dga ASTM D3612					
															ppm	grade	H ₂	O ₂	N ₂	CH ₄	CO	CO ₂
Standard yang dipakai								ASTM D974	ASTM D971	IEC 156	ASTM D1500	ASTM D4052	ASTM D1524	ASTM D1698	ASTM D1533	hydrogen	oksigen	nitrogen	methane	carbon monoksida	carbon dioksida	
		BATASAN OPERASI						< 0,06	> 32	> 30	< 3,5	> 0,84	C		< 20		< 100			< 120	< 350	< 2.500
9	12	21/05/2018	Trafo 2 ESP	3	007008428	2010	731 Zhejian	0,022		28	0,5		C		30	E						
	12	28/06/2018						0,025	30,2	34	0,5	0,8080	C		16	C	43	22.272	68.719	4	38	1.226
	12	24/07/2018						0,022		30	0,5		C		25	D						
	12	25/08/2018						0,022		67	0,5		C		11	C						
	12	25/09/2018						0,022		31	0,5		C		32	D						
	12	23/10/2018						0,025		54	0,5		C		13	B						
	12	22/11/2018						0,025		33	0,5		C		38	D						
	12	08/12/2018						0,025		30	0,5		C		32	C						
	12	21/05/2019						0,028		40	1,0		C		18	C						
	12	20/06/2019						0,028	31,3	41	1,0	0,8163	C		18	D	13	21.221	65.168	7	48	1.870
	12	25/07/2019						0,031		60	1,0		C		21	D						
	12	20/08/2019						0,028		48	1,0		C		19	D						
	12	17/09/2019						0,031		43	1,0		C		20	D						
10	13	21/05/2018	Trafo 3 ESP	3	007208428	2010	731 Zhejian	0,014		54	0,5		C		23	D						
	13	28/06/2018						0,017	38,4	43	0,5	0,8075	C		22	C	30	15.202	64.188	4	65	1.833
	13	24/07/2018						0,014		43	0,5		C		20	C						
	13	25/08/2018						0,014		76	0,5		C		11	C						
	13	25/09/2018						0,020		47	0,5		C		20	B						
	13	23/10/2018						0,014		49	0,5		C		15	A						
	13	22/11/2018						0,017		39	0,5		C		15	A						
	13	08/12/2018						0,014		34	0,5		C		18	A						
	13	21/05/2019						0,014		41	0,5		C		20	C						
	13	20/06/2019						0,020	38,5	36	0,5	0,8215	C		23	C	14	18.302	64.811	6	86	2.181
	13	25/07/2019						0,020		36	0,5		C		20	D						
	13	20/08/2019						0,017		32	0,5		C		19	C						
	13	17/09/2019						0,020		43	0,5		C		20	C						
11	14	21/05/2018	Trafo 4 ESP	3	007108428	2010	731 Zhejian	0,028		37	1,0		C		21	D						
	14	28/06/2018						0,025	30,5	71	1,0	0,8442	C		11	A	20	14.690	67.822	2	22	683
	14	24/07/2018						0,022		42	1,0		C		11	C						
	14	25/08/2018						0,025		66	1,5		C		11	B						
	14	25/09/2018						0,022		51	1,5		C		11	B						
	14	23/10/2018						0,022		56	1,5		C		12	B						
	14	22/11/2018						0,022		44	1,5		C		11	B						
	14	08/12/2018						0,022		49	1,0		C		13	C						
	14	21/05/2019						0,022		58	1,0		C		11	C						
	14	20/06/2019						0,022	30,3	51	1,0	0,8451	C		12	C	19	16.312	66.417	4	37	732
	14	25/07/2019						0,020		75	1,0	0,8451	C		11	C						
	14	20/08/2019						0,022		49	1,0	0,8451	C		11	B						
	14	17/09/2019						0,025		51	1,5	0,8451	C		12	C						
12	15	21/05/2018	Ash Handling		10820108	2011	1.023 Wolong	0,022		33	1,0		C		26	C						
	15	28/06/2018						0,025	37,5	42	1,0	0,8804	C		24	C	53	10.939	69.394	20	557	5.425
	15	24/07/2018						0,022		39	1,0		C		20	B						
	15	25/08/2018						0,025		60	1,5		C		16	B						
	15	25/09/2018						0,025		43	1,5		C		17	A						
	15	23/10/2018						0,022		28	1,5		C		19	C						
	15	22/11/2018						0,022		24	1,5		C		28	B						
	15	08/12/2018						0,022		20	1,5		C		28	B						



no	Test Cer.	Date Test	nama unit	m cennix											corr. sul	keterangan	MALAYSIAN LAB RECOMMENDATION	
								lpf (C)		dbpc	furan	metal in oil						
				C ₂ H ₆	C ₂ H ₄	C ₂ H ₂	TOT	25°	100°			Al	Fe	Cu				
Standa				ethane	ethylene	acethylene		ASTM D924		ASTM D2668	ASTM D5837	ASTM D3635			ASTM D1275B			
					< 65	<50	< 2	< 687	< 0.1	< 2.9	> .2	< 100	0,00	0,00	0,00		Non corrosive	
9	12	21/05/2018	Trafo 2 ESP	3														Perform OIL PURIFICATION
	12	28/06/2018			0	0	0	85	0,000	0,040	0,19	0	0,00	0,00	0,02	3 A	Suspec Corrosive	Retest 12 months: Specific Gravity Add Passivator
	12	24/07/2018																Perform OIL REGENERATION
	12	25/08/2018																Periodic condition monitoring (Purifying on end of July 2018)
	12	25/09/2018																Perform OIL REGENERATION
	12	23/10/2018																Periodic condition monitoring
	12	22/11/2018																Perform for Purification
	12	08/12/2018																Perform for Purification
	12	21/05/2019																Periodic condition monitoring
	12	20/06/2019			0	0	0	68	0,000	0,010	0,19	180	0,00	0,00	0,02	3A	Non corrosive	Periodic condition monitoring
	12	25/07/2019																Preparing for Purification
	12	20/08/2019																Preparing for Purification
	12	17/09/2019																Preparing for Purification
10	13	21/05/2018	Trafo 3 ESP	3														Perform OIL PURIFICATION
	13	28/06/2018			0	0	0	99	0,000	0,010	0,20	4	0,00	0,00	0,02	2 E	Non corrosive	Retest 12 months: Specific Gravity Retest 6 months: Dielectric and Water Content Add Passivator
	13	24/07/2018																Perform OIL PURIFICATION
	13	25/08/2018																Periodic condition monitoring (Purifying on end of July 2018)
	13	25/09/2018																Perform OIL PURIFICATION
	13	23/10/2018																Periodic condition monitoring
	13	22/11/2018																Periodic condition monitoring
	13	08/12/2018																Periodic condition monitoring
	13	21/05/2019																ReTest in 6 months : Water Content and BDV - Prepare for PURIFICATION
	13	20/06/2019			0	0	0	106	0,000	0,070	0,19	0	0,00	0,00	0,02	2E	Non corrosive	ReTest in 6 months : Water Content and BDV - Prepare for PURIFICATION
	13	25/07/2019																Preparing for Purification
	13	20/08/2019																Periodic condition monitoring
	13	17/09/2019																Periodic condition monitoring
11	14	21/05/2018	Trafo 4 ESP	3														Retest 6 months: Dielectric and Water Content
	14	28/06/2018			0	0	0	44	0,000	0,550	0,00	0	0,00	0,03	0,02	1 B	Non corrosive	Add inhibitor 2,6-DBPC and PASSIVATOR
	14	24/07/2018																Periodic condition monitoring
	14	25/08/2018																Periodic condition monitoring (Purifying on end of July 2018)
	14	25/09/2018																Periodic condition monitoring
	14	23/10/2018																Periodic condition monitoring
	14	22/11/2018																Periodic condition monitoring
	14	08/12/2018																Periodic condition monitoring
	14	21/05/2019																Periodic condition monitoring
	14	20/06/2019			0	0	0	60	0,000	0,490	0,00	0	0,00	0,03	0,01	1B	Non corrosive	Periodic condition monitoring
	14	25/07/2019																Periodic condition monitoring
	14	20/08/2019																Periodic condition monitoring
	14	17/09/2019																Periodic condition monitoring
12	15	21/05/2018	Ash Handling															Periodic condition monitoring
	15	28/06/2018			9	8	0	647	0,000	0,460	0,22	0	0,00	0,01	0,04	1 B	Non corrosive	Add passivator
	15	24/07/2018																Periodic condition monitoring
	15	25/08/2018																Periodic condition monitoring
	15	25/09/2018																Periodic condition monitoring
	15	23/10/2018																Periodic condition monitoring
	15	22/11/2018																Monitoring : Water Content and BDV - Prepare for PURIFICATION
	15	08/12/2018																Retest in 6 months : Water Content and BDV - Prepare for PURIFICATION



no	Test Cer.	Date Test	nama unit	PAK SOETJAHJONO (TXM ADVISOR) RECOMMENDATION	
Standar					
9	12	21/05/2018	Trafo 2 ESP	3	
	12	28/06/2018			
	12	24/07/2018			
	12	25/08/2018			
	12	25/09/2018			
	12	23/10/2018			
	12	22/11/2018			
	12	08/12/2018			
	12	21/05/2019			
	12	20/06/2019			
	12	25/07/2019			
	12	20/08/2019			
	12	17/09/2019			
10	13	21/05/2018	Trafo 3 ESP	3	
	13	28/06/2018			
	13	24/07/2018			
	13	25/08/2018			
	13	25/09/2018			
	13	23/10/2018			
	13	22/11/2018			
	13	08/12/2018			
	13	21/05/2019			
	13	20/06/2019			
	13	25/07/2019			
	13	20/08/2019			
	13	17/09/2019			
11	14	21/05/2018	Trafo 4 ESP	3	
	14	28/06/2018			
	14	24/07/2018			
	14	25/08/2018			
	14	25/09/2018			
	14	23/10/2018			
	14	22/11/2018			
	14	08/12/2018			
	14	21/05/2019			
	14	20/06/2019			
	14	25/07/2019			
	14	20/08/2019			
	14	17/09/2019			
12	15	21/05/2018	Ash Handling		
	15	28/06/2018			
	15	24/07/2018			
	15	25/08/2018			
	15	25/09/2018			
	15	23/10/2018			
	15	22/11/2018			
	15	08/12/2018			




no	Test Cer.	Date Test	nama unit	Serial number	thn opr	Jumlah minyak, liter	Buatan	hasil test laboratorium														
								acid	ift	diel.	color	spec. Graf.	visual	sedi.	moisture		dga ASTM D3612					
															ppm	grade	H ₂	O ₂	N ₂	CH ₄	CO	CO ₂
Standard yang dipakai								ASTM D974	ASTM D971	IEC 156	ASTM D1500	ASTM D4052	ASTM D1524	ASTM D1698	ASTM D1533	hydrogen	oksigen	nitrogen	methane	carbon monoksida	carbon dioksida	
		BATASAN OPERASI						< 0,06	> 32	> 30	< 3,5	> 0,84	C		< 20		< 100			< 120	< 350	< 2.500
	15	21/05/2019						0,022		28	1,5		C		29	C						
	15	20/06/2019						0,022	36,6	27	1,5	0,8890	C		29	C	53	14.032	65.585	13	487	5.360
	15	25/07/2019						0,025		49	1,0		C		21	B						
	15	20/08/2019						0,022		30	1,0		C		20	B						
	15	17/09/2019						0,025		52	1,5		C		21	B						
13	16	21/05/2018	Ash Handling	10820107	2011	1.023	Wolong	0,020		24	1,5		C		32	D						
	16	28/06/2018						0,022	35,0	50	1,5	0,8811	C		16	B	32	22.904	67.139	4	249	3.112
	16	24/07/2018						0,020		27	1,5		C		30	C						
	16	25/08/2018						0,022		45	1,5		C		16	B						
	16	25/09/2018						0,022		36	1,5		C		19	B						
	16	23/10/2018						0,022		36	1,5		C		23	B						
	16	22/11/2018						0,022		30	1,5		C		25	B						
	16	08/12/2018						0,022		32	1,5		C		24	B						
	16	21/05/2019						0,022		32	1,5		C		23	B						
	16	20/06/2019						0,022	36,8	37	1,5	0,8889	C		24	B	39	11.205	66.397	21	439	5.998
	16	25/07/2019						0,025		42	1,5		C		27	B						
	16	20/08/2019						0,025		36	1,5		C		29	B						
	16	17/09/2019						0,028		37	1,5		C		26	C						
14	17	21/05/2018	Trafo 1 ESP	2	10037	1010	731	0,025		24	1,0		C		32	E						
	17	28/06/2018						0,025	32,9	77	1,0	0,8693	C		11	B	93	17.225	43.231	5	57	775
	17	24/07/2018						0,028		69	1,0		C		11	B						
	17	25/08/2018						0,031		74	1,5		C		12	B						
	17	25/09/2018						0,028		74	1,5		C		10	B						
	17	23/10/2018						0,028		54	1,5		C		11	B						
	17	22/11/2018						0,028		54	1,5		C		10	B						
	17	08/12/2018						0,028		46	1,5		C		10	B						
	17	21/05/2019						0,031		67	1,5		C		12	B						
	17	20/06/2019						0,031	31,0	62	1,0	0,8776	C		13	C	62	18.560	46.166	5	50	839
	17	25/07/2019						0,031		64	1,0		C		11	B						
	17	20/08/2019						0,034		63	1,0		C		11	B						
		17						17/09/2019						0,034		19	1,0		C		62	E
15	18	21/05/2018	Trafo 2 ESP	2	10036	1010	731	0,053			1,0		C		16	C						
	18	28/06/2018						0,056	31,3	66	1,0	0,8573	C		13	C	8	22.714	64.906	5	67	879
	18	24/07/2018						0,059		79	1,5		C		8	A						
	18	25/08/2018						0,062		67	1,5		C		10	B						
	18	25/09/2018						0,056		51	1,5		C		9	B						
	18	23/10/2018						0,062		67	1,5		C		13	B						
	18	22/11/2018						0,062		61	1,5		C		8	A						
	18	08/12/2018						0,062		59	1,5		C		8	A						
	18	21/05/2019						0,065		77	1,0		C		11	B						
	18	20/06/2019						0,065	29,7	76	1,0	0,8655	C		12	B	5	29.439	65.338	5	25	977
	18	25/07/2019						0,062		47	1,5		C		11	B						
	18	20/08/2019						0,065		41	1,5		C		12	B						
	18	17/09/2019						0,067		59	1,5		C		11	B						
16	19	21/05/2018	Trafo 3 ESP	2	10033	1010	731	0,059			1,5		C		18	D						
	19	28/06/2018						0,062	26,3	78	1,5	0,8602	C		14	C	14	17.627	48.672	4	47	935
	19	24/07/2018						0,070		67	1,5		C		12	B						
	19	25/08/2018						0,067		73	1,5		C		13	C						
	19	25/09/2018						0,067		59	1,5		C		12	B						
	19	23/10/2018						0,070		86	1,5		C		13	B						
	19	22/11/2018						0,070		13	1,5		C		84	E						
	19	08/12/2018						0,070		8	1,5		C		84	E						



no	Test Cer.	Date Test	nama unit	m cennix											keterangan	MALAYSIAN LAB RECOMMENDATION		
								lpf (C)		dbpc	furan	metal in oil					corr. sul	
				C ₂ H ₆	C ₂ H ₄	C ₂ H ₂	TOT	25°	100°			Al	Fe	Cu				
Standa				ethane	ethylene	acethylene		ASTM D924		ASTM D2668	ASTM D5837	ASTM D3635			ASTM D1275B			
					< 65	<50	< 2	< 687	< 0.1	< 2.9	> .2	< 100	0,00	0,00	0,00		Non corrosive	
	15	21/05/2019																Perform for PURIFICATION
	15	20/06/2019			0	11	0	564	0,000	0,360	0,21	0	0,00	0,00	0,02	2e	Non corrosive	Perform for PURIFICATION
	15	25/07/2019																Periodic condition monitoring
	15	20/08/2019																Periodic condition monitoring
	15	17/09/2019																Periodic condition monitoring
13	16	21/05/2018	Ash Handling															Perform OIL PURIFICATION
	16	28/06/2018			0	5	0	290	0,000	0,490	0,20	0	0,00	0,00	0,02	3 A	Suspec Corrosive	Retest 6 months: DGA Add Passivator
	16	24/07/2018																Perform OIL PURIFICATION
	16	25/08/2018																Periodic condition monitoring (Purifying on end of July 2018)
	16	25/09/2018																Periodic condition monitoring
	16	23/10/2018																Periodic condition monitoring
	16	22/11/2018																Periodic condition monitoring
	16	08/12/2018																Periodic condition monitoring
	16	21/05/2019																Periodic condition monitoring
	16	20/06/2019			11	9	0	519	0,000	0,680	0,20	0	0,01	0,00	0,02	3A	Non corrosive	Periodic condition monitoring
	16	25/07/2019																Periodic condition monitoring
	16	20/08/2019																Periodic condition monitoring
	16	17/09/2019																Periodic condition monitoring
14	17	21/05/2018	Trafo 1 ESP	2														OIL PURIFICATION
	17	28/06/2018			0	2	0	157	0,030	3,420	0,00	0	0,00	0,06	0,03	2 C	Non corrosive	Add inhibitor 2,6-DBPC and PASSIVATOR
	17	24/07/2018																Periodic condition monitoring
	17	25/08/2018																Periodic condition monitoring
	17	25/09/2018																Periodic condition monitoring
	17	23/10/2018																Periodic condition monitoring
	17	22/11/2018																Periodic condition monitoring
	17	08/12/2018																Periodic condition monitoring
	17	21/05/2019																Periodic condition monitoring
	17	20/06/2019			0	0	0	117	0,000	0,720	0,00	0	0,00	0,00	0,02	3A	Non corrosive	Monitoring : Acidity, IFT and LPF
	17	25/07/2019																Periodic condition monitoring
	17	20/08/2019																Periodic condition monitoring
	17	17/09/2019																Perform OIL PURIFICATION
15	18	21/05/2018	Trafo 2 ESP	2														Retest 6 months: Acidity and IFT
	18	28/06/2018			0	0	0	80	0,000	0,680	0,00	42	0,00	0,00	0,02	3 A	Suspec Corrosive	Add inhibitor 2,6-DBPC and PASSIVATOR
	18	24/07/2018																Periodic condition monitoring
	18	25/08/2018																Periodic condition monitoring
	18	25/09/2018																Perform OIL REGENERATION
	18	23/10/2018																Perform OIL REGENERATION
	18	22/11/2018																Perform OIL REGENERATION
	18	08/12/2018																Perform OIL REGENERATION
	18	21/05/2019																Perform OIL REGENERATION
	18	20/06/2019			0	0	0	35	0,000	0,450	0,00	0	0,00	0,00	0,02	3A	Non corrosive	Perform OIL REGENERATION
	18	25/07/2019																Perform OIL REGENERATION
	18	20/08/2019																Perform OIL REGENERATION
	18	17/09/2019																Perform OIL REGENERATION
16	19	21/05/2018	Trafo 3 ESP	2														Retest 6 months: Acidity and IFT
	19	28/06/2018			0	0	0	65	0,000	0,570	0,00	0	0,00	0,00	0,02	3 A	Suspec Corrosive	Perform OIL REGENERATION
	19	24/07/2018																Perform OIL REGENERATION
	19	25/08/2018																Perform OIL REGENERATION
	19	25/09/2018																Perform OIL REGENERATION
	19	23/10/2018																Perform OIL REGENERATION
	19	22/11/2018																Perform OIL REGENERATION
	19	08/12/2018																Perform OIL REGENERATION



no	Test Cer.	Date Test	nama unit	PAK SOETJAHJONO (TXM ADVISOR) RECOMMENDATION	
Standar					
	15	21/05/2019			
	15	20/06/2019			
	15	25/07/2019			
	15	20/08/2019			
	15	17/09/2019			
13	16	21/05/2018	Ash Handling		
	16	28/06/2018			
	16	24/07/2018			
	16	25/08/2018			
	16	25/09/2018			
	16	23/10/2018			
	16	22/11/2018			
	16	08/12/2018			
	16	21/05/2019			
	16	20/06/2019			
	16	25/07/2019			
	16	20/08/2019			
	16	17/09/2019			
14	17	21/05/2018	Trafo 1 ESP	2	
	17	28/06/2018			
	17	24/07/2018			
	17	25/08/2018			
	17	25/09/2018			
	17	23/10/2018			
	17	22/11/2018			
	17	08/12/2018			
	17	21/05/2019			
	17	20/06/2019			
	17	25/07/2019			
	17	20/08/2019			
	17	17/09/2019			
15	18	21/05/2018	Trafo 2 ESP	2	
	18	28/06/2018			
	18	24/07/2018			
	18	25/08/2018			
	18	25/09/2018			
	18	23/10/2018			
	18	22/11/2018			
	18	08/12/2018			
	18	21/05/2019			
	18	20/06/2019			
	18	25/07/2019			
	18	20/08/2019			
	18	17/09/2019			
16	19	21/05/2018	Trafo 3 ESP	2	
	19	28/06/2018			
	19	24/07/2018			
	19	25/08/2018			
	19	25/09/2018			
	19	23/10/2018			
	19	22/11/2018			
	19	08/12/2018			





no	Test Cer.	Date Test	nama unit		m cennix											corr. sul	keterangan	MALAYSIAN LAB RECOMMENDATION
									lpf (C)		dbpc	furan	metal in oil					
					C ₂ H ₆	C ₂ H ₄	C ₂ H ₂	TOT	25 ^o	100 ^o			Al	Fe	Cu			
Standards					ethane	ethylene	acetylene		ASTM D924		ASTM D2668	ASTM D5837	ASTM D3635			ASTM D1275B		
					< 65	<50	< 2	< 687	< 0.1	< 2.9	> .2	< 100	0,00	0,00	0,00		Non corrosive	
	19	21/05/2019																Perform OIL REGENERATION
	19	20/06/2019			0	0	0	79	0,010	0,790	0,00	0	0,00	0,00	0,02	3A	Non corrosive	Perform OIL REGENERATION
	19	25/07/2019																Perform OIL REGENERATION
	19	20/08/2019																Perform OIL REGENERATION
	19	17/09/2019																Perform OIL REGENERATION
17	20	21/05/2018	Trafo 4 ESP	2														Periodic condition monitoring
	20	28/06/2018			0	0	0	112	0,000	1,620	0,01	0	0,00	0,00	0,03	2 C	Non corrosive	Add inhibitor 2,6-DBPC and PASSIVATOR
	20	24/07/2018																Periodic condition monitoring
	20	25/08/2018																Periodic condition monitoring
	20	25/09/2018																Periodic condition monitoring
	20	23/10/2018																Periodic condition monitoring
	20	22/11/2018																Periodic condition monitoring
	20	08/12/2018																Periodic condition monitoring
	20	21/05/2019																Periodic condition monitoring
	20	20/06/2019			0	0	0	72	0,020	1,150	0,01	7	0,00	0,00	0,02	2C	Non corrosive	Monitoring : Acidity, IFT and LPF
	20	25/07/2019																Periodic condition monitoring
	20	20/08/2019																Periodic condition monitoring
	20	17/09/2019																Periodic condition monitoring
18	21	21/05/2018	Main Trafo	2														Periodic condition monitoring
	21	28/06/2018			0	2	0	224	0,000	0,410	0,22	113	0,00	0,00	0,03	1 B	Non corrosive	Retest 6 months: Furan and DGA Add Passivator
	21	24/07/2018																Periodic Condition monitoring
	21	25/08/2018																Periodic condition monitoring
	21	25/09/2018																Periodic condition monitoring
	21	23/10/2018																Periodic condition monitoring
	21	22/11/2018																Periodic condition monitoring
	21	08/12/2018																Periodic condition monitoring
	21	21/05/2019																Periodic condition monitoring
	21	20/06/2019			0	2	0	127	0,010	0,730	0,22	0	0,00	0,00	0,02	2E	Non corrosive	Periodic condition monitoring
	21	25/07/2019																Periodic condition monitoring
	21	20/08/2019																Periodic condition monitoring
	21	17/09/2019																Periodic condition monitoring



no	Test Cer.	Date Test	nama unit		PAK SOETJAHJONO (TXM ADVISOR) RECOMMENDATION
Standar					
	19	21/05/2019			
	19	20/06/2019			
	19	25/07/2019			
	19	20/08/2019			
	19	17/09/2019			
17	20	21/05/2018	Trafo 4 ESP	2	
	20	28/06/2018			
	20	24/07/2018			
	20	25/08/2018			
	20	25/09/2018			
	20	23/10/2018			
	20	22/11/2018			
	20	08/12/2018			
	20	21/05/2019			
	20	20/06/2019			
	20	25/07/2019			
	20	20/08/2019			
	20	17/09/2019			
18	21	21/05/2018	Main Trafo	2	
	21	28/06/2018			
	21	24/07/2018			
	21	25/08/2018			
	21	25/09/2018			
	21	23/10/2018			
	21	22/11/2018			
	21	08/12/2018			
	21	21/05/2019			
	21	20/06/2019			
	21	25/07/2019			
	21	20/08/2019			
	21	17/09/2019			