



Europe - Plate

Inspection Certificate (A02)

EN 10204:2004/3.1

Page 1 of 4
Date of creation: (Z02) 19.01.2026
Certificate No.: (A03) 229495/1

Our order No.: (A08) 5175342 Your order No.: (A07) A126172 Order registration date: 07.10.2025 Date of dispatch: 19.01.2026 B

Material requirements and customer information

Product: (B01) Plate	Steel standard and grade: (B02) EN10025-2:2019 S355J2+N	Surface tolerance: EN 10163-2 A3
Delivery condition: (B04) Furnace normalized (N)		Length tolerance: EN 10029 Table 3
Customer name and address (A06) 2173 TERRAMET-STÅLCENTER AB GRANARPSVÄGEN 5 556 52 JÖNKÖPING Sweden	Certificate address 2173001 CERTIFIKAT@TSAB.COM Sweden CERTIFIKAT@TSAB.COM	Width tolerance: EN 10029 Table 2 Thickness tolerance: EN 10029 Class A Flatness tolerance: EN 10029 Table 4 Class N

Supplementary information: (C04)
Fully Killed and Fine Grain
Plates <= 25mm are Normalised at 900°C for 3 minutes.
Plates > 25mm are Normalised at 900°C for 5 minutes.

Visual examination and dimensional checking: Satisfactory. The results of tests performed are in compliance with the requirements. (Z01)

Details of supplied materials dimensions, weights and pieces

Heat/Slab (B07)	Plate No. (B06)	Item	Thickness mm (B09)	Width mm (B10)	Length mm (B11)	Pieces (B08)	Gross kg (B12)	Hard stamp	Stamp location	Customer remark (B99)
68923E4	4403N	7	50.0	2500	8000	2	15 700	S355J2+N	Head	TSAB-A126172
						2	15 700			



Europe - Plate

Inspection Certificate (A02)

EN 10204:2004/3.1

Page 2 of 4
Date of creation: (Z02) 19.01.2026
Certificate No.: (A03) 229495/1

Our order No.: (A08) 5175342 Your order No.: (A07) A126172 Order registration date: 07.10.2025 Date of dispatch: 19.01.2026 B

Chemical composition (heat analysis)															all results in %					
Heat No. (B07)		C	Mn	Si	P	S	Cr	Cu	Ni	Mo	Al	Nb	V	Ti		N	B			
Set values:	min.			0.15							0.003									
	max.	0.22	1.60	0.25	0.025	0.025	0.290	0.400	0.300	0.080	0.100	0.060	0.100	0.050		0.0120	0.0008			
68923		0.16	1.49	0.21	0.014	0.002	0.029	0.022	0.011	0.001	0.036	0.041	0.001	0.002		0.0035	0.0002			
Heat No. (B07)		CEV																	Remark (C70)	
Set values:	min.																			
	max.	0.47																		
68923		0.42																	1 3 4 5 6	
Supplementary information (C99)																				
CEV = C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15																				
1 = Basic Oxygen Steel, 2 = Electric Arc Furnace, 3 = Ladle Refined, 4 = Calcium Treated, 5 = Vacuum Degassed, 6 = Continuous Cast, 7 = Ingot																				



Europe - Plate

Inspection Certificate

EN 10204:2004/3.1

Page 3 of 4
Date of creation: (Z02) 19.01.2026
Certificate No.: (A03) 229495/1

Our order No.: (A08) 5175342 Your order No.: (A07) A126172 Order registration date: 07.10.2025 Date of dispatch: 19.01.2026 B

Tensile testing Tensile tests were performed in accordance with EN 10002/ISO 6892-1 with results as stated below:

Heat/slab (B07)	Plate ID (B06)	Thickness mm	Shape (C10)	Loc. (C01)	Dir. (C02)	Yield MPa (C11)	Yield type	UTS Rm MPa (C12)	Elong. type	Elongation % (C13)	Yield/UTS
68923E4	4403N-1-1	50.0	R	H	T	377	REH	522	A5	31	0.72
68923E4	4403N-1-2	50.0	R	H	T	377	REH	522	A5	31	0.72

Supplementary Information (C99)
Loc.: (C01) H = head, T = tail
Dir.: (C02) T = transversal, L = longitudinal
Shape: (C10) Ø = round, R = rectangular
Original gauge length: 200 mm

Impact testing Impact tests were performed in accordance with EN 10045/ISO 148-1 with results as stated below:

Heat/slab (B07)	Plate ID (B06)	Position (C01)	Notch (C40)	Shape (C41)	Loc. (C01)	Dir. (C02)	Temp. °C (C03)	SV J (C42)	SV J (C42)	SV J (C42)	AV J (C43)
68923E4	4403N-1-1	1	CV	10x10	H	L	-20	258	238	210	235
68923E4	4403N-1-2	1	CV	10x10	H	L	-20	258	238	210	235

Supplementary Information (C99)
Position: (C01) 1 = surface, 2 = middle, 3 = 1/3 of thickness, 4 = 1/4 of thickness
Notch: (C40) CU = Charpy U-notch, CV = Charpy V-notch, CVA = Charpy V-notch (ASTM)
Loc.: (C01) H = head, T = tail
Dir.: (C02) T = transversal, L = longitudinal





Europe - Plate

Inspection Certificate ^(A02)

EN 10204:2004/3.1

Page 4 of 4

Date of creation: ^(Z02) 19.01.2026

Certificate No.: ^(A03) 229495/1

Our order No.: ^(A08) 5175342

Your order No.: ^(A07) A126172

Order registration date: 07.10.2025

Date of dispatch: 19.01.2026 B

We hereby certify that the material has been made and tested in accordance with the mentioned specification(s).

Certified according to Construction Products Regulations (305/2011/EU) by TÜV NORD Systems GmbH (Notified Body Reg. No. 0045).

Certified according to The Construction Products (Amendment etc.)(EU Exit) Regulations 2019 (S.I. 2019/465) by TÜV UK (Notified Body Reg. No. 0879)

For Declaration of Performance please see www.DanSteel.dk and DoP number 009CPR2013-07-01.



TÜV UK 0879-CPR-10025-1-DE00011
Intended use: Welded, bolted and riveted structures.



TÜV-NORD 0045-CPR-0554
Year of initial inspection: 2005
Intended use: Welded, bolted and riveted structures.

Our products are Cobalt, Gold, Mercury free and are free of radioactive substances and do not exceed the clearing limit value of 100 Bg/kg, which guarantees the compliance with limit values given in the Radiation Protection Ordinance (StrlSchV) for the unrestricted clearance of solid material (StrlSchV Annex III, Section 5) for ferrous nuclides.

Manufactured in Denmark



DanSteel ^(A01)

Havnevej 33,
3300 Frederiksværk - Denmark



^(A04)

Inspection representative NLMK DanSteel A/S ^(A05)

Zibrandt Greisen

Information description

acc. to EN 10168

A Commercial transactions and parties involved

A01 Manufacturer's works
A02 Type of inspection document
A03 Document number
A04 Manufacturer's mark
A05 Originator of the inspection document
A06 Customer consignee
A07 Purchaser's order number and, where applicable, item number
A08 Manufacturer's works order number
A09 Customer article number
A10 to A99 Supplementary information

B Description of Products

B01 Product
B02 Steel designation
B03 Any supplementary requirements
B04 Product delivery condition
B05 Reference (heat) treatment of samples
B06 Marking of the product
B07 Identification of the product
B08 Number of pieces
B09 to B11 Product dimensions
B12 Theoretical mass
B13 Actual mass
B14 to B99 Supplementary information

C Inspection

C00 Identification of the sample
C01 Location of the sample
C02 Direction of the test pieces
C03 Test temperature
C04 to C09 Supplementary information

C10 Shape of the test piece
C11 Yield or proof strength
C12 Tensile strength
C13 Elongation after fracture
C14 to C29 Supplementary information
C30 Method of test
C31 Individual values
C32 Mean value
C33 to C39 Supplementary information
C40 Type of test piece
C41 Width of test piece
C42 Individual values
C43 Mean value
C44 to C49 Supplementary information
C50 to C69 Supplementary information
C70 Steelmaking process
C71 to C92 Chemical composition
C93 to C99 Supplementary information

D Other tests

D01 Marking and identification, surface appearance, shape and dimensional properties
D02 to D50 Non-destructive tests
D51 to D99 Supplementary information

Z Validation

Z01 Statement of compliance
Z02 Date of issue and validation
Z03 Stamp of the inspection representative
Z04 CE marking
Z05 to Z99 Supplementary information