



INSPECTION CERTIFICATE

A02 EN 10 204-3.1 (2004)

A03 A 29438 -002
16.04.2025

Purchaser A06
STÅLGROSS I SVERIGE AB
TUVULLSVÄGEN 5
554 75 JÖNKÖPING SWEDEN

Order Confirmation A08
29438

Consignee A06
NORDISK BETINDUSTRI
INDUSTRIVÄGEN
795 22 RÄTTVIK SWEDEN

Date Z02
22.04.2025
Mark of the Manufacturer A04



Certificate A02
31

Quality Marking B06
STRENX 700 E

Stamp of Inspector Z03

Stamp of Surveyor

Mxx

Other Stamps

Delivery type
REST DELIVERY

Cast No. Plate No. B07
X X X X X X X X X X X X X

Technical terms of Delivery and/or Official Regulations

Product B01
HEAVY PLATES
Grade B02
STRENX 700 E
Quality Specifications B02
QUENCHED AND TEMPERED STEEL

Tolerances
STRENX, EN 10029:2010 CLASS A

A07 Item	B09-B11 Dimensions mm	A09 Marke	B08 Pcs	B12/B13 Weight kg	B07 Cast plate No	B07 SP No	D02 UT	D03 MT	B03 Safety mark
-------------	--------------------------	--------------	------------	----------------------	----------------------	--------------	-----------	-----------	--------------------

QUENCHED AND TEMPERED STEEL PLATES
IN BUNDLES
MEETS REQUIREMENTS OF EN10025-6 S690QL
SURFACE CONDITION EN 10 163-2:2005 CLASS A3
001 16.00 X 1500 X 3000

6 3390 70703 021 021

*** 6 3390

Raahe Steel Works A01
Testing and Inspection A05

Z01
We hereby certify that the material described above has been tested and complies with the terms of the order confirmation.

Minna Valkama

MINNA VALKAMA
Authorized inspection representative Z02

Company name: SSAB Europe Oy
Registered Office: HÄMEENLINNA

Address: PL 93, P.O Box 93
FIN-92101 RAAHE, FINLAND

Telephone: 020 5911
+358 20 5911

Business ID: 2389445-7



TEST REPORT

A03 A 29438 -002
16.04.2025

Purchaser A06
STÅLGROSS I SVERIGE AB
TUVULLSVÄGEN 5
554 75 JÖNKÖPING SWEDEN
Order No. A07
22154

Order Confirmation A08
29438

Consignee A06
NORDISK BETINDUSTRI
INDUSTRIVÄGEN
795 22 RÄTTVIK SWEDEN
Shipping mark
22154

Date
22.04.2025
Mark of the Manufacturer A04
AMH



Grade B02
STRENX 700 E
Quality Specifications B02

Additional requirements B03

Oxygen steel, continuous casting
Fully killed, Fine grain practiced C70

QUENCHED AND TEMPERED STEEL

A07 Item	B07 Cast. test No	B04 Cond	Tensile test C11												C50 Bend test		C04-C09 Nb	B05 Tempering °C
			C00 K2	C03 °C	C11 MPa RP02	C11 MPa RT05	C11 MPa REL	C11 MPa REH	C12 1	RM 2	MPa 3	C13 % 50	A % 80	200	RE/RM	RM * A5	RAZ % 1 2 3	Average

001 70703 021 QT 51 739 799 19

K2: 51=BOTTOM,TRANSV.

QT=QUENCHED + TEMPERED

A07 Item	B07 Cast. test No	Impact test								FA %				LE (mm)		*Specimen Unbroken		C53 Special Tests					C04-C09 Nb	B05 Tempering °C	
		C00 K3	C03 °C	C42 1	C42 2	C42 3	C43 Average	C41 W (mm)	C51 1	C51 2	C51 3	C51 Average	C52 1	C52 2	C52 3	C52 Average	C00 K4	C03 °C	C53 1	C53 2	C53 Average				

FA =Shear fracture appearance

LE = Lateral Expansion

001 70703 021 151 -040 183 224 159 189
152 -040 213 239 206 219

K3: 151=CH-V/ISO-V(J),10X10,BOTTOM,LONGIT,KV600 152=CH-V/ISO-V(J),10X10,BOTTOM,TRANSV,KV600

Raahe Steel Works A01

Testing and Inspection A05

MINNA VALKAMA

Authorized inspection representative Z02

Company name: SSAB Europe Oy
Registered Office: HAMEENLINNA

Address: PL 93, P.O Box 93
FIN-92101 RAAHE, FINLAND

Telephone: 020 5911
+358 20 5911

Business ID: 2389445-7

Z01
We hereby certify that the material described above has been tested and complies with the terms of the order confirmation.

