



INSPECTION CERTIFICATE

A02

EN 10 204-3.1 (2004)

A03

A 14983 -002
02.02.2026

Purchaser A06
STÅLGROSS I SVERIGE AB
TUVULLSVÄGEN 5
554 75 JÖNKÖPING SWEDEN
Order No. A07
23587

Order Confirmation A08
14983

Consignee A06
NORDISK BETINDUSTRI
INDUSTRIVÄGEN
795 22 RÄTTVIK SWEDEN
Shipping mark
23587

Date Z02
03.02.2026
Mark of the Manufacturer A04



Certificate A02
31

Quality Marking B06
STRENX 700 E

Stamp of Inspector Z03

Stamp of Surveyor

Mxx

Other Stamps

Delivery type
REST DELIVERY

Cast No. Plate No. B07
X X X X X X X X X X X X

Technical terms of Delivery and/or Official Regulations

Product B01
HEAVY PLATES
Grade B02
STRENX 700 E
Quality Specifications B02
QUENCHED AND TEMPERED STEEL

Tolerances
STRENX, EN 10029:2010 CLASS A

A07 Item	B09-B11 Dimensions mm	A09 Marke	B08 Pcs	B12/B13 Weight kg	B07 Cast plate No	B07 SP No	D02 UT	D03 MT	B03 Safety mark	A10 Origin	A10 Melt and Pour
-------------	--------------------------	--------------	------------	----------------------	----------------------	--------------	-----------	-----------	--------------------	---------------	----------------------

QUENCHED AND TEMPERED STEEL PLATES
IN BUNDLES

MEETS REQUIREMENTS OF EN10025-6 S690QL
SURFACE CONDITION EN 10 163-2:2005 CLASS A3

001	12.00	X	1500	X	3000	8	3392	86143	015	015	FI	SSAB FI RAAHE
001	12.00	X	1500	X	3000	8	3392	86143	016	016	FI	SSAB FI RAAHE

MEETS REQUIREMENTS OF EN10025-6 S690QL
SURFACE CONDITION EN 10 163-2:2005 CLASS A3

002	15.00	X	1500	X	3000	14	7420	87210	021	021	FI	SSAB FI RAAHE
002	15.00	X	1500	X	3000	14	7420	87210	022	022	FI	SSAB FI RAAHE

MEETS REQUIREMENTS OF EN10025-6 S690QL
SURFACE CONDITION EN 10 163-2:2005 CLASS A3

003	16.00	X	1500	X	3000	8	4520	87206	041	041	FI	SSAB FI RAAHE
-----	-------	---	------	---	------	---	------	-------	-----	-----	----	---------------

*** 52 26144

Raahe Steel Works

A01

Testing and Inspection A05

Z01

We hereby certify that the material described above has been tested and complies with the terms of the order confirmation.

Minna Valkama

MINNA VALKAMA

Authorized inspection representative Z02

Company name: SSAB Europe Oy
Registered Office: HÄMEENLINNA

Address: PL 93, P.O Box 93
FIN-92101 RAAHE, FINLAND

Telephone: 020 5911
+358 20 5911

Business ID: 2389445-7



TEST REPORT

A03 A 14983 -002
02.02.2026

Purchaser A06
STÅLGROSS I SVERIGE AB
TUVULLSVÄGEN 5
554 75 JÖNKÖPING SWEDEN
Order No. A07
23587

Order Confirmation A08
14983

Consignee A06
NORDISK BETINDUSTRI
INDUSTRIVÄGEN
795 22 RÄTTVIK SWEDEN
Shipping mark
23587

Date
03.02.2026
MAH
Mark of the Manufacturer A04



Grade B02
STREX 700 E
Quality Specifications B02

Additional requirements B03

Oxygen steel, continuous casting
Fully killed, Fine grain practiced C70

QUENCHED AND TEMPERED STEEL

A07 Item	B07 Cast. test No	B04 Cond	Tensile test C11															C50 Bend test		C04-C09 Nb	B05 Temperin °C
			C00 K2	C03 °C	C11 MPa RP02	C11 MPa RT05	C11 MPa REL	C11 MPa REH	C12 1	RM 2	MPa 3	C13 %	A % 50	80	200	RE/RM	RM * A5	RAZ % 1	Average 2 3		
001	86143	015	QT	51		760					821								17		
001	86143	016	QT	51		780					833								16		
002	87210	021	QT	51		795					840								17		
002	87210	022	QT	51		815					855								18		
003	87206	041	QT	51		813					860								15		

K2: 51=BOTTOM,TRANSV.

QT=QUENCHED + TEMPERED

A07 Item	B07 Cast. test No	Impact test								FA %				LE (mm)		*Specimen Unbroken		C53 Special Tests					C04-C09 Nb	B05 Tempering °C		
		C00 K3	C03 °C	C42 1	C42 2	C42 3	C43 Average	C41 W (mm)	C51 1	C51 2	C51 3	C51 Average	C52 1	C52 2	C52 3	C52 Average	C00 K4	C03 °C	C53 1	C53 2	C53 Average					
		FA =Shear fracture appearance										LE = Lateral Expansion														
001	86143	015	155	-040	150	78	64	97																		
			156	-040	64	106	115	95																		
001	86143	016	155	-040	126	113	133	124																		
			156	-040	143	142	142	142																		
002	87210	021	151	-040	179	187	156	174																		
			152	-040	148	160	200	169																		
002	87210	022	151	-040	163	165	223	184																		
			152	-040	122	201	189	171																		
003	87206	041	151	-040	140	167	201	169																		
			152	-040	120	108	139	122																		

K3: 155=CH-V/ISO-V(J),7.5X10,BOTTOM,LONGIT,KV600 156=CH-V/ISO-V(J),7.5X10,BOTTOM,TRANSV,KV600 151=CH-V/ISO-V(J),10X10,BOTTOM,LONGIT,KV600 152=CH-V/ISO-V(J),10X10,BOTTOM,TRANSV,KV600

Raahe Steel Works A01

Testing and Inspection A05

Minna Valkama

MINNA VALKAMA

Authorized inspection representative Z02

Company name: SSAB Europe Oy
Registered Office: HAMEENLINNA

Z01

We hereby certify that the material described above has been tested and complies with the terms of the order confirmation.

Address: PL 93, P.O Box 93
FIN-92101 RAAHE, FINLAND

Telephone: 020 5911
+358 20 5911

Business ID: 2389445-7



ANALYSIS CERTIFICATE

B07 Cast No	B07 Test No	A07 Item	C93-99 Ceq	C71-C92 Chemical composition % (*ppm)																Date Z02 03.02.2026 MAH	
				C	SI	MN	P	S	AL	NB	V	TI	CU	CR	NI	MO	N	B	CET		
86143		001	.42	.163	.31	1.15	.010	.001	.095	.001	.030	.011	.011	0.21	0.04	.081	.003	.0014	.30		
87210		002	.42	.158	.33	1.14	.010	.001	.083	.002	.031	.014	.012	0.21	0.06	.080	.003	.0014	.29		
87206		003	.43	.168	.34	1.16	.010	.001	.077	.003	.033	.016	.012	0.22	0.05	.079	.004	.0015	.30		

Ceq=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15

CET=C+(Mn+Mo)/10+(Cr+Cu)/20+Ni/40

Raahe Steel Works A01

Testing and Inspection A05

MINNA VALKAMA
Authorized inspection representative Z02

SSAB Europe Oy, Raahe Steel Works testing laboratories T002 and T010 are accredited by the FINAS accreditation service (finas.fi), accreditation requirement SFS-EN ISO/IEC 17025.
Steel manufactured and supplied by Raahe Steel Works is free from radiation.



INSPECTION CERTIFICATE

A02 EN 10 204-3.1 (2004)

A03 A 14983 -002 A
02.02.2026

Purchaser A06
STÅLGROSS I SVERIGE AB
TUVULLSVÄGEN 5
554 75 JÖNKÖPING SWEDEN

Order Confirmation A08
14983

Consignee A06
NORDISK BETINDUSTRI
INDUSTRIVÄGEN
795 22 RÄTTVIK SWEDEN

Shipping mark
23587

Date Z02
03.02.2026
Mark of the Manufacturer A04



Certificate A02
31

Quality Marking B06
S690QL

Stamp of Inspector Z03

Stamp of Surveyor

Mxx

Other Stamps

Delivery type
REST DELIVERY

Cast No. Plate No. B07
X X X X X X X X X X X X

Technical terms of Delivery and/or Official Regulations

Product B01
HEAVY PLATES
Grade B02
S690QL EN 10025-6:2019
Quality Specifications B02
QUENCHED AND TEMPERED STEEL

Tolerances
STRENGTH, EN 10029:2010 CLASS A

A07 Item	B09-B11 Dimensions mm	A09 Marke	B08 Pcs	B12/B13 Weight kg	B07 Cast plate No	B07 SP No	D02 UT	D03 MT	B03 Safety mark	A10 Origin	A10 Melt and Pour
-------------	--------------------------	--------------	------------	----------------------	----------------------	--------------	-----------	-----------	--------------------	---------------	----------------------

QUENCHED AND TEMPERED STEEL PLATES
IN BUNDLES

SURFACE CONDITION EN 10 163-2:2005 CLASS A3

001	12.00 X 1500	X	3000	8	3392	86143	015	015		FI	SSAB FI RAAHE
-----	--------------	---	------	---	------	-------	-----	-----	--	----	---------------

001	12.00 X 1500	X	3000	8	3392	86143	016	016		FI	SSAB FI RAAHE
-----	--------------	---	------	---	------	-------	-----	-----	--	----	---------------

SURFACE CONDITION EN 10 163-2:2005 CLASS A3

002	15.00 X 1500	X	3000	14	7420	87210	021	021		FI	SSAB FI RAAHE
-----	--------------	---	------	----	------	-------	-----	-----	--	----	---------------

002	15.00 X 1500	X	3000	14	7420	87210	022	022		FI	SSAB FI RAAHE
-----	--------------	---	------	----	------	-------	-----	-----	--	----	---------------

SURFACE CONDITION EN 10 163-2:2005 CLASS A3

003	16.00 X 1500	X	3000	8	4520	87206	041	041		FI	SSAB FI RAAHE
-----	--------------	---	------	---	------	-------	-----	-----	--	----	---------------

***	52	26144
-----	----	-------

Raahe Steel Works

A01

Testing and Inspection A05

M Valkama

MINNA VALKAMA

Authorized inspection representative Z02

Z01

We hereby certify that the material described above has been tested and complies with the terms of the order confirmation.

Company name: SSAB Europe Oy
Registered Office: HÄMEENLINNA

Address: PL 93, P.O Box 93
FIN-92101 RAAHE, FINLAND

Telephone: 020 5911
+358 20 5911

Business ID: 2389445-7



TEST REPORT

A03 A 14983 -002 A
02.02.2026

Purchaser A06
STÅLGROSS I SVERIGE AB
TUVULLSVÄGEN 5
554 75 JÖNKÖPING SWEDEN
Order No. A07
23587

Order Confirmation A08
14983

Consignee A06
NORDISK BETINDUSTRI
INDUSTRIVÄGEN
795 22 RÄTTVIK SWEDEN
Shipping mark
23587

Date
03.02.2026
Mark of the Manufacturer A04



Grade B02
S690QL
Quality Specifications B02

Additional requirements B03

Oxygen steel, continuous casting
Fully killed, Fine grain practiced C70

QUENCHED AND TEMPERED STEEL

A07 Item	B07 Cast. test No	B04 Cond	Tensile test C11															C50 Bend test		C04-C09 Nb	B05 Temper °C
			C00 K2	C03 °C	C11 MPa RP02	C11 MPa RT05	C11 MPa REL	C11 MPa REH	C12 1	RM 2	MPa 3	C13 %	A % 50	80	200	RE/RM	RM * A5	RAZ % 1	Average 2 3		
001	86143 015	QT	51		760					821			17								
001	86143 016	QT	51		780					833			16								
002	87210 021	QT	51		795					840			17								
002	87210 022	QT	51		815					855			18								
003	87206 041	QT	51		813					860			15								

K2: 51=BOTTOM,TRANSV.

QT=QUENCHED + TEMPERED

A07 Item	B07 Cast. test No	Impact test								FA %					LE (mm)		*Specimen Unbroken		C53 Special Tests					C04-C09 Nb	B05 Tempering °C	
		C00 K3	C03 °C	C42 1	C42 2	C42 3	C43 Average	C41 W (mm)	C51 1	C51 2	C51 3	C51 Average	C52 1	C52 2	C52 3	C52 Average	C00 K4	C03 °C	C53 1	C53 2	C53 Average					
		FA =Shear fracture appearance								LE = Lateral Expansion																
001	86143 015	155	-040	150	78	64	97																			
		156	-040	64	106	115	95																			
001	86143 016	155	-040	126	113	133	124																			
		156	-040	143	142	142	142																			
002	87210 021	151	-040	179	187	156	174																			
		152	-040	148	160	200	169																			
002	87210 022	151	-040	163	165	223	184																			
		152	-040	122	201	189	171																			
003	87206 041	151	-040	140	167	201	169																			
		152	-040	120	108	139	122																			

K3: 155=CH-V/ISO-V(J),7.5X10,BOTTOM,LONGIT,KV600 156=CH-V/ISO-V(J),7.5X10,BOTTOM,TRANSV,KV600 151=CH-V/ISO-V(J),10X10,BOTTOM,LONGIT,KV600 152=CH-V/ISO-V(J),10X10,BOTTOM,TRANSV,KV600

Raahe Steel Works A01

Testing and Inspection A05

Minna Valkama

MINNA VALKAMA

Authorized inspection representative Z02

Company name: SSAB Europe Oy
Registered Office: HAMEENLINNA

Z01

We hereby certify that the material described above has been tested and complies with the terms of the order confirmation.

Address: PL 93, P.O Box 93
FIN-92101 RAAHE, FINLAND

Telephone: 020 5911
+358 20 5911

Business ID: 2389445-7



ANALYSIS CERTIFICATE

B07 Cast No	B07 Test No	A07 Item	C93-99 Ceq	C71-C92 Chemical composition % (*ppm)																Date Z02 03.02.2026		MAH
				C	SI	MN	P	S	AL	NB	V	TI	CU	CR	NI	MO	N	B	CET			
86143		001	.42	.163	.31	1.15	.010	.001	.095	.001	.030	.011	.011	0.21	0.04	.081	.003	.0014	.30			
87210		002	.42	.158	.33	1.14	.010	.001	.083	.002	.031	.014	.012	0.21	0.06	.080	.003	.0014	.29			
87206		003	.43	.168	.34	1.16	.010	.001	.077	.003	.033	.016	.012	0.22	0.05	.079	.004	.0015	.30			

CEQ=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15

CET=C+(Mn+Mo)/10+(Cr+Cu)/20+Ni/40

Raahe Steel Works A01

Testing and Inspection A05

MINNA VALKAMA
Authorized inspection representative Z02

SSAB Europe Oy, Raahe Steel Works testing laboratories T002 and T010 are accredited by the FINAS accreditation service (finas.fi), accreditation requirement SFS-EN ISO/IEC 17025.
Steel manufactured and supplied by Raahe Steel Works is free from radiation.

Declaration of performance
(according to EU No 305/2011 and 574/2014)

DoP id. P048_02

Hot rolled Plate product S690QL / 1.8928
according to
EN 10025-6:2019
for bolted, welded and riveted structures.

SSAB
P.O Box 70
101 20 Stockholm
SWEDEN
T: +46 8 45 45 700
Email: info@ssab.com
Website: ssab.com

TÜV NORD Systems GmbH & Co. KG
Grosse Bahnstrasse 31
D-22525 Hamburg
Germany
T: +49 40 8557 2368

Assessment system and verification for constancy
of performance
System 2+

The performance of the product identified in this document is
in conformity with the set of declared performance. This declaration of performance
is issued in accordance with Regulations (EU) No 305/2011 and 574/2014,
under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:



Jarkko Matkala
Vice President, hot rolled plate and strip products,
SSAB Europe Oy, Raahе Steelworks
Raahе 2015-06-09



05
0045-CPR-0573
EN 10025-1:2004

Dop id: P048_02 EN 10025-6:2019		Performance		Harmonized technical specification
S690QL	Thickness	Tolerances on the nominal thickness (acc. EN 10029 Class A unless otherwise stated)		EN 10025-1:2004
Tolerances on dimensions and shapes.	Nominal thickness (mm)	Lower	Upper	
	$3 \leq t < 5$	-0,3	+0,7	
	$5 \leq t < 8$	-0,4	+0,8	
	$8 \leq t < 15$	-0,5	+0,9	
	$15 \leq t < 25$	-0,6	+1,0	
	$25 \leq t < 40$	-0,7	+1,3	
	$40 \leq t < 80$	-0,9	+1,7	
	$80 \leq t < 150$	-1,1	+2,1	
	$150 \leq t < 250$	-1,2	+2,4	
Width	Nominal thickness	Tolerances		
		Lower	Upper	
	$t < 40$	0	+20	
	$40 \leq t < 150$	0	+25	
	$150 \leq t \leq 400$	0	+30	
	Tolerances on width for plates with untrimmed edges (NK) shall be the subject of agreement between the manufacturer and purchaser at the time of enquiry and order.			
Length	Nominal length	Tolerances		
	l	Lower	Upper	
	$l < 4000$	0	+20	
	$4000 \leq l < 6000$	0	+30	
	$6000 \leq l < 8000$	0	+40	
	$8000 \leq l < 10\ 000$	0	+50	
	$10\ 000 \leq l < 15\ 000$	0	+75	
	$15\ 000 \leq l \leq 20\ 000$	0	+100	
	Tolerances on plates with nominal length $l > 20\ 000$ mm shall be agreed at the time of enquiry and order.			
	Flatness	Nominal thickness t	Measuring length	
t		1000	2000	
$3 \leq t < 5$		9	14	
$5 \leq t < 8$		8	12	
$8 \leq t < 15$		7	11	
$15 \leq t < 25$		7	10	
$25 \leq t < 40$		6	9	
$40 \leq t < 250$		5	8	

Yield strength	thickness mm	min (Mpa)	max (Mpa)
	$\geq 3 \leq 50$	690	
	$> 50 \leq 100$	650	
	$> 100 \leq 150$	630	
Tensile strenght	thickness mm	min (Mpa)	max (Mpa)
	$\geq 3 \leq 50$	770	940
	$> 50 \leq 100$	760	930
	$> 100 \leq 150$	710	900
Elongation	thickness mm	min %	
		14	
Impact strength	thickness mm	temperature, °C	min. energy, J
		-40	30
Weldability CEV	thickness mm	CEV max%	
	≤ 50	0.65	
	$> 50 \leq 100$	0.77	
	$> 100 \leq 150$	0.83	
Durability (chemical composition)	element	Max %	
	C	0.20	
	Si	0.80	
	Mn	1.70	
	P	0.020	
	S	0.010	
	N	0.015	
	B	0.0050	
	Cr	1.50	
	Cu	0.50	
	Mo	0.70	
	Nb	0.06	
	Ni	2.0	
	Ti	0.05	
	V	0.12	
	Zr	0.15	

Declaration of performance
(according to UK CPR 2020 No 1359)

DoP id. P048_02

Hot rolled Plate product S690QL / 1.8928
according to
EN 10025-6:2019
for bolted, welded and riveted structures.

SSAB
P.O Box 70
101 20 Stockholm
SWEDEN
T: +46 8 45 45 700
Email: info@ssab.com
Website: ssab.com

LRQA Verification Limited (Reg. No. 4929226)
Registered office
1 Trinity Park, Bickenhill Lane
Birmingham
B37 7ESA

Assessment system and verification for constancy
of performance
System 2+

The performance of the product identified in this document is
in conformity with the set of declared performance. This declaration of performance
is issued in accordance with Regulations (EU) No 305/2011 and 574/2014,
under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:



Jarkko Matkala
Vice President, hot rolled plate and strip products,
SSAB Europe Oy, Raahe Steelworks
Raahe 2015-06-09

UK
CA**05**

0038/CPR/PRJ11100341405/ 01

EN 10025-1:2004

Dop id: P048_02 EN 10025-6:2019		Performance		Harmonized technical specification
S690QL	Thickness	Tolerances on the nominal thickness (acc. EN 10029 Class A unless otherwise stated)		EN 10025-1:2004
Tolerances on dimensions and shapes.	Nominal thickness (mm)	Lower	Upper	
Thickness	$3 \leq t < 5$	-0,3	+0,7	
	$5 \leq t < 8$	-0,4	+0,8	
	$8 \leq t < 15$	-0,5	+0,9	
	$15 \leq t < 25$	-0,6	+1,0	
	$25 \leq t < 40$	-0,7	+1,3	
	$40 \leq t < 80$	-0,9	+1,7	
	$80 \leq t < 150$	-1,1	+2,1	
	$150 \leq t < 250$	-1,2	+2,4	
Width	Nominal thickness	Tolerances		
		Lower	Upper	
	$t < 40$	0	+20	
	$40 \leq t < 150$	0	+25	
	$150 \leq t \leq 400$	0	+30	
	Tolerances on width for plates with untrimmed edges (NK) shall be the subject of agreement between the manufacturer and purchaser at the time of enquiry and order.			
Length	Nominal length	Tolerances		
	l	Lower	Upper	
	$l < 4000$	0	+20	
	$4000 \leq l < 6000$	0	+30	
	$6000 \leq l < 8000$	0	+40	
	$8000 \leq l < 10\,000$	0	+50	
	$10\,000 \leq l < 15\,000$	0	+75	
	$15\,000 \leq l \leq 20\,000$	0	+100	
	Tolerances on plates with nominal length $l > 20\,000$ mm shall be agreed at the time of enquiry and order.			
	Flatness	Nominal thickness t	Measuring length	
t		1000	2000	
$3 \leq t < 5$		9	14	
$5 \leq t < 8$		8	12	
$8 \leq t < 15$		7	11	
$15 \leq t < 25$		7	10	
$25 \leq t < 40$		6	9	
$40 \leq t < 250$		5	8	

Yield strength	thickness mm	min (Mpa)	max (Mpa)
	$\geq 3 \leq 50$	690	
	$> 50 \leq 100$	650	
	$> 100 \leq 150$	630	
Tensile strenght	thickness mm	min (Mpa)	max (Mpa)
	$\geq 3 \leq 50$	770	940
	$> 50 \leq 100$	760	930
	$> 100 \leq 150$	710	900
Elongation	thickness mm	min %	
		14	
Impact strength	thickness mm	temperature, °C	min. energy, J
		-40	30
Weldability CEV	thickness mm	CEV max%	
	≤ 50	0.65	
	$> 50 \leq 100$	0.77	
	$> 100 \leq 150$	0.83	
Durability (chemical composition)	element	Max %	
	C	0.20	
	Si	0.80	
	Mn	1.70	
	P	0.020	
	S	0.010	
	N	0.015	
	B	0.0050	
	Cr	1.50	
	Cu	0.50	
	Mo	0.70	
	Nb	0.06	
	Ni	2.0	
	Ti	0.05	
	V	0.12	
	Zr	0.15	