



Created 09/10/2007
Rev. 2 – 01/06/2019
Rev. 3 – 06/06/2024

PRODUCT TECHNICAL AND SAFETY DATA SHEET:

REONYX



Code:




REONYX12.5

REONYX5

DESCRIPTION:

Breathable water-based interior wall paint, based on vinyl resin with a special broad-spectrum inhibitor against mold, fungi and algae, has a good white point, is easy to apply both with a roller and a brush, has excellent brushability, excellent coverage even on mold residues and excellent yield. Suitable for home and industrial environments such as kitchens, bathrooms, cellars, changing rooms and in general in rooms subject to the formation of mold and condensation.

CHARACTERISTICS:

I WAIT	Opaque
SPECIFIC WEIGHT	REONYX: 1.63 Kg/l \pm 0.03 at 20°C
DRY RESIDUE	58.00 p/p \pm 5%
WASHING RESISTANCE	REONYX: LOW
WATER VAPOR PERMEABILITY	ONYX: HIGH
DIRT GRIP	LOW
COLOR	White (Colourable with Universal Dyes)
DRYING	For recoating: 6 hours, full: 48 hours (data refers to 20°C and 65% RH) full: 48 hours
(data referred to 20°C and 65% RH)	
PRACTICAL YIELD	REONYX: 10-14 m ² /L per coat depending on the absorption of the support Add 1st coat: Brush application 30% drinking water, roller application 20% drinking water. Add 2nd coat: Brush application 20% drinking water, roller application 20% drinking water. Airless spray: add between 30% and 40% of drinking water. Recommended tips: LP419-LP519-LP619- LP421-LP521-LP624
DILUTION	
TOOLS	 brush  Roller  spray
SUPPORTS	civil plaster, plasterboard, fibre cement, stuccoed walls

APPLICATION

PREPARATION OF THE SUPPORT

The substrate must be healthy, dry, clean and consistent, free from damp stains, traces of dirt, grease, mold, etc. Old inconsistent or flaking paint must be removed by brushing or sanding the surface. Imperfections, cracks, flaking must be eliminated and filled with an appropriate filler.

NEW SUPPORTS FREE FROM MOLD

ALREADY PAINTED SUPPORTS

	PLASTER	HANDS	PLASTERBOARD	HANDS	WITH MOLD STAINS	HANDS	WASHABLE WELL ANCHORED	HANDS
FUND	JANTAR	1	UNIQUE	1	RE-23	1	RE-23	1
FINISH	REONYX	2	REONYX IF NECESSARY 2nd coat	1	JANTAR REONYX	1 2	JANTAR REONYX	1 2

GENERAL WARNINGS

In order not to alter the typical breathable properties of the product, the quantity of base dye must not exceed 20%. Store the product in a cool place and protect from frost. Do not apply the product at temperatures below 5° or above 30° centigrade, with relative humidity above 85% or on walls exposed to wind or sun.